PRODUCT DATA SHEET

DUROPOXY CLEAR COAT 100

Epoxy Based Durable Floor Sealer

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

DuroPoxy Clear coat 100 is a solvent free, non-pigmented two component epoxy based sealer. DuroPoxy clear coat100 is used as a sealer over dense concrete and cementitious surfaces and can also be used as a

FEATURES

- High adhesive strength – creates an extremely good bond to concrete substrates and aggregates
- Lower viscosity
- Excellent cure rate low temperatures
- Chemical resistance
- Excellent adhesion to dry, damp and or dense surfaces
- Multipurpose epoxy Clear Sealer
- Non- flammable
- Very low VOC content

Use Area

- Dense concrete sealer
- Mortar sealer
- Screed Sealer
- Primer for trafficable epoxy systems
- Primer for polyurethane membranes
- Primer for damp substrates

COMPONENT PROPERTES

Property	Resin	Hardener
Appearance	Straw to amber colour liquid	Straw to amber colour liquid
Specific gravity g/cm3	1.16 ± 3	1.03 ± 3
Viscosity @ 25°C	910 ± 50	100 – 300 cps

MIXING AND CURING CONDITIONS

Property	Resin/ Hardener
Mix ratio by weight (resin/ weight)	00/50
Solids Content	100%
Mixed specific gravity	1.09 g/cm3
Work Time (150 grams)	16 ± 3 minutes @ 25°c
Ready for traffic	Less than 8 hours @ 25°C
Recoat time	16 to 24 hours @25°C

Typical Physical Properties

Property	Resin/ Hardener
Hardness	89 Shore D
Adhesion to concrete	>1.5 MPa
Service Temp (Max)	100°C

SINCE 1977

APPLICATION

Surface Preparation: The surface must be clean and dry and free from loose particles, including dust, grease, coatings and curing compounds and other foreign matter. The substrate must be prepared by any way of degreasing, grinding or captive shot blasting to expose aggregate and provide a profile. Allow floor to dry if degreasing has been carried out, before applying DuroPoxy clear coat100.

The compressive strength of substrates shall not be less than 25MPa. A minimum direct tensile pull off is 1.5 MPa. The moisture content of substrate shall not be higher than 8% throughout and the temperature of the substrate must be 3°C above the current dew point.

Mixing: Prior to mixing, the temperature of the components must be between 10-30°C. Pour hardener into the resin container and ensure all contents in the hardener is emptied completely. To achieve a homogeneous mix, both parts must be mechanically stirred with a mixing paddle at about 300-600 rpm. Ensure the mixing device reaches the side and bottom of the vessel and stir for 2 minutes and scrape down the sides of the drum and mix for another 1 to 2 minutes until uniform.

How: After mixing, allow mixed material to stand for 5 minutes, then apply the Duropoxy clear coat 100 to the clean substrate using a brush or roller. The working time is decreased by increase in temperature and lower temperatures will extend the working time. To fully cure the product the substrate temperature must not fall below 5°C in the first 24 hours.

Curing: After application, the DuroPoxy clear coat 100 should be protected from direct contact with water for approximately 6 hours at 25 ± 3°C.

ESTIMATING DATA

The consumption will depend upon substrate condition or type. Apply to give a coverage of 0.2mm thickness per square metre. A second coat of Duropoxy clear coat100 may be required for porous substrate.

Coverage rate will be approx. 5M² per litre.

STORAGE

Duropoxy clear coat100 should be stored in its original sealed containers for up to 12 months in controlled environment. Place out of direct sunlight at temperatures between 15-30°C.

PACKAGING and COLOUR AVAILABILITY

Duropoxy clear coat100 is supplied as an 8.1L Kit (5.4L Resin / 2.7L Hardener).
Colour: Clear Amber

CLEANING

Clean the tools and equipment with rags, then wipe off using a solvent such as xylene before the resin system hardens.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use the product, please make sure that you obtain a copy MSDS.

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet