PRODUCT DATA SHEET

DUROPOXY CRACK SEAL

CRACK SEAL EPOXY

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

This is a low viscous two part epoxy material used for filling cracks in concrete.

This material has very low shrinkage and the adhesion is excellent. This has good crack filling capacity as the viscosity is very low and easily penetrates into crevices.

FEATURES

Kits – no onsite mixing errors

- 100% solvent free
- Touch Dry in 4 hours
- Chemical resistant
- Easy to use
- Fast Application
- Non flammable
- Can be coloured – enhance the solution for client needs

USE AREA

- Workshops
- Garage floors
- Factory floor
- Warehouses
- Shop floors
- Driveways
- Railway platforms

TECHNICAL INFORMATION

PROPERTY	Resin	Hardener
Appearance	Clear	Straw to amber
Specific gravity g/cm³	1.1 - 1.16	1.1 -1.16
Viscosity @ 25°C	600 – 1,000 cps	100 – 300 cps

MIXING AND CURING CONDITIONS

PROPERTY	RESIN / HARDENER
Mix ratio by weight or volume	2:1
Solids Content	100%
Mixed specific gravity	1.15 gms/cm³
Work Time (600ml kit)	20 minutes @ 25°c
Recoat Time	Less than 4-6 hours @ 25°C
Ready for Paint over	4-6 hours @ 25°C

SINCE 1977

TYPICAL PHYSICAL PROPERTIES

PROPERTY	Method	Resin/Hardener
Hardness	AS/NZS 1683.15	80 Shore D
Tensile Strength	AS/NZS 1683.11	23MPa
Compressive Strength	ASTM D1621-04	67 MPa
% Elongation	AS/NZS 1683.11	5%

These values are typical properties and are not to be used for specification

APPLICATION

Surface Preparation: The surface must be clean, dry and free from loose particles, including dust, grease, coatings and curing compounds and other foreign matter. If the cracks are small, cut open the crack to 3-5 mm and blow off the dust. If the crack is too deep, use backing foam to avoid the use of excess crack seal.

Mixing: Prior to mixing, the temperature of the components must be between 10-30°C. Remove the lids of Part A and Part B.

Pour the contents of Part B int o the bigger bottle (Part A).

Close the lid of Part A.

Shake the bottle vigorously for 1 minute to ensure that A+B are mixed well.

Cut open the nozzle of the bottle.

Squeeze the liquid into the cracks and spread if necessary.

Allow this to stand for 4 hours and the material is hard enough for grinding the excess.

NOTE: Working time is approximately 20 minutes. This will vary depending on ambient conditions, quantity mixed and placed (see Dry and Curing times).

PACKAGING AND COLOR AVAILABILITY

600 ml kits (A+B)
Other sizes available on request
Natural colour available.
Special colours available on request

CLEANING

Clean the tools and equipment with rags, then wipe off using a solvent such as xylene before the resin system hardens.

HEALTH & SAFETY

Please observe the precautionary notices displayed on container. Use under well ventilated conditions. Avoid skin contact. Spillage on the skin should be removed immediately with suitable cleanser, soap and water. Eyes should be well flushed with water and seek medical attention immediately.

For the full health and safety hazard information and how to safely handle and use the product, please make sure you refer to relevant MSDS.

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©

ISO 9001 Quality Certified System
ISO 14001 Environment Certified System
ISO 45001 Health and Safety Certified System