PRODUCT DATA SHEET

DUROPOXY POLYSEAL

CLEAR NON-YELLOWING POLYURETHANE COATING

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Duropoxy Polyseal is a tough, flexible sealer that provides a clear non-yellowing finish to concrete and epoxy coatings.

It has excellent abrasion, scratch and stain resistance.

USE AREAS

Duropoxy Polyseal is ideally suited as a finish coat to seamless epoxy flooring. It contains UV absorbers which help protect the epoxy undercoats from UV light and thus reducing the yellowing tendencies of epoxies upon exposure to sunlight or other UV sources.

Duropoxy Polyseal produces a gloss finish which is resistant to outdoor exposure, making the product useful as a topcoat for water based epoxy coatings in outdoor environments.

TYPICAL APPLICATIONS

The product can be applied to:

- Ground concrete slabs
- Benchtops & stone furniture
- Floor tiles exposed to restaurant grime
- Tilers & paving slabs in walkways and public squares
- Brickwork & precast walls of public structures

TECHNICAL INFORMATION

Colour	Light yellow, clear coating
Viscosity	90 MPa @ 30°C
Specific gravity	0.95
Solids content	45%
Coverage	8–10 sqm/litre
Water resistance	Excellent
Chemical resistance	Good resistance to acids, alkalis, alcohols, aromatic hydrocarbons, brake fluid, diesel, and machine oil.

PACKAGING

Available in 4 litre tins and 20 litre pails.

SINCE 1977

PRODUCT APPLICATION

- The surface must be clean and dust free.
- Apply product with a short nap mohair roller.
- Duropoxy polyseal should be applied when the temperature is 15–30°C and relative humidity below 75%.
- A second coat should be done once first coat is dry and within 24 hours.
- If a maintenance coat or re-coating beyond that window is required, then the surface should be sanded.
- Light foot traffic can resume after 24 hours and heavier traffic a minimum 48 hours.
- Full chemical resistance is achieved after 7 days.

PRE-CONDITIONING PRODUCT

It is important to note that even when the application environment is warm, products which have been stored in cold or cooler conditions should always be pre-conditioned ideally to 20–25°C to ease mixing, application and help avoid other potential issues such as amine bloom or blushing.

Applying a cold product in a warm environment is not recommended.

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au



"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©

ISO 9001 Quality Certified System
ISO 1400 FC Environment Certified System
ISO 45001 Health and Safety Certified System