PRODUCT DATA SHEET

DUROPROOF PU 340

Grey Polyurea/Polyurethane Hybrid

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

DUROPROOF PU 340 is a 100% solids (solvent free), grey two component, fast-cure polyurea/ polyurethane hybrid elastomer coating designed specifically for waterproofing or corrosion resistance applications.

The isocyanate recommended for this system is Suprasec® 2058.

FEATURES

- Good Abrasion Resistance.
- High Tensile Strength and Elongation.
- Contains no volatile or flammable solvents.
- Good resistance to many dilute acids, alkalis, salts and solvents.

TECHNICAL INFORMATION (21°C)

Appearance:	Grey Liquid
Specific Gravity	1.07
Viscosity (cPs)	300 - 500
Flash Point (°C)	>149
Solids Content (%)	100
Mix Ratio (by Vol)	1:1

PACKAGING

Nett 207 kg per drum.

STORAGE AND HANDLING PRECAUTIONS

To prevent ingress of moisture, drums must be kept tightly sealed when not in use. Store in sealed containers between 20 - 30°C

Storage Stability
This product has a storage stability of approximately 12 months.
For prolonged storage, it is recommended that the temperature should not exceed 30°C.

This material is alkaline, store away from acids, oxidising agents and nitrites. Keep containers closed at all times - check regularly for leaks.

Cured Product Typical Physical Properties

PROPERTY	TEST METHOD BASIS	TYPICAL RESULT
Tensile Strength	ASTM D 412-92	21 MPa
Elongation @ 24°C	ASTM D 412-92	>400 %
Tear Strength	ASTM D 624-86	79 N/mm
Hardness	ASTM D 2240-91, Shore D Shore A	50 90
Abrasion Resistance	ASTM C501-84, H18 wheel 1000 rev, with 1000g weight	170 mg
Water Vapour Transmission Rate	E96-05 (B)	5.9 g/24h.m2
Water Absorption	AS 3558.1	< 2%

DUROTECH INDUSTRIES

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet