DUROTECH

DUROPROOF ATC

Provides Greater UV Protection & Colour Fastness For Membranes

Duroproof ATC is single pack, aliphatic polyurethane waterproofing top coat which has been formulated as a complimentary and compatible top coat for UV and Duroproof PUM. Aliphatic technology provides greater UV protection, colour fastness and anti-chalking properties and is designed to extend the life of exposed aromatic polyurethanes. ATC forms a tough, flexible, seamless, highly UV stable, waterproof coating. ATC meets the 'Green Star' enviromental criteria.

BENEFITS AND ADVANTAGES

ATC represents the highest standards in aliphatic polyurethane waterproofing technology and provides the following benefits and advantages:

- Provides excellent UV protection.
- Extends the life of the waterproofing membrane system.
- Metts the 'Green Star' environmental criteria.
- Single pack - no mixing.
- Curing (usually within) 24 hours.
- Permanently flexible
- Suitable for immersion in water.
- Good chemical resistance.
- High strength and puncture resistant.
- Provides seamless membrane (no joints or laps)
- Easily repaired and or maintained.
- Easy to apply.

USES

ATC is primarily formulated as a highly UV stable top coat over and Duroproof PUM to give greater long term UV protection and colour fastness thereby extending the life and performance of the waterproofing membrane.

SUITABLE SURFACES

ATC have been formulated as top coat over Duroproof PUM.

SPECIFICATION

The information contained in this product data sheet is typical but does not constitute a full specification as conditions and specific requirements may vary from project to project. The instructions should be considered as a minimum requirement but the applicator or contractor must use their skill, knowledge and experience to carry out additional works as may be necessary to meet the requirements of the project. Specification for specific projects should be sought from the Company in writing.

LIMITATIONS

Suitable for maintenance foot traffic and not intended as a general trafficable membrane.

PRECAUTIONS IN USE

Risk is considered low when properly used but precautions on can, label and / or data sheets should be observed. Do not use in confined areas with poor ventilation. Uncured product is flammable.

PRIMING AND SURFACE PREPARATION

Good preparation is essential. Surfaces must be sound, stable, dry, clean and free of dust, loose, flaking, friable material and substances that may diminish adhesion.

As its main purpose is to be applied over cured Durorproof PUM, it can be applied as follows:

Providing the existing membranes are clean, dry and that the Duroproof ATC is being applied within 48 hours of applying the Duroproof membranes - no other preparation is required.

APPLICATION

Apply ATC to Duroproof PUM membranes by brush, roller, broom and squeegee usually in one or two coats at the rate of 3m^2 per litre per coat, so that the minimum dry film thickness is 300 microns.

COVERAGE

The stated average coverage rate may vary depending upon type, condition, porosity, texture of the surface and application technique.

ATC Top Coat: Generally, 3m^2 per litre per coat.

COLOURS

Grey

DRYING AND CURING

Drying and curing of the product is affected by type, dryness and porosity of the surface, temperature, humidity, ventilation, climate conditions and application technique and therefore drying and curing can only be given as a guide.

Generally Duroproof ATC is weather resistant within 6 to 8 hours with fulll cure within 24 hours.

STORAGE

Keep in cool, dry place away from heat, flame, combustible material and all sources of ignition. Product contains flammable solvents. Class 3 dangerous goods must be declared prior to transportation. Available in 15 lt pails.

Self life: 6 - 12 months in unopened container but best used within 6 months. As this is a polyurethane some skinning of the product may occur. This should be cut out and removed. Balance of the product will be suitable for use.

CLEAN UP

Avoid spills. They are difficult to clean particularly off porous surfaces. Wet spills use a cloth and Duroproof Solvent. Do not clean off carpets as it is better to allow product to cure and then shave the carpet. Equipment should be immediately cleaned with Duroproof Solvent.

TILING, TOPPING OR TOP COATING

Generally not covered, although membrane may be covered with drainage cloth and pebbles, ensuring not to damage membrane.

SAFETY & PRECAUTIONS

ATC is solvent based. The use of solvent resistant gloves and goggles (against splashes) are recommended. Use in ventilated areas. If spraying, in confined areas the use of self contained breathing apparatus is recommended. If swallowed do not induce vomiting, give plenty of water to drink. Seek urgent medical advice. If in eyes, flush thoroughly with clean water, holding open lid to ensure any trapped product may be flushed away. If on skin, remove contaminated clothing and wash skin with soap and water.

If inhaled, unlikely due to viscosity of the product, remove person to fresh air and apply artificial respiration if required and seek urgent medical attention. Product is flammable when wet. Keep away from all sources of ignition. Ensure adequate ventilation. Vapours may collect in low lying areas.

DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.