DUROTECH

Duroseal Superflex 25

Low Modulus MS Polymer Sealant

Duroseal Superflex 25 is a one component, high performance sealant based on advance MS Polymer Technology. It is Solvent, Silicone and isocyanates Free and Non-staining for natural stones applications. It has an excellent UV, weather and temperature resistance. It has excellent adhesion over a wide variety of substrates and is paintable with most common industrial paints. This sealant has been specifically formulated as a non staining sealant and for application to difficult substrates associated with modern facade construction.

ADVANTAGES

- Non staining including Hydrophobic staining
- Good primerless adhesion on many common construction substrates
- Damp surface tolerant
- Low dirt pick up
- Excellent adhesion to a wide variety of substrates
- High movement accommodation
- High UV and aggressive atmosphere resistance
- Anti Fungus / Mildew resistant
- Comprehensive colour range
- Environmentally friendly
- Excellent low temperature gunnability
- Improved gun and tooling characteristics

APPLICATIONS

- For sealing joints to building facades where: -
- High movement is anticipated
- Non staining is a requirement
- Prestige finish is important
- Extreme weather conditions are expected
- Ideal for connection and expansion joints in building.

TECHNICAL INFORMATION

Curing System	Moisture Curing
Colour	White / Black / Grey / Buff (Special colour on request)
Density Approx.	1.50 g/mL
Skin over time	35 - 60 minutes
Curing time @ 23°C/ 50% RH	2 – 3 mm / 24 hr
Elongation at break (ASTM D412)	> 700%
Shore A Hardness (ASTM C661)	20 – 30
VOC content	< 3%
Application Temperature	5°C to 40°C
Service Temperature	-30°C to 100°C
M A F	30%

SPECIFICATIONS

- BS EN ISO 11600-F-25LM
- ASTM C 920
- ASTM C 1248 for Non Staining
- Manufactured under ISO 9001

SURFACE PREPARATION

Ensure that all surfaces are clean, dry, and free from all loose dirt, dust, laitance, oil, grease or any other contaminants, which may impair adhesion. Metal surfaces should be cleaned and degreased. For a neat finish, apply masking tape and remove it before sealant has skinned over.

APPLICATION

Cut tip off cartridge / sausage with a sharp knife. Cut nozzle at 45° angle to desire bead-width and apply to substrate with cartridge gun. Firmly extrude the sealant into slot ensuring complete contact with joint faces. Tooling time is 30 minutes, tack free time is 35 - 60 minutes. The sealant should be tooled shortly after application before skin forms to ensure good contact with joint substrates.

Uncured sealant can be cleaned up with mineral spirits. Use approved backing material for joints over 10mm deep.

LIMITATION

Duroseal Superflex 25 should not be:

- Used for areas subject to continuous chlorinated water immersion, such as swimming pools, spas etc.
- Constant immersed in salt water.
- Used for PE, PP, Teflon, Neoprene and bituminous surfaces.
- Used for glazing applications.
- Painted with alkyd resin paint because it will inhibit the curing of the paint.
- Used in trafficable joints greater than 10mm width

PAINTING

Duroseal Superflex 25 may be over-painted with water based paints, however due to the large number of coatings available, it is advisable to carry out a compatibility test before application. For alkyd paints a suitable water based undercoat must be used.

Paint Type	Suitability
Water based emulsion paint	OK
Water based primer sealer	OK(If over coating with other paints check suitability)
Water based undercoat	OK
Water based top coat	OK
Alkyd resin based paint	Use water based undercoat first
Traditional solvent	Use water based undercoat first
Traditional oil based paint	Use water based undercoat first
Traditional exterior	Use water based gloss paint undercoat first
Cellulose based auto paint	OK
P U based auto paint	OK

COVERAGE

The coverage below is the approximate linear meter coverage per pack size (600ml):

Joint Size	6 mm x 6 mm	10 mm x 10 mm	20 mm x 10 mm
Estimated Length	17.2 meter	6.8 meter	3.5 meter

Formula: (W x D x L) ÷ 1000 = litre, where W = Width (mm) D = Depth (mm) L = Length (meter)

SAFETY PRECUATION

Uncured adhesive / sealant causes skin and eyes irritation upon contact.

- Avoid contact with eyes, skin and mouth.
- In case of contact with eyes, flush with water immediately for 15 minutes. If irritation persists, seek medical attention.
- Keep out of reach of children. Use in well ventilated areas.

PACKING

Duroseal Superflex 25 is supplied in 600ml Al foil Sausage packed in boxes of 20 and 280 ml plastic cartridge packed in boxes of 25.

STORAGE

Store in a dry and cool place with temperature below +30°C. Use within 12 months from date of production.

DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | 1300 791 177 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.