PRODUCT DATA SHEET

DUROSEAL HYBRID 40

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Duroseal Hybrid 40 is a one component, gun-grade, Non-sag, moisture-cure advanced polymer sealant designed to skin and cure rapidly. This high performance product is designed with outstanding UV resistance and long term durability.

FEATURES

- Paintable
- Single component & Convenient Packing
- Excellent adhesion without Priming
- Highly resistant to sea water, diluted acids and alkalis.
- Odourless
- UV Resistant/ Fast Curing
- Low VOC

USES

- Sealant is designed to seal construction joints.
- To seal waterproof rivet seams and roof rails.
- To seal perimeter joints around windows and doors.
- Sealing corner moldings, fabricated roof-lap seams, bumper assemblies and body-to-cab joints in motor homes. Sealing door hinges, skylights and pot holes.
- Sealing Air conditioning equipment, flashing and gutters.

ADVANTAGES

- Flexible, excellent weather ability
- Easy to gun, Easy to tool
- Cures to a tough, durable, elastic consistency with
- Excellent cut and tear resistance
- Paintable, non-sticky after cure

TECHNICAL SPECIFICATION

Physical Properties	Test Method	Typical Value
Specific Gravity @ 25 ◦C, g/ml	ASTM D1475	1.40 – 1.44
Skin over time @ 25 ◦C, Minutes	-	20 - 25
Tack Free Time @ 25 ◦C, Minutes	ASTM C679	30 - 50
Flow (sag or slump)	ASTM C639	Non-Sag
Depth cure per day, mm	-	<2
Shrinkage,%	-	<5
VOC, (g/L)	USEPA Method 24	<25
Tensile Strength, N/mm²	ASTM D412	1 – 1.5
Elongation at break , %	ASTM D412	600-700
Hardness : Shore A	ASTM D2240	27 - 33
Joint Movement Capability, %	ASTM C920	±50
Peel Strength on concrete, N	ASTM C794	>30
Effects of Accelerated Ageing @ 300 hrs. UV exposure	ASTM C793	No deterioration
Application Temperature (°C)	-	+5 to +40
Service Temperature, (°C)	-	-20 to +80

PACKAGING

600ml sausage, 20 sausages per carton

COLOURS

- Grey
- Off-white, white, black (made to order)

SINCE 1977

EXPANSION JOINT DESIGN

Duroseal Hybrid 40 may be used in any joint designed in accordance with accepted architectural/engineering practices. Joint width should be at least 4 times anticipated movement, and not less than (5mm).

While applied on an expansion joint the depth (D) of the sealant should be equal to the width (W) of the joints that are less than 10mm wide. For wider joints, width to depth ratio should be 2 : 1.

The maximum width of the joint on which Tritosil W70C can be applied is 25mm.
Meter per 600 ml

STORAGE AND SHELF LIFE

C has a shelf life of 12 months when stored in tightly closed original casks, in a dry place at a temperature between +5°C and +25°C

JOINT BACKING

Closed cell hybrid sealant backer rod is recommended as joint backing to control sealant depth and to ensure intimate contact of sealant with joint walls when tooling. Where depth of joint is insufficient for the use of backer rod, an adhesive backed polyethylene tape (bond breaker tape) should be used to prevent three-sided adhesion. All backing should be dry at time of sealant application. Avoid using sharp tools.

YIELD

The following formula is an approximate guideline to calculate foreseen yield for a standard 600ml sausage of Duroseal Hybrid 40.

L = 600 / (W x D)
Where: L = Length of sealant in metres obtained per cartridge.
D = Depth of the joint in mm
W = Width of the joint in mm

Joint Width (mm	10	12	15	20	25
Joint Depth (mm)	6	8	8	10	12
Joint Length (m)/600 ml	10	6.2	5	3	2

SUBSTRATE PREPARATION

Surfaces must be sound, clean, and dry. All release agents, dust, loose mortar, laitance, paints, or other loose particles must be removed. This can be accomplished with a thorough wire brushing, sanding, or solvent washing, depending on the contamination. Triton recommends that surface temperatures be below 40˚C at the time the sealant is applied.

PRIMING

DUROSEAL HYBRID 40 typically adheres to common construction substrates without primers; however,mockup or field adhesion test can be performed on the actual materials
being used on the job to verify the need for a primer.

CLEAN UP

Excess sealant and smears adjacent to the joint interface can be carefully removed with xylene or mineral spirits before the sealant cures. Any utensils used for tooling can also be cleaned with xylene or mineral spirits.

APPLICATION STANDARDS

DUROSEAL HYBRID 40 meets or exceeds the requirements of the following specifications:
ASTM C 920 Type S, Grade NS, Class 50.

APPLICATION

is easy to apply with conventional caulking equipment. Ensure that the backer rod is friction fitted properly. Mask the sides of the joint with masking tape prior to filling for a cleaner finish. Fill the joint completely with a proper width-to-depth ratio and tool to ensure intimate contact of sealant with joint walls. Dry tooling is always preferred, although xylene can be used in limited amounts to slick the spatula if needed following the initial dry tooling.

FOR OPTIMUM PERFORMANCE

- In cool or cold weather, store container at room temperature for at least 24 hours before using.
- DUROSEAL HYBRID 40 can adhere to other residual sealantsin restoration applications. For best results always cleanthe joint as advised in the Surface Preparation section of this data guide. A product field adhesion test for DUROSEAL PU within the specific application is always recommended to confirm
- adhesion and suitability of the application.

  When using DUROSEAL HYBRID 40 in a traffic-bearing horizontal joint, use a firmer joint backing, such as neoprene rodor polyethylene foam block, and recess the surface of sealant (3mm - 6mm).

- Pursuant to accepted industry standards and practices, using rigid paints and/or coatings over flexible sealants can result in a loss of adhesion of the applied paint and/or coating, due to the potential movement of the sealant however, should painting and/or coating be desired it is required that the applicator of the paint and/or coating conduct on-site testing to determine compatibility and adhesion.

- Proper application is the responsibility of the user. Field visits by Durotech personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

LIMITATIONS

- Do not apply over damp or contaminated surfaces.
- Do not use DUROSEAL HYBRID 40 as a structural (load transferring) sealant

STORAGE AND SHELF LIFE

DUROSEAL HYBRID 40 C has a shelf life of 12 months when stored in tightly closed original casks, in a dry place at a temperature between +5°C and +25°C

CURING TIME

DUROSEAL HYBRID 40 generally cures at a rate of 2mm per day at 25°C and 50% relative humidity.Lower temperatures and humidity will extend curing time.

HEALTH AND SAFETY

Use only with adequate ventilation. Prevent contact with skin, eyes and clothing. Wash thoroughly after handling. Avoid breathing vapors. DO NOT take internally. Use impervious gloves, eye protection if the TLV is exceeded or used in a poorly ventilated area. Always utilize the accompanying SDS for information on Personal Protective Equipment (PPE) and health Hazards.

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet