PRODUCT DATA SHEET

DUROSPRAY HA300

TWO-PACK WATERPROOFING MEMBRANE

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Durospray HA300 is a high performance, hand-applied, >99% VOC-free, quick curing two-pack elastomeric polyurethane waterproofing membrane. Durospray HA300 is suitable for foot traffic.

FEATURES

- Monolithic membrane – no lap, wield or seams
- >99% VOC-free, complies with Green Star requirements
- UV resistant but not light stable
- Quick curing time
- High resistance to puncture
- High resistance to stagnant water
- High elongation
- No reinforcement required
- Excellent crack bridging capability
- Elastomeric behaviour: remains flexible at low temperatures
- Available in grey colour

USE AREAS

It is designed for waterproofing diverse parts of a building including balconies, terraces, podium decks, wet areas, roofs, etc.

Grades

Self-levelling grade:

High flow and low thixotropy. Ideal for horizontal surfaces when a nice finish is required. Easy application by brush, roller or notched trowel.

Green Roofs grade:

Root penetration resistant membrane, perfect for green roofs issues. Root penetration testing has to be carried out.

TYPICAL PHYSICAL PROPERTIES

Composition	Two-Pack >99% VOC-free Polyurethane
Mix Ratio (w/w)	100:23.3
Specific Gravity(g/cm^3)	1.05-1.10
Service Temperature (C)	-20 to +80
Curing time (Hours)	3-5 hours depending on T°
Pot life(minutes)	20-35 minutes depending on T°
Shelf life(months)	12
Non volatiles (%)	>99%
Tensile Strength(MPa)	5.2
Elongation (%)	310
Hardness (Shore A)	90
Angle Tear Strength (kN/m)	31
UV resistance	No chalking, no cracking but yellowing
Re-coating interval(days)	Maximum 24 hours after application
Recommended substrate temperature (°C)	+5 to +35
Recommended relative humidity (%)	Between 20 and 90

SINCE 1977

APPLICATION

Durospray HA300 is supplied in pre-dosed kits.

Preparation:

Surface must be clean, sound, smooth and dust-free as well as oil-free.

A compatible primer, such as Durorime LV452, Duroprime MV601 or Durobond 2K Epoxy should be applied to ensure the adhesion of the membrane to the substrate as well as preventing outgassing from the concrete.

In the case of high porosity, wet concrete (humidity >5%) or in any doubt, it is recommended to use a hydro-epoxy primer. Compatibility of the primer with the membrane must be checked prior to application.

Application:

Durospray HA300 Part B must be mixed thoroughly for at least 2-3 minutes using a paint mixer at 300-400RPM. Once mixed pour part B into part A and mix both components for a further 3 minutes at 300-400 rpm. An excess of mixing will generate aeration within the membrane.

Durospray HA300 can be applied with a brush or a roller or a notched trowel to the desired thickness.
A spike roller can be used to eliminate air bubbles if required.

Durospray HA300 can be applied between 0.5 and 3 mm thick.

Durospray HA300 can be subject to light traffic after 24 hours.
Vehicle traffic is not permitted on Durospray HA300 without the application of a top coat.

Durospray HA300 can be recoated with a top coat. Check with your Durotech Representative the compatibility before application.

Recoating instructions:

In normal conditions, Durospray HA300 can be recoated with another layer of Durospray HA300 after 5 hours and within 24 hours. In case of rain or if the recoating interval was exceeded, come back to the substrate by grinding.

Coverage

1 coat of 1000 g/m^2 is required to achieve a 1 mm dry film thickness

Clean-up

Reusable tools should be cleaned carefully with Xylene or MEK before curing.

Shelf life

Shelf life of sealed Durospray HA300 in its original container is 12 months.

Always store closed containers in cool, ventilated and dry location, away from heat and oxidizing agents. Do not store in direct sunlight or in temperatures below 10°C or above 35°C.

Safety

Please refer to the Material Safety Data Sheet (MSDS) for personal protection, proper handling and storage.

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet