PRODUCT DATA SHEET

DUROTECH DUROCEM PU TC

Topcoat for polyurethane concrete

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Durotech Durocem PU TC is specially designed as a topcoat for Durotech Durocem PU SL and TR flooring systems. It can also be used as a stand alone concrete coating. It has excellent chemical resistance properties. Durotech Durocem PU TC is used to seal in the aggregate in a broadcast polyurethane cement topping. It is also used as a non-slip coating over a Durotech Durocem PU SL smooth base.

CHEMICAL RESISTANCE

CHEMICAL	CHEMICAL
Acids	
Acetic acid	20%
Boric acid	4%
Chromic acid	10%
Citric acid	20%
Formic acid	5%
Hydrochloric acid	10%
Lactic acid	25%
Phosphoric acid	25%
Sulphuric acid	25%
Alkalis	
Ammonium hydroxide	5%
Peroxide	10%
Potassium hydroxide	10%
Sodium hydroxide	50%
Other	
Diesel	
Petrol	
Sugar solutions	

Features

- Adjustable rate of cure – Accelerator can be added for low temperature cure.
- Chemical Resistant – excellent resistance to acids and alkalis.
- Low VOC Emission – environmentally friendly.
- Low Odour – does not taint food.
- Matt Finish.
- Colour Availability – available in a range of colours.

TYPICAL APPLICATIONS

- Food & Beverage production facilities
- Factory production floors
- Stock & Plant rooms
- Workshops

TECHNICAL INFORMATION

Mixing ratio by weight - corresponds to packaging in kg	
A : B **A : B : C**	1 : 1 1 : 1 : 2
Pot life @ 25 °C	approx. 20 minutes
Application temperature (min. 3 °C above dew point)	10 to +30 °C
Overcoating @ 25 °C	12 -24 hours
Cure time @ 25 °C:	
Foot traffic **heavy traffic** **chemical exposure**	12 - 20 hours 2 days 7 days
Adhesive strength	> 1.5 MPa
Temperature resistance	-20 °C to 120 °C
Hardness (Shore D)	80 (7 days)

SURFACE PREPARATION

Concrete Coating

The concrete substrate should be firm, clean and dry. The compressive strength of the surface must be a minimum of 25 MPa and the surface tensile strength a minimum of 1.5 Mpa.

New concrete is to be a minimum of 7 days old. The surface of the concrete will need to be mechanically prepared by either diamond grinding, shot blasting or scarifying. All weak and loose material, surface laitance, contaminants and coatings or curing compounds must be completely removed. It is preferred that the prepared surface has a profile to ensure both excellent chemical and mechanical adhesion.

MIXING

- Mix components A and B together for 30 seconds. Add aggregate bag and mix until a smooth consistency without lumps is achieved, 1-2 minutes should be sufficient.

APPLICATION GUIDLINES

Do not apply over damp or wet surfaces. Do not apply where there is water vapour transmission

Non-Slip Finish

- Apply to substrate and broadcast anti-slip aggregate into the wet surface and allow to cure. The size of the aggregate that is used depends on the level of slip resistance required.
- Apply a second coat of Durotech Durocem PU TC to seal the surface. Keep in mind not to flood the surface so much as you lose the slip resistant effect of the
- Durotech Durocem PU TC may also be applied over either a self-levelling or broadcast Durotech Durocem

COVERAGE

The following information is a guide only.

Over a smooth surface the expected coverage is about 4.5 sqm/kit
Pigment - coverage 1 per kit

SAFETY PRECAUTIONS

Wear gloves, eye protection, masks and overalls during mixing and application.

PACKAGING

Durotech Durocem PU TC is a 3 component product consisting of a resin, hardener and blended fillers.

Component breakdown:

Part A	1 kg
Part B	1 kg
Part C Aggregate	2 kg

The mixed product will yield approximately 2.75 litres.

LIMITATIONS

Durotech Durocem PU TC is an industrial flooring finish which may discolour on exposure to UV light from the sun or an artifical source. The severity of discolouration is dependant on colour choice. Any such discolouration has no effect on the performance of the product.

SHELF LIFE

This product has a shelf life of 12 months from date of manufacture, stored under shelter at 25°C in original un-opened container.

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System
ISO 14001 Environment Certified System
ISO 45001 Health and Safety Certified System