PRODUCT DATA SHEET

DUROMASTIC P15 UV

High performance high strength Australian made rapid cure waterproofing membrane formulated for both internal and external applications whilst exhibiting, excellent adhesion and outstanding elongation.

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Duromastic P15 UV is a High performance high strength Australian made P15 cure waterproofing membrane formulated for both internal and external applications whilst exhibiting, excellent adhesion and outstanding elongation. Duromastic P15 UV is compliant to AS/NZS 4858:2004 and AS 4654.1:2012, satisfying the requirements of AS3740:2010 and AS4654.2:2012 for waterproofing to internal and external areas.

FEATURES

- Fast drying
- Water based, easy clean up
- Complies with AS:4858
- Very low VOC
- No reinforcing fabric required
- Extends to over 400%UV stable
- No re-emulsification

USE AREA

- Internal & External Wet Areas
- Balconies & Decks
- Bathrooms, Kitchens, Laundries
- Roof Tops
- Tanks

SURFACE

- Concrete and concrete blockwork
- Masonry, brick
- Fibrous cement sheeting

TECHNICAL INFORMATION

Elongation at break	400%
Recoat Time at 25°C, 50% R.H.	1 – 2 hours
Full Cure at 25°C, 50% R.H.	3 days
Minimum screed & Tiling time at 25°C, 50% R.H.	24 hours
Minimum application temperature & RH	10°C minimum maximum 85% RH
Resistance to UV	Good durability under prolonged exposure
Tensile strenght	1.75 mpa

PACKAGING

- 4 Litre
- 18 Kg

SINCE 1977

PREPARATION

- Remove dirt, dust, loose particles, old adhesives and coatings, grime and unsound concrete.
- Wash down and remove oily, dirt contaminated, or powdery surfaces with dilute detergent, then rinse and dry thoroughly.
- Allow new concrete and render to fully cure. Ensure all sheeting and surfaces are dry, stable, sound and fully secured. Fix any rising damp problems beforehand.
- For timber floor surfaces use fibre cement sheeting as a replacement orcover. Remove or flatten all sharp concrete edges, mortardroppings, screw and nail heads.
- Prime wall and floor surfaces with Durotech Primer.
- Use Durotech Etch primer for PVC fittings.
- For larger cracks, expansion joints, floor and pipe penetrations wall or hob junctions, seal neatly with Duroseal Sealant 12mm angle fillets to all internal corners, Penetrations and joints.

PRIMING

Duromastic P15 UV membrane must be applied onto primed surfaces: Duroprime ARW – for general porous vertical and horizontal building surfaces. Brush or roller apply primer to total surface area at a minimum coverage of 1 litre per 6m² and allow drying for 30 minutes or once wet film dries to a clear transparent coating. Duromix WBE HIBUILD epoxy primer – for surfaces with residual moisture or subject to rising damp. Refer to individual data sheets for specific coverage details. Allow respective primer to dry for a minimum 24 hours before applying membrane. Renders, Screeds, Damp Surfaces (MC <15%): Apply 1coat of Duromix WBE HIBUILD EPOXY as a primer in accordance with Product Data Sheet to the prepared substrate. Concrete Block Water Tanks: Apply 2 coats of Duormix WBE HIBUILD EPOXY as a primer in accordance with Product Datasheet to the prepared substrate.

Note: Refer to data sheets for above primers before using.

APPLICATION

- Do not apply externally if rain is expected presently.
- Do not apply below 10 C or above 30 C externally.
- Ensure that the primer coat is completely dry.
- Apply evenly and check for missed areas and pin-holes.
- Apply further coats from cross directions after 1 to 2 hours.Check drying times before application.
- Do not apply as one coat.
- Install Durotech Joint Band to wall/floor joints and corners, where greater movement is anticipated or a premium solution is required.
- Good air flow and warmth will speed drying.

NOTE: Allow each coat to sufficiently dry before proceeding to the next coat. Thicker coats will take longer to dry.

APPLICATION RATES

Use Area	Wet Film Thickness (per coat)	Coats Required	Dry Film Thickness
Wet Area Walls	1.0mm	1	0.6mm
Wet Area Floors	0.8mm	2	1.0mm
External Areas	0.8mm	2	1.0mm
Water Tanks	1.0mm	2	1.2mm
Roof tops	1.0mm	2	1.2mm

SUBSTRATES

Durotech Duromastic P15 UV is suitable for use over the following substrates:

- New Concrete - Cured for min. 28 days
- Fibre Cement Sheets - Walls (min. 6mm)
- Renders and Screeds - Cured for min. 7 days
- Compressed Fibre Cement (min. 15mm)
- Plasterboard walls - Wet area grade only (min. 10mm)
- Plywood (PAA) - Wet area grade only

NOTE: Do not apply Durotech Duromastic P15 UV to any concrete that has received concrete curing compounds.

COVERAGE

The coverage of Duromastic P15 UV will depend upon the type of substrate and its condition. When prepared and primed in accordance with the instructions above, the following average coverage rates should be expected.

Internal Wet area walls	0.6mm Dry film thickness 1.0 litre/ m², 15m² per pail
Internal Wet area floors	1.0mm Dry film thickness 1.5 litre/ m², 10m² per pail
Bathroom (internal walls & floor combined	Average 1.13 litre/ m², 13m² per pail
External floors, Walls, Basement, Roofs & Decks	1.0mm Dry film thickness 1.5 litre/ m², 10m² per pail
Masonry water tanks (walls & floor)	1.2mm Dry film thickness 1.8 litre/ m², 8m² per pail
Exposed Roof Tops	1.2mm Dry film thickness 1.8 litre/ m², 8m² per pail

BOND BREAKING

Apply Duroseal PU25 or Duroseal 40FC to form smooth,12mm angle fillets to all internal corners, penetration sand joints. Allow to cure prior to application of Duromastic P15 UV. Alternatively, install Durotech Joint Band to wall/ floor joints and corners, where greater movement is anticipated or a premium solution is required.

CLEAN UP

Before drying, clean up with water. Scrape off when dry or use paint stripper for spot removal.

SHELF LIFE

12 months at 20°C in original unopened containers.
Protect from freezing

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au



"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IVQA
ISO 1400 FC Environment Certified System IVQA
ISO 45001 Health and Safety Certified System IVQA