PRODUCT DATA SHEET

DUROPOXY CLEAR CAST 100

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Epoxy based general purpose casting system for processing and curing at room temperature.
Product highlights include: low initial viscosity, good thermal stability at temperature 20°C to 70°C, and good mechanical properties.

TECHNICAL INFORMATION

Resin

Viscosity at 25°C	mPa.s	500 – 1000
Specific Gravity at 25°C	g/cm³	1.1 – 1.15
Colour		Clear liquid

Hardener

Viscosity at 25°C	mPa.s	200-260
Specific Gravity at 25°C	g/cm³	1.0-1.05
Colour		Clear liquid

Handling Properties

Mix Ratio	Resin : Hardener by weight	100 : 40
Usable life	(200g mix) @ 15°C	60-70 minutes Peak Exotherm 110°C
	(200g mix) @ 25°C	30-40 minutes Peak Exotherm 125°C
	(200g mix) @ 35°C	10-20 minutes Peak Exotherm 150°C

Handling Precautions

This resin and hardener combination has been formulated with the objective of being as safe as possible, however, in common with most epoxy resins and hardeners, consistent skin contact with uncured materials may cause irritation of sensitive skins. For this reason, contact with the uncured materials should be avoided at all times.

Materials will become very hot during curing (up to 160°C). Do not touch in under the specified demoulding time or burns to the skin may occur. Our testing is based on a 200g sample size. Larger amounts of resin and hardener will get hotter during curing. Ensure that casting is done in a well ventilated area as some vapors will be released at these curing temperatures. Please refer to the Materials Safety Data Sheet for more information.

Storage

Store the components in a dry place at 18 - 25°C, in tightly sealed original containers.

DUROTECH INDUSTRIES

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet