DUROTECH

DURO MASTIC™ AC NON SLIP

DURO MASTIC™ Non Slip is a modified DURO MASTIC™ AC membrane with added fine grade aggregate to provide a non-slip, textured surface for decks and other exposed areas. Suitable for light foot traffic.

PRINCIPLE CHARACTERISTICS

- Single component
- Non-toxic, water clean up.
- Permanently flexible
- Seamless
- Environmentally friendly
- UV stable
- Fungal and algae resistant
- Easily maintained
- Low odour

USE AREA

- Foot trafficable roof decks
- Balconies and decks with or without tiling

PACKAGING

- 15 Litre

TECHNICAL INFORMATION

Colour	Grey, Graphite. Other colours available on application
Dry time	2 hours @20ºC
Re-coat	4-6 hours
Coverage	2 coats each at 1 litre/m²[1.0m²/litre]
Dry film thickness	1.2mm total
Solids content	57% by volume
Elongation	+80%
Shelf life	12 months, unopened @ 20ºC

PREPRATION

All surfaces shall be sound, clean, dry and free of release curing agents and other contaminants. Check adhesion by applying to a test area. Concrete is to be at least 28 days old, dry and free of voids and other surface defects. Make sure painted surfaces are sound and remove any chalking by pressure spray or light detergent wash. Roof decks should be properly drained for long-term serviceability of DURO MASTIC™ NON SLIP. A 12mm fillet of neutral cure silicone sealant is to be applied at all surface junctions.

- Concrete: Remove laitance or unsound concrete by water blast or mechanical means. Fill all porous or honeycombed concrete with appropriate and approved material.
- Compressed Fibre cement sheets to be installed as per manufacturers specification and all joints to be sealed.
- Movement cracks and cold joints to be cut out and filled with neutral cure silicone sealant, then overlaid with DURO MASTIC™ NON SLIP reinforced with 140mm min. wide bandage.

Note: All sheet joints to have an expansion gap. Seal all surface joints and screw holes with neutral cure silicone sealant, and further seal joints and spread across a min. 20mm of the surface and overlay with tape and DURO MASTIC™ NON SLIP reinforced with 140mm (min.) wide bandage. Note: All sheet joints to have an expansion gap. Seal all surface joints and screw holes with neutral cure silicone sealant, and further seal joints and spread across a min. 20mm of the surface and overlay with tape and DURO MASTIC™ NON SLIP reinforced with 140mm (min.) wide bandage.

PRIMING

Prime surfaces with one or more coats of Duromix™ WBE at a rate of 4-6 m^2/ litre [0.25-.017 litres/m^2]. Allow to dry 24 hours @ 25°C before overcoating with Duro Mastic™ Non Slip.

APPLICATION

To the prepared surface, apply a first coat of DURO MASTIC™ NON SLIP by brush or roller at approximate rate of 1.0 litres/m^2 per coat. Apply the second coat in the same direction to provide an even texture and finish. Check when dry and apply a further coat to give a total DFT of 1.2mm.

PRECAUTIONS

Do not apply above 30°C or below 10°C ambient temperature. Be sure coating is cured before contact with water. Wash equipment with water before dry. Provide sufficient expansion and contraction control joints. This is particularly important with FC sheet flooring. Clean periodically to maintain surface and re-coat when necessary.

CLEANUP

Use fresh water before material has set. Remove cured material with mineral turps.





DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.