14 Essex Street, P.O Box 5092, Minto, NSW 2566
+61 2 9603 1177
+61 2 9475 5059
sales@durotechindustries.com.au
www.durotechindustries.com.au
ABN: 33 738 594 170

DUROTECH
Waterproofing • Sealants • Adhesives

Bathroom rectification Waterproofing Specification

Waterproofing Specification – Wet area shower

Location: The 4 seasons Hotel Sydney CBD

Product Applicator: Saba Tilingg

Suggested Membrane(s) / System(s) for Below Ground wall

1. Duroseal PU (sealant)
2. Repair Mortar
3. Duromix Hibuild Epoxy Primer
4. Duromasitc P15

Scope:

Liquid membranes applied to suitably prepared substrates to form fully bonded seamless, Positive and negative pressure membrane on the positive side against water penetration.

The information provided in this technical bulletin is as correct in detail as possible and is intended to give a fair description of the product and its capabilities. In practice, the substrate and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and that the product is not used beyond its physical limitations. The product is guaranteed providing that it is applied in accordance with the manufacturer's instructions as stated in this data sheet and any relevant Standard or Code, and provided that the building and installation is structurally sound. Durotech terms and conditions of sale apply.

14 Essex Street, P.O Box 5092, Minto, NSW 2566
+61 2 9603 1177
+61 2 9475 5059
sales@durotechindustries.com.au
www.durotechindustries.com.au
ABN: 33 738 594 170

Applications:

Typical applications where the membrane will be used include;

- Non Exposed roofs, decks and balconies
- Internal wet ares

Substrates:

The substrate recommended for this liquid applied, membrane system to
Concrete

Substrate Preparation:

Substrates to which the liquid membrane is to be applied must be structurally sound and free of all contaminants (e.g. laitance, form release agents). All holes/voids filled with cement based patching mortars and all surface protrusions ground flat. Ensure all drainage wastes are fitted with suitable flanges onto which the membrane can be terminated.

Concrete Substrate Checklist:

1. All concrete and masonry should be cured for 28 days.
2. Ensure that all protrusions have been removed and the substrate is clean, dry, and free from laitance, dust, oil, curing compounds and other contaminants. The substrate must not contain any flaky/powdery cement or residues that may affect the membrane adhesion.
3. Voids and honeycomb areas should be patched with a non-shrinking, quick setting grout. Allow the patched/ rendered areas to fully cure.
4. Movement joints should be treated in the appropriate manner.
5. Allow substrate to dry completely.
6. Broom clean substrate.

Concrete finish shall be a light steel trowel followed by a fine hair broom, or equivalent finish.

The information provided in this technical bulletin is as correct in detail as possible and is intended to give a fair description of the product and its capabilities. In practice, the substrate and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and that the product is not used beyond its physical limitations. The product is guaranteed providing that it is applied in accordance with the manufacturer's instructions as stated in this data sheet and any relevant Standard or Code, and provided that the building and installation is structurally sound. Durotech terms and conditions of sale apply.

14 Essex Street, P.O Box 5092, Minto, NSW 2566
+61 2 9603 1177
+61 2 9475 5059
sales@durotechindustries.com.au
www.durotechindustries.com.au
ABN: 33 738 594 170

Treatment of Cracks for Liquid Applied Membrane

Cracks – non-movement and hairline cracks less than 1.5mm may be pre-treated with a 1mm detail coating of the specified membrane 150mm wide centered over the crack. Movement cracks greater than 1.5mm shall be routed out, install a backer rod and fill with Polyurethane sealant then coat with a 1mm detail coat of the specified membrane extending to 75mm either side of the joint.

Prior to applying membranes make sure that the substrate contains less than 7% moisture.

Reinforcement Steel:

In the event of exposed reinforcing steel, the exposed portions of steel shall be ground to expose clean, bright, metal and primed with a suitable Non-Porous Primer.

Drainage:

All drains shall be cleaned and operative. Drain flanges shall be recessed lower than the deck surface. The surface shall be sloped to the drain to Australian standard falls for positive drainage. Non-Porous Primer is required if fittings are PVC or metal.

Priming: (Duromix Hibuild WBE)

Prime floor area using Duromix Hibuild WBE. Dilute 1st coat using 10% water. Apply 2nd coat neat. Allow to dry as per Duromix Hibuild WBE datasheet recommendations.

Liquid Applied Membrane System: (Duromastic P15)

Duromastic P15 is a waterbased flexible membrane coating. This liquid applied membrane is to be applied in a minimum of 2 light coats to achieve the dry film thickness recommended on the product data sheet.

Repair Mortar Rapidset Repair Mortar

Rapid hardening. construction mortar, which can withstand traffic after just 45 minutes and ready for floor coverings after 1 hour. Ideal for filling cracks and holes over a variety of surfaces.

Curing/Drying Time:

Liquid applied membranes require some time to cure and fully harden. Please refer to the individual product data sheets for the recommended curing/drying periods. Membrane Protection is neccesary to ensure no damage is occured during the curing of the membrane.

The information provided in this technical bulletin is as correct in detail as possible and is intended to give a fair description of the product and its capabilities. In practice, the substrate and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and that the product is not used beyond its physical limitations. The product is guaranteed providing that it is applied in accordance with the manufacturer's instructions as stated in this data sheet and any relevant Standard or Code, and provided that the building and installation is structurally sound. Durotech terms and conditions of sale apply.

14 Essex Street, P.O Box 5092, Minto, NSW 2566
+61 2 9603 1177
+61 2 9475 5059
sales@durotechindustries.com.au
www.durotechindustries.com.au
ABN: 33 738 594 170

Film Thickness

Wet film thickness gauges are used to ensure the correct amount of materials is applied to achieve the recommended dry film thicknesses. In some cases, three coats may be required to ensure pinholes are not present through the membrane.

Flood Testing:

When water testing, make sure it is carried out to the relevant Australian standard and allow for the membrane to dry prior to water testing. Allow membrane to dry after removing water. Ensure membrane is dry before applying further coatings or finishing with other coverings.

Care & Maintenance:

Proper care and maintenance will extend the service life of Durotech membranes. Be sure to follow the maintenance regime outlined in the 'Care & Maintenance' instructions. These steps are even more critical in the days following application of the membrane.

- Prior to installation, all reference should be made to current TDS and MSDS as provided by Durotech Industries.
- Visual observations will be conducted on site by a Durotech Industries representative at critical hold points.
- Upon completion of membrane installation and testing, Durotech will issue a 10-year materials warranty made out to the client upon request received in writing from installing contractor.

Any queries, please feel free to contact a Durotech representative on (02) 9603 1177.

The information provided in this technical bulletin is as correct in detail as possible and is intended to give a fair description of the product and its capabilities. In practice, the substrate and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and that the product is not used beyond its physical limitations. The product is guaranteed providing that it is applied in accordance with the manufacturer's instructions as stated in this data sheet and any relevant Standard or Code, and provided that the building and installation is structurally sound. Durotech terms and conditions of sale apply.