PRODUCT DATA SHEET

Enviro 700X

envirosystems
environmentally responsible technology

Low Odour High Performance Polyurethane Waterproofing Membrane

DESCRIPTION

Enviro 700X is an Australian Made, single component, low odour, moisture cured polyurethane elastomer waterproofing system. Enviro 700X, once applied on vertical or horizontal applications, both internally and externally forms a seamless, durable and flexible membrane which protects structures from water penetration.

FEATURES

- Low odour
- Low VOC content
- Australian Made & Designed
- High performance system suitable for a wide range of applications
- User friendly single component liquid
- Seamless & durable
- Immersion tolerant
- Remains flexible at low temperatures
- Chemically resistant
- AS/NZS 4858:2004 Class 3 Approved
- Complies and tested to AS4654.1

TYPICAL USES

Enviro 700X is suitable for use on a variety of substrates including concrete, block, render, timber, CFC, CLT, GRC and steel. Enviro 700X, once applied produces a seamless, impervious, and durable waterproof membrane suitable for industrial, commercial and residential applications.

- Wet Areas
- Podiums
- Basements
- Walls and Floors
- Retaining walls
- Plant rooms
- Bathrooms
- Balconies

PHYSICAL PROPERTIES

Colour	Grey
Tensile Strength	>25 kg/cm2
Elongation	>600%
Shore A Hardness	70±5
Solids Content	90±3%
Tear Strength	>15kg/cm

SUBSTRATE PREPARATION

Surfaces must be clean, dry and free from contamination such as dust, laitance, grease, coatings and curing compounds. Remove all sharp edges including screws, nails and concrete/mortar projections.

Apply Enviro Flex Pro or Enviro Flex FC (and allow to cure), to all joints, cracks etc. prior to the application of Enviro 700X.

Enviro 700X is suitable for use over the following substrates:

- New Concrete - Cured for min. 28 days
- Fibre Cement Sheets - Walls (min. 6mm)
- Renders and Screeds - Cured for min. 7 days
- Compressed Fibre Cement (min. 15mm)
- Plasterboard walls - Wet area grade only (min. 10mm)
- Plywood (PAA) - Wet area grade only
- Enviro HP1200 – (contact Envirosystems for further information)

NOTE: Mechanical abrasion of the substrate is recommended for pedestrian traffic applications.

For further information on substrate preparation or for project specific advice, please consult Envirosystems.
customerservice@envirosystems.com.au

AUSTRALIAN MADE
Australian Designed & Manufactured
Environmentally Responsible Technology
Master Builders Association MEMBER
GREEN ROOFS AUSTRALASIA

PRIMING

Substrate condition and other requirements will dictate primer selection.

Enviro Prime SB or a diluted coat of Enviro 700X (diluted 15% with Thinner No.1 (v/v) can be used to prime dry masonry surfaces such as concrete slabs and renders in non-exposed areas such planter boxes, retaining walls and under tiles.

Enviro Prime P2 or **Enviro Epoxy B-LV** (substrate dependant) is recommended for use when Enviro 700X is used in exposed UV applications or when pedestrian traffic is expected.
Enviro Shield can be used as an alternative primer for damp masonry surfaces in non-exposed and exposed applications.

For non-porous surfaces such as metal and PVC, abrade the surface to be treated before priming with **Enviro Prime ME** and **Enviro Prime 789** respectively. Some building materials such as CFC can be supplied with factory applied water resistant coatings. Care should be taken when waterproofing over these products to mitigate risk of incompatibility.

NOTE: For further information on applications that may require priming or for project specific advice, please consult Envirosystems.
customerservice@envirosystems.com.au

BOND BREAKING

Apply Enviro Flex Pro or Enviro Flex FC to form smooth, 12mm flexible cove to all internal corners, penetrations and joints. Allow to cure prior to application of Enviro 700X. Alternatively, install Enviro Joint Band to wall/floor joints and corners, where greater movement is anticipated, or a premium solution is required.

MIXING

Enviro 700X should be thoroughly mixed with a mechanical mixer at low speed (less than 400 RPM) prior to application.

APPLICATION

Enviro 700X is to be applied using brush, roller or squeegee and is generally applied to the required Dry Film Thickness (DFT) in 2 coats. Please see application rates table.

NOTE: Allow product to cure for 12 hours before recoating. Care should be taken when walking over newly installed Enviro 700X to ensure the membrane is not damaged. If damage occurs, consult Envirosystems Technologies for recommended repair methods.

For further information regarding application of Enviro 700X or for project specific advice please consult Envirosystems.
customerservice@envirosystems.com.au

RECOAT

Enviro 700X can be recoated after allowing the product to cure for at least 12 hours depending on weather conditions.

APPLICATION RATES

Type	Rate WFT	Rate DFT	Number of Coats
External Application	1.6mm	1.5mm	2
Internal Floor Application	1.6mm	1.5mm	2
Internal Wall Application	1.1mm	1.0mm	1-2

NOTE: WFT = Wet Film Thickness
DFT = Dry Film Thickness

WFT Gauges are available from Envirosystems upon request.

OVERCOATING

Direct Tiling – If tiling directly to Enviro 700X, after achieving the required dry film thickness, it is recommended that and additional thin coat of Enviro 700X be applied and broadcast with aggregate at a rate 0.5kg/m² to promote adhesion. Typically, the optimum tiling window is 24-72hrs.

Screed / Mortar Bed – Care should be taken to prevent any damage to the membrane during screed / mortar bed placement. It is the responsibility of the screed / mortar bed installer to determine the design, strength, thickness etc. of screed / mortar bed. Typically, the optimum screed placement window is 24-72hrs.

Below Ground – Areas such as retaining walls, basement walls and planter boxes should be installed as per normal recommendations and allowed to dry for a minimum 24 hrs. Once dry, it is recommended that the membrane be protected before soil placement with corflute and filtered drainage cell ("dimple" drainage or coreflute sheets are not suitable for horizontal applications). Where possible, it is recommended that drainage pipe and aggregate be placed to allow water to freely drain.

Exposed UV Areas – For external use where a non-yellowing aesthetic finish is required, it is recommended that a suitable UV topcoat such as Enviro 800PUR T.C. or 850PUR T.C. be applied. For light pedestrian traffic (maintenance) these UV topcoats can be broadcast with aggregate for a textured slip reducing finish.

Pedestrian Traffic – Refer to the Enviro Trafficable product data sheet for areas where regular pedestrian traffic is expected.

Maintenance Traffic (Pedestrian) – For internal areas that are not exposed to UV such as plant rooms floors, Enviro 700X can be applied and broadcast with aggregate (to required slip resistance) when light maintenance traffic is expected.

Soft & Hard Landscape – When Enviro 700X is installed to areas being covered with hard landscaping materials such as ballast, rocks, stone etc., it is recommended that filtered drainage cell ("dimple" drainage or coreflute sheets are not suitable for horizontal applications) be placed over the cured Enviro 700X prior to hard landscape placement.

COVERAGE

External Application	1.5mm Dry Film Thickness - 1.67 litres/m²
Internal Floor Application	1.5mm Dry Film Thickness - 1.67 litres/m²
Internal Wall Application	1.0mm Dry Film Thickness - 1.12 litres/m²

PACKAGING & COLOURS

Enviro 700X is supplied in 15L drums and is available in Grey.

CURE

Enviro 700X will reach full cure after 7 days.

CLEANING

Enviro 700X should be removed from all tools and equipment, prior to curing with Enviro Thinners No.1. Observe all OH&S and MSDS information pertaining to safe usage and handling of solvents. Cured material can only be removed mechanically.

SHELF LIFE

Enviro 700X can be stored in its original sealed containers for 6 months in controlled environments. During storage, a skin of Enviro 700X may form which is easily removed. This does not affect the performance of the product.

NOTE: Enviro700X is sensitive to airborne moisture. It is preferable to use all contents of container after opening.

HEALTH & SAFETY ADVICE

When using Enviro 700X always provides adequate ventilation and wear appropriate Personal Protection Equipment (PPE) during use. Avoid contact with skin. Avoid breathing vapours. Wear protective eyewear. If inhalation effects occur, remove to fresh air. If discomfort persists, any breathing difficulties occur or if swallowed, seek medical attention. Refer to Safety Data Sheet for full details.

KEEP OUT OF REACH OF CHILDREN

NOTE: Safety Data Sheets are available upon request by emailing customerservice@envirosystems.com.au

We're here to help you!

It is a good idea to keep a journal of your waterproofing job, whether big or small.

- Take pictures at all stages of your work, including preparation
- Record the quantity and description of products used with corresponding batch numbers
- Record dates and times of when you applied products, from start to finish

Please do not hesitate to contact us for any questions you may have.

Envirosystems Technologies Pty Ltd

Address 295 Princes Highway, St Peters NSW 2044
Sydney, Australia
Phone +61 2 8595 8699
Fax +61 2 8595 8660
Email customerservice@envirosystems.com.au
Web www.envirosystems.com.au

ISSUE 1

DATE September 2019

envirosystems
environmentally responsible technology

STATEMENT OF RESPONSIBILITY
The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use of application and no warranty as to accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use.
Note: Field service where provided, does not constitute supervisory responsibility. Suggestions made by Envirosystems Technologies either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Envirosystems Technologies are responsible for carrying out procedures appropriate to a specific application.