PRODUCT DATA SHEET

# KODEX 25LM

Kodex
Sealants & Waterproofing

## DESCRIPTION

Kodex 25LM is polyurethane based one component sealant for construction. Resistance to surface movements.

## APPLICATION FIELD:

It is used at interior and exterior expansions joints in buildings, all vertical & horizontal dilatations between prefabricate elements in high buildings, towers, terrace dilatations, wood, metal-based joints as a joint waterproofing sealant.

## Removal

Wet sealant can be cleaned with ethyl acetate or other suitable solvents. Dry sealant only removed by mechanical applications.

## SPECIFICATIONS:

- Suitable for outdoor usage
- UV resistance
- Paint applicable
- Resistance to different weather conditions (-300C / + 1200C)
- Perfect adhesion
- Create smooth surface

## TECHNICAL INFORMATION

| | |
|---|---|
| **Colour** | White, Grey |
| **Density** | 1.40 gr/cm3 |
| **Working Temperature** | +50C/ + 300C |
| **Shore Hardness** | 25 |
| **Hardness Time** | 24 hours for 2mm |
| **Movement Accommodation Factor** | 25% |
| **Skinning Time** | 60 minutes |
| **Flexibility** | >600% |
| **UV Resistance** | Good |
| **Max. Joint Edge Width** | 4 cm |
| **Shelf Life** | 12 months |

## PACKAGING:

600ml Sausage ..... 20 per carton

## APPLICATION:

Surface preparation: the joint edges must be clean,all oil, dust, dirt, and any other materials that may be used before must be removed. Water affects the Kodex 25LM so joint edges must be dry and Kodex 25LM must protected from water unless the chemical hardness occured. Kodex 25LM can be applied without primer application. Polyethylene wicks must be used for filling to avoid adhesion of sealant to the bottom of joint edges. This gives ability for two way movement. Wick's diameter should bigger than 20-25% of joint edge's diameter. Width and deep of the edge should not be less than 5mm. Up to 15mm; the width size of the edge should be equal to its deep size. For wider joint edges, the deep size adjusted to 20-25mm. For hand applications; place the sealant Kodex 25LM into the gun and inject the sealant into the joint without causing any air bubble.

## STORAGE

Kept in sealed drums, storage temperature should be normal room temperature to ensure max shelf life (12 month). Production date is on label.

## HEALTH AND SAFETY:

If it touches with skin wash with water and soap. Do not use the empty packages for the storage of nutriment.

*The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Kodex terms and conditions of sale apply.*

Kodex
Sealants & Waterproofing