Parameter Sheet

# Quartz Grits Q1

| Silica | Color | Humidity |
| --- | --- | --- |
| $SiO_2$ > 99.0% | L 91 min | Max 0.3% |

## Chemical Parameters

| Parameter | Result |
| --- | --- |
| $SiO_2$ | > 99.0% |
| $Na_2O$ | 0.05% max |
| CaO | 0.03% max |
| $Fe_2O_3$ | 0.06% max |
| $K_2O$ | 0.02% max |
| $TiO_2$ | 0.04% max |
| $Al_2O_3$ | 0.1% max |
| L.O.I | 0.1 max |

## Physical Parameters


deep@jadewavesenterprise.com | +91-999-883-5503

| Parameter | Result |
|---|---|
| Color L | 91 min |
| Color a | 1.0 max |
| Color b | 2.5 max |
| Particle size distribution | Size in range > 90%; upper size < 5%; lower size < 5% |
| Black particles / 100 g | 5 |
| Other color particles / 100 g | 5 |
| Humidity | Max 0.3% |

## Available Size Ranges

| Size Range | Availability |
|---|---|
| 0.1-0.4 mm | Available |
| 0.3-0.7 mm | Available |
| 0.6-1.2 mm | Available |
| 1.2-2.5 mm | Available |
| 2.5-4.0 mm | Available |
| 4.0-6.0 mm | Available |
| Custom sizing available | Available |


deep@jadewavesenterprise.com | +91-999-883-5503

## Supply Reference

| | |
|---|---|
| **Forms** | Quartz grits |
| **Packing** | Jumbo bags |
| **Typical use** | Ceramics, glass manufacturing, engineered stone, and mineral systems |
| **HSN code** | 25061020 |


deep@jadewavesenterprise.com | +91-999-883-5503

Parameter Sheet

# Quartz Grits Q2

| Silica | Color | Humidity |
| --- | --- | --- |
| $SiO_2$ > 99.0% | L 90 min | Max 0.3% |

## Chemical Parameters

| Parameter | Result |
| --- | --- |
| $SiO_2$ | > 99.0% |
| $Na_2O$ | 0.05% max |
| CaO | 0.03% max |
| $Fe_2O_3$ | 0.06% max |
| $K_2O$ | 0.02% max |
| $TiO_2$ | 0.04% max |
| $Al_2O_3$ | 0.1% max |
| L.O.I | 0.1 max |

## Physical Parameters


deep@jadewavesenterprise.com | +91-999-883-5503

| Parameter | Result |
|---|---|
| Color L | 90 min |
| Color a | 2.0 max |
| Color b | 3.5 max |
| Particle size distribution | Size in range > 90%; upper size < 5%; lower size < 5% |
| Black particles / 100 g | 15 |
| Other color particles / 100 g | 15 |
| Humidity | Max 0.3% |

## Available Size Ranges

| Size Range | Availability |
|---|---|
| 0.1-0.4 mm | Available |
| 0.3-0.7 mm | Available |
| 0.6-1.2 mm | Available |
| 1.2-2.5 mm | Available |
| 2.5-4.0 mm | Available |
| 4.0-6.0 mm | Available |
| Custom sizing available | Available |


deep@jadewavesenterprise.com | +91-999-883-5503

## Supply Reference

| | |
|---|---|
| **Forms** | Quartz grits |
| **Packing** | Jumbo bags |
| **Typical use** | Ceramics, glass manufacturing, engineered stone, and mineral systems |
| **HSN code** | 25061020 |


deep@jadewavesenterprise.com | +91-999-883-5503

Parameter Sheet

# Quartz Powder

| Silica | Residue | Mesh |
|---|---|---|
| $SiO_2$ > 99.0% | < 1% | 200 / 325 / 400 |

## Chemical Parameters

| Parameter | Result |
|---|---|
| $SiO_2$ | > 99.0% |
| $Na_2O$ | 0.05% max |
| CaO | 0.03% max |
| $Fe_2O_3$ | 0.06% max |
| $K_2O$ | 0.02% max |
| $TiO_2$ | 0.04% max |
| $Al_2O_3$ | 0.1% max |
| L.O.I | 0.1 max |

## Color Profile


deep@jadewavesenterprise.com | +91-999-883-5503

| Metric | Q1 | Q2 |
|---|---|---|
| L | 91 min | 89 min |
| a | 1.0 max | 2.0 max |
| b | 2.5 max | 3.5 max |

## Physical Parameters

| Parameter | Result |
|---|---|
| Particle size distribution | Residue < 1% |
| Humidity | Max 0.3% |
| Available mesh | 200 mesh BSS (75 microns) / 325 mesh BSS (45 microns) / 400 mesh BSS (38 microns) |
| Custom sizing available | Available |


deep@jadewavesenterprise.com | +91-999-883-5503