EXPORT QUALITY CERTIFICATE

Certificate of Analysis

Executive COA for Quartz Silica

JADE WAVES ENTERPRISE

Jade Waves Enterprise
Ahmedabad, Gujarat, India

PRODUCT

Quartz Silica

Representative sample analysis

AUTHORIZED BY

Deep Mehta

Managing Partner

SILICA (SIO2)
98.07%

MOISTURE
< 0.10%

AFS
42

TECHNICAL ANALYSIS

Representative material specification

Sr No.	Parameters	Unit	Result	Protocol
1	Moisture	%	< 0.10	IS:1918:1966
2	Loss on Ignition	%	0.29	IS:1917:P-1:1991
3	Silica as SiO2	%	98.07	IS:1917:P-3:1991
4	Alumina as Al2O3	%	0.59	By ICP
5	Iron as Fe2O3	%	0.30	By ICP
6	Titania as TiO2	%	0.05	By ICP
7	Calcium as CaO	%	0.30	By ICP
8	Magnesium as MgO	%	0.03	By ICP
9	Sodium as Na2O	%	0.01	By ICP
10	Potassium as K2O	%	< 0.01	By ICP
11	Sieve Analysis (-1700 Microns +850 Microns)	%	NIL	IS:1607:2013
12	Sieve Analysis (-850 Microns to +600 Microns)	%	0.07	IS:1607:2013
13	Sieve Analysis (-600 Micron to +425 Micron)	%	15.09	IS:1607:2013
14	Sieve Analysis (-425 Micron to +300 Micron)	%	62.97	IS:1607:2013
15	Sieve Analysis (-300 Micron to +212 Micron)	%	18.57	IS:1607:2013
16	Sieve Analysis (-212 Micron to +150 Micron)	%	1.98	IS:1607:2013
17	Sieve Analysis (-150 Microns to +106 Microns)	%	0.81	IS:1607:2013
18	Sieve Analysis (-106 Micron to +75 Micron)	%	0.33	IS:1607:2013
19	Sieve Analysis (-75 Microns to +53 Microns)	%	0.09	IS:1607:2013
20	Sieve Analysis (-53 Microns)	%	0.09	IS:1607:2013
21	AFS Grain Fineness	No.	42	By calculation

COMMERCIAL REFERENCE

APPLICATION
Glass manufacturing, water filtration media, foundry moulding systems, artificial turf, paints, and construction fillers

FORMS
Grits and powder

TYPICAL GRADE RANGE
SiO2 98-99%; glass-oriented Fe2O3 can be aligned to 150-200 PPM

PACKING OPTIONS
50 Kg bags and jumbo bags

HSN CODE
25061020

INQUIRY CONTACT
deep@jadewavesenterprise.com | +91-999-883-5503