



KROMA EDGE

— BEYOND REFLECTION —



Instruction Manual

About KROMA EDGE

KROMA EDGE utilizes advanced **Self-Organization Technology**, allowing metallic particles to rise to the surface of the coating film and align themselves uniformly. This process enables an unprecedented **mirror-like reflection and deep metallic brilliance**, achieved **solely through painting**, without additional plating or polishing processes.

IMPORTANT NOTICE

Before applying KROMA EDGE, **READ THIS MANUAL CAREFULLY**.

KROMA EDGE is a **two-component coating system (with hardener)** and behaves fundamentally differently from conventional metallic or urethane paints. Failure to follow these instructions **WILL result in coating defects or performance loss**.

Product Components and Lineup

KROMA EDGE Sets

- Mirror Seeds Formula
- Binder
- Hardener
- Thinner

KROMA EDGE Dedicated TOPCOAT CLEAR

- Clear Base
- Hardener
- Thinner

Mixing Ratio and Mixing Procedure (Important)

KROMA EDGE - Mixed by Weight (RECOMMENDED) (140g Kit Example)

- **Add Reducer to Binder** : Add **100% Reducer (50 g)** to **KROMA EDGE Binder (Resin) 50 g**.
- **Add Hardener** : To the **100 g mixture** above, add **20% Hardener (20 g)**.
- **Mix Thoroughly** : Thoroughly stir the total **120 g mixture** until fully uniform.
- **Add Mirror Seeds Formula**: **Mirror Seeds Formula (metallic filler)** settles easily. Shake well before use, then add **20% (20 g)** to the **100 g mixture** prepared in Step 1, and mix thoroughly.

Mix Ratio by Parts

BINDER : REDUCER : HARDENER : MIRROR SEEDS FORMULA = 5 : 5 : 2 : 2

MIX TIP: Mix **Binder and Reducer 1:1 (50/50)**. Then Mix your **Reduced Binder at 5:1:1 with Hardener & Mirror Seeds**, using an appropriate mixing cup with a 5:1:1 ratio column.

⚠ WARNING:

Improper mixing ratios or insufficient agitation **WILL cause uneven metallic alignment and coating failure.**

Expanded Batch Mix Chart by Weight					Approximate Fluid Ounces
Total Mixed	Binder	Reducer	Hardener	Mirror Seeds	Reference
14 g	5 g	5 g	2 g	2 g	0.5 oz
28 g	10 g	10 g	4 g	4 g	1.0 oz
42 g	15 g	15 g	6 g	6 g	1.5 oz
56 g	20 g	20 g	8 g	8 g	2.0 oz
70 g	25 g	25 g	10 g	10 g	2.5 oz
84 g	30 g	30 g	12 g	12 g	3.0 oz
98 g	35 g	35 g	14 g	14 g	3.5 oz
112 g	40 g	40 g	16 g	16 g	4.0 oz
126 g	45 g	45 g	18 g	18 g	4.5 oz
140 g	50 g	50 g	20 g	20 g	Small kit 5 oz
210 g	75 g	75 g	30 g	30 g	7.0 oz
280 g	100 g	100 g	40 g	40 g	9.5 oz
350 g	125 g	125 g	50 g	50 g	12 oz
420 g	150 g	150 g	60 g	60 g	Medium kit 15 oz
560 g	200 g	200 g	80 g	80 g	19 oz
700 g	250 g	250 g	100 g	100 g	24 oz
840 g	300 g	300 g	120 g	120 g	28 oz
980 g	350 g	350 g	140 g	140 g	33 oz
1,120 g	400 g	400 g	160 g	160 g	38 oz
1,260 g	450 g	450 g	180 g	180 g	Large kit 45 oz

KROMA EDGE Dedicated TOPCOAT CLEAR

Clear Base : Hardener = 10 : 1

Thinner: **70–100% relative to the clear base**

⚠ WARNING:

Improper mixing ratios or insufficient agitation **WILL cause uneven metallic alignment and coating failure.**

Painting Specifications

KROMA EDGE Item	Mixing Amount	Mixing Order	Recommended Film Thickness	Drying Conditions	Pot Life
KROMA EDGE Binder (Resin)	50g	1	25 ± 5 µm / 1 mil	140°F: 1 hour or longer 68°F: 24 hours or longer	3 hours
Reducer	50g	2			
Hardener	20g	3			
Mirror Seeds Formula (Metallic Filler)	20g	4			

- **Recommended Film Thickness: 25 ± 5 µm (0.025 ± 0.005 mm) / 1 mil**
- **Pot Life:** 3 hours / Limited working time after mixing binder and hardener
- **Forced Drying:** 140°F for a minimum of 1 hour, followed by approximately 24 hours at room temperature. (See below for more details)

KROMA EDGE Dedicated Topcoat Clear Item	Mixing Amount	Recommended Film Thickness	Drying Conditions	Pot Life
Base (Main)	100g	25 ± 5 µm / 1 mil	140°F: 1 hour or longer 68°F: 24 hours or longer	4 hours
Hardener	10g			
Reducer	70 – 100g			

- **Recommended Film Thickness: 25 ± 5 µm (0.025 ± 0.005 mm) / 1 mil**
- **Pot Life:** 4 hours / Limited working time after mixing binder and hardener

Materials must be mixed strictly in the order indicated above.
Failure to follow the specified mixing order may result in improper performance.

Spray Gun Requirements

Application Area	Recommended Spray Gun Nozzle	Recommended Air Pressure
4 in x 4 in	Airbrush nozzle Ø 0.3–0.5 mm	25-45 PSI
20 in x 20 in	Spray gun nozzle Ø 0.6–1.4 mm	See Spray Gun Mfg. Rec.
40 in x 40 in	Spray gun nozzle Ø 1.4–2.0 mm	See Spray Gun Mfg. Rec.

The coating film **MUST remain wet until spraying is completed.**

When painting large objects:

- Increase nozzle size as required
- Control spray time and film thickness carefully

⚠ Large-area applications **REQUIRE advanced spraying skill and proper workflow** to maintain mirror quality.

Ideal Environmental Conditions and Application Settings

Ambient Temperature & Humidity	68°F or higher, humidity has no significant effect	At temperatures below 68°F, solvent evaporation slows down, which may cause pinholes on the coated surface.
Atomization Pressure	Higher pressure is preferable	Atomization pressure affects surface smoothness. KROMA EDGE tends to level less easily; finer atomization improves smoothness.
Material Output (Fluid Volume)	Lower output is preferable	Reducing output and achieving finer atomization improves smoothness. However, if output is too low, drying becomes too fast and may interfere with self-organization, resulting in reduced gloss.
Gun Speed	Slower speed is preferable	Faster gun movement produces a thinner film, which may negatively affect self-organization and reduce gloss.
Gun Movement Technique	Apply continuously until all coated areas are dry	When coating large areas, drying times differ between the first and last sections. Adjust application to prevent mist from the final passes from settling on areas coated earlier.
Film Thickness	15–30 μm / 0.6 - 1.2 mil	Below 15 μm , the substrate may influence smoothness. Above 40 μm , sagging may occur.
Setting Time	Until solvents evaporate and gloss appears	When applying KROMA EDGE in two or more coats, always apply the next coat only after self-organization is complete and sufficient gloss has developed.

Surface Preparation and Application Conditions

- Apply over a fully cured suitable primer/sealer (for best results), base coat or clear coat then sand with **#600–#1000 grit**. *A **Gloss Black** is **NOT Required** for this product!
- **DO NOT apply** KROMA EDGE over absorbent substrates or insufficiently cured base coats, primers or clear coats. This **WILL cause shrinkage and loss of surface smoothness**.
- Degrease using **silicone remover or isopropyl alcohol only**. Wipe away any residue
- Use **low-lint, low-oil wipes**.
- Always strain paint using an ultra finer **~5 μm strainer or Yoshino paper**. To eliminate contamination or speckling

CRITICAL APPLICATION RULES

✗ DO NOT

- Apply mist coats
- Apply tack coats

✓ MUST

- Apply **one continuous wet coat**

⚠ WARNING:

Failure to apply a full wet coat **WILL result in pinholes, fish eyes, or loss of reflectivity.**

Film Thickness Control

⚠ WARNING:

Film thickness exceeding **40 µm (0.040 mm / 1.6 mil)** **WILL cause cracking, sagging, or coating failure.** Strict film thickness control is mandatory.

Environmental Conditions

- **Minimum application temperature: 68°F**

⚠ Applying below this temperature **WILL delay solvent evaporation and WILL cause pinholes or surface defects.**

Coating Film Structure

After application, the coating consists of:

1. Binder layer
2. Reducer (thinner) layer
3. Mirror Seeds Formula layer

Immediately after spraying, the surface may appear slightly cloudy.

As solvent evaporates, **self-organization occurs**, forming the metallic mirror layer.

DO NOT disturb the surface during this process.

Number of Coats

- Standard method: **ONE COAT ONLY**
- A second coat is **ONLY permitted** when:
 - Self-organization is fully completed
 - Metallic film is completely formed
 - A uniform mirror surface is visible

⚠ Applying additional coats prematurely **WILL permanently damage the chrome-like surface.**

- **Maximum coats: 3**

Rework Procedure

- Remove coating with appropriate thinner
- Allow full drying
- Reapply from the beginning

If defects persist after 2–3 coats:

Drying Process

AIR CURE:

- Cure for a minimum of **36 hours**
- Try not to **exceed 48 hours**
- After 48 hours **use adhesion promoter**

FORCE CURE:

- Wait **5 minutes** after mirror has formed
- Force dry at **140-160°F for 1-2 hours**
- Then dry **24 hours** at room temperature

**Adjust your cure times based on environmental conditions accordingly. Temp / Humidity / Air Movement*

Topcoat Clear Application

⚠ WARNING – CLEAR COAT APPLICATION

- Apply clear **ONLY** after **KROMA EDGE** is fully cured
- Applying clear too early **WILL soften the resin layer and WILL cause permanent cloudiness or distortion**
- Slight cloudiness immediately after clear application is normal and will recover as curing progresses

⚠ **ONLY KROMA EDGE Dedicated Topcoat Clear is approved.**

Use of non-approved clear coats constitutes **improper application.**

Shelf Life

This product **MUST be used within 3 months** after opening.

Key Technology Advantage

Unlike conventional chrome-like coatings, KROMA EDGE's metallic layer cures while remaining firmly bonded to the substrate.

This prevents metallic particle lifting during clear coating and **maintains high reflectivity even after topcoat application.**

DISCLAIMER

KROMA EDGE performance is guaranteed **ONLY** when applied strictly in accordance with this instruction manual.

The manufacturer & distributor assume **no responsibility** for defects caused by improper surface preparation, application outside recommended conditions, or use of non-approved materials.

Troubleshooting

Issue	Cause	Corrective Action
Gloss gradually decreases during continuous application	Mirror Seeds Formula settled in the cup	Stir periodically or apply while continuously agitating the paint to prevent Mirror Seeds Formula from settling.
	Pot life was exceeded	Mirror Seeds Formula begins its pot life once mixed with Binder or other components. Mix immediately before application.
Poor gloss / pinholes appear	Insufficient application volume (insufficient amount for proper alignment of Mirror Seeds Formula)	Apply KROMA EDGE wet and increase film thickness sufficiently.
	Mist from the second coat remained on the first coat after film formation	After film formation of the first coat, apply the second coat wet and evenly over the entire surface.
Sagging and cracking occur on vertical or inclined surfaces	Excessive film thickness (40 µm or more)	Keep film thickness below 40 µm and adjust the number of coats and application conditions to achieve proper appearance.
Slight haze appears after KROMA EDGE application	Forced drying was performed before self-organization was completed	Always allow self-organization to complete and the surface to become mirror-like, then wait approximately 5 minutes before forced drying.
Poor surface smoothness after drying	Insufficient atomization of spray	Increase atomization pressure and increase material output.

Distributed in the USA by:
COAST AIRBRUSH

Placentia, CA U.S.A
714-635-5557

kustom@coastairbrush.com
www.coastairbrush.com