

KROMA EDGE

— BEYOND REFLECTION —

KROMA EDGE Dedicated Topcoat Clear

○ Product Composition and Product Lineup

KROMA EDGE Dedicated Topcoat Clear 180 SET

Paintable area: approx. 1.5 m²

(Total mixed amount: 378 g)

- Clear main agent: 180 g
- Hardener: 18 g
- Thinner: 180 g

KROMA EDGE Dedicated Topcoat Clear 900 SET

Paintable area: approx. 6 m²

(Total mixed amount: 1,890 g)

- Clear main agent: 900 g
- Hardener: 90 g
- Thinner: 900 g

KROMA EDGE Dedicated Topcoat Clear 3600 SET

Paintable area: approx. 24 m²

(Total mixed amount: 7,560 g)

- Clear main agent: 3,600 g
- Hardener: 360 g
- Thinner: 3,600 g

○ Mixing Ratio

Clear main agent : Hardener = 10 : 1

Thinner: 70-100% of the clear main agent amount.

KROMA EDGE

— BEYOND REFLECTION —

KROMA EDGE Dedicated Topcoat Clear

KROMA EDGE Dedicated TOP COAT CLEAR	Mix Ratio	Recommended Film Thickness	Drying Conditions	Pot Life
Main agent	100 g	15 ± 2 µm	60°C: 1 hour or more 20°C: 24 hours or more	4 hours
Hardener	10 g			
Thinner	70-100 g			

Note: Film thickness: 15 ± 2 µm (0.015 ± 0.002 mm)

Note: Pot life is the usable time after mixing the main agent and hardener.

○ Painting Process and Precautions

After KROMA EDGE has completely dried, finish with the topcoat clear.

Apply the tack coat / dust coat of topcoat clear as a fine mist as much as possible, evenly over the entire surface.

Apply it thinly so that the chrome-like surface is only slightly wetted, and check that no defects such as fisheyes are occurring.

Note: If the particles in the tack coat are too coarse, they may affect the surface texture / gloss of the topcoat.

After the tack coat, allow an interval of approximately 5 minutes, then apply the full coat of topcoat clear.

Apply enough material to bring out sufficient gloss on the surface and to ensure the particles from the tack coat are fully buried.

Because this clear has good flow, apply while watching carefully for runs caused by excessive film build.

After painting, check the surface texture. If the surface has an orange-peel texture, or if you want to ensure additional clear film thickness, allow it to dry to the touch and then apply another coat to restore gloss.

If topcoat clear is applied while KROMA EDGE is insufficiently dried, the solvent in the topcoat clear can penetrate into the KROMA EDGE resin layer and soften the coating film.

KROMA EDGE

— BEYOND REFLECTION —

KROMA EDGE Dedicated Topcoat Clear

○ Painting Process and Precautions - Continued

This may cause fine surface roughness or cloudiness on the chrome-like surface. Always allow KROMA EDGE to dry thoroughly before applying the topcoat.

Even when KROMA EDGE has been thoroughly dried, the finish may appear slightly cloudy immediately after topcoat clear application.

However, when using KROMA EDGE Dedicated Topcoat Clear, brightness will gradually recover as drying progresses. Allow sufficient drying time after clearcoat application.

KROMA EDGE Dedicated Topcoat Clear is a clear with excellent drying characteristics.

After forced drying at 60°C for 1 hour, followed by approximately 30 minutes of natural drying, it hardens to a level suitable for polishing.

Drying conditions will vary depending on the environment, so dry as thoroughly as possible.

Topcoat clear: use of the dedicated product is recommended. If a non-dedicated clear is used, depending on compatibility such as solvent strength, the KROMA EDGE resin layer may soften and cloudiness may occur.

If you want to further increase surface strength, the recommended method is to apply the dedicated topcoat clear, scuff the surface after it has cured, and then apply your own clear over it.

Use this product within 3 months after opening.

Key Point!

With conventional chrome-like paints, the metal layer is not sufficiently hardened. When topcoat clear is applied, the influence of the resin causes the metal layer to lift, the particle alignment collapses, and cloudiness occurs.

However, KROMA EDGE uses a highly adhesive dedicated resin that cures while strongly bonding the painted object and the metal layer. As a result, even when topcoat clear is applied, the particles do not lift, the alignment of the metal layer is maintained, and high brightness can be preserved.