

## Project summary:

Project No: P00083  
Evaluation date: 07/03/2016  
Evaluated by:  
Material:  
Sample No:

Standard: ASTM E 112  
Method: Automatic  
No of images: 1  
Mean Grain Size: 16.00  
Checked by:

## Order:


Order No:  
Description:

## Acquisition parameters:

Objective: EC Epiplan 100x/0.8 H M27  
Camera: AxioCam1 Cc1\_2  
Contrast Method: Brightfield Refl.light  
Scaling: 0.0933 Micrometer /Pixel

Comment:

## Grain Size Distribution over all images



Results image 1



Mean Grain Size: 16.00

## Grain Size distribution %

00	0	0.5	1.0	1.5	2.0	2.5	3.0	3.5	4.0	4.5	5.0	5.5	6.0	6.5	7.0	7.5
0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00

8.0	8.5	9.0	9.5	10.0	10.5	11.0	11.5	12.0	12.5	13.0	13.5	14.0	Standard
0.00	0.00	0.09	0.09	0.09	0.18	0.09	0.35	0.80	0.53	1.15	0.71	95.93	ASTM E 112

Grain Size Distribution



Original image




Image with Annotations