



Chicago Bronze

Cast Right. Machine Tight. Since 1980.

Alloy CuAl10Fe5Ni5-C (EN CC333G)

Composition (wt.%)		Mechanical Properties	
Element	Wt.%	Property	Value
Cu	78.00%	Density	7650 kg/m ³
Al	10.00%	Hardness (BHN)	180
Fe	5.00%	UTS	700 MPa
Ni	5.00%	Yield (0.2%)	360 MPa
		Elongation	12 %
		Machinability	Fair (rating 2)

Applications	Standards
Plain & flanged bearings (SAE 660 class), thrust washers, gears, pump components.	ASTM B271 ASTM B505 ASTM B584

CHICAGO BRONZE ENGINEERED CASTINGS LLC

11417 Irving Park Road (IL-19), Suite B-3-6, Franklin Park, IL, 60131
dersan@chicago-bronze.com · www.chicago-bronze.com

Values are typical. Verify against relevant ASTM/AMS standards. © Chicago Bronze.