Material (model)	Young's Modulus (GPa)			
	Reported	Identified	Numerical	Damping
Rigur, vertical (jumper)	1.9 ± 0.2	1.66	0.65	1.64E-04
Rigur, horizontal (jumper)	1.9 ± 0.2	2.06	0.81	1.40E-04
DM4825, horizontal (plant)	1.2 ± 0.3	1.57	0.72	2.55E-04
TangoBlackPlus (jumper)	(2±1)E-04	6.32E-04	4.625E-04	9.10E-02