"SUMIRESIN EXCEL" CRM-1076DJ-G

Electrical conductive die attach paste

T E C H N I C A L D A T A S H E E T

Characteristics

- *Good Adhesion and Lower Modulus at High Temp*
- *Better Dispensability with Oven Fast Cure Property*

Typical Properties

Item		unit	CRM-1076DJ-G	Test method	Test condition
Appearance		-	Silver color		Visual checking
Filler type		-	Silver		
Filler content		Wt %	75	CR-M-3268	
Specific gravity		-	3.5	CR-M-3264	
Viscosity-1		Pa.s (PS)	17.0 (170)	CR-M-001	E-type viscometer @2.5rpm
Thixotropic index-1		-	3.8	CR-M-001	E-type viscometer 0.5rpm/2.5rpm
Viscosity-2		Pa.s (PS)	7.5 (75)	CR-M-031	Brookfield viscometer @5.0rpm
Thixotropic index-2		-	5.6	CR-M-031	Brookfield viscometer 0.5rpm/5.0rpm
Water Extracted	Na+	ppm	3	CR-M-020	Ionic Impurity measurement equipment PCT 125°C20hrs
	Cl-		30		
Volume resistivity		Ohm-cm	1E-03	CR-M-3265	Mili-ohm meter @RT
Mount strength	RT	N/2x2mm (gf/2x2mm)	49 (4970)	CR-M-3267	Die shear tester LF:Ag plated Cu Chip:2x2mm
	@250°C		12 (1220)		
Elastic modulus	RT	MPa (kgf/mm^2)	10000 (1020)		DMA -100^300°C (5°C/min), 10Hz
	@250°C		100 (10)		
Tg		°C	60	CR-M-010	TMA -100^300°C (10°C/min)
CTE	Alpha-1	ppm	50	CR-M-010	
	Alpha-2		130		
Moisture absorption		%	0.4		Electric balance 85°C/85%/72hrs
Thermal conductivity		W/mK	0.9		Laser-flash method @RT

Cure & Storage

Typical cure condition : Ramp 30 min to 175°C + Hold 30min at 175°C in Oven
Ramp 30 min to 150°C + Hold 45min at 150°C in Oven

Shelf life : 6months (Store at -15°C), 12months (Store at -40°C)

Pot life : 24hrs (Store at 25°C)
48 hours within 25% increase in viscosity

TYPICAL, NOT GUARANTEED PROPERTIES

Dec. 2011, rev6