"SUMIRESIN EXCEL" CRM-1076NS

Electrical conductive die attach paste

T E C H N I C A L D A T A S H E E T

Characteristics

- *High MSL on Ni-Pd/ Au frame*
- *Mid Thermal conductivity*

Typical Properties

Item		unit	CRM-1076NS	Test method	Test condition
Appearance		-	**Silver color**		Visual checking
Filler type		-	**Silver**		
Filler content		Wt %	**80**	CR-M-3268	
Specific gravity		-	**4.0**	CR-M-3264	
Viscosity-2		Pa.s (PS)	**10.0 (100)**	CR-M-031	Brookfield viscometer @5.0rpm
Thixotropic index-2		-	**5.5**	CR-M-031	Brookfield viscometer 0.5rpm/5.0rpm
Water Extracted	Na+	ppm	**2**	CR-M-020	Ionic Impurity measurement equipment PCT 125°C20hrs
	Cl-		**11**		
Volume resistivity		Ohm-cm	**2E-04**	CR-M-3265	Mili-ohm meter @RT
Mount strength	RT	N/2x2mm (gf/2x2mm)	**40 (4060)**	CR-M-3267	Die shear tester LF:Ag plated Cu Chip:2x2mm
	@250°C		**12 (1220)**		
Elastic modulus	RT	MPa (kgf/mm^2)	**10000 (1020)**		DMA -100^300°C (5°C/min), 10Hz
	@250°C		**600 (60)**		
Tg		°C	**100**	CR-M-010	TMA -100^300°C (10°C/min)
CTE	Alpha-1	ppm	**45**	CR-M-010	
	Alpha-2		**95**		
Moisture absorption		%	**0.25**		Electric balance 85°C/85%/72hrs
Thermal conductivity		W/mK	**2**		Laser-flash method @RT

Cure & Storage

Typical cure condition	:	Ramp 30 min to 175°C + Hold 30min at 175°C in Oven
Shelf life	:	6months (Store at -20°C), 12months (Store at -40°C)
Pot life	:	24hrs (Store at 25°C)

TYPICAL, NOT GUARANTEED PROPERTIES

Feb. 2024, rev4