Modeling internal defects in conductive materials using electric potential measurements

Dia Avalur*, Nitika Kishore, and Anika Tokala

Science & Engineering Magnet Program, Manalapan High School, Englightown, NJ 07726 USA

(Dated: January 29, 2026)

In this project, a numerical model was developed to study how electric potential behaves inside a conductive material and how internal defects can affect its electrical response. The material was represented as a two-dimensional grid, where each grid corresponds to an electric potential. Using basic principles of electrical conduction, the system was modeled under steady-state conditions and solved numerically using a finite-difference approach to Laplace's equation. Boundary conditions were applied by setting one side of the grid to a high potential while the other sides were grounded. After getting a steady-state solution, an internal defect was introduced by blocking a small region of the grid to simulate an insulating flaw. The resulting potential distributions were compared before and after the defect was added. The results showed that the presence of an internal defect caused noticeable changes in the potential pattern. These findings suggest that electrical measurements taken at the surface of a conductive object can give information about internal features, which supports the use of electrical methods or non-destructive testing.

I. INTRODUCTION

Electrical conduction in a material is determined by the relationship between electric field, current flow, and electric potential, as described by Ohm's law [1]. Variations in electric potential create an electric field, and this drives current through a conductive medium [3]. Charge is conserved and does not accumulate within the material at steady state. This leads to an equation for the potential, known as Laplace's equation. To computationally study this behavior, the conductive region can be represented as a 2D grid with uniform spacing. Here, each grid point corresponds to the electric potential at that specific location. Boundary conditions are applied by fixing the potential on certain edges of the grid, such as holding one side at a high potential while keeping the other sides grounded [3]. Solving Laplace's equation on this grid would produce the steady state potential distribution and form the basis for analyzing how the internal features can change the system's electrical response.

II. NUMERICAL METHOD

To model the electric potential inside the conductive region, Laplace's equation was solved using a finite-difference method on a 2-dimensional grid [2]. The region was evenly divided into grid points, with each point representing the electric potential at that place. Boundary conditions were applied by fixing the potential along the edges of the grid, with one side held at a higher potential than the rest.

In a steady-state conductive material, no charge accumulates within the region because all charge is conserved. The continuity equation expresses this condition:

$$\nabla \cdot \mathbf{J} = 0, \qquad (1)$$

where J is the current density. Current density and electrical field are related through Ohm's law,

$$\mathbf{J} = \sigma \mathbf{E}, \qquad (2)$$

and the electric field is related to the electric potential by

$$\mathbf{E} = -\nabla V. \qquad (3)$$

These relationships combine, assuming the material has uniform conductivity, giving Laplace's equation:

$$\nabla^2 V = 0, \qquad (4)$$

This equation controls the electric potential throughout the conductive region. On the grid, this was done by setting each interior point equal to the average of its four surrounding points. The process was repeated until the potential value stopped changing and was stabilized.

III. COMPUTATIONAL MODEL

The conductive material was represented using a two-dimensional grid. The grid consists of a 50x50 array, with the left boundary held at a high potential and the other boundaries grounded. Each point on the grid corresponds to the electric potential at that location, and the grid as a whole acts as a simplified model of the material. This allows the electric behavior of the system to be studied numerically instead of analytically.

Boundary conditions were applied by fixing the potential values along the edges of the grid. One side of the grid was set to a high potential to represent an applied voltage, while the remaining sides were set to ground. These fixed boundaries remained constant throughout the course of the simulation, while the interior grid points were free to update.

The potential values at the interior points were iteratively updated based on their surrounding neighbors until the grid itself reached a steady state. This steady-state solution represents how the electric potential would distribute itself throughout the material under the applied boundary conditions. By modifying the grid, such as introducing an internal blocked region to represent a defect, changes in the overall electrical response of the system can be observed. The computational grid and boundary conditions used in this model are shown in Figure 1.

Figure 1. Computational Grid and Boundary Conditions



IV. PROCEDURES

First, the basic physical principles controlling electrical conduction were identified. Ohm's law was used to relate current flow to the electric field, and the electric field was related to electric potential. Since charge does not accumulate in a steady-state system, these relationships combine and produce Laplace's equation, which describes how electric potential behaves inside a uniform conductive material.

To model this behavior computationally, the conductive material was represented using a Python program as a two-dimensional square grid. The grid was implemented as a 50x50 NumPy array, where each element corresponds to the electric potential at a specific location in the material. Boundary conditions were applied by directly assigning fixed potential values to the grid edges. One side of the grid was set to a high potential in order to represent an applied voltage, while the other sides were set to zero to represent ground. These boundary values were held constant throughout the simulation.

The interior poinrs of the grid were solved

using an iterative finite-difference method. In the beginning, the potential at every interior point was updated to equal the average of its four closest neighboring points. This update was performed using nested loops in the code, while skipping the boundary points so their values stayed fixed. The update process was repeated for several thousand iterations until the potential value changes became negligible, which indicated that a steady-state solution was reached.

Once the baseline solution was obtained, an internal defect was introduced into the model. This defect was represented by choosing a small square portion near the center of the grid and stopping those points from being updated during the iteration process. In the code, this was handled using a conditional statement that excluded the defect section from the averaging step. This region behaved as an insulating flaw within the material.

Lastly, the simulation results were visualized using Matplotlib. Heatmaps were generated to show the steady-state potential distribution for both the intact material and the material containing the defect. A difference plot was also created by subtracting the baseline potential grid from the defect grid. This showed how the defect changed the overall potential distribution.

V. RESULTS

After running the simulation, the electric potential across the grid settled into a smooth pattern from the high-voltage side toward the sides that are grounded. This is what we expect from a solution to Laplace's equation, and it showed that the numerical method was working correctly. The potential values stopped changing after multiple iterations, indicating that the system had reached a steady state. This electrical potential distribution obtained from the simulation is shown in Figure 2.

Figure 2. Steady-State Poyential Distribution (No Defect)



When a defect was added by blocking a small portion of the grid, the potential pattern changed. The values around the defect were distorted, and thisdisturbance spread outward toward the grid edges. The resulting electric potential distribution with the defect present is shown in Figure 3.

Figure 3. Potential Distribution With Internal Defect



Comparing the boundary values before and after adding the defect showed noticeable differences. This suggests that changes in the material can be detected by only looking at measurements taken along the surface.

VI. DISCUSSION

The results of this simulation show that internal changes within a conductive material can influence the electrical behavior observed at its surface. Even though the defect was located in the grid, its presence still altered the potential near the boundaries. This is important because it means that information about the interior of a material can be inferred without directly accessing it, which is the main idea behind non-destructive testing [4].

The distortion caused by the defect was not limited to the immediate area around it. Instead, the effect spread outward and affected the overall potential pattern. This suggests that electrical measurements taken at the surface are sensitive to internal features. Even when those features are not visible or are relatively small.

Even though this model is simplified, it captures the behavior of steady-state electrical conduction. The fact that a basic grid-based simulation is able to show these effects support the idea that electrical probing can be a useful tool for detecting internal mistakes. More detailed models could likely improve accuracy, but the trends observed are consistent with the expected physical behavior.

VII. LIMITATIONS

This model uses many simplifying assumptions that limit how closely it represents a real physical system. The simulation is two-dimensional, while real conductive objects are three-dimensional, which means that some effects present in real materials are not captured here. The conductivity of the material is also assumed to be uniform, even though real materials can have variations that affect current flow. Also, the defect is represented as a completely blocked region, which is a simplified way of modeling an internal flaw. Lastly, the grid resolution is limited, so very detailed or small figures may not be accurately represented. These limitations are illustrated in Figure 4, which shows that the effect of the defect appears as a broad change in the potential rather than a defined feature.

Figure 4. Difference in Electric Potential Due to an Internal Defect



VIII. CONCLUSION

This project showed that a simple numerical model can still reveal meaningful information about how electricity behaves in a conductive material. By modeling the material as a grid and solving for the steady-state potential, it became clear that internal changes, like an insulating defect, can affect the electrical behavior seen at the surface. Even with a basic setup, the defect caused noticeable distortions in the potential pattern, especially near the boundaries. This supports the idea that electrical measurements taken at the surface can be used to learn about what is happening inside a material. Overall, this model provides a clear example of how numerical methods can be used to explore non-destructive testing concepts in a straightforward and effective way.

IX. ACKNOWLEDGEMENTS

DA developed the computational model, implemented the numerical simulation, and performed the analysis of the results. NK helped with developing the numerical approach, helped test and verify the simulation results, and contributed to editing and revising the written sections. AT supported the project by reviewing the model setup, helping with interpretation of the results, and providing feedback during the writing process.

X. REFERENCES

[1] R. D. Knight, Physics for Scientists and Engineers: A Strategic Approach, 4th ed. Pearson, 2017.

[2] W. H. Press, S. A. Teukolsky, W. T. Vetterling, and B. P. Flannery,
Numerical Recipes in C: The Art of Scientific Computing, 2nd ed., Cambridge University Press, 1992.

[3] J. D. Jackson, Classical Electrodynamics, 3rd ed., John Wiley & Sons, 1999.

[4] M. H. Loke, J. E. Chambers, D. F. Rucker, O. Kuras, and P. B. Wilkinson,
"Recent developments in the direct-current geoelectrical imaging method," Journal of Applied Geophysics

---

XI. APPENDIX A

This appendix contains the Python code used to generate the numerical simulations shown in this report. The code solves Laplace's equation on a two-dimensional grid using a finite-difference method, applies the boundary conditions described in the methods section, and produces the potential maps shown in Figures 2, 3, and 4. NumPy was used for numerical calculations and Matplotlib was used for visualization.

```
import numpy as np
import matplotlib.pyplot as plt

# ----------------------------
# Settings (change if needed)
# ----------------------------
N = 50        # grid dimensions: N x N
ITERATIONS = 5000   # number of relaxation iterations
V_HIGH = 1.0     # high potential boundary value
V_GROUND = 0.0    # grounded boundary value

# Defect settings (square block in the center)
DEFECT_HALF_WIDTH = 4 # defect will be (2*half_width + 1) by (2*half_width + 1)

# ----------------------------
# Helper: apply boundary conditions
# ----------------------------
def apply_boundary_conditions(V: np.ndarray) -> None:
    """
    Left boundary set to high potential.
    Other boundaries grounded.
    """
```

```
 V[:, 0] = V_HIGH     # left = high
    V[:, -1] = V_GROUND   # right = ground
    V[0, :] = V_GROUND    # top = ground
    V[-1, :] = V_GROUND   # bottom = ground

# ----------------------------
# Solver: finite difference relaxation (Gauss-Seidel style)
# ----------------------------
def solve_laplace(N: int, iterations: int, defect_mask: np.ndarray | None = None) -> np.ndarray:
    """
    Solves Laplace's equation on an N x N grid using iterative neighbor-averaging.
    If defect_mask is provided, True cells are treated as "blocked" (not updated).
    """
    V = np.zeros((N, N), dtype=float)
    apply_boundary_conditions(V)

    for _ in range(iterations):
        # Update interior points
        for i in range(1, N - 1):
            for j in range(1, N - 1):
                if defect_mask is not None and defect_mask[i, j]:
                    continue # blocked region (defect)

                V[i, j] = 0.25 * (
                    V[i + 1, j] + V[i - 1, j] +
                    V[i, j + 1] + V[i, j - 1]
                )

        # Re-apply boundaries each iteration just to be safe
        apply_boundary_conditions(V)

    return V


# ----------------------------
# Make defect mask
# ----------------------------
def make_center_defect_mask(N: int, half_width: int) -> np.ndarray:
    """
    Creates a boolean mask with a square defect near the center.
    True = defect (blocked), False = normal update.
    """
    mask = np.zeros((N, N), dtype=bool)
```

```
c = N // 2
    mask[c - half_width : c + half_width + 1, c - half_width : c + half_width + 1] = True
    return mask


# ----------------------------
# Plot helpers
# ----------------------------
def save_figure1_grid_setup(filename: str, N: int) -> None:
    grid = np.zeros((N, N))
    plt.figure(figsize=(6, 6))
    plt.imshow(grid, cmap="gray")
    plt.axis("off")
    plt.title("2D Grid and Boundary Conditions", pad=20)

    # Labels (matches your paper figure)
    plt.text(N/2, -3.5, "High Potential", ha="center", fontsize=11)
    plt.text(N/2, N + 2.5, "Ground", ha="center", fontsize=11)
    plt.text(-4.5, N/2, "Ground", rotation=90, va="center", fontsize=11)
    plt.text(N + 3.5, N/2, "Ground", rotation=90, va="center", fontsize=11)

    plt.savefig(filename, dpi=300, bbox_inches="tight")
    plt.close()

def save_heatmap(V: np.ndarray, filename: str, title: str, cmap: str) -> None:
    plt.figure(figsize=(6, 6))
    plt.imshow(V, cmap=cmap)
    plt.colorbar(label="Electric Potential")
    plt.title(title)
    plt.axis("off")
    plt.savefig(filename, dpi=300, bbox_inches="tight")
    plt.close()


def save_difference_map(deltaV: np.ndarray, filename: str, title: str) -> None:
    plt.figure(figsize=(6, 6))
    plt.imshow(deltaV, cmap="bwr")
    plt.colorbar(label="Change in Electric Potential")
    plt.title(title)
    plt.axis("off")
    plt.savefig(filename, dpi=300, bbox_inches="tight")
    plt.close()
```

```
# ----------------------------
# Main run
# ----------------------------
def main():
    # Figure 1 (diagram)
    save_figure1_grid_setup("Figure1_GridSetup.png", N)

    # Baseline solution (no defect)
    V_base = solve_laplace(N, ITERATIONS)
    save_heatmap(
        V_base,
        "Figure2_BaselinePotential.png",
        "Steady-State Potential Distribution (No Defect)",
        cmap="inferno"
    )

    # Defect solution
    defect_mask = make_center_defect_mask(N, DEFECT_HALF_WIDTH)
    V_defect = solve_laplace(N, ITERATIONS, defect_mask=defect_mask)
    save_heatmap(
        V_defect,
        "Figure3_DefectPotential.png",
        "Potential Distribution with Internal Defect",
        cmap="inferno"
    )

    # Difference map (Figure 4)
    deltaV = V_defect - V_base
    save_difference_map(
        deltaV,
        "Figure4_PotentialDifference.png",
        "Difference in Electric Potential Due to an Internal Defect"
    )

    print("Done. Generated Figure1–Figure4 PNG files.")


if __name__ == "__main__":
    main()
```