


NABUK

COLOR BODY GLAZED PORCELAIN STONEWARE

20"x20"

7^{5/8}"x20"

RAGNO  USA



R1C8 Nabuk BI

20"x20"

R1Q1 Nabuk BI*

20"x20"

R1Q5 Nabuk BI*

7^{5/8}"x20"



R1C9 Nabuk BG

20"x20"

R1Q2 Nabuk BG*

20"x20"

R1Q6 Nabuk BG*

7^{5/8}"x20"



R1D0 Nabuk MA

20"x20"

R1Q3 Nabuk MA*

20"x20"

R1Q7 Nabuk MA*

7^{5/8}"x20"



R1D1 Nabuk AN

20"x20"

R1Q4 Nabuk AN*

20"x20"

R1Q8 Nabuk AN*

7^{5/8}"x20"



R1N7 Belt L. BI

1^{1/4}"x20"



R1N8 Belt L. BG

1^{1/4}"x20"



R1N9 Belt L. MA

1^{1/4}"x20"



R1P0 Belt L. AN

1^{1/4}"x20"



R1R3 Clay F. BI

7^{5/8}"x20"



R1R4 Clay F. AN

7^{5/8}"x20"



R1R5 Clay FR. BI

1"x20"



R1R6 Clay FR. AN

1"x20"



Field Tile



Wall Tile



Rectified Tile



Decorative Tile



Trim Available



Suitable for
Outdoors



Uniform Variation



Frost Resistant



Meets ADA
Recommendations



Abrasion Resistance



C.O.F. (Wet)



C.O.F. (Dry)



SINGLE BULLNOSE



R1Q9 Nabuk BI Bullnose

R1R0 Nabuk BG Bullnose

R1R1 Nabuk MA Bullnose

R1R2 Nabuk AN Bullnose

4"x20"

* Rectified

After installation, be sure no traces of cement or adhesive are left on the tile surface.

TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	6	MOHS SCALE
Breaking Strength	20"x20"	≥ 250 lbf.	≥ 500 lbf.
	7 ^{5/8} "x20"	≥ 250 lbf.	≥ 600 lbf.
Facial Dimension	-3.0 % < Nominal < 2.0 %	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.25 % or +/- 0.8 mm*	Within Standard	C502
Warpage (Flatness)	+/- 0.40 % or +/- 1.3 mm*	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
C.O.F. (Wet)	As Reported	0.60 ≤ COF < 0.70	C1028
C.O.F. (Dry)	As Reported	0.60 ≤ COF < 0.70	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

* Whichever is less

