

REVISION

COLOR BODY PORCELAIN STONEWARE

24"x24"

12"x24"

12"x48"

RAGNO  USA



R4P3 Revision BI
24"x24"
R4Q3 Revision BI
12"x24"
R4P8 Revision BI
12"x48"



R4P4 Revision BG
24"x24"
R4Q4 Revision BG
12"x24"
R4P9 Revision BG
12"x48"



R4P6 Revision RS
24"x24"
R4Q6 Revision RS
12"x24"
R4Q1 Revision RS
12"x48"



R4P5 Revision MA
24"x24"
R4Q5 Revision MA
12"x24"
R4Q0 Revision MA
12"x48"



R4P7 Revision NE
24"x24"
R4Q7 Revision NE
12"x24"
R4Q2 Revision NE
12"x48"



Field Tile



Wall Tile



Modular Tile



Rectified Tile



Decorative Tile



Trim Available



Suitable for
Outdoors



Uniform
Appearance



Frost Resistant



Abrasion Resistance



C.O.F. (Wet)



C.O.F. (Dry)



R5P4 Revision BI
Mosaic
12"x24"



R5P5 Revision BG
Mosaic
12"x24"



R5P7 Revision RS
Mosaic
12"x24"



R5P6 Revision MA
Mosaic
12"x24"



R5P8 Revision NE
Mosaic
12"x24"



R5P1 Nest BI
Insert
12"x48"



R5P2 Nest MA
Insert
12"x48"



R5P3 Nest NE
Insert
12"x48"

TRIMS



R4W8 Revision BI Bullnose
R4W9 Revision BG Bullnose
R4X1 Revision RS Bullnose
R4X0 Revision MA Bullnose
R4X2 Revision NE Bullnose
4"x24"



Contributes to
LEED Credits

TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	6	MOHS SCALE
Breaking Strength	12"x24"	≥ 250 lbf.	≥ 995 lbf. C648
	12"x48"	≥ 250 lbf.	≥ 1450 lbf. C648
	24"x24"	≥ 250 lbf.	≥ 995 lbf. C648
Facial Dimension	-3.0 % < Nominal < 2.0 %	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.25 % or +/- 0.8 mm*	Within Standard	C502
Warpage (Flatness)	+/- 0.40 % or +/- 1.8 mm*	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class III	C1027
C.O.F. (Wet)	As Reported	0.30 ≤ COF < 0.40	C1028
C.O.F. (Dry)	As Reported	0.70 ≤ COF < 0.80	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

* Whichever is less

