

LASTRICATO

GLAZED PORCELAIN STONEWARE

12"x18"

12"x12"

5^{7/8}"x12"

5^{7/8}"x5^{7/8}"

3^{7/8}"x3^{7/8}"

RAGNO  USA



3Y79 Surbo BI

12"x18"

3Y82 Surbo BI

12"x12"

3Y85 Surbo BI

5^{7/8}"x12"

3Y88 Surbo BI

5^{7/8}"x5^{7/8}"

3Y91 Surbo BI

3^{7/8}"x3^{7/8}"



3Y77 Trani BG

12"x18"

3Y80 Trani BG

12"x12"

3Y83 Trani BG

5^{7/8}"x12"

3Y86 Trani BG

5^{7/8}"x5^{7/8}"

3Y89 Trani BG

3^{7/8}"x3^{7/8}"



3Y78 Borriol BR

12"x18"

3Y81 Borriol BR

12"x12"

3Y84 Borriol BR

5^{7/8}"x12"

3Y87 Borriol BR

5^{7/8}"x5^{7/8}"

3Y90 Borriol BR

3^{7/8}"x3^{7/8}"



2X54 Porfido GR

12"x18"

2X51 Porfido GR

12"x12"

2X57 Porfido GR

5^{7/8}"x12"

2X60 Porfido GR

5^{7/8}"x5^{7/8}"

2X80 Porfido GR

3^{7/8}"x3^{7/8}"



2X52 Porfido RS

12"x18"

2X49 Porfido RS

12"x12"

2X55 Porfido RS

5^{7/8}"x12"

2X58 Porfido RS

5^{7/8}"x5^{7/8}"

2X78 Porfido RS

3^{7/8}"x3^{7/8}"



2X53 Basalto NE

12"x18"

2X50 Basalto NE

12"x12"

2X56 Basalto NE

5^{7/8}"x12"

2X59 Basalto NE

5^{7/8}"x5^{7/8}"

2X79 Basalto NE

3^{7/8}"x3^{7/8}"



Field Tile



Wall Tile



Trim Available



Suitable for
Outdoors



Slight Variation



Frost Resistant



Meets ADA
Recommendations



Abrasion Resistance



C.O.F. (Wet)



C.O.F. (Dry)



Contributes to
LEED Credits

TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	8	MOHS SCALE
Breaking Strength	12"x18"	≥ 250 lbf.	≥ 500 lbf.
	12"x12"	≥ 250 lbf.	≥ 655 lbf.
Facial Dimension	-3.0 % < Nominal < 2.0 %	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.50 % or +/- 2.0 mm*	Within Standard	C502
Warpage (Flatness)	+/- 0.75 % or +/- 2.3 mm*	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
C.O.F. (Wet)	As Reported	0.60 ≤ COF < 0.70	C1028
C.O.F. (Dry)	As Reported	0.70 ≤ COF < 0.80	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

* Whichever is less

