




*live inspired*

# ARTE

COLOR BODY PORCELAIN TILE | RECTIFIED



**AJ3P** Arte BI  
20"x20" Rectified  
**AJ3L** Arte BI  
13"x13" Rectified  
**AJ3S** Arte BI  
12"x24" Rectified  
**AJ3V** Arte BI  
3 1/4"x6 1/2" Rectified

**AJ3N** Arte BG  
20"x20" Rectified  
**AJ3K** Arte BG  
13"x13" Rectified  
**AJ3R** Arte BG  
12"x24" Rectified  
**AJ3U** Arte BG  
3 1/4"x6 1/2" Rectified

**AJ3Q** Arte MA  
20"x20" Rectified  
**AJ3M** Arte MA  
13"x13" Rectified  
**AJ3T** Arte MA  
12"x24" Rectified  
**AJ3W** Arte MA  
3 1/4"x6 1/2" Rectified



**AJ3Y** Arte BI  
Brick Mosaic  
13"x13"

**AJ3X** Arte BG  
Brick Mosaic  
13"x13"

**AJ3Z** Arte MA  
Brick Mosaic  
13"x13"

## TRIMS



**AJ33** Arte BI Bullnose  
**AJ32** Arte BG Bullnose  
**AJ34** Arte MA Bullnose  
3"x13"



Floor Tile



Wall Tile



Rectified Tile



Decorative Tile



Trim Available



Suitable for  
Outdoors



Moderate Variation



Frost Resistant



Meets ADA  
Recommendations



Abrasion Resistance



C.O.F. (Wet)



C.O.F. (Dry)



Certified No VOC



21% Minimum  
Pre-Consumer  
Recycled Content



Contributes to  
LEED Credits

## TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	6	MOHS SCALE
Breaking Strength	20"x20" ≥ 250 lbf.	≥ 605 lbf.	C648
	13"x13" ≥ 250 lbf.	≥ 407 lbf.	C648
Facial Dimension	-3.0 % < Nominal < 2.0 %	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.25 % or +/- 0.8 mm*	Within Standard	C502
Warpage (Flatness)	+/- 0.40 % or +/- 1.8 mm*	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
C.O.F. (Wet)	As Reported	0.60 ≤ COF < 0.70	C1028
C.O.F. (Dry)	As Reported	0.70 ≤ COF < 0.80	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

\* Whichever is less

