



live inspired

REVISION

COLOR BODY PORCELAIN TILE | RECTIFIED




R4P3 Revision BI
24"x24" Rectified
R4Q3 Revision BI
12"x24" Rectified
R4P8 Revision BI
12"x48" Rectified



R5P4 Revision BI
Mosaic
12"x24"



R5P1 Nest BI
Insert
12"x48"



R4P4 Revision BG
24"x24" Rectified
R4Q4 Revision BG
12"x24" Rectified
R4P9 Revision BG
12"x48" Rectified




R5P5 Revision BG
Mosaic
12"x24"




R5P2 Nest MA
Insert
12"x48"



R4P6 Revision RS
24"x24" Rectified
R4Q6 Revision RS
12"x24" Rectified
R4Q1 Revision RS
12"x48" Rectified




R5P7 Revision RS
Mosaic
12"x24"



R4P5 Revision MA
24"x24" Rectified
R4Q5 Revision MA
12"x24" Rectified
R4Q0 Revision MA
12"x48" Rectified



R5P6 Revision MA
Mosaic
12"x24"



R4P7 Revision NE
24"x24" Rectified
R4Q7 Revision NE
12"x24" Rectified
R4Q2 Revision NE
12"x48" Rectified



R5P8 Revision NE
Mosaic
12"x24"



Floor Tile



Wall Tile



Modular Tile



Rectified Tile



Decorative Tile



Trim Available



Uniform
Appearance



Frost Resistant



Abrasion Resistance



C.O.F. (Wet)



C.O.F. (Dry)



45% Minimum
Pre-Consumer
Recycled Content



Certified No VOC

TRIMS



R4W8 Revision BI Bullnose
R4W9 Revision BG Bullnose
R4X1 Revision RS Bullnose
R4X0 Revision MA Bullnose
R4X2 Revision NE Bullnose
4"x24"



Contributes to
LEED Credits

TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	6	MOHS SCALE
Breaking Strength	12"x24"	≥ 250 lbf.	≥ 995 lbf.
	12"x48"	≥ 250 lbf.	≥ 1450 lbf.
	24"x24"	≥ 250 lbf.	≥ 995 lbf.
Facial Dimension	-3.0 % < Nominal < 2.0 %	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.25 % or +/- 0.8 mm*	Within Standard	C502
Warpage (Flatness)	+/- 0.40 % or +/- 1.8 mm*	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class III	C1027
C.O.F. (Wet)	As Reported	0.30 ≤ COF < 0.40	C1028
C.O.F. (Dry)	As Reported	0.70 ≤ COF < 0.80	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

* Whichever is less

