



live inspired

HARBOUR ROCK

GLAZED PORCELAIN TILE



AG2V Bombay BG
18"x18"
AG2S Bombay BG
12"x12"
AG2P Bombay BG
6"x6"



AG2W Boston GR
18"x18"
AG2T Boston GR
12"x12"
AG2Q Boston GR
6"x6"



AG2X Sydney NO
18"x18"
AG2U Sydney NO
12"x12"
AG2R Sydney NO
6"x6"

TRIMS



AG3C Bombay BG Bullnose
AG3D Boston GR Bullnose
AG3E Sydney NO Bullnose
3"x12"



AG26 Bombay BG Bead
AG27 Boston GR Bead
AG28 Sydney NO Bead
1"x6"



AG3J Palace
Border
1 1/4"x13"



AG3L Palace
Corner
1 1/4"x1 1/4"



AG3K Palace
Insert
1 1/4"x1 1/4"



AG29 Bombay BG Beak
AG3A Boston GR Beak
AG3B Sydney NO Beak
1"x1"



AG2Y Bombay BG V-Cap
AG2Z Boston GR V-Cap
AG2Z Sydney NO V-Cap
2"x6"



AG23 Bombay BG V-Cap Corner
AG24 Boston GR V-Cap Corner
AG25 Sydney NO V-Cap Corner
7/8"x2"



Floor Tile



Wall Tile



Decorative Tile



Trim Available



Suitable for
Outdoors



Moderate Variation



Frost Resistant



Meets ADA
Recommendations



Abrasion Resistance



C.O.F. (Wet)



C.O.F. (Dry)
7% Minimum
Pre-Consumer
Recycled Content



Certified No VOC



Contributes to
LEED Credits

TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	7	MOHS SCALE
Breaking Strength	18"x18"	≥ 250 lbf.	≥ 535 lbf.
	12"x12"	≥ 250 lbf.	≥ 480 lbf.
Facial Dimension	-3.0 % < Nominal < 2.0 %	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.50 % or +/- 2.0 mm*	Within Standard	C502
Warpage (Flatness)	+/- 0.75 % or +/- 2.3 mm*	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
C.O.F. (Wet)	As Reported	0.60 ≤ COF < 0.70	C1028
C.O.F. (Dry)	As Reported	0.70 ≤ COF < 0.80	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

* Whichever is less

