

# CERAMIC TILE

## FLOOR TILE

### GLAZED CERAMIC

Water Absorption  
Vitreous: 0.5% -  $\leq$  3.0%  
Semi-Vitreous: 3.0% -  $\leq$  7.0%

Firing Temperature  
2050° F

Body Properties  
Red or white clays

### PORCELAIN TILE

Water Absorption  
Impervious:  $<$  0.5%

Firing Temperature  
2200° F

Body Properties  
Purified, refined, kaolin-rich clays

## WALL TILE

### WALL TILE

Water Absorption  
Non-Vitreous: 7.0% -  $\leq$  20.0%

Firing Temperature  
1900° F

Body Properties  
Shrinkage-controlled red or  
white clays

### UNGLAZED

#### THROUGH BODY

Continuous colors  
and patterns  
permeate the entire  
tile body

### GLAZED

#### WHITE BODY

Glaze layer applied  
atop fine white  
porcelain body

#### COLOR BODY

Colors of both glaze  
and body are  
synchronized

#### THROUGH BODY

Continuous colors  
and patterns  
permeate the entire  
tile body