



*live inspired*

# BORGOFORTE

GLAZED PORCELAIN TILE



**AG2H** Siena GR

18"x18"

**AG2D** Siena GR

12"x12"



**AG3P** Siena GR Listelli

1 1/2"x12"



**AG3T** Siena GR Insert

1 1/2"x1 1/2"



**AG2E** Cassino BG

18"x18"

**AG2A** Cassino BG

12"x12"



**AG2N** Cassino BG Listelli

1 1/2"x12"



**AG3Q** Cassino BG Insert

1 1/2"x1 1/2"



**AG2F** Orvieto BL

18"x18"

**AG2B** Orvieto BL

12"x12"



**AG3M** Orvieto BL Listelli

1 1/2"x12"



**AG3R** Orvieto BL Insert

1 1/2"x1 1/2"



**AG2G** Perugia MA

18"x18"

**AG2C** Perugia MA

12"x12"



**AG3N** Perugia MA Listelli

1 1/2"x12"



**AG3S** Perugia MA Insert

1 1/2"x1 1/2"

## SINGLE BULLNOSE



**AG2M** Siena GR  
**AG2K** Orvieto BL  
**AG2J** Cassino BG  
**AG2L** Perugia MA  
3"x12"

Bullnose  
Bullnose  
Bullnose  
Bullnose



Floor Tile



Wall Tile



Decorative Tile



Trim Available



Suitable for  
Outdoors



Slight Variation



Frost Resistant



Meets ADA  
Recommendations



Abrasion Resistance



C.O.F. (Wet)



C.O.F. (Dry)



Certified No VOC



7% Minimum  
Pre-Consumer  
Recycled Content



Contributes to  
LEED Credits

## TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	6	MOHS SCALE
Breaking Strength 18"x18"	≥ 250 lbf.	≥ 550 lbf.	C648
12"x12"	≥ 250 lbf.	≥ 480 lbf.	C648
Facial Dimension	-3.0 % < Nominal < 2.0 %	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.25 % or +/- 0.8 mm*	Within Standard	C502
Warpage (Flatness)	+/- 0.40 % or +/- 1.3 mm*	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
C.O.F. (Wet)	As Reported	0.60 ≤ COF < 0.70	C1028
C.O.F. (Dry)	As Reported	0.60 ≤ COF < 0.70	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

\* Whichever is less

