

Phyllis2

bamboo sawdust char (#2823)

[Download XLSX](#) [Download PDF](#)

ID-number	#2823
Material	bamboo sawdust char
Classification	ECN Phyllis classification ▶ Biochar ▶ Grass NTA 8003 classification ▶ [800] samengestelde stromen ▶ [804] brandstof na carbonisatie
Submitter organisation	ECN (Netherlands)
Submission date	2008-07-24
Remarks	Char from pyrolysis at 405°C. Bamboo sawdust data in preceding record, bio-oil data in following records.
Literature	S.-H. Jung, B.-S. Kang, J.-S. Kim: Production of bio-ol from rice straw and bamboo sawdust.....J. Anal. Appl. Pyrolysis 82 (2008) 240-247

Values

Property	Unit	Value			Std dev	Det lim	Lab	Date	Method	Remarks
		ar	dry	daf						
Main biomass properties										
Proximate analysis										
Moisture content	wt%	0.00	← Edit							
Ash content	wt%	34.60	34.60							
Ultimate analysis (macroelements)										
Carbon	wt%	35.50	35.50	54.28					Measured	
Hydrogen	wt%	1.81	1.81	2.77					Measured	
Oxygen	wt%	26.89	26.89	41.12					Calculated	
Nitrogen	wt%	1.18	1.18	1.80					Measured	
Sulphur	wt%	0.02	0.02	0.03					Measured	
Total (with halides)	wt%	100.00	100.00	100.00					Calculated	
Heating value										
HHV _{Milne}	MJ/kg	10.79	10.79	16.49					Calculated	
Trace elements composition										