Corrosion-resistant Bolting for Use in the Petroleum and Natural Gas Industries

API SPECIFICATION 20F SECOND EDITION, MAY 2018

EFFECTIVE DATE: NOVEMBER 1, 2018



Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

Users of this specification should not rely exclusively on the information contained in this document. Sound business, scientific, engineering, and safety judgment should be used in employing the information contained herein.

Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patents.

Shall: As used in a standard, "shall" denotes a minimum requirement in order to conform to the specification.

Should: As used in a standard, "should" denotes a recommendation or that which is advised but not required in order to conform to the specification

May: As used in a standard, "may" denotes a course of action permissible within the limits of a standard.

Can: As used in a standard, "can" denotes a statement of possibility or capability.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, NW, Washington, D.C. 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually and updated quarterly by API, 1220 L Street, NW, Washington, D.C. 20005.

Suggested revisions are invited and should be submitted to the Standards Department, API, 1220 L Street, NW, Washington, D.C. 20005, standards@api.org.

Contents

| | Pa | age |
|--------------------------------------|--|--------------------------|
| 1 1.1 1.2 1.3 1.4 1.5 | Scope | . 1 . 1 . 1 . 1 |
| 2 | Normative References | |
| 3 3.1 3.2 | Terms, Definitions, Acronyms, and Abbreviations | . 3 . 4 |
| 4 | Qualification Bolting | |
| 4.1 4.2 | GeneralQualification Testing | |
| 4.2 | Materials and Dimensions | |
| 4.4 | Acceptance of Qualification Bolting | . 5 |
| 4.5 | Records of Qualification | |
| 4.6 | Limits of Bolting Qualification-BSL-2 and BSL-3 | . 6 |
| 5 | Production of Qualified Bolting | |
| 5.1 | Qualification of Procurement Sources for Raw Material | |
| 5.2 5.3 | Qualification of Suppliers for Subcontracted Operations | |
| 5.4 | Manufacturing Process Specification | |
| 5.5 | Raw Material | |
| 5.6 | Chemical Analysis | 11 |
| 5.7 | Mechanical Properties | |
| 5.8 | Metallurgical Requirements | |
| 5.9 5.10 | Examination and Test Requirements | |
| 5.10 | Nondestructive Examination (NDE) Requirements | |
| | Final Positive Material Identification | |
| 6 | Calibration Systems | 13 |
| 7 | Test Report | 14 |
| 8 8.1 | Marking Requirements Product Marking | 14 14 |
| 9 | Record Retention | 15 |
| 10 | Storage and Shipping | 16 |
| Anne | ex A (informative) API Monogram Program-Use of the API Monogram by Licensees | 17 |
| Ann | ex B (normative) Avoidance of Contamination of Nickel Alloys | 21 |
| Bibli | ography | 22 |

Contents

| | | Page |
|------|--|------|
| Tabl | les | |
| 1 | Bolting Test Requirements | 5 |
| 2 | Sampling for Dimensional, Surface NDE, and Visual Inspection | |
| 3 | API 6ACRA and UNS R30035 Grade Identification Markings | 15 |

Corrosion-resistant Bolting for Use in the Petroleum and Natural Gas Industries

1 Scope

1.1 Purpose

This standard specifies requirements for the qualification, production, and documentation of corrosion-resistant bolting used in the petroleum and natural gas industries.

1.2 Applicability

This standard applies when referenced by an applicable API equipment standard or otherwise specified as a requirement for compliance.

1.3 Bolting Specification Levels (BSL)

This standard establishes requirements for two bolting specification levels (BSL). These two BSL designations define different levels of technical, quality, and qualification requirements: BSL-2 and BSL-3. The BSLs are numbered in increasing levels of requirements in order to reflect increasing technical, quality, and qualification criteria. BSL-2 and BSL-3 are intended to be comparable to BSL-2 and BSL-3, as found in API 20E. BSL-1 is omitted from this standard.

1.4 Bolting Types for Qualification

This standard covers the following product forms, processes, and sizes:

- machined studs;
- machined bolts, screws, and nuts;
- cold-formed bolts, screws, and nuts with cut or cold-formed threads;
- hot-formed bolts and screws <1.5 in. (38.1 mm) nominal diameter;
- hot-formed bolts and screws ≥1.5 in. (38.1 mm) nominal diameter;
- f) roll threaded studs, bolts, and screws <1.5 in. (38.1 mm) diameter;
- roll threaded studs, bolts, and screws ≥1.5 in. (38.1 mm) diameter;
- hot-formed nuts <1.5 in. (38.1 mm) nominal diameter;
- i) hot-formed nuts ≥1.5 in. (38.1 mm) nominal diameter.

1.5 Application of the API Monogram

If the product is manufactured at a facility licensed by API and is intended to be supplied bearing the API Monogram, the requirements of Annex A apply.

Normative References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document applies (including any addenda/errata).

API Specification Q1, Specification for Quality Management System Requirements for Manufacturing Organizations for the Petroleum and Natural Gas Industry

API 6A, Specification for Wellhead and Christmas Tree Equipment

GRDER REGISTRATION NO. ORDF03-0019 API 6HT, Heat Treatment and Testing of Carbon and Low Alloy Steel Large Cross Section and Critical Sectio Components

API Standard 6ACRA, Age-hardened Nickel-based Alloys for Oil and Gas Drilling and Production Equipment

ANSI/NCSL Z540.3¹, Requirements for the Calibration of Measuring and Test Equipment

ASTM A370², Standard Test Methods and Definitions for Mechanical Testing of Steel Products

ASTM A453, Standard Specification for High-Temperature Bolting, with Expansion Coefficients Comparable

ASTM A370', Standard Test Methods and Definitions for Mechanical Testing of Steel Products

ASTM A453, Standard Specification for High-Temperature Bolting, with Expansion Coefficients Comparable 100 Austenitic Stainless Steels

ASTM A953, Standard Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

ASTM A962-17, Standard Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

ASTM E10, Standard Specification for Common Requirements for Bolting Intended for Use at Any Temperature/
from Cryogenic to the Creep Range

ASTM E10, Standard Test Method for Brinell Hardness of Metallic Materials

ASTM E18, Standard Test Methods for Rockwell Hardness of Metallic Materials

ASTM E354 Standard Method for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similed Materials

ASTM E1876, Standard Specification for Surface Discontinuities of Bolts, Screws, and Studs, Inch and Metric Series

ASTM F1812, Standard Specification for Surface Discontinuities of Bolts, Screws, and Studs, Inch and Metric Series

ASTM F1812, Standard Specification for Surface Discontinuities of Nuts, Inch and Metric Series

ISO 9001, Quality management systems - Requirements

ISO/IEC 17020, Conformity assessment - Requirements for the operation of various types of bodies performing inspection

ISO/IEC 17025, General requirements for the competence of testing and calibration laboratories

NACE MR0175/ISO 151563, Petroleum and natural gas industries—Materials for use in H;S-containing environments in oil and gas production, parts 1, 2, and 3

SAE AMS 27504, Pyrometry

SAE AMS 5844, Alloy, Corrosion-Resistant, Round Bars, 20Cr-35Ni-35Co-10Mo, Vacuum Induction Plus Magnetics and Work Strengthened

NCSL International, 1995 Wilderness Place, Suite 107, Boulder, Colorado 80301-5404, www.ncsli.org.

ASTM International, 1995 Wilderness Place, Suite 107, Boulder, Colorado 80301-5404, www.astm.org.

NACE International, 19835 Park Ten Place, Houston, TX 77084, www.nace.org

⁴ SAE International, <u>www.sae.org</u>

SUPPLIED BY BSB EDGE UNDER LICENCE FROM API FOR HEAVY EQUIPMENT MAINTENANCE (HEMT) - MUSCAT VIDE BSB EDGE ORDER REGISTRATION NO. ORDF03-0019 ON

SAE AMS H-6875, Heat Treatment of Steel Raw Materials

3 Terms, Definitions, Acronyms, and Abbreviations

3.1 Terms and Definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

bolting

All-thread studs, tap-end studs, double-ended studs, headed bolts, cap screws, screws, and nuts.

3.1.2

bolting manufacturer

An organization that, through the use of manufacturing equipment and processes appropriate for the bolting product form, transforms raw material into finished bolting.

3.1.3

cold-formed bolts, screws, and nuts

Parts formed through the mechanical cold upsetting of wire, rod, or bar in order to generate the bolt or screw head (cold heading) or the configuration of the nut.

3.1.4

corrosion-resistant bolting

Bolting manufactured from metal that achieves improved resistance to corrosion through the addition of alloying elements.

3.1.5

heat

Material originating from a final melt, or for remelted alloys, the raw material originating from a single remelted ingot.

3.1.6

heat lot

- a) Batch furnace: bolting or raw material of a single heat and diameter, heat treated together as a single solution annealing, quenching, and aging or precipitation hardening charge;
- b) Continuous furnace (applies to ASTM A453 Grade 660 Class D only): bolting or raw material of a single heat and diameter heat treated without interruption in a continuous charge, as defined in ASTM A453.

3.1.7

hot-formed bolts, screws, and nuts

Parts formed through the mechanical hot upsetting of wire, rod, or bar in order to generate the bolt or screw head (hot heading) or the configuration of the nut.

3.1.8

machined bolts, screws, and nuts

Parts manufactured by machining from raw material to generate the bolt, screw head, or the configuration of the nut.

3.1.9

manufacturing process specification

MPS

A written document describing the complete production sequence and method.

NOTE MPSs are usually proprietary by manufacturer and not for general publication, but are available to customers or authorized third parties for information.

3.1.10

production lot

Bolting of a single nominal diameter and grade made from the same heat lot.

3.1.11

raw material

Bar, coil, rod, or wire used to manufacture bolting.

3.1.12

raw material supplier

A melting mill where raw material is manufactured to be used in qualified bolting.

NOTE

3.1.13

technical authority

A competent and technically qualified person or organization with evidence to demonstrate the expertise, skills, as experience regarding quality and manufacturing processes necessary to perform the required verification(s).

3.1.14

wrought structure

A structure that contains no cast dendritic elements.

3.2 Abbreviations

BSL bolting specification level

MPS

NDE

OEM original equipment manufacturer UT

ultrasonic testing

Qualification Bolting

4.1 General

- aterial supplier
 ing mill where raw material is manufactured to be used in qualified bolting.

 A distributor is not considered a raw material supplier.

 Cal authority
 petent and technically qualified person or organization with evidence to demonstrate the expertise, skills, and ence regarding quality and manufacturing processes necessary to perform the required verification(s).

 Abbreviations

 bolting specification level
 manufacturing process specification
 nondestructive examination
 original equipment manufacturer UT
 inic testing

 Jualification Bolting

 General

 This standard states the requirements for two bolting specification levels (BSL) and nine bolting types. The acturer may qualify to one or more of the bolting types listed in 1.4 and to one or both BSLs. Each individually types shall be qualified. Qualification to the higher BSL shall qualify to the lower BSL. The following paragraphs and the paragraphs manufacturer may qualify to one or more of the bolting types listed in 1.4 and to one or both BSLs. Each individual bolting type shall be qualified. Qualification to the higher BSL shall qualify to the lower BSL. The following paragraphs: describe the conditions that, when met, allow the bolting to meet the appropriate bolting type and BSL classification level.
- Qualification bolts and nuts shall be produced from raw material procured from an approved supplier as defined in 5.1 and manufactured in accordance with an applicable manufacturing process specification (MPS) for a

- 4.2 Qualification Testing

 4.2 Qualification bolting shall be tested and evaluated by the bolting manufacturer in order to establish qualification to the bolting types listed in 1.4 and a BSL. Qualification bolting shall meet all of the requirements indicated in Table 1 for the applicable sections of this standard.
- All required tests, including those certified by the raw material supplier, shall be performed by a laboratory qualified in accordance with ISO/IEC 17025. For ultrasonic examination, magnetic particle inspection, and liquid penetrant inspection, qualification to ISO/IEC 17020 is an acceptable alternative to ISO/IEC 17025.

 4.2.3 Qualification may be performed on parts specifically manufactured for qualification or random parts selected from a production lot. A sufficient number of parts shall be used to provide adequate material for all required tests.

- **4.2.4** The manufacturer shall have a quality management system that, at a minimum, meets the requirements of API Q1.
- **4.2.5** The manufacturer shall retain and have available an MPS (see 5.3) and qualification records (see 4.5) for each product qualified. The qualification records shall show all of the products, processes, and sizes qualified and all of the Table 1 requirements for each qualification, including the results of tests and inspections.

Table 1—Bolting Test Requirements

| BSL | Material | Heat Treatment | Chemistry | Mechanical | Metallurgical | Hardness | NDE Surface | NDE Volumetric |
|-------|----------|-------------------|-----------|------------|---------------|----------|----------------|-------------------|
| BSL-2 | 5.5.1 | 5.4.5 | 5.6 | 5.7.2 | 5.8. | 5.9.2 | 5.10.1.1 | 5.10.1.2 |
| BSL-3 | 5.5.2 | 5.4.5 | 5.6 | 5.7.3 | 5.8 | 5.9.2 | 5.10.2.1 | 5.10.2.2 |

4.3 Materials and Dimensions

- **4.3.1** The following bolting materials are covered by this standard:
- precipitation hardened nickel-based alloys in accordance with API 6ACRA;
- precipitation hardened austenitic iron-based ASTM A453 Grade 660 Class D;
- cold-reduced only, or cold-reduced and high-temperature aged heat treated condition cobalt-based alloy UNS R30035.
- **4.3.2** All requirements of API 6ACRA, ASTM A453, or UNS R30035 shall be met, except as modified by this standard. In the case of conflict between the requirements of referenced specifications and this standard, the requirements of this standard shall apply.
- **4.3.3** For UNS R30035, the bolting manufacturer shall have a written specification that complies with the SAE AMS 5844 chemistry, melting practice, solution annealing, furnace tolerances, and average grain size, with additional requirements shown below.
- **4.2.1.1** For UNS R30035 with a maximum hardness of 35 HRC, raw material shall be supplied in the solution annealed and cold-reduced condition and not subsequently aged.
- **4.2.1.2** For UNS R30035 with a maximum hardness of 51 HRC, raw material shall be supplied in the solution annealed, cold-reduced, and one of the aged conditions specified in NACE MR0175-3/ISO 15156-3.
- **4.2.1.3** UNS R30035 shall only be heat treated/reheat treated by the raw material supplier.
- **4.3.4** Oversizing of nut threads or undersizing of bolt threads is not permissible.
- **4.3.5** Welding is not permitted.

4.4 Acceptance of Qualification Bolting

4.4.1 General

Results of the tests specified in Table 1 shall comply with the acceptance criteria specified in Section 5 and the bolting manufacturer's written specification. Results shall be documented in accordance with 4.5.

4.4.2 Qualification Samples

4.4.2.1 Samples failing to meet acceptance criteria shall be cause for re-evaluation of the MPS and the processes and procedures used. Requalification is required.

- 4.4.2.2 When a qualification sample is selected from a production lot, as defined in 3.1.10, and fails to mee acceptance criteria, the entire lot shall be rejected.

 4.4.2.3 Should the manufacturer choose to continue the qualification process with the same lot, the entire lot shall be
- 4.4.2.3 Should the manufacturer choose to continue the qualification process with the same lot, the entire lot shall be reprocessed. A maximum of two full reheat treatment cycles is permitted for API 6ACRA alloys and ASTMP A453 Grade 660 Class D.
- **4.4.2.4** For reprocessed lots, all qualification tests shall be repeated. Should any of the qualification tests fail to meet the acceptance criteria, the entire lot shall be rejected.
- the acceptance criteria, the entire lot shall be rejected.

 4.4.2.5 If reprocessing results in any changes to the MPS, the MPS shall be revised to reflect the new processor control variables.

4.5 Records of Qualification

The following records are required to document the qualification of bolting:

- edition and alloy of API 6ACRA, ASTM A453 Grade 660 Class D (including revision level), or applicable manufacturer specification for UNS R30035 (including revision level);
- heat number, heat lot, and production number for API 6ACRA alloys, ASTM A453 Grade 660 Class D, and UNS R30035 materials;
- c) raw material supplier;
- d) raw material refining method;
- e) size;
- f) process control variables;
- g) MPS;
- h) forming, as applicable;
- i) heat treatment;
- j) machining, as applicable;
- k) thread rolling, as applicable;
- I) record of test results, as applicable, in Section 4 and Section 5;
- m) inspection;
- n) personnel qualifications;
- test laboratory qualification;
- p) records of qualification test failures and corrective action; and
- q) subcontractor(s) name, address, and records of qualification (as specified in 5.2) for each subcontracted process.

4.6 Limits of Bolting Qualification—BSL-2 and BSL-3

The following are the limits of bolting qualification. A change in any of these variables requires requalification:

SPECIFICATION 20F 7

- a) change of heat treat method (type of equipment, furnace control method, cooling methods);
- b) addition of raw material supplier not previously qualified in accordance with Section 5;
- c) change of machining or threading methods (type of equipment, control);
- d) change of hot-forming practice (type of equipment, heating method, temperature control method);
- e) for UNS R30035, change in the amount of total cold reduction (work strengthening); f)

subcontractor of processes listed in 5.2.1.

5 Production of Qualified Bolting

5.1 Qualification of Procurement Sources for Raw Material

- **5.1.1** Only sources for raw material that are approved by the bolting manufacturer are to be used to supply raw material. The bolting manufacturer shall have a documented and fully implemented procedure for qualifying raw material suppliers for each grade and heat treat condition of material. The approval process shall be based on both a quality assurance evaluation and technical evaluation. The approval process shall establish the methodology by which the raw material supplier will be evaluated on an ongoing basis to maintain their status as an approved supplier.
- **5.1.2** In addition to the maintenance of a quality management system meeting an applicable standard, such as API Q1 or ISO 9001, the raw material supplier shall maintain documented evidence of their technical capability to produce materials meeting this standard, and shall have documented procedures that demonstrate their capability to consistently produce acceptable product. The methods for the technical approval of a raw material supplier for the two BSL are the following:
- a) BSL-2

Use of three or more of the following four methods:

- raw material receipt inspection that includes volumetric and surface NDE, chemistry check, metallurgical properties, mechanical properties and dimensions, as applicable;
- raw material first article evaluation;
- demonstration of technical capability, such as tests/inspections, quality of material received, nonconformance analysis;
- on-site technical audits at scheduled 3-year intervals, at a minimum.
- b) BSL-3

All of the four methods listed in 5.1.2.a) shall be used.

- **5.1.3** The bolting manufacturer is responsible for ensuring that a raw material supplier has implemented controls addressing the following for each grade of raw material ordered:
- a) chemistry controls;
- b) melting practice controls;
- c) pouring practice;
- d) hot work practice controls;
- e) heat treatment controls, as applicable;

- f) raw material inspection and acceptance criteria (cleanliness requirements, limitations on porosity or inclusions, grain size, secondary phases, microstructure, as applicable);
 g) controls to assure that no welding was performed.

 5.2 Qualification of Suppliers for Subcontracted Operations

 5.2.1 General

 If any of the following operations are subcontracted, the suppliers of the subcontracted operations shall be qualified by the manufacturer in accordance with this section:
 a) head forging/head forming of individual fasteners;
 b) heat treatment;
 c) threading;
 d) plating/coating;
 e) NDE;
 f) mechanical and hardness testing;
 g) metallurgical examination as specified in 5.8;
 h) chemical analysis.

 5.2.2 Qualification Requirements

 5.2.2.1 Only qualified suppliers shall be used to perform subcontracted operations. The bolting manufacturer shalls have a documented and fully implemented procedure for qualifying subcontracted suppliers for operations. 5.2.2.1 Only qualified suppliers shall be used to perform subcontracted operations. The bolting manufacturer shalls have a documented and fully implemented procedure for qualifying subcontracted suppliers for operations performed. The qualification process shall include:

 a) a quality management system evaluation in accordance with ISO 9001 or API Q1 for all bolting specification levels;

 b) an onsite process evaluation performed by a technical authority per methods listed in 5.2.3; and

 c) test laboratory evaluation in accordance with ISO/IEC 17020 (for NDE only) or ISO/IEC 17025, at a minimum.

 5.2.2.2 Suppliers of subcontracted operations shall have an onsite technical authority available, and the technical authority's competency shall be documented.

 5.2.3 Technical Evaluation

 The technical evaluation of suppliers of subcontracted processes shall include the requirements for the various BSLs_1 listed in a) and b) below.

 a) BSL-2 requirements:

 1) a quality management system evaluation, ensuring that the subcontractor's QMS is compliant with ISO 9001, API Q1, ISO/IEC 17020 (for NDE only), or ISO/IEC 17025;

 2) independent or third-party evidence of conformance to ISO/IEC 17020 or ISO/IEC 17025 for the required laboratory service is acceptable in lieu of an onsite audit or technical evaluation:

- - independent or third-party evidence of conformance to ISO/IEC 17020 or ISO/IEC 17025 for the require laboratory service is acceptable in lieu of an onsite audit or technical evaluation;
 - 3) onsite process audit performed by a technical authority at an interval no greater than 3 years;

SPECIFICATION 20F 9

4) evaluation of the supplier's documented evidence of technical capability to perform subcontracted operations in accordance with 5.2. At a minimum, the evaluation shall include certifications, calibration of test and measurement equipment, production logs, written procedures, and nonconformance analyses.

- b) BSL-3 eequirements:
 - 1) requirements specified for BSL-2 are required for BSL-3;
 - 2) first article evaluation of each subcontracted process per manufacturer's documented procedure.

5.3 Material Specifications

- **5.3.1** The bolting manufacturer shall prepare and document raw material requirements in the form of a material specification. Material specifications shall include the following items as applicable per the referenced API, ASTM, SAE AMS, NAC/ISO standards, or OEM or bolting manufacturer's purchasing specification:
- a) material grade, including element chemistry and allowable ranges;
- b) acceptable melt practices and ladle refinement;
- c) acceptable hot work reduction range (not required for cold-reduced UNS R30035 material);
- d) acceptable microstructure (applicable to alloys covered by API 6ACRA only);
- e) heat treatment requirements, including mill heat treatments;
- f) mechanical properties;
- g) acceptable inspection practices and criteria, as applicable per BSL.
- **5.3.2** The bolting manufacturer shall document acceptance of incoming raw material to the requirements of the material specification prior to use in the production of bolting.

5.4 Manufacturing Process Specification

5.4.1 General

The bolting manufacturer shall prepare an MPS to include, at a minimum, allowable levels for all bolting manufacturing parameters, including the process control variables listed in 5.4.2, the forging/hot heading parameters listed in 5.4.3, and the heat treatment parameters listed in 5.4.4.

The requirements of Annex B shall be followed during processing.

5.4.2 General Variables

The following are general variables, as applicable:

- a) heading equipment;
- b) hot-forming heating method;
- c) hot-forming temperature control method;
- d) heat treating equipment and processes;
- e) machining and threading equipment: single point (lathe), multiple chaser, roll, cutting tap; form tap; f)

machining and threading control methods;

g) mill source (name and address); and

SUPPLIED BY BSB EDGE

- h) outsourced activity supplier (name and address).

 5.4.3 Forging/Hot Heading Parameters
 The following are forging/hot heading parameters, as applicable;
 a) equipment;
 b) heating method (furnace, induction);
 c) temperature control (thermocouple, optical, or infrared pyrometer, fail safe cut-off);
 d) times and temperatures; and
 e) dimensional control.

 5.4.4 Heat Treatment Parameters
 The following are heat treatment parameters, as applicable:
 a) equipment (batch, continuous);
 b) times and temperatures;
 c) cooling media (e.g. type, polymer concentration, quench temperature, agitation);
 d) control and calibration methods;
 e) furnace load diagram or photo. For mill heat treated products, this requirement is waived, provided that the bolting manufacturer has performed first article evaluation in accordance with 5.1.2 a) 2).

 5.4.5 BSL-2 and BSL-3 Requirements
 5.4.5.1 Forging and hot heading shall be in accordance with the manufacturer's standard procedure.
 5.4.5.2 Heat treatment shall be in accordance with the relevant API, NACE/ISO, or ASTM standard.
 5.4.5.3 Heat treatment of API 6ACRA material shall be performed and qualified after the material's final hot-forming and age hardening times and temperatures shall be in accordance with the requirements of API Standard 6ACRA. operation. Heat treatment equipment qualification and calibration, temperature monitoring, solution annealing, and age hardening times and temperatures shall be in accordance with the requirements of API Standard 6ACRA.

 5.4.5.4 Heat treatment of ASTM A453 660 Class D shall be in accordance with ASTM A453.
- qualification shall be in accordance with API 6A, SAE AMS 2750, or SAE AMS H-6875. Solution annealing and aging furnace tolerance shall be +/- 25 °F.
- 5.4.5.6 Manufacturing processes shall be performed so as to avoid the introduction of stress risers that can occur from sharp angles and tool marks. Threads may be cut or rolled. Thread form shall be UN for internal threads and UNR for external threads, per ANSI/ASME B1.1.
- **5.4.5.7** The following apply to material not heat treated by the raw material supplier:
- a) Furnace loading shall be in accordance with API 6HT, Section 6.3.3.
- b) A furnace loading diagram or photo shall be prepared for each load configuration.
- Temperature shall be monitored using a contact thermocouple or a heat sink placed at the center of the load.

e) The manufacturer shall have a written forging procedure defining, at a minimum, the parameters defined in 5.4.3. W hen induction heating is used for forging, the manufacturer's procedure shall include temperature monitoring equipment and an automatic fail-safe system to prevent overheating.

5.4.6 Plating and Coating

- **5.4.6.1** Plating and coating shall be provided only when specified in the purchase agreement.
- **5.4.6.2** Plating and coating shall be specified in accordance with the industry standard or the purchaser's specification.

5.5 Raw Material

5.5.1 BSL-2

- **5.5.1.1** The metal shall have a fully wrought structure.
- **5.5.1.2** The hot work reduction ratio based on starting material diameter shall be a minimum of 4.0:1. This requirement does not apply to UNS R30035.
- **5.5.1.3** The metal shall conform to the requirements of the relevant API or ASTM Standard, or to AMS 5844 for UNS R30035.
- 5.5.1.4 All elements intentionally added to the heat, except those used for processing, shall be reported.

5.5.2 BSL-3

- **5.5.2.1** The requirements specified for BSL-2 are required for BSL-3.
- **5.5.2.2** In addition to the heat analysis performed by the mill, the bolting manufacturer shall perform a product analysis in accordance with ASTM A453 Grade 660 Class D, API 6ACRA, or UNS R30035.

5.6 Chemical Analysis

Methods and practices relating to chemical analysis shall be in accordance with ASTM A751 or ASTM A354, as applicable. The frequency of chemical analysis shall be one per heat. Results shall be documented on the test report.

5.7 Mechanical Properties

5.7.1 General

Mechanical properties testing shall be performed by the raw material supplier or bolting manufacturer after all thermal treatments, including precipitation hardening and strain hardening. All mechanical property tests required by the applicable API standard, NACE/ISO standard, ASTM standard, or manufacturer's specification shall be performed on each heat lot. Results shall be documented on the test report.

5.7.2 BSL-2

The results shall conform to the requirements of the relevant API standard, NACE/ISO standard, ASTM standard, or manufacturer's specification for UNS R30035.

5.7.3 BSL-3

The requirements for BSL-2 are required for BSL-3. When any of the testing has been performed by the raw material supplier, the bolting manufacturer shall perform a retest.

8

5.8 Metallurgical Requirements

Metallurgical requirements shall be performed by the raw material supplier or bolting manufacturer after all thermal? treatments, including precipitation hardening and strain hardening. All microstructure tests required by the applicable API standard, NACE/ISO standard, ASTM standard, or manufacturer's specification shall be performed on each heat lot Results shall be documented on the test report. The microstructure of nickel base alloys shall conform to the REGISTRATION NO. requirements of API 6ACRA.

5.9 Examination and Test Requirements

5.9.1 General

When inspecting or testing production lots, a sample that fails to meet the applicable requirements shall result in rejection of the entire lot. The rejected lot shall be scrapped, reworked, or, where practical, inspected 100 %, and the defective parts removed. In the case of rework or 100 % inspection, the lot shall be re-inspected or tested for the faile &

- defective parts removed. In the case of rework or 100 % inspection, the lot shall be re-inspected or tested for the failed characteristic and any characteristic affected by rework.

 5.9.2 Hardness Test Requirements

 5.9.2.1 General

 Hardness testing, including specimen preparation, shall be performed in accordance with ASTM A370, including Annex A3, except that testing shall also be in conformance with ASTM E10 or ASTM E18. Results shall be documented or the test report.

 5.9.2.2 BSL-2 and BSL-3

 The hardness test results shall conform to the requirements of API 6ACRA, ASTM A453, or NACE MR0175-3/ ISOM 15156-3 for UNS R30035. Each piece shall be tested.

 5.10 Nondestructive Examination (NDE) Requirements

 5.10.1.1 Surface NDE is required. Liquid penetrant examination is required for ASTM A453 Grade 660 Class D, the alloys covered by API 6ACRA, and UNS R30035. Liquid penetrant examination shall be in accordance with ASTM A962 S56. Acceptance criteria shall be per ASTM A962 S57. The number of pieces examined shall be astered in Table 2. Results shall be per ASTM A962 S57. The number of pieces examined shall be astered in Table 2. Results shall be on accordance with a standing to the content of the conten ASTM A962 S56. Acceptance criteria shall be per ASTM A962 S57. The number of pieces examined shall be as stated in Table 2. Results shall be documented on an examination report.
- **5.10.1.2** Volumetric NDE is required on bar, rod, and wire, and on bolting 2.5 in. (63.5 mm) or greater nominal diameter prior to threading and after any heading and heat treat operations, with the exception of aging performed after threading. Ultrasonic examination shall be performed in conformance with the methods and acceptance criteria of API 6A, volumetric NDE examination of stems (PSL-3). Each piece shall be examined. Results shall be documented on the test report.

 5.10.2 BSL-3

- 5.10.2.1 Surface NDE is required. Liquid penetrant examination is required for ASTM A453 Grade 660 Class D, the alloys covered by API 6ACRA, and UNS R30035. Liquid penetrant examination shall be in accordance with ASTM A962 S56. Acceptance criteria shall be per ASTM A962 S57. Each piece shall be examined. Results shall be un documented on an examination report.
- 5.10.2.2 Volumetric NDE is required on bar, rod, and wire, and on bolting 1 in. (25.4 mm) or greater nomina diameter prior to threading and after any heading or heat treat operations, with the exception of aging performed after threading. Ultrasonic examination shall be performed in conformance with the methods and acceptance criteria of APL 6A, volumetric NDE examination of stems (PSL-3). Each piece shall be examined. Results shall be documented on the test report.

5.11 Dimensional Inspection and Visual Inspection

5.11.1 General

All dimensions shall meet the requirements of ASTM A962. Visual inspection shall be performed in accordance with ASTM F788 and ASTM F812. Dimensions not specified by ASTM A962 shall be as specified by the purchaser. Results shall be documented on an inspection report. Oversizing of nut threads or undersizing of bolt threads is not permissible.

5.11.2 BSL-2 Sample Size

Sample size shall be in accordance with Table 2.

5.11.3 BSL-3 Sample Size

Each piece shall be dimensionally inspected.

Table 2—Sampling for Dimensional, Surface NDE, and Visual Inspection

| Lot Size | Sample Size |
|---|-----------------------------|
| 2 to 8 | ALL |
| 9 to 50 | 8 |
| 51 to 90 | 13 |
| 91 to 150 | 20 |
| 151 to 280 | 32 |
| 281 to 500 | 50 |
| 501 to 1200 | 80 |
| Based on ANSI/ASQ Z1.4 Table 1 | General Inspection Level II |
| NOTE 1 Acceptance number is zero. NOTE 2 Sample shall be random. | |

5.12 Final Positive Material Identification

5.12.1 General

Pieces shall be examined using methods conforming to ASTM E1476 and ASTM A751 to confirm the material type.

5.12.2 BSL-2 Sample Size

Sample size shall be in accordance with Table 2. If any of the samples fail, the entire lot shall be examined.

5.12.3 BSL-3 Sample Size

Each piece shall be examined.

6 Calibration Systems

Inspection, measuring, and testing equipment used for acceptance shall be identified, inspected, calibrated, and adjusted at specific intervals in accordance with ANSI/NCSL Z540.3 and this standard. Calibration standards shall be traceable to the applicable national or international standards agency and shall be no less stringent than the requirements included herein. Inspection, measuring, and testing equipment shall be used only within the calibrated range. Calibration intervals shall be established based on repeatability and degree of usage.

7 Test Report

| The test report shall be supplied to the purchaser and shall include the following as ap | plicable: — |
|--|-------------|
|--|-------------|

copy of original mill certificate;

— cold-reduced production run number (for UNS R30035 only); —

chemistry check analysis;

- hot work reduction ratio (not required for UNS R30035);
- heat treat procedure, including times, temperatures, and quench media, and diagram or photo of furnace loading (diagram or photo exception for mill heat treated bar; see 5.4.4.e);
- results of mechanical tests;
- results of macrostructure evaluations (not required for Grade 660D or UNS R30035);

results of microstructure evaluations (not required for Grade 660D or UNS R30035); —

results of dimensional inspection;

— results of any surface modification operations, if applicable, per Section 5.4.6; —

results of NDE inspections;

- BSL qualification level;
- certification that the product meets the requirements of this standard;

results of Positive Material Identification;

- additional certification requirements stated in API 6ACRA and ASTM A453, and the purchaser's or manufacturer's specification for UNS R30035;
- statement of no weld repair.

8 Marking Requirements

8.1 Product Marking

- 8.1.1 Product marking for Grade 660 Class D shall be in accordance with ASTM A453.
- **8.1.2** Product marking for API 6ACRA and UNS R30035 shall consist of the manufacturer's identification and the grade identification listed in Table 3.

Table 3—API 6ACRA and UNS R30035 Grade Identification Markings

| API 6ACRA or UNS and Material Designation | Marking |
|---|---------|
| N07716 120K | N1A |
| N07716 140K | N1B |
| N07718 120K | N2A |
| N07718 140K | N2B |
| N07725 120K | N3A |
| N09925 110K | N4A |
| N09935 110K | N5A |
| N09945 125K | N6A |
| N09945 140K | N6B |
| N09946 150K | N7A |
| N09946 160K | N7B |
| R30035 work strengthen only | R3A |
| R30035 work strengthen and aged 1300 °F | R3B |
| R30035 work strengthen and aged 1350 °F | R3C |
| R30035 work strengthen and aged 1425 °F | R3D |
| R30035 work strengthen and aged 1450 °F | R3E |
| R30035 work strengthen and aged 1475 °F | R3F |
| R30035 work strengthen and aged 1500 °F | R3G |

8.1.1 Additional Marking Required by this Standard

Bolting shall be marked with unique heat lot identification and the following:

- "20F2" for BSL-2; a)
- "20F3" for BSL-3. b)

Each piece 1 in. (25.4 mm) nominal diameter and larger shall be marked. For bolting less than 1 in. (25.4 mm) nominal diameter, the bolting shall be securely containerized to maintain heat lot identification and traceability. Multiple heat lots shall not be mixed in a single container. Containers used in the processing, storing, and shipping of bolting not individually marked shall be clearly labeled with all marking information required by the ASTM specification, as applicable, and this standard.

Record Retention

The bolting manufacturer shall establish and maintain documented procedures to control all documents and data required by this standard. Records required by this standard shall be maintained for a minimum of 10 years from the date of manufacture. Documents and data may be in any type of media (hard copy or electronic) and shall be:

- maintained to demonstrate conformance to specified requirements;
- legible;
- retained and readily retrievable;
- stored in an environment to prevent loss.

10 Storage and Shipping

Bolting shall be packaged for storage and shipping in accordance with the written specifications of the boltings manufacturer.

No storage and Shipping in accordance with the written specifications of the boltings with the written specification with the written specifi

Annex A (informative)

API Monogram Program Use of the API Monogram by Licensees

A.1 Scope

The API Monogram® is a registered certification mark owned by the American Petroleum Institute (API) and The API Monogram® is a registered certification mark owned by the American Petroleum Institute (API) and authorized for licensing by the API Board of Directors. Through the API Monogram Program, API licenses product manufacturers to apply the API Monogram to new products which comply with product specifications & and have been manufactured under a quality management system that meets the requirements of API Spec Q1. API maintains a complete, searchable list of all Monogram licensees on the API Composite List website (http://compositelist.api.org).

The application of the API Monogram and license number on products constitutes a representation and warranty by the licensee to API and to purchasers of the products that, as of the date indicated, the products were manufactured under a quality management system conforming to the requirements of API Spec Q1 and that the product conforms in every detail with the applicable standard(s) or product specification(s). API Monogram Program licenses are issued only after on-site audits have verified that an organization has ₹ Spec Q1 and that the resulting products satisfy the requirements of the applicable API product specification(s) and/or standard(s). Although any manufacturer may claim that its products meet API product requirements with a license from API and are the standard of the standard of the applicable API product requirements with a license from API and are the standard of the standard of the applicable applicable. without monogramming them, only manufacturers with a license from API can apply the API Monogram to their by products.

Together with the requirements of the API Monogram license agreement, this annex establishes the requirements for those organizations who wish to voluntarily obtain an API license to provide API wonogrammed products that estisfy the requirements of the applicable API product specification(s) and/or by the requirements of the applicable API product specification(s) and/or by the requirements of the applicable API product specification(s) and/or by the requirements of the applicable API product specification(s) and/or by the requirements of the applicable API product specification(s) and/or by the requirements of the applicable API product specification(s) and/or by the applicable API product specification(s) and the applicable applicable applicable applicable applicable applicable applicable applicable applicable applicable

monogrammed products that satisfy the requirements of the applicable API product specification(s) and/or standard(s) and API Monogram Program requirements.

For information on becoming an API Monogram Licensee, please contact API, Certification Programs, 1220 L Street, NW, Washington, DC 20005 at Certification@api.org.

A.2 Normative References

For Licensees under the Monogram Program, the latest version of this document shall be used. The requirements identified therein are mandatory.

A.3 Terms and Definitions

For purposes of this annex, the following terms and definitions apply.

A.3.1

API monogrammable product

Product that has been newly manufactured by an API Licensee utilizing a fully implemented API Spec Q1 compliant quality management system and that meets all the API-specified requirements of the applicable AP product specification(s) and/or standard(s).

A.3.2

API product specification

Prescribed set of rules, conditions, or requirements attributed to a specified product that address the definition of terms; classification of components; delineation of procedures; specified dimensions; manufacturing criteria; \(\overline{5} \) material requirements, performance testing, design of activities; and the measurement of quality and quantity $\overline{\phi}$ with respect to materials; products, processes, services, and/or practices.

A.3.3

API-specified requirements

Requirements, including performance and Licensee-specified requirements, set forth in API Spec Q1 and the applicable API product specification(s) and/or standard(s).

NOTE Licensee-specified requirements include those activities necessary to satisfy API-specified requirements.

A.3.4

design package

Records and documents required to provide evidence that the applicable product has been designed in accordance with API Spec Q1 and the requirements of the applicable product specification(s) and/or standard(s).

A.3.5

licensee

Organization that has successfully completed the application and audit process, and has been issued a license by API to use the API Monogram Mark.

A.4 Quality Management System Requirements

An organization applying the API Monogram to products shall develop, maintain, and operate at all times a quality management system conforming to API Spec Q1.

A.5 Control of the Application and Removal of the API Monogram

Each licensee shall control the application and removal of the API Monogram in accordance with the following: a)

Products that do not conform to API specified requirements shall not bear the API Monogram.

- Each licensee shall develop and maintain an API Monogram marking procedure that documents the marking/monogramming requirements specified by this annex and any applicable API product specification(s) and/or standard(s). The marking procedure shall:
 - 1) define the authority responsible for application and removal of the API Monogram and license number;
 - 2) define the method(s) used to apply the Monogram and license number;
 - 3) identify the location on the product where the API Monogram and license number are to be applied;
 - 4) require the application of the date of manufacture of the product in conjunction with the use of the API Monogram and license number:
 - 5) require that the date of manufacture, at a minimum, be two digits representing the month and two digits representing the year (e.g. 05-12 for May 2012) unless otherwise stipulated in the applicable API product specification(s) or standard(s); and
 - define the application of all other required API product specification(s) and/or standard(s) marking requirements.
- Only an API licensee shall apply the API Monogram and its designated license number to API monogrammable products.
- The API Monogram and license number, when issued, are site-specific and subsequently the API Monogram shall only be applied at that site specific licensed facility location.
- The API Monogram may be applied at any time appropriate during the production process but shall be e) removed in accordance with the licensee's API Monogram marking procedure if the product is subsequently

found to be out of conformance with any of the requirements of the applicable API product specification(s) and/or standard(s) and API Monogram Program.

For certain manufacturing processes or types of products, alternative API Monogram marking procedures may

be acceptable. Requirements for alternative API Monogram marking are detailed in the, API Alternative Marking 2 Agreement (AMA), which is available on the API Monogram Program website at: http://www.api.org/productsand-services/api-monogram-and-apigr/documents#tab certification-documents

A.6 Design Package Requirements

Each licensee and/or applicant for licensing shall maintain a current design package for all of the applicable Each licensee and/or applicant for licensing shall maintain a current design package for all of the applicable by products that fall under the scope of each Monogram license. The design package information shall provide by objective evidence that the product design meets the requirements of the applicable and most current API by the content of the applicable and most current of the applicable and t objective evidence that the product design meets the requirements of the applicable and most security product specification(s) and/or standard(s). The design package(s) shall be made available during API audits of

In specific instances, the exclusion of design activities is allowed under the Monogram Program, as detailed in Advisory # 6, available on the API Monogram Program website of http://

In specific instances, the exclusion of design activities is allowed under the Monogram Program, as detailed in Machinery # 6, available on the API Monogram Program website at http://www.api.org/products-and-services/api-monogram-and-apiqr#tab_advisories.

A.7 Manufacturing Capability

The API Monogram Program is designed to identify facilities that have demonstrated the ability to manufacture equipment that conforms to API specifications and/or standards. API may refuse initial licensing or suspend accurrent licensing based on a facility's level of manufacturing capability. If API determines that additional review is supported by the conformation of the API may refuse initial licensing or suspending the current licensing based on a facility's level of manufacturing capability. If API determines that additional review is supported by the current licensing based on a facility's level of manufacturing capability. If API determines that additional review is supported by the current licensing based on a facility's level of manufacturing capability. current licensing based on a facility's level of manufacturing capability. If API determines that additional review is

warranted, API may perform additional audits (at the organization's expense) of any primary subcontractors to be ensure their compliance with applicable specifications.

Facilities with capabilities that are limited to the processes or activities defined below do not meet the manufacturing capability requirements to produce new products, and therefore, shall not be licensed or be the basis for licensing under the API Monogram Program:

- Capabilities that are limited to performing final inspection and testing of the product, except for testing agencies as Specified in API Spec 14A and/or API Spec 6AV1
- Buying, selling and/or distributing finished products and materials;

Design and development activities;

- Tearing-down and/or re-assembling of products/components; and,
- Repairing or remanufacturing of existing, used, worn or damaged products.

SUPPLIED BY BSB EDGE UNDER LICENCE FROM API FOR HEAVY EQUIPMENT In all instances where requirements for manufacturing or manufacturing facilities are explicitly identified within the API product specification, those requirements shall take precedence over this advisory.

A. 8 Product Marking Requirements

A.8.1 General

These marking requirements shall apply only to those API Licensees wishing to mark applicable products in conjunction with the requirements of the API Monogram Program.

A.8.2 Product Specification Identification

Manufacturers shall mark products as specified by the applicable API specifications or standards. Marking shall include reference to the applicable API specification and/or standard. Unless otherwise specified, reference to

SUPPLIED BY BSB EDGE UNDER LICENCE FROM API FOR HEAVY EQUIPMENT MAINTENANCE (HEMT) - MUSCAT VIDE BSB EDGE ORDER REGISTRATION NO. ORDF03-0019 ON

the API specifications and/or standards shall be, as a minimum, "API [Document Number]" (e.g. API 6A, or API 600). Unless otherwise specified, when space allows, the marking may include use of "Spec" or "Std", as applicable (e.g. API Spec 6A or API Std 600).

A.8.3 Units

Products shall be marked with units as specified in the API specification and/or standard. If not specified, equipment shall be marked with U.S. customary (USC) units. Use of dual units [USC units and metric (SI) units] may be acceptable, if such units are allowed by the applicable product specification and/or standard.

A.8.4 Nameplates

Nameplates, when applicable, shall be made of a corrosion-resistant material unless otherwise specified by the API specification and/or standard. Nameplate shall be located as specified by the API specification and/or standard. If the location is not specified, then the licensee shall develop and maintain a procedure detailing the location to which the nameplate shall be applied. Nameplates may be attached at any time during the manufacturing process.

The API Monogram and license number shall be marked on the nameplate, in addition to the other product marking requirements specified by the applicable product specification and/or standard.

A.8.5 License Number

The API Monogram license number shall not be used unless it is marked in conjunction with the API Monogram. The license number shall be used in close proximity to the API Monogram.

A.9 API Monogram Program: Nonconformance Reporting

API solicits information on products that are found to be nonconforming with API specified requirements, as well as field failures (or malfunctions), which are judged to be caused by either specification and/or standard deficiencies or nonconformities against API specified requirements. Customers are requested to report to API all problems with API monogrammed products. A nonconformance may be reported using the API Nonconformance Reporting System available at http://ncr.api.org/ncr.aspx.

Annex B (normative)

Avoidance of Contamination of Nickel Alloys

B.1 Introduction

Nickel alloys may become contaminated during various manufacturing operations. Contamination with some substances may result in embrittlement and cracking failures, while contamination with other substances may substances may result in embrittlement and cracking failures, while contamination with other substances may result in pitting and corrosion failures.

B.2 Lubricants

Sulfur can embrittle nickel alloys at elevated temperatures, such as those used for heat treating or forging the pidel alloys. Sulfur cantaining lubricants may be used during manufacturing operations. Contamination with some substances may result in pitting and corrosion failures.

Sulfur can embrittle nickel alloys at elevated temperatures, such as those used for heat treating or forging the pidel alloys. Sulfur cantaining lubricants may be used during manufacturing but shall be completely some and arises.

Sulfur can embrittle nickel alloys at elevated temperatures, such as those used for heat treating or forging the nickel alloys. Sulfur-containing lubricants may be used during manufacturing, but shall be completely removed prior to any hot forging or heat treatment operations.

Chlorine can promote pitting corrosion of nickel alloys after long exposure. Chlorine-containing lubricants may be used for cold forming but shall be completely removed after the forming operations.

Pigmented oils and greases should be selected with care. Oils and greases with lead carbonate, zinc oxide, or other low melting point metals shall not be used. These low melting point metallic compounds can embrittle nick alloys during exposure to elevated temperatures, such as those used for heat treating or forging nickel alloys.

B.3 Marking Materials

Markers containing sulfur, chlorine, phosphorus, and low melting point metals can cause embrittlement corrosion issues as described above and shall not be used. nickel alloys. Sulfur-containing lubricants may be used during manufacturing, but shall be completely removed pri

Bibliography

[1] ASTM A193-15, Standard Specification for Alloy-Steel and Stainless Steel Bolting for High Temperature or High Pressure Service and Other Special Purpose Applications, 2015



1220 L Street, NW Washington, DC 20005-4070 USA

202-682-8000

Additional copies are available online at www.api.org/pubs

Phone Orders: 1-800-854-7179 (Toll-free in the U.S. and Canada)

303-397-7956 (Local and International)

Fax Orders: 303-397-2740

Information about API publications, programs and services is available on the web at www.api.org.

Product No. G20F02