# CSC Drafting Workspace

# MASTER DATA REPORT

Export Date: 2026-03-10 14:15:04

Total Specifications: 280

Total Parameters: 2171

Total Revisions: 0

Specs with Impact Analysis: 0

## Specification Summary

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/CCA/03/2026 | FLUID LOSS ADDITIVE FOR FRESH WATER CEMENT SLURRIES | v1 | Published | — | Master Data | 08 Mar 2026, 13:40 IST |
| ONGC/CCA/04/2026 | FLUID LOSS ADDITIVE FOR SEA WATER CEMENT SLURRIES | v1 | Published | — | Master Data | 08 Mar 2026, 13:41 IST |
| ONGC/CCA/06/2026 | HAEMATITE FOR CEMENT SLURRIES | v1 | Published | — | Master Data | 08 Mar 2026, 13:42 IST |
| ONGC/CCA/07/2026 | HIGH TEMPERATURE RETARDER | v1 | Published | — | Master Data | 08 Mar 2026, 13:43 IST |
| ONGC/CCA/08/2026 | LIQUID DEFOAMER FOR CEMENT SLURRIES | v1 | Published | — | Master Data | 08 Mar 2026, 13:44 IST |
| ONGC/CCA/09/2026 | LOW TEMPERATURE RETARDER | v1 | Published | — | Master Data | 08 Mar 2026, 13:44 IST |
| ONGC/CCA/10/2026 | MEDIUM RANGE RETARDER | v2 | Published | — | Master Data | 08 Mar 2026, 20:32 IST |
| ONGC/CCA/11/2026 | MICROFINE CEMENT | v1 | Published | — | Master Data | 08 Mar 2026, 13:50 IST |
| ONGC/CCA/12/2026 | SILICA FLOUR (COARSE) | v1 | Published | — | Master Data | 08 Mar 2026, 13:51 IST |
| ONGC/CCA/13/2026 | SILICA FLOUR (FINE) | v1 | Published | — | Master Data | 08 Mar 2026, 13:52 IST |
| ONGC/CCA/17/2026 | TURBULANCE INDUCER / FRICTION REDUCER FOR FRESH WATER CEMENT SLURRIES | v1 | Published | — | Master Data | 08 Mar 2026, 13:53 IST |
| ONGC/CCA/19/2026 | WATER WETTING PREFLUSH FOR CEMENTATION | v1 | Published | — | Master Data | 08 Mar 2026, 14:02 IST |
| ONGC/CCA/20/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY–I (40-60°C BHCT) | v1 | Published | — | Master Data | 08 Mar 2026, 14:05 IST |
| ONGC/CCA/21/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY– II (40-60°C BHCT) GAS TIGHT SLURRY | v1 | Published | — | Master Data | 08 Mar 2026, 14:11 IST |
| ONGC/CCA/22/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY-III (60-75°C BHCT) | v1 | Published | — | Master Data | 08 Mar 2026, 14:12 IST |
| ONGC/CCA/23/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY – IV ( 75-90°C BHCT ) | v1 | Published | — | Master Data | 08 Mar 2026, 14:13 IST |
| ONGC/CCA/24/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY – V (90-110°C BHCT) | v1 | Published | — | Master Data | 08 Mar 2026, 14:15 IST |
| ONGC/CCA/25/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY–VI (90-110°C BHCT) GAS TIGHT SLURRY | v1 | Published | — | Master Data | 08 Mar 2026, 14:25 IST |
| ONGC/CCA/26/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY–VII (110-140°C BHCT) | v1 | Published | — | Master Data | 08 Mar 2026, 14:26 IST |
| ONGC/CCA/27/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY–VIII (110-140°C BHCT) GAS TIGHT HEAVY WEIGHT SLURRY | v1 | Published | — | Master Data | 08 Mar 2026, 14:28 IST |
| ONGC/CCA/28/2026 | SILICA FUME | v1 | Published | — | Master Data | 08 Mar 2026, 14:35 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/CCA/29/2026 | METAKAOLIN | v1 | Published | — | Master Data | 08 Mar 2026, 14:37 IST |
| ONGC/CCA/30/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY–IX (140-170°C BHCT) FOR GAS TIGHT HEAVY WEIGHT SLURRY | v1 | Published | — | Master Data | 08 Mar 2026, 14:39 IST |
| ONGC/CCA/31/2026 | CEMENT ADDITIVE PACKAGE FOR CATEGORY–X (170-200°C BHCT) FOR GAS TIGHT HEAVY WEIGHT SLURRY | v1 | Published | — | Master Data | 08 Mar 2026, 14:41 IST |
| ONGC/CCA/32/2026 | TRI MANGANESE TETROXIDE | v1 | Published | — | Master Data | 08 Mar 2026, 14:43 IST |
| ONGC/CCA/33/2026 | DEAD BURNT MAGNESITE | v1 | Published | — | Master Data | 08 Mar 2026, 14:50 IST |
| ONGC/CCA/34/2026 | PVC RESIN | v1 | Published | — | Master Data | 08 Mar 2026, 14:56 IST |
| ONGC/CCA/35/2026 | WEIGHTED SPACER SURFACTANT | v1 | Published | — | Master Data | 08 Mar 2026, 14:56 IST |
| ONGC/CCA/36/2026 | OIL WELL CEMENT | v1 | Published | — | Master Data | 08 Mar 2026, 14:59 IST |
| ONGC/CCA/37/2026 | Graphite for Cement Slurries | v1 | Published | — | Master Data | 08 Mar 2026, 15:04 IST |
| ONGC/DFC/01/2026 | ALUMINIUM STEARATE | v2 | Published | — | Master Data | 08 Mar 2026, 16:32 IST |
| ONGC/DFC/03/2026 | BARYTES | v1 | Published | — | Master Data | 08 Mar 2026, 10:34 IST |
| ONGC/DFC/04/2026 | BENTONITE | v1 | Published | — | Master Data | 08 Mar 2026, 10:36 IST |
| ONGC/DFC/07/2026 | CALCIUM CARBONATE (COARSE) | v1 | Published | — | Master Data | 08 Mar 2026, 10:41 IST |
| ONGC/DFC/09/2026 | CALCIUM CARBONATE (MEDIUM) | v1 | Published | — | Master Data | 08 Mar 2026, 10:42 IST |
| ONGC/DFC/10/2026 | CALCIUM CARBONATE (MICRONISED) | v1 | Published | — | Master Data | 08 Mar 2026, 10:43 IST |
| ONGC/DFC/100/2026 | CLAY FREE KCL-PHPA –POLYOL (60-72°C) | v1 | Published | — | Master Data | 08 Mar 2026, 13:13 IST |
| ONGC/DFC/101/2026 | CLAY FREE KCl-PHPA –POLYOL (75-87°C) | v1 | Published | — | Master Data | 08 Mar 2026, 13:14 IST |
| ONGC/DFC/103/2026 | CLAY FREE NDDF SYSTEM | v1 | Published | — | Master Data | 08 Mar 2026, 13:15 IST |
| ONGC/DFC/104/2026 | FORMATE BASED NON | v1 | Published | — | Master Data | 08 Mar 2026, 13:16 IST |
| ONGC/DFC/105/2026 | HIGH PERFORMANCE EP LUBRICANT | v1 | Published | — | Master Data | 08 Mar 2026, 13:20 IST |
| ONGC/DFC/106/2026 | BASE OIL FOR LTSOBM | v1 | Published | — | Master Data | 08 Mar 2026, 13:24 IST |
| ONGC/DFC/107/2026 | STEARIC ACID | v1 | Published | — | Master Data | 08 Mar 2026, 13:24 IST |
| ONGC/DFC/108/2026 | OLEIC ACID | v1 | Published | — | Master Data | 08 Mar 2026, 13:24 IST |
| ONGC/DFC/109/2026 | LIGHT MAGNESIUM OXIDE | v1 | Published | — | Master Data | 08 Mar 2026, 13:25 IST |
| ONGC/DFC/11/2026 | CALCIUM CHLORIDE | v1 | Published | — | Master Data | 08 Mar 2026, 10:44 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/DFC/110/2026 | LIQUID POLY VINYL ALCOHOL (20%) | v1 | Published | — | Master Data | 08 Mar 2026, 13:28 IST |
| ONGC/DFC/111/2026 | ECO FRIENDLY DEFOAMER | v1 | Published | — | Master Data | 08 Mar 2026, 13:31 IST |
| ONGC/DFC/112/2026 | SINGLE SACK LOSS CONTROL | v1 | Published | — | Master Data | 08 Mar 2026, 13:35 IST |
| ONGC/DFC/113/2026 | SAW DUST | v1 | Published | — | Master Data | 08 Mar 2026, 13:36 IST |
| ONGC/DFC/16/2026 | CAUSTICISED LIGNITE | v1 | Published | — | Master Data | 08 Mar 2026, 10:46 IST |
| ONGC/DFC/18/2026 | CHROME FREE DEFLOCCULANT | v1 | Published | — | Master Data | 08 Mar 2026, 10:47 IST |
| ONGC/DFC/25/2026 | DRILLING DETERGENT | v1 | Published | — | Master Data | 08 Mar 2026, 10:53 IST |
| ONGC/DFC/27/2026 | E. P. LUBRICANT | v1 | Published | — | Master Data | 08 Mar 2026, 10:54 IST |
| ONGC/DFC/31/2026 | HAEMATITE FOR DRILLING FLUIDS | v1 | Published | — | Master Data | 08 Mar 2026, 10:55 IST |
| ONGC/DFC/33/2026 | HYDRATED LIME FOR DRILLING FLUIDS | v1 | Published | — | Master Data | 08 Mar 2026, 10:56 IST |
| ONGC/DFC/37/2026 | LIMESTONE POWDER | v1 | Published | — | Master Data | 08 Mar 2026, 10:56 IST |
| ONGC/DFC/41/2026 | MICA FLAKES | v1 | Published | — | Master Data | 08 Mar 2026, 10:57 IST |
| ONGC/DFC/42/2026 | MODIFIED GUAR GUM | v1 | Published | — | Master Data | 08 Mar 2026, 11:00 IST |
| ONGC/DFC/43/2026 | OXALIC ACID | v1 | Published | — | Master Data | 08 Mar 2026, 11:00 IST |
| ONGC/DFC/45/2026 | PHPA FOR DRILLING FLUIDS (HIGH TEMPERATURE) | v1 | Published | — | Master Data | 08 Mar 2026, 11:01 IST |
| ONGC/DFC/46/2026 | PHPA FOR DRILLING FLUIDS (LOW TEMPERATURE) | v1 | Published | — | Master Data | 08 Mar 2026, 11:02 IST |
| ONGC/DFC/48/2026 | POLY ANIONIC CELLULOSE (LOW VISCOSITY GRADE) | v1 | Published | — | Master Data | 08 Mar 2026, 11:04 IST |
| ONGC/DFC/49/2026 | POLY ANIONIC CELLULOSE (REGULAR GRADE) | v1 | Published | — | Master Data | 08 Mar 2026, 11:07 IST |
| ONGC/DFC/51/2026 | POLYOL (GRADE-I) | v1 | Published | — | Master Data | 08 Mar 2026, 11:24 IST |
| ONGC/DFC/52/2026 | POLYOL (GRADE-II) | v1 | Published | — | Master Data | 08 Mar 2026, 11:30 IST |
| ONGC/DFC/55/2026 | POTASSIUM HYDROXIDE FOR DRILLING FLUIDS | v1 | Published | — | Master Data | 08 Mar 2026, 11:36 IST |
| ONGC/DFC/56/2026 | POTASSIUM LIGNITE | v1 | Published | — | Master Data | 08 Mar 2026, 11:38 IST |
| ONGC/DFC/57/2026 | PREGELATINIZED STARCH | v1 | Published | — | Master Data | 08 Mar 2026, 11:39 IST |
| ONGC/DFC/59/2026 | RESINATED LIGNITE | v1 | Published | — | Master Data | 08 Mar 2026, 11:40 IST |
| ONGC/DFC/60/2026 | SODA ASH | v1 | Published | — | Master Data | 08 Mar 2026, 11:41 IST |
| ONGC/DFC/61/2026 | SODIUM BICARBONATE | v1 | Published | — | Master Data | 08 Mar 2026, 11:41 IST |
| ONGC/DFC/64/2026 | SODIUM HYDROXIDE | v1 | Published | — | Master Data | 08 Mar 2026, 11:42 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/DFC/67/2026 | SPOTTING FLUID (NON-WEIGHTED) | v1 | Published | — | Master Data | 08 Mar 2026, 11:47 IST |
| ONGC/DFC/68/2026 | SPOTTING FLUID (WEIGHTED) | v1 | Published | — | Master Data | 08 Mar 2026, 11:50 IST |
| ONGC/DFC/69/2026 | SULPHONATED ASPHALT | v1 | Published | — | Master Data | 08 Mar 2026, 11:51 IST |
| ONGC/DFC/72/2026 | WALNUT SHELL / COCONUT SHELL | v1 | Published | — | Master Data | 08 Mar 2026, 11:52 IST |
| ONGC/DFC/73/2026 | XC POLYMER FOR DRILLING FLUIDS | v1 | Published | — | Master Data | 08 Mar 2026, 12:00 IST |
| ONGC/DFC/74/2026 | ZINC CARBONATE (BASIC) | v1 | Published | — | Master Data | 08 Mar 2026, 12:00 IST |
| ONGC/DFC/75/2026 | SUPERIOR GRADE SODIUM CHLORIDE | v1 | Published | — | Master Data | 08 Mar 2026, 12:00 IST |
| ONGC/DFC/77/2026 | POTASSIUM FORMATE | v1 | Published | — | Master Data | 08 Mar 2026, 12:03 IST |
| ONGC/DFC/78/2026 | SODIUM FORMATE | v1 | Published | — | Master Data | 08 Mar 2026, 12:04 IST |
| ONGC/DFC/79/2026 | HIGH TEMPERATURE DEFLOCCULANT | v1 | Published | — | Master Data | 08 Mar 2026, 12:09 IST |
| ONGC/DFC/82/2026 | CLAY HYDRATION SUPPRESSANT (POLYAMINE) | v1 | Published | — | Master Data | 08 Mar 2026, 12:13 IST |
| ONGC/DFC/83/2026 | HIGH TEMPERATURE AND HIGH-PRESSURE FLUID LOSS REDUCING POLYMER | v1 | Published | — | Master Data | 08 Mar 2026, 12:14 IST |
| ONGC/DFC/84/2026 | NON-INVASIVE FLUID | v1 | Published | — | Master Data | 08 Mar 2026, 12:17 IST |
| ONGC/DFC/85/2026 | BACTERICIDE FOR DRILLING FLUIDS | v1 | Published | — | Master Data | 08 Mar 2026, 12:22 IST |
| ONGC/DFC/86/2026 | LTSOBM FORMULATION (10 ppg) (OFFSHORE & ONSHORE AREAS) | v2 | Published | — | Master Data | 08 Mar 2026, 20:25 IST |
| ONGC/DFC/87/2026 | LTSOBM FORMULATION (12 ppg) (OFFSHORE & ONSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 12:33 IST |
| ONGC/DFC/88/2026 | LTSOBM FORMULATION FOR HPHT WELLS | v1 | Published | — | Master Data | 08 Mar 2026, 12:45 IST |
| ONGC/DFC/89/2026 | LTSOBM FORMULATION FOR FLAT RHEOLOGY | v1 | Published | — | Master Data | 08 Mar 2026, 12:53 IST |
| ONGC/DFC/90/2026 | SPUD DRILLING FLUID (OFFSHORE & ONSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 12:55 IST |
| ONGC/DFC/91/2026 | CLAY FREE KCL-PHPA –POLYOL | v1 | Published | — | Master Data | 08 Mar 2026, 12:57 IST |
| ONGC/DFC/92/2026 | CLAY FREE KCL-PHPA–POLYOL DRILLING FLUID FOR LOWER SECTION (OFFSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 12:59 IST |
| ONGC/DFC/93/2026 | HPHT POLYMERIC BASED DRILLING FLUID SYSTEM (OFFSHORE & ONSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 13:02 IST |
| ONGC/DFC/94/2026 | GEL POLYMER DRILLING FLUID SYSTEM (OFFSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 13:04 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/DFC/95/2026 | CLAYFREE NON-DAMAGING DRILLLING FLUID SYSTEM (OFFSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 13:06 IST |
| ONGC/DFC/96/2026 | FORMATE BASED NON-DAMAGING DRILLING FLUID SYSTEM (OFFSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 13:08 IST |
| ONGC/DFC/98/2026 | GEL –POLYMER DRILLING FLUID SYSTEM (ONSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 13:10 IST |
| ONGC/DFC/99/2026 | DISPERSED DRILLING FLUID SYSTEM (ONSHORE AREAS) | v1 | Published | — | Master Data | 08 Mar 2026, 13:12 IST |
| ONGC/LPG/01/2026 | ACTIVATED ALUMINA (GRADE I AND II) | v1 | Published | — | Master Data | 10 Mar 2026, 11:30 IST |
| ONGC/LPG/04/2026 | ACTIVATED CARBON FOR AMINE FILTRATION | v1 | Published | — | Master Data | 10 Mar 2026, 11:31 IST |
| ONGC/LPG/06/2026 | AQUEOUS SULPHOLANE | v1 | Published | — | Master Data | 10 Mar 2026, 11:33 IST |
| ONGC/LPG/07/2026 | CAUSTIC SODA LYE | v1 | Published | — | Master Data | 10 Mar 2026, 11:34 IST |
| ONGC/LPG/08/2026 | ETHYL MERCAPTAN | v1 | Published | — | Master Data | 10 Mar 2026, 11:35 IST |
| ONGC/LPG/09/2026 | METHANOL (COMMERCIAL GRADE) | v1 | Published | — | Master Data | 10 Mar 2026, 11:35 IST |
| ONGC/LPG/10/2026 | METHYL DI-ETHANOL AMINE (MDEA) | v1 | Published | — | Master Data | 10 Mar 2026, 11:38 IST |
| ONGC/LPG/12/2026 | MOLECULAR SIEVE TYPE - 4Ao FOR NATURAL GAS AND LIQUID DRIERS (3 MM AND 1.5 MM DIAMETER PELLETS) | v1 | Published | — | Master Data | 10 Mar 2026, 12:01 IST |
| ONGC/LPG/14/2026 | MONOETHYLENE GLYCOL (MEG) | v1 | Published | — | Master Data | 10 Mar 2026, 12:03 IST |
| ONGC/LPG/15/2026 | NITROGEN (IOLAR – 3 GRADE OR EQUIVALENT) | v1 | Published | — | Master Data | 10 Mar 2026, 12:08 IST |
| ONGC/LPG/17/2026 | POTASSIUM HYDROXIDE FOR SULPHUR RECOVERY UNIT | v1 | Published | — | Master Data | 10 Mar 2026, 12:09 IST |
| ONGC/LPG/18/2026 | SPHERICAL CERAMIC ALUMINA BALLS (TYPE - I AND II) FOR URAN AND HAZIRA PLANTS | v1 | Published | — | Master Data | 10 Mar 2026, 12:23 IST |
| ONGC/LPG/19/2026 | STRONG ACID CATION EXCHANGE RESINS FOR USE IN DE- MINERALISATION / SOFTENING PLANTS | v1 | Published | — | Master Data | 10 Mar 2026, 12:50 IST |
| ONGC/LPG/20/2026 | STRONG BASE ANION EXCHANGE RESINS (TYPE- I) FOR USE IN DE-MINERALISATION PLANT | v1 | Published | — | Master Data | 10 Mar 2026, 12:52 IST |
| ONGC/LPG/21/2026 | TRIETHANOL AMINE | v1 | Published | — | Master Data | 10 Mar 2026, 12:52 IST |
| ONGC/LPG/22/2026 | WEAK BASE ANION EXCHANGE RESINS FOR USE IN DE- MINERALISATION PLANT | v1 | Published | — | Master Data | 10 Mar 2026, 12:53 IST |
| ONGC/LPG/23/2026 | ACCELERATED AMINE MIXTURE | v1 | Published | — | Master Data | 10 Mar 2026, 12:54 IST |
| ONGC/LPG/24/2026 | STORAGE STABILITY ADDITIVES FOR HSD | v1 | Published | — | Master Data | 10 Mar 2026, 12:57 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/LPG/25/2026 | PIPERAZINE AQUEOUS SOLUTION | v1 | Published | — | Master Data | 10 Mar 2026, 12:58 IST |
| ONGC/LPG/26/2026 | FILTER CLAY (ATTAPULGITE CLAY FOR ATF POLISHING) | v1 | Published | — | Master Data | 10 Mar 2026, 13:00 IST |
| ONGC/LPG/27/2026 | ROCK SALT | v1 | Published | — | Master Data | 10 Mar 2026, 13:01 IST |
| ONGC/LPG/28/2026 | STRONG BASE ANION EXCHANGE RESINS | v1 | Published | — | Master Data | 10 Mar 2026, 13:02 IST |
| ONGC/LPG/29/2026 | SCALE INHIBITOR, URAN PLANT | v1 | Published | — | Master Data | 10 Mar 2026, 13:03 IST |
| ONGC/LPG/32/2026 | ACID ACTIVATED MONTMORILLONITE CLAY | v1 | Published | — | Master Data | 10 Mar 2026, 13:06 IST |
| ONGC/PC/01/2026 | CHROMIUM ACETATE | v1 | Published | — | Master Data | 08 Mar 2026, 21:06 IST |
| ONGC/PC/02/2026 | CORROSION INHIBITOR FOR COMPRESSED GAS LINES OF AHMEDABAD ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:09 IST |
| ONGC/PC/03/2026 | CORROSION INHIBITOR FOR GAS LINE | v1 | Published | — | Master Data | 08 Mar 2026, 21:11 IST |
| ONGC/PC/04/2026 | CORROSION INHIBITOR FOR OIL LINE | v1 | Published | — | Master Data | 08 Mar 2026, 21:14 IST |
| ONGC/PC/05/2026 | CORROSION INHIBITOR FOR OIL AND GAS LINES IN PRESENCE OF HYDROGEN SULPHIDE (H2S) | v1 | Published | — | Master Data | 08 Mar 2026, 21:16 IST |
| ONGC/PC/06/2026 | DEMULSIFIER FOR AHMEDABAD ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:22 IST |
| ONGC/PC/07A/2026 | DEMULSIFIER FOR ANKLESHWAR FIELD, ANKLESHWAR ASSET | v1 | Published | — | Master Data | 10 Mar 2026, 13:32 IST |
| ONGC/PC/07B/2026 | DEMULSIFIER FOR GANDHAR FIELD, ANKLESHWAR ASSET | v1 | Published | — | Master Data | 10 Mar 2026, 13:36 IST |
| ONGC/PC/08/2026 | WATER SOLUBLE DEMULSIFIER FOR LAKWA FIELD OF ASSAM ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:26 IST |
| ONGC/PC/09/2026 | DEMULSIFIER FOR KATHANA FIELD, CAMBAY ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:28 IST |
| ONGC/PC/10/2026 | DEMULSIFIER FOR RAJAHMUNDRY ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:28 IST |
| ONGC/PC/11/2026 | DEMULSIFIER FOR MEHSANA ASSET | v1 | Published | — | Master Data | 10 Mar 2026, 13:54 IST |
| ONGC/PC/11B/2026 | DEMULSIFIER FOR BECHARAJI GGS-I, MEHSANA ASSET | v1 | Published | — | Master Data | 10 Mar 2026, 13:58 IST |
| ONGC/PC/12/2026 | DEMULSIFIER FOR MUMBAI ASSETS | v1 | Published | — | Master Data | 08 Mar 2026, 21:29 IST |
| ONGC/PC/13/2026 | DEOILER FOR ASSAM ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:30 IST |
| ONGC/PC/14/2026 | DE-OILER FOR GANDHAR FIELD, | v1 | Published | — | Master Data | 08 Mar 2026, 21:31 IST |
| ONGC/PC/16/2026 | DEOILER FOR NORTH SANTHAL FIELD, | v1 | Published | — | Master Data | 08 Mar 2026, 21:31 IST |
| ONGC/PC/17/2026 | DEOILER FOR RAJAHMUNDRY ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:32 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/PC/18/2026 | DEOILING POLYELECTROLYTE FOR | v1 | Published | — | Master Data | 08 Mar 2026, 21:33 IST |
| ONGC/PC/20/2026 | DE-WATERING POLYELECTROLYTE FOR WASTE WATER TREAMENT PLANT, GANDHAR FIELD, ANKLESHWAR ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:34 IST |
| ONGC/PC/24/2026 | MAGNESIUM CHLORIDE | v1 | Published | — | Master Data | 08 Mar 2026, 21:35 IST |
| ONGC/PC/25/2026 | PHPA FOR WATER SHUT OFF (HIGH TEMPERATURE) | v2 | Published | — | Master Data | 09 Mar 2026, 08:35 IST |
| ONGC/PC/26/2026 | PHPA FOR WATER SHUT OFF (LOW TEMPERATURE) | v2 | Published | — | Master Data | 09 Mar 2026, 08:40 IST |
| ONGC/PC/27/2026 | POLY ALUMINIUM CHLORIDE | v1 | Published | — | Master Data | 08 Mar 2026, 21:50 IST |
| ONGC/PC/28/2026 | POUR POINT DEPRESSANT (PPD) FOR GOPAVARAM CRUDE, RAJAHMUNDRY ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 21:52 IST |
| ONGC/PC/29/2026 | POUR POINT DEPRESSANT (PPD)/ FLOW IMPROVER FOR ASSAM ASSET) | v1 | Published | — | Master Data | 08 Mar 2026, 21:54 IST |
| ONGC/PC/34/2026 | THERMAL FLUID | v1 | Published | — | Master Data | 08 Mar 2026, 21:56 IST |
| ONGC/PC/35/2026 | TRIETHYLENE GLYCOL | v1 | Published | — | Master Data | 08 Mar 2026, 21:57 IST |
| ONGC/PC/36/2026 | TOLUOLE (INDUSTRIAL TOLUENE) | v1 | Published | — | Master Data | 08 Mar 2026, 22:02 IST |
| ONGC/PC/37/2026 | WAX DISPERSANT / INHIBITOR FOR GANDHAR FIELD, ANKLESHWAR ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 22:03 IST |
| ONGC/PC/39/2026 | MIXED XYLENE | v1 | Published | — | Master Data | 08 Mar 2026, 22:08 IST |
| ONGC/PC/40/2026 | HEXAMINE | v1 | Published | — | Master Data | 08 Mar 2026, 22:10 IST |
| ONGC/PC/41/2026 | HYDROQUINONE | v1 | Published | — | Master Data | 08 Mar 2026, 22:12 IST |
| ONGC/PC/42/2026 | NAPHTHALENE | v1 | Published | — | Master Data | 08 Mar 2026, 22:19 IST |
| ONGC/PC/46/2026 | Low Temperature Demulsifier for MH Asset | v1 | Published | — | Master Data | 08 Mar 2026, 22:26 IST |
| ONGC/PC/47/2026 | WAX INHIBITOR/DISPERSANT FOR JOTANA FIELD OF MEHSANA ASSET | v2 | Published | — | Master Data | 09 Mar 2026, 08:42 IST |
| ONGC/PC/48/2026 | Linear Alkyl Benzene Sulphonic Acid | v1 | Published | — | Master Data | 08 Mar 2026, 22:30 IST |
| ONGC/PC/49/2026 | NONYL PHENOL ETHOXYLATE (9.5 MOLE) | v1 | Published | — | Master Data | 08 Mar 2026, 22:31 IST |
| ONGC/PC/51/2026 | OIL SOLUBLE DEMULSIFIER FOR ASSAM ASSET | v1 | Published | — | Master Data | 08 Mar 2026, 22:37 IST |
| ONGC/PC/52/2026 | FLOW IMPROVER / PPD FOR B-193 OF B&S ASSET | v1 | Published | — | Master Data | 09 Mar 2026, 06:36 IST |
| ONGC/PC/53/2026 | Alkali (Soda Ash) for EOR | v1 | Published | — | Master Data | 09 Mar 2026, 06:40 IST |
| ONGC/PC/54/2026 | POLYMER for EOR | v1 | Published | — | Master Data | 09 Mar 2026, 06:59 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/PC/55/2026 | SURFACTANT for EOR | v1 | Published | — | Master Data | 09 Mar 2026, 07:07 IST |
| ONGC/PC/56/2026 | PPD/FLOW IMPROVER FOR KATHANA GGS OF CAMBAY ASSET | v1 | Published | — | Master Data | 09 Mar 2026, 07:17 IST |
| ONGC/PC/57/2026 | LIQUID HYDROGEN SULPHIDE SCAVENGER | v1 | Published | — | Master Data | 09 Mar 2026, 07:18 IST |
| ONGC/PC/58/2026 | PPD/FLOW IMPROVER FOR ANKLAV | v2 | Published | — | Master Data | 09 Mar 2026, 08:44 IST |
| ONGC/PC/59/2026 | PPD/FLOW IMPROVER FOR JOLWA GGS OF ANKLESHWAR ASSET | v1 | Published | — | Master Data | 09 Mar 2026, 07:33 IST |
| ONGC/PC/60/2026 | DEMULSIFIER FOR COMPOSITE EMULSION OF ANKLAV FIELD | v1 | Published | — | Master Data | 09 Mar 2026, 07:38 IST |
| ONGC/PC/61/2026 | CORE FOAM STICKS FOR GAS WELLS | v1 | Published | — | Master Data | 09 Mar 2026, 07:40 IST |
| ONGC/PC/62/2026 | LIQUID CATIONIC POLYELECTROLYTE FOR MEHSANA ASSET | v1 | Published | — | Master Data | 09 Mar 2026, 07:53 IST |
| ONGC/PC/63/2026 | DEMULSIFIER FOR CAUVERY ASSET | v1 | Published | — | Master Data | 09 Mar 2026, 07:54 IST |
| ONGC/PC/64/2026 | Flow Improver for Ratna (R-Series) Crude, NH Asset | v1 | Published | — | Master Data | 09 Mar 2026, 08:01 IST |
| ONGC/PC/65/2026 | Flow Improver for Asphaltic Crude | v1 | Published | — | Master Data | 09 Mar 2026, 08:05 IST |
| ONGC/PC/66/2026 | Demulsifier for Padra GGS of Cambay Asset | v1 | Published | — | Master Data | 09 Mar 2026, 08:11 IST |
| ONGC/PC/67/2026 | OVERHEAD CORROSION INHIBITOR FOR TATIPAKA REFINERY | v1 | Published | — | Master Data | 09 Mar 2026, 08:17 IST |
| ONGC/PC/68/2026 | LOW TEMPERATURE DEMULSIFIER FOR HEERA PLATFORM EMULSION | v1 | Published | — | Master Data | 09 Mar 2026, 08:19 IST |
| ONGC/PC/69/2026 | PPD/ FLOW IMPROVER FOR CRUDE OIL OF JOTANA FIELD OF MEHSANA ASSET | v1 | Published | — | Master Data | 09 Mar 2026, 08:26 IST |
| ONGC/UTL/04/2026 | ANTISCALENT | v1 | Published | — | Master Data | 10 Mar 2026, 08:59 IST |
| ONGC/UTL/05/2026 | CHLORINE | v1 | Published | — | Master Data | 10 Mar 2026, 08:59 IST |
| ONGC/UTL/06/2026 | DI-AMMONIUM PHOSPHATE | v1 | Published | — | Master Data | 10 Mar 2026, 09:00 IST |
| ONGC/UTL/09/2026 | HEDP | v1 | Published | — | Master Data | 10 Mar 2026, 09:01 IST |
| ONGC/UTL/10/2026 | HYDRATED LIME | v1 | Published | — | Master Data | 10 Mar 2026, 09:02 IST |
| ONGC/UTL/11/2026 | HYDRAZINE HYDRATE | v1 | Published | — | Master Data | 10 Mar 2026, 09:02 IST |
| ONGC/UTL/12/2026 | HYDROCHLORIC ACID | v1 | Published | — | Master Data | 10 Mar 2026, 09:03 IST |
| ONGC/UTL/14/2026 | LIQUOR AMMONIA | v1 | Published | — | Master Data | 10 Mar 2026, 09:03 IST |
| ONGC/UTL/15/2026 | MORPHOLINE | v1 | Published | — | Master Data | 10 Mar 2026, 09:04 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/UTL/16/2026 | SAND FOR GRAVITY FILTERS | v1 | Published | — | Master Data | 10 Mar 2026, 09:05 IST |
| ONGC/UTL/17/2026 | SAND FOR PRESSURE FILTERS | v1 | Published | — | Master Data | 10 Mar 2026, 09:06 IST |
| ONGC/UTL/18/2026 | SODIUM ACID PYROPHOSPHATE | v1 | Published | — | Master Data | 10 Mar 2026, 09:06 IST |
| ONGC/UTL/19/2026 | SODIUM BISULPHITE | v1 | Published | — | Master Data | 10 Mar 2026, 09:34 IST |
| ONGC/UTL/20/2026 | SODIUM HEXAMETAPHOSPHATE | v1 | Published | — | Master Data | 10 Mar 2026, 09:35 IST |
| ONGC/UTL/22/2026 | SODIUM SULPHITE | v1 | Published | — | Master Data | 10 Mar 2026, 09:36 IST |
| ONGC/UTL/23/2026 | SULPHURIC ACID FOR COOLING | v1 | Published | — | Master Data | 10 Mar 2026, 09:37 IST |
| ONGC/UTL/24/2026 | TRISODIUM PHOSPHATE (ANHYDROUS) | v1 | Published | — | Master Data | 10 Mar 2026, 09:39 IST |
| ONGC/UTL/25/2026 | UREA | v1 | Published | — | Master Data | 10 Mar 2026, 09:42 IST |
| ONGC/UTL/26/2026 | ZINC SULPHATE HEPTAHYDRATE | v1 | Published | — | Master Data | 10 Mar 2026, 09:46 IST |
| ONGC/UTL/27/2026 | BLEACHING POWDER (STABLE) | v1 | Published | — | Master Data | 10 Mar 2026, 09:47 IST |
| ONGC/UTL/28/2026 | CLEANING AND DEGREASING AGENT FOR | v1 | Published | — | Master Data | 10 Mar 2026, 09:48 IST |
| ONGC/UTL/29/2026 | CYCLOHEXYLAMINE | v1 | Published | — | Master Data | 10 Mar 2026, 09:48 IST |
| ONGC/UTL/30/2026 | SODIUM CHLORITE 25% SOLUTION | v1 | Published | — | Master Data | 10 Mar 2026, 09:49 IST |
| ONGC/UTL/31/2026 | Poly Aluminum Chloride (Solid) | v1 | Published | — | Master Data | 10 Mar 2026, 09:54 IST |
| ONGC/UTL/32/2026 | Hydrogen Peroxide | v1 | Published | — | Master Data | 10 Mar 2026, 09:55 IST |
| ONGC/WCF/01/2026 | CALCIUM BROMIDE | v1 | Published | — | Master Data | 08 Mar 2026, 15:04 IST |
| ONGC/WCF/02/2026 | CALCIUM BROMIDE -ZINC BROMIDE SOLUTION | v1 | Published | — | Master Data | 08 Mar 2026, 15:05 IST |
| ONGC/WCF/03/2026 | THIOUREA | v1 | Published | — | Master Data | 10 Mar 2026, 13:10 IST |
| ONGC/WCF/04/2026 | ZINC BROMIDE | v1 | Published | — | Master Data | 08 Mar 2026, 15:06 IST |
| ONGC/WIC/01/2026 | AMMONIUM BISULPHITE SOLUTION | v1 | Published | — | Master Data | 09 Mar 2026, 09:28 IST |
| ONGC/WIC/02/2026 | AMMONIUM THIOCYANATE | v1 | Published | — | Master Data | 09 Mar 2026, 09:30 IST |
| ONGC/WIC/03/2026 | ANTHRACITE | v1 | Published | — | Master Data | 09 Mar 2026, 09:33 IST |
| ONGC/WIC/04/2026 | BACTERICIDE (ALDEHYDE TYPE) | v1 | Published | — | Master Data | 09 Mar 2026, 09:36 IST |
| ONGC/WIC/05/2026 | BACTERICIDE (AMINE TYPE) | v1 | Published | — | Master Data | 09 Mar 2026, 09:41 IST |
| ONGC/WIC/06/2026 | CALCIUM CARBONATE SCALE INHIBITOR | v1 | Published | — | Master Data | 09 Mar 2026, 09:42 IST |
| ONGC/WIC/07/2026 | CORROSION INHIBITOR FOR EFFLUENT USED | v1 | Published | — | Master Data | 09 Mar 2026, 09:44 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/WIC/09/2026 | CORROSION INHIBITOR FOR WATER INJECTION IN MUMBAI ASSETS | v1 | Published | — | Master Data | 09 Mar 2026, 09:46 IST |
| ONGC/WIC/10/2026 | DEFOAMER FOR WATER INJECTION | v1 | Published | — | Master Data | 09 Mar 2026, 09:48 IST |
| ONGC/WIC/11/2026 | EDTA - DISODIUM SALT | v1 | Published | — | Master Data | 09 Mar 2026, 09:50 IST |
| ONGC/WIC/12/2026 | FERRIC CHLORIDE HEXAHYDRATE | v1 | Published | — | Master Data | 09 Mar 2026, 09:52 IST |
| ONGC/WIC/13/2026 | FERRIC CHLORIDE (LIQUID) | v1 | Published | — | Master Data | 09 Mar 2026, 09:53 IST |
| ONGC/WIC/14/2026 | FERRIC SULPHATE | v1 | Published | — | Master Data | 09 Mar 2026, 09:55 IST |
| ONGC/WIC/15/2026 | GARNET (COARSE) | v1 | Published | — | Master Data | 09 Mar 2026, 09:57 IST |
| ONGC/WIC/16/2026 | GARNET (FINE) | v1 | Published | — | Master Data | 09 Mar 2026, 10:41 IST |
| ONGC/WIC/18/2026 | POLYELECTROLYTE | v1 | Published | — | Master Data | 09 Mar 2026, 10:43 IST |
| ONGC/WIC/20/2026 | STRONTIUM SULPHATE SCALE INHIBITOR | v1 | Published | — | Master Data | 09 Mar 2026, 10:45 IST |
| ONGC/WIC/21/2026 | BACTERICIDE NON-ALDEHYDE NON-AMINE TYPE | v1 | Published | — | Master Data | 09 Mar 2026, 10:48 IST |
| ONGC/WIC/22/2026 | CORROSION INHIBITOR FOR WATER INJECTION, GANDHAR FIELD, ANKLESHWAR | v1 | Published | — | Master Data | 09 Mar 2026, 10:51 IST |
| ONGC/WIC/23/2026 | CORROSION INHIBITOR FOR WATER INJECTION IN ASSAM ASSET | v1 | Published | — | Master Data | 09 Mar 2026, 10:54 IST |
| ONGC/WIC/24/2026 | CORROSION INHIBITOR FOR WATER INJECTION FOR WESTERN ONSHORE ASSETS | v1 | Published | — | Master Data | 09 Mar 2026, 10:57 IST |
| ONGC/WIC/25/2026 | Glutaraldehyde | v1 | Published | — | Master Data | 09 Mar 2026, 10:58 IST |
| ONGC/WIC/26/2026 | Tetrakis (Hydroxymethyl) Phosphonium Sulphate (THPS) | v1 | Published | — | Master Data | 09 Mar 2026, 11:00 IST |
| ONGC/WIC/27/2026 | NITRITE BASED CORROSION INHIBITOR FOR KAKINADA | v1 | Published | — | Master Data | 09 Mar 2026, 11:02 IST |
| ONGC/WIC/28/2026 | ISOTHIAZOLIN BASED NON-OXIDISING BIOCIDE | v1 | Published | — | Master Data | 09 Mar 2026, 11:03 IST |
| ONGC/WIC/29/2026 | IMIDAZOLE BASED | v1 | Published | — | Master Data | 09 Mar 2026, 11:04 IST |
| ONGC/WM/03/2026 | CAUSTIC SODA FOR WATER MAKER | v1 | Published | — | Master Data | 10 Mar 2026, 08:52 IST |
| ONGC/WM/04/2026 | CITRIC ACID FOR WATER MAKER | v1 | Published | — | Master Data | 10 Mar 2026, 08:54 IST |
| ONGC/WM/14/2026 | SODIUM HYPOCHLORITE | v1 | Published | — | Master Data | 10 Mar 2026, 08:56 IST |
| ONGC/WS/01/2026 | ACETIC ACID | v1 | Published | — | Master Data | 08 Mar 2026, 15:09 IST |
| ONGC/WS/02/2026 | ACID CORROSION INHIBITOR(GRADE I,II, III, IV and IA) | v1 | Published | — | Master Data | 08 Mar 2026, 15:18 IST |
| ONGC/WS/07/2026 | AMMONIUM BIFLUORIDE | v1 | Published | — | Master Data | 08 Mar 2026, 15:21 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/WS/08/2026 | AMMONIUM CHLORIDE | v1 | Published | — | Master Data | 08 Mar 2026, 15:25 IST |
| ONGC/WS/09/2026 | AMMONIUM PERSULPHATE | v1 | Published | — | Master Data | 08 Mar 2026, 15:26 IST |
| ONGC/WS/12/2026 | BENZOIC ACID | v2 | Published | — | Master Data | 08 Mar 2026, 20:34 IST |
| ONGC/WS/13/2026 | BORAX | v1 | Published | — | Master Data | 08 Mar 2026, 15:39 IST |
| ONGC/WS/14/2026 | CITRIC ACID MONOHYDRATE | v1 | Published | — | Master Data | 08 Mar 2026, 15:40 IST |
| ONGC/WS/17/2026 | ETHYL ACETATE | v1 | Published | — | Master Data | 08 Mar 2026, 15:41 IST |
| ONGC/WS/18/2026 | ETHYLENE GLYCOL MONO BUTYL | v1 | Published | — | Master Data | 08 Mar 2026, 15:41 IST |
| ONGC/WS/21/2015 | GELLING AGENTS (GRADE I, II, III) | v1 | Published | — | Master Data | 08 Mar 2026, 16:11 IST |
| ONGC/WS/22/2026 | HIGH STRENGTH PROPPANT CERAMIC/SINTERED BAUXITE (12/20 AND 20/40) | v2 | Published | — | Master Data | 08 Mar 2026, 20:40 IST |
| ONGC/WS/24/2026 | HYDROCHLORIC ACID | v1 | Published | — | Master Data | 08 Mar 2026, 16:22 IST |
| ONGC/WS/25/2026 | HYDROXY ETHYL CELLULOSE | v1 | Published | — | Master Data | 08 Mar 2026, 16:30 IST |
| ONGC/WS/26/2026 | ISOPROPYL ALCOHOL | v1 | Published | — | Master Data | 08 Mar 2026, 16:30 IST |
| ONGC/WS/27/2026 | LOW STRENGTH PROPPANT | v2 | Published | — | Master Data | 08 Mar 2026, 18:20 IST |
| ONGC/WS/28/2026 | MONOETHYLENE GLYCOL FOR WELL | v1 | Published | — | Master Data | 08 Mar 2026, 18:21 IST |
| ONGC/WS/33/2026 | NON-EMULSIFIER FOR WATER BASE FRACTURING FLUIDS | v1 | Published | — | Master Data | 08 Mar 2026, 18:27 IST |
| ONGC/WS/35/2026 | POTASSIUM CHLORIDE FOR WELL STIMULATION | v1 | Published | — | Master Data | 08 Mar 2026, 18:28 IST |
| ONGC/WS/36/2026 | POTASSIUM IODIDE | v1 | Published | — | Master Data | 08 Mar 2026, 18:29 IST |
| ONGC/WS/41/2026 | SODIUM ACETATE (ANHYDROUS) | v1 | Published | — | Master Data | 08 Mar 2026, 18:30 IST |
| ONGC/WS/42/2026 | SODIUM NITRITE | v1 | Published | — | Master Data | 08 Mar 2026, 18:31 IST |
| ONGC/WS/44/2026 | SODIUM THIOSULPHATE FOR HYDROFRACTURING | v1 | Published | — | Master Data | 08 Mar 2026, 18:33 IST |
| ONGC/WS/46/2026 | SURFACTANT | v1 | Published | — | Master Data | 08 Mar 2026, 18:36 IST |
| ONGC/WS/47/2026 | WATER FOAMER | v1 | Published | — | Master Data | 08 Mar 2026, 18:41 IST |
| ONGC/WS/48/2015 | INTERMEDIATE STRENGTH PROPPANT | v1 | Published | — | Master Data | 08 Mar 2026, 19:02 IST |
| ONGC/WS/49/2026 | DIETHYLENE TRIAMINE PENTA- ACETIC ACID (DTPA) | v1 | Published | — | Master Data | 08 Mar 2026, 19:04 IST |
| ONGC/WS/50/2026 | POLY OXYETHYLENE SORBITAN MONO OLEATE (TWEEN-80) | v1 | Published | — | Master Data | 08 Mar 2026, 19:05 IST |
| ONGC/WS/51/2026 | SORBITAN MONO OLEATE (SPAN-80) | v1 | Published | — | Master Data | 08 Mar 2026, 19:07 IST |

| Spec Number | Chemical Name | Revision | Stage | Issue Date | Status | Last Updated |
|---|---|---|---|---|---|---|
| ONGC/WS/52/2026 | SODIUM GLUCONATE | v1 | Published | — | Master Data | 08 Mar 2026, 19:08 IST |
| ONGC/WS/53/2026 | SODIUM BROMATE | v1 | Published | — | Master Data | 08 Mar 2026, 19:09 IST |
| ONGC/WS/54/2016 | FAST HYDRATING GUAR GUM | v1 | Published | — | Master Data | 08 Mar 2026, 19:30 IST |
| ONGC/WS/55/2019 | INTERMEDIATE STRENGTH PROPPANT 30/50 (CERAMIC / SINTERED BAUXITE) | v1 | Published | — | Master Data | 08 Mar 2026, 19:36 IST |
| ONGC/WS/56/2026 | GELLANT SUSPENDING AGENT | v1 | Published | — | Master Data | 08 Mar 2026, 19:17 IST |
| ONGC/WS/57/2026 | N-Methly-2-Pyrrolidone | v1 | Published | — | Master Data | 08 Mar 2026, 19:18 IST |
| ONGC/WS/58/2026 | LIGHT WEIGHT PROPPANT 20/40 | v1 | Published | — | Master Data | 08 Mar 2026, 19:39 IST |
| ONGC/WS/60/2026 | POLY LACTIC ACID POWDER | v1 | Published | — | Master Data | 08 Mar 2026, 19:40 IST |
| ONGC/WS/61/2025 | Intermediate Strength Proppant 16/30 @6000 psi | v1 | Published | — | Master Data | 08 Mar 2026, 20:12 IST |
| ONGC/WS/62/2025 | Intermediate Strength Proppant 12/20 @6000 psi (INDIGENOUS) | v1 | Published | — | Master Data | 08 Mar 2026, 20:16 IST |
| ONGC/WS/63/2025 | GUAR GUM FOR STIMULATION (80 °C) | v1 | Published | — | Master Data | 08 Mar 2026, 20:23 IST |
| ONGC/WS/64/2026 | BORIC ACID | v1 | Published | — | Master Data | 08 Mar 2026, 19:41 IST |

## Impact Score Summary

| Spec Number | Op | Safety | Supply | No Sub | Total | Grade | Reviewed |
|---|---|---|---|---|---|---|---|
| ONGC/CCA/03/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/04/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/06/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/07/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/08/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/09/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/10/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/11/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/12/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/13/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/17/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/19/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/20/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/21/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/22/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/23/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/24/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/25/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/26/2026 | — | — | — | — | — | — | — |

| Spec Number | Op | Safety | Supply | No Sub | Total | Grade | Reviewed |
|---|---|---|---|---|---|---|---|
| ONGC/CCA/27/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/28/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/29/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/30/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/31/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/32/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/33/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/34/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/35/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/36/2026 | — | — | — | — | — | — | — |
| ONGC/CCA/37/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/01/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/03/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/04/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/07/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/09/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/10/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/100/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/101/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/103/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/104/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/105/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/106/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/107/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/108/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/109/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/11/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/110/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/111/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/112/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/113/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/16/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/18/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/25/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/27/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/31/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/33/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/37/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/41/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/42/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/43/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/45/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/46/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/48/2026 | — | — | — | — | — | — | — |

| Spec Number | Op | Safety | Supply | No Sub | Total | Grade | Reviewed |
|---|---|---|---|---|---|---|---|
| ONGC/DFC/49/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/51/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/52/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/55/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/56/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/57/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/59/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/60/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/61/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/64/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/67/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/68/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/69/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/72/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/73/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/74/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/75/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/77/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/78/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/79/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/82/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/83/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/84/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/85/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/86/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/87/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/88/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/89/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/90/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/91/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/92/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/93/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/94/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/95/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/96/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/98/2026 | — | — | — | — | — | — | — |
| ONGC/DFC/99/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/01/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/04/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/06/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/07/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/08/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/09/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/10/2026 | — | — | — | — | — | — | — |

| Spec Number | Op | Safety | Supply | No Sub | Total | Grade | Reviewed |
|---|---|---|---|---|---|---|---|
| ONGC/LPG/12/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/14/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/15/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/17/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/18/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/19/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/20/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/21/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/22/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/23/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/24/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/25/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/26/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/27/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/28/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/29/2026 | — | — | — | — | — | — | — |
| ONGC/LPG/32/2026 | — | — | — | — | — | — | — |
| ONGC/PC/01/2026 | — | — | — | — | — | — | — |
| ONGC/PC/02/2026 | — | — | — | — | — | — | — |
| ONGC/PC/03/2026 | — | — | — | — | — | — | — |
| ONGC/PC/04/2026 | — | — | — | — | — | — | — |
| ONGC/PC/05/2026 | — | — | — | — | — | — | — |
| ONGC/PC/06/2026 | — | — | — | — | — | — | — |
| ONGC/PC/07A/2026 | — | — | — | — | — | — | — |
| ONGC/PC/07B/2026 | — | — | — | — | — | — | — |
| ONGC/PC/08/2026 | — | — | — | — | — | — | — |
| ONGC/PC/09/2026 | — | — | — | — | — | — | — |
| ONGC/PC/10/2026 | — | — | — | — | — | — | — |
| ONGC/PC/11/2026 | — | — | — | — | — | — | — |
| ONGC/PC/11B/2026 | — | — | — | — | — | — | — |
| ONGC/PC/12/2026 | — | — | — | — | — | — | — |
| ONGC/PC/13/2026 | — | — | — | — | — | — | — |
| ONGC/PC/14/2026 | — | — | — | — | — | — | — |
| ONGC/PC/16/2026 | — | — | — | — | — | — | — |
| ONGC/PC/17/2026 | — | — | — | — | — | — | — |
| ONGC/PC/18/2026 | — | — | — | — | — | — | — |
| ONGC/PC/20/2026 | — | — | — | — | — | — | — |
| ONGC/PC/24/2026 | — | — | — | — | — | — | — |
| ONGC/PC/25/2026 | — | — | — | — | — | — | — |
| ONGC/PC/26/2026 | — | — | — | — | — | — | — |
| ONGC/PC/27/2026 | — | — | — | — | — | — | — |
| ONGC/PC/28/2026 | — | — | — | — | — | — | — |
| ONGC/PC/29/2026 | — | — | — | — | — | — | — |
| ONGC/PC/34/2026 | — | — | — | — | — | — | — |

| Spec Number | Op | Safety | Supply | No Sub | Total | Grade | Reviewed |
|---|---|---|---|---|---|---|---|
| ONGC/PC/35/2026 | — | — | — | — | — | — | — |
| ONGC/PC/36/2026 | — | — | — | — | — | — | — |
| ONGC/PC/37/2026 | — | — | — | — | — | — | — |
| ONGC/PC/39/2026 | — | — | — | — | — | — | — |
| ONGC/PC/40/2026 | — | — | — | — | — | — | — |
| ONGC/PC/41/2026 | — | — | — | — | — | — | — |
| ONGC/PC/42/2026 | — | — | — | — | — | — | — |
| ONGC/PC/46/2026 | — | — | — | — | — | — | — |
| ONGC/PC/47/2026 | — | — | — | — | — | — | — |
| ONGC/PC/48/2026 | — | — | — | — | — | — | — |
| ONGC/PC/49/2026 | — | — | — | — | — | — | — |
| ONGC/PC/51/2026 | — | — | — | — | — | — | — |
| ONGC/PC/52/2026 | — | — | — | — | — | — | — |
| ONGC/PC/53/2026 | — | — | — | — | — | — | — |
| ONGC/PC/54/2026 | — | — | — | — | — | — | — |
| ONGC/PC/55/2026 | — | — | — | — | — | — | — |
| ONGC/PC/56/2026 | — | — | — | — | — | — | — |
| ONGC/PC/57/2026 | — | — | — | — | — | — | — |
| ONGC/PC/58/2026 | — | — | — | — | — | — | — |
| ONGC/PC/59/2026 | — | — | — | — | — | — | — |
| ONGC/PC/60/2026 | — | — | — | — | — | — | — |
| ONGC/PC/61/2026 | — | — | — | — | — | — | — |
| ONGC/PC/62/2026 | — | — | — | — | — | — | — |
| ONGC/PC/63/2026 | — | — | — | — | — | — | — |
| ONGC/PC/64/2026 | — | — | — | — | — | — | — |
| ONGC/PC/65/2026 | — | — | — | — | — | — | — |
| ONGC/PC/66/2026 | — | — | — | — | — | — | — |
| ONGC/PC/67/2026 | — | — | — | — | — | — | — |
| ONGC/PC/68/2026 | — | — | — | — | — | — | — |
| ONGC/PC/69/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/04/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/05/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/06/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/09/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/10/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/11/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/12/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/14/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/15/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/16/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/17/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/18/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/19/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/20/2026 | — | — | — | — | — | — | — |

| Spec Number | Op | Safety | Supply | No Sub | Total | Grade | Reviewed |
|---|---|---|---|---|---|---|---|
| ONGC/UTL/22/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/23/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/24/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/25/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/26/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/27/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/28/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/29/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/30/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/31/2026 | — | — | — | — | — | — | — |
| ONGC/UTL/32/2026 | — | — | — | — | — | — | — |
| ONGC/WCF/01/2026 | — | — | — | — | — | — | — |
| ONGC/WCF/02/2026 | — | — | — | — | — | — | — |
| ONGC/WCF/03/2026 | — | — | — | — | — | — | — |
| ONGC/WCF/04/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/01/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/02/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/03/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/04/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/05/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/06/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/07/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/09/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/10/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/11/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/12/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/13/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/14/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/15/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/16/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/18/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/20/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/21/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/22/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/23/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/24/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/25/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/26/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/27/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/28/2026 | — | — | — | — | — | — | — |
| ONGC/WIC/29/2026 | — | — | — | — | — | — | — |
| ONGC/WM/03/2026 | — | — | — | — | — | — | — |
| ONGC/WM/04/2026 | — | — | — | — | — | — | — |
| ONGC/WM/14/2026 | — | — | — | — | — | — | — |

| Spec Number | Op | Safety | Supply | No Sub | Total | Grade | Reviewed |
|---|---|---|---|---|---|---|---|
| ONGC/WS/01/2026 | — | — | — | — | — | — | — |
| ONGC/WS/02/2026 | — | — | — | — | — | — | — |
| ONGC/WS/07/2026 | — | — | — | — | — | — | — |
| ONGC/WS/08/2026 | — | — | — | — | — | — | — |
| ONGC/WS/09/2026 | — | — | — | — | — | — | — |
| ONGC/WS/12/2026 | — | — | — | — | — | — | — |
| ONGC/WS/13/2026 | — | — | — | — | — | — | — |
| ONGC/WS/14/2026 | — | — | — | — | — | — | — |
| ONGC/WS/17/2026 | — | — | — | — | — | — | — |
| ONGC/WS/18/2026 | — | — | — | — | — | — | — |
| ONGC/WS/21/2015 | — | — | — | — | — | — | — |
| ONGC/WS/22/2026 | — | — | — | — | — | — | — |
| ONGC/WS/24/2026 | — | — | — | — | — | — | — |
| ONGC/WS/25/2026 | — | — | — | — | — | — | — |
| ONGC/WS/26/2026 | — | — | — | — | — | — | — |
| ONGC/WS/27/2026 | — | — | — | — | — | — | — |
| ONGC/WS/28/2026 | — | — | — | — | — | — | — |
| ONGC/WS/33/2026 | — | — | — | — | — | — | — |
| ONGC/WS/35/2026 | — | — | — | — | — | — | — |
| ONGC/WS/36/2026 | — | — | — | — | — | — | — |
| ONGC/WS/41/2026 | — | — | — | — | — | — | — |
| ONGC/WS/42/2026 | — | — | — | — | — | — | — |
| ONGC/WS/44/2026 | — | — | — | — | — | — | — |
| ONGC/WS/46/2026 | — | — | — | — | — | — | — |
| ONGC/WS/47/2026 | — | — | — | — | — | — | — |
| ONGC/WS/48/2015 | — | — | — | — | — | — | — |
| ONGC/WS/49/2026 | — | — | — | — | — | — | — |
| ONGC/WS/50/2026 | — | — | — | — | — | — | — |
| ONGC/WS/51/2026 | — | — | — | — | — | — | — |
| ONGC/WS/52/2026 | — | — | — | — | — | — | — |
| ONGC/WS/53/2026 | — | — | — | — | — | — | — |
| ONGC/WS/54/2016 | — | — | — | — | — | — | — |
| ONGC/WS/55/2019 | — | — | — | — | — | — | — |
| ONGC/WS/56/2026 | — | — | — | — | — | — | — |
| ONGC/WS/57/2026 | — | — | — | — | — | — | — |
| ONGC/WS/58/2026 | — | — | — | — | — | — | — |
| ONGC/WS/60/2026 | — | — | — | — | — | — | — |
| ONGC/WS/61/2025 | — | — | — | — | — | — | — |
| ONGC/WS/62/2025 | — | — | — | — | — | — | — |
| ONGC/WS/63/2025 | — | — | — | — | — | — | — |
| ONGC/WS/64/2026 | — | — | — | — | — | — | — |

# Parameter Tables by Specification

## 1. ONGC/CCA/03/2026 — FLUID LOSS ADDITIVE FOR FRESH WATER CEMENT SLURRIES

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:40 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

### *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

### *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of free flowing powder, free from visible impurities. | — |
| 2 | Solubilityof the Additive in Fresh water at 24±2°C | Shall be soluble / dispersible | — |
| 3 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 4 | Filtration loss at 1000 psi pressure and 90°C of 44% slurry made from API Class ‘G’ (HSR) Type Cement and Fresh water, ml | Record the filtration loss of the neat slurry | — |
| 5 | Filtration loss at 1000 psi and 90°C of 44% slurry made from API Class ‘G’ (HSR) Type Cement and Fresh water and treated with 1.0% BWOC of the sample, ml | Filtration loss of the treated slurry should not be more than 20% of the value obtained for the neat slurry | — |
| 6 | Consistency of the Treated slurry as before and after the temperature is raised from 24°C to 90°C, Bc, using an Atmospheric Consistometer. Initial and 60 minutes consistency of the treated slurry when temperature is raised, Bc | 30 (Maximum) | — |
| 7 | API Free Water Content of the Treated slurry, ml | API Free Water Content of the treated slurry shall be nil | — |
| 8 | Thickening Time of 44% slurry made from API Class ‘G’ (HSR) Type Cement and Fresh water at 6000 psi and 90°C (raised in 30 minutes), minutes | Record the Thickening Time of the neat slurry | — |
| 9 | Thickening Time of 44% slurry made from API Class ‘G’ (HSR) Type Cement and Fresh water and treated with 0.5% BWOC of the sample at 6000 psi and 90°C (raised in 30 minutes). minutes | Shall not be more than 2 times the value obtained for the neat slurry | — |
| 10 | Thickening Time of 44% slurry made from API Class ‘G’ (HSR) Type Cement and Fresh water at 6000 psi and 120°C (raised in 40 minutes). minutes | Record the Thickening Time of the neat slurry | — |
| 11 | Thickening Time of 44% slurry made from API Class ‘G’ (HSR) Type Cement and Fresh water and treated with 1.0% BWOC of the sample at 6,000 psi and 120°C (raised in 40 minutes). Minutes. | Should not be less than the value obtained for the neat slurry | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 2. ONGC/CCA/04/2026 — FLUID LOSS ADDITIVE FOR SEA WATER CEMENT SLURRIES

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of free flowing powder, free from visible impurities. | — |
| 2 | Solubility / Dispersibility of the Additive in Sea Water at 24±2°C | Shall be soluble / dispersible | — |
| 3 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 4 | Filtration loss at 62°C and 1000 psi, as per API Test Procedure of neat slurry, ml | Record the filtration loss of the neat slurry | — |
| 5 | filtration loss at 62°C and 1000 psi of teated slurry with 1.0% BWOC of the sample, ml | Shall not be more than 15% of value obtained for neat slurry | — |
| 6 | Consistency of the Treated slurry when temperature is raised from 24 to 62°C, using an Atmospheric Consistometer, Bc | 35 (Maximum) | — |
| 7 | APIFreeWaterContentof the Treated slurry, ml | API Free Water Content of the treated slurry shall be nil | — |
| 8 | Thickening time of neat slurry at 6000 psi and 90°C (raised in 30 minutes), minutes | Record the Thickening Time of the neat slurry | — |
| 9 | Thickening Time of treated slurry with 0.5% BWOC of the sample at 6000 psi and 90°C (raised in 30 minutes), minutes | Thickening Time of the treated slurry shall not be more than 2 times the value obtained for the neat slurry | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 3. ONGC/CCA/06/2026 — HAEMATITE FOR CEMENT SLURRIES

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:42 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Specific Gravity at 24±2°C | 4.90 (Minimum) | — |
| 3 | Water Soluble Matter, percent by mass | 0.1 (Maximum) | — |
| 4 | Purity as $Fe_2O_3$, percent by mass | 94.0 (Minimum) | — |
| 5 | Wet Sieve Analysis : Fraction retained on 100 Mesh BSS or equivalent sieve, percent by mass | Nil | — |
| 6 | Wet Sieve Analysis : Fraction retained on 200 Mesh BSS or equivalent sieve, percent by mass | 25 ± 5 | — |
| 7 | Wet Sieve Analysis : Fraction retained on 300 Mesh BSS or equivalent sieve, percent by mass | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 4. ONGC/CCA/07/2026 — HIGH TEMPERATURE RETARDER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:43 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of free flowing powder, free from visible impurities. | — |
| 2 | Solubilityof the sample in fresh water at 24±2°C | Freely soluble | — |
| 3 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 4 | Thickening Time of treated slurry (44% slurry, made from API Class ‘G’ (HSR) Type Cement and fresh water and treated with 33% silica flour and 1.0% BWOC of the sample at 10,000 psi pressure and 150°C (raised in 40 minutes). minutes | 120 (Minimum) | — |
| 5 | Consistency of the treated slurry in a High Pressure Consistometer, Bc | Shall remain below 20 Bc for period equal to at least 75% of thickening time as obtained above | — |
| 6 | API Free Water Content (44% slurry, made from API Class ‘G’ (HSR) Type Cement and Fresh water and treated with 1.0% BWOC of the sample at 24±2°C and Atmospheric Pressure, ml | Shall not be more than 10% by volume ofthe total slurry | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 5. ONGC/CCA/08/2026 — LIQUID DEFOAMER FOR CEMENT SLURRIES

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:44 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of clear liquid or emulsion, free from all visible impurities and shall easily be pourable from its container. | — |
| 2 | Calculated Specific gravity of cement slurry (184 ml of Fresh water add 0.8% Retarder, 0.8% Turbulence Inducer, and 1% filtration loss Additive (BWOC) Add 400 g API Class ‘G’ (HSR) Cement blended with 33% Silica Flour (BWOC) to obtain a 46% slurry) | Record the calculated SG of the cement slurry | — |
| 3 | Specific Gravity of the defoamer treated (0.1% (1000 ppm BWOC) slurry | Should not be lower by more than 0.02 from the calculated SG of the cement slurry | — |
| 4 | Specific Gravity of the antifoamer treated slurry | SG of the antifoamer treated slurry should not be lower by more than 0.02 from the calculated SG of cement slurry | — |
| 5 | Thickening Time of untreated slurry at 12000 psi pressure and 150°C (raised in 40 minutes), minutes | Record the Thickening Time of the untreated slurry | — |
| 6 | Thickening Time of the treated slurry (0.1% (1000 ppm) BWOC of the Defoamer sample) at 12000 psi pressure and 150°C (raised in 40 minutes). minutes | Should not be less than the thickening time of the untreated slurry | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 6. ONGC/CCA/09/2026 — LOW TEMPERATURE RETARDER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:44 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of free flowing powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | Solubility of 2% (w/v) sample in Fresh water at 24±2°C. | Should be completely soluble | — |
| 4 | Thickening Time of the treated slurry (consisting of 100 g of API Class ‘G’ (HSR) Cement, 44 g of Fresh water and 0.3 g of Low Temperature Retarder sample, at 6000 psi pressure and 90°C temperature (raised in 30 minutes), minutes | 130 (Minimum) | — |
| 5 | Consistency of the treated Cement slurry using a High Pressure Consistometer, Bc | Shall remain below 20 Bc for period equal to at least 75% of the thickening time as obtained above | — |
| 6 | Free Water separation of the Cement slurry (consisting of 100 g of Class ‘G’ (HSR) Cement, 44 g of Fresh water and 1 g of Low Temperature Retarder sample, at 24°C Temperature and Atmospheric Pressure), ml | Shall not be more than 10% by volumeof the total slurry | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 7. ONGC/CCA/10/2026 — MEDIUM RANGE RETARDER

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 20:32 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical Requirement | The material shall be a free flowing powder, free from visible impurities. | — |
| 2 | Solubility in Fresh water at 24±2°C | Should be freely soluble | — |
| 3 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 4 | Thickening Time of the treated slurry (46% slurry, API Class ‘G’ (HSR) Cement and Fresh water and treated with 33% Silica Flour and 0.3% BWOC of the sample at 10,000 psi and 100° C, (raised in 40 minutes), minutes | 120 (Minimum) | — |
| 5 | Consistency of the treated slurry using a High Pressure Consistometer, Bc | Shall remain below 20 Bc for period equal to at least 75% of the thickening time | — |
| 6 | API Free Water Content of 44% slurry prepared from API Class ‘G’ (HSR) Type Cement and Fresh water and treated with 1% BWOC of the sample at 24°C Temperature and Atmospheric Pressure | Shall not be more than 10% by volume of the total slurry | — |
| 7 | Thickening time of the treated slurry (46% slurry made from API Class ‘G’ (HSR) Cement and Fresh water and treated with 33% Silica flour of ONGC specifications and 0.5% BWOC of the sample at 10,000 psi pressure and 120°C (raised in 40 minutes), minutes | 240 (Minimum) | — |
| 8 | Consistency of the treated slurry using a High Pressure Consistometer | Consistency of the treated slurry shall remain below 20 Bc for period equal to at least 75% of the thickening time | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 8. ONGC/CCA/11/2026 — MICROFINE CEMENT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:50 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Surface Area (Blaine), cm2 / g | 6500 (Minimum) | — |
| 3 | Fraction up to 5 microns, percent by mass | 50 (Minimum) | — |
| 4 | Fraction up to 15 microns, percent by mass | 100 | — |
| 5 | Density of Microfine Cementand 100% Fresh water (BWOC) slurry, g/cc | 1.50 ± 0.02 | — |
| 6 | Free water content, percent by mass | 1.4 (Maximum) | — |
| 7 | Thickening Time of Microfine Cement and 100% fresh water (BWOC) slurry at 60°C and3000 psi (raised simultaneously in 30 minutes), minutes | 70 (Minimum) | — |
| 8 | Consistency of Cement slurry during 15 - 30 minutes of thickening time test, Bc | 20 (Maximum) | — |
| 9 | Compressive Strength (psi) of Microfine Cement and 100% fresh water (BWOC) slurry at 38°C and atmospheric pressure after 8 hrs | 100 (Minimum) | — |
| 10 | Compressive Strength (psi) of Microfine Cement and 100% fresh water (BWOC) slurry at 90°C and 3000 psi pressure after 24 hrs | 1000 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 9. ONGC/CCA/12/2026 — SILICA FLOUR (COARSE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:51 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of Crystalline free flowing powder (shall not be amorphous), free from visible impurities and lumps. | — |
| 2 | Dry Sieve Analysis : Fraction retained on 52 Mesh BSS or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 3 | Dry Sieve Analysis : Fraction retained on 120 Mesh BSS or equivalent sieve, percent by mass | 60.0 (Minimum) | — |
| 4 | Dry Sieve Analysis : Fraction passing through 200 Mesh BSS or equivalent sieve, percent by mass | 2.0 (Maximum) | — |
| 5 | Wet Sieve Analysis, Fraction retained on 350 Mesh BSS or equivalent sieve, percent by mass | 65 (Minimum) | — |
| 6 | Silica Content as SiO2,percent by mass | 98.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 10. ONGC/CCA/13/2026 — SILICA FLOUR (FINE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:52 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of Crystalline free flowing powder (shall not be amorphous), free from visible impurities and lumps. | — |
| 2 | Dry Sieve Analysis : Fraction retained on 120 Mesh BSS or equivalent sieve, percent by mass | 20 (Maximum) | — |
| 3 | Dry Sieve Analysis : Fraction retained on 200 Mesh BSS or equivalent sieve, percent by mass | 45 (Maximum) | — |
| 4 | Dry Sieve Analysis : Fraction retained on 350 Mesh BSS or equivalent sieve, percent by mass | — | — |
| 5 | Wet Sieve Analysis, Fraction retained on 350 Mesh BSS or equivalent sieve, percent by mass | 65 (Minimum) | — |
| 6 | Silica Content as SiO2,percent by mass | 98.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 11. ONGC/CCA/17/2026 — TURBULANCE INDUCER / FRICTION REDUCER FOR FRESH WATER CEMENT SLURRIES

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:53 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Solubility of 2% (w/v) sample in fresh water at 24±2°C | Should be completely soluble | — |
| 3 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 4 | Critical Velocity of the neat slurry (44% Cement slurry by mixing API Class ‘G’ Oil Well Cement (HSR) and Fresh water, Critical Velocity at 80°C and ambient pressure for 3” equivalent diameter | Record the Critical Velocity | — |
| 5 | Critical Velocity of the treated slurry (0.8% BWOC (Max) of the sample) | Shall not be more than 50% of the value obtained for neat slurry | — |
| 6 | Thickening Time of neat at 8200 psi and 100°C (raised in 34 minutes), minutes | Record the thickening Time of the neat slurry | — |
| 7 | Thickening Time of treated (1.0% BWOC of sample) slurry with at 8200 psi and 100°C (raised in 34 minutes), minutes | Shall be more than that of the neat slurry | — |
| 8 | Filtration Loss of the neat slurry at 90 °C and 1000 psi, ml | Record the filtration loss | — |
| 9 | Filtration Loss of the treated (1.0% BWOC of the sample) at 90°C and 1000 psi, ml | Shall not be more than 75% of the valueobtained for neat slurry | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 12. ONGC/CCA/19/2026 — WATER WETTING PREFLUSH FOR CEMENTATION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of clear liquid, free from visual impurities. | — |
| 2 | Miscibility in Water at 24±2°C | Shall be miscible in all proportions | — |
| 3 | Surface Tension of 0.5% (w/v) Solution of Preflush in Water at 24±2°C, dynes / cm | 30 (Maximum) | — |
| 4 | Wettability characteristics with Bentonite | Shall be water wet | — |
| 5 | Measure rheological characteristics at 1000 psi and 90 0C. (Mix API Class ‘G’ (HSR) Type Cement (44%) slurry in fresh water and Spacer solution containing 0.5% (w/v) of the Additive in the ratio of 7 : 3 | Non viscous mass should be formed | — |
| 6 | Thickening time of the neat slurry at 1000 psi and 90°C, minutes | Record Thickening time | — |
| 7 | Thickening Time at 1000 psi and 90 °C (Mix API Class ‘G’ (HSR) Type Cement (44%) slurry in fresh water and Spacer solution containing 0.5% (w/v) of the Additive in the ratio of 7:3, minutes | There should not be decrease in thickening time with respect to neat test slurry | — |
| 8 | Rheology of Cl-CLS mud Spacer solution (containing 0.5% (w/v) of the Additive in the ratio of 7:3. Mix it thoroughly on Hamilton Beach Mixer for 5 minutes at low speed and observe rheology) | It should not form viscous mass | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 13. ONGC/CCA/20/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY–I (40-60°C BHCT)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:05 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a)Solid Additives : The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Solubility/ Miscibility / Dispersibility of the additives as per recommended dosage indicated in the package in Distilled water at 24±2°C. (a)Preparation of slurry: Prepare 44%slurry with API Class ‘G’ Cement, recommended dosage of the vendor’s additives and laboratory tap water. (b) Test Conditions: Pressure: 3500 psi Temperature: 60°C, Raising Time: 30 minutes, BHST: 1.4 times of BHCT (contd.) | Shall be soluble /miscible/ dispersible | — |
| 3 | Specific Gravity | 1.90±0.02 | — |
| 4 | Thickening Time, minutes | 220±30 | — |
| 5 | Initial Consistency, Bc | 15 (Maximum) | — |
| 6 | Filtration Loss, ml | 200 (Maximum) | — |
| 7 | Free Fluid, percent by volume | 0.5 (Maximum) | — |
| 8 | Critical Velocity (3” Diameter), ft/sec | 7 (Maximum) | — |
| 9 | Compressive Strength, 24 hrs, psi | 2000 (Minimum) | — |
| 10 | Stability test : Difference in densities of top and bottom of set cement column, gm/cc | 0.05 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 14. ONGC/CCA/21/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY– II (40-60°C BHCT) GAS TIGHT SLURRY

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:11 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State: | a) Solid Additives: The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Solubility/ Miscibility / Dispersibility of the Additives as per recommended dosage indicated in the package in Distilled water at 24±2°C. (a) Preparation of slurry: Prepare 44%slurry with API Class ‘G’ Cement, recommended dosage of the vendor’s additives and laboratory tap water. (b) Test Conditions: Pressure: 3500 psi Temperature: 60°C, Raising Time: 30 minutes, BHST: 1.4 times of BHCT | Shall be soluble /miscible/ dispersible | — |
| 3 | Specific Gravity | 1.90 ± 0.02 | — |
| 4 | Thickening Time, minutes | 220 ± 30 | — |
| 5 | Initial Consistency, Bc | 20 (Maximum) | — |
| 6 | Filtration Loss, ml | 50 (Maximum) | — |
| 7 | Free Fluid, percent by volume | Nil | — |
| 8 | Critical Velocity (3” Diameter), ft/sec | 8 (Maximum) | — |
| 9 | Compressive Strength, 24 hrs, psi | 2000 (Minimum) | — |
| 10 | Stability test: Difference in densities of top and bottom of set cement column, gm/cc | 0.05 (Maximum) | — |
| 11 | Static Gel Strength Test (SGS) : Transition time from 100 to 500 lbf/100sq. ft, minutes | 30 (maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 15. ONGC/CCA/22/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY-III (60-75°C BHCT)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:12 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a) Solid Additives: The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Solubility/ Miscibility / Dispersibility of the Additives as per recommended dosage indicated in the package in Distilled water at 24±2°C. (a) Preparation of slurry: Prepare 44% slurry with API Class ‘G’ Cement, recommended dosage of the vendor’s additives and laboratory tap water. (b) Test Conditions: Pressure: 4500 psi Temperature: 75°C, Raising Time: 30 minutes, BHST: 1.4 times of BHCT | Shall be soluble /miscible/ dispersible | — |
| 3 | Specific Gravity | 1.90±0.02 | — |
| 4 | Thickening Time, minutes | 220±30 | — |
| 5 | Initial Consistency, Bc | 15 (Maximum) | — |
| 6 | Filtration Loss, ml | 200 (Maximum) | — |
| 7 | Free Fluid, percent by volume | 0.5 (Maximum) | — |
| 8 | Critical Velocity (3” Diameter), ft/sec | 7 (Maximum) | — |
| 9 | Compressive Strength, 24 hrs, psi | 2000 (Minimum) | — |
| 10 | Stability test : Difference in densities of top and bottom of set cement column, gm/cc | 0.05 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 16. ONGC/CCA/23/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY – IV ( 75-90°C BHCT )

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:13 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a) Solid Additives : The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Solubility/ Miscibility / Dispersibility of the Additives as per recommended dosage indicated in the package in Distilled water at 24±2°C. (a) Preparation of slurry: Prepare 46% slurry with API Class ‘G’ Cement, 35% (BWOC) Silica flour, recommended dosage of the vendor’s additives and laboratory tap water. Test Conditions: Pressure: 5000 psi Temperature: 90°C, Raising Time: 30 minutes, BHST: 1.4 times of BHCT | Shall be soluble /miscible/ dispersible | — |
| 3 | Specific Gravity | 1.97±0.02 | — |
| 4 | Thickening Time, minutes | 250±30 | — |
| 5 | Initial Consistency, Bc | 20 (Maximum) | — |
| 6 | Filtration Loss, ml | 150 (Maximum) | — |
| 7 | Free Fluid, percent by volume | 0.1 (Maximum) | — |
| 8 | Critical Velocity (3” Diameter), ft/sec | 7 (Maximum) | — |
| 9 | Compressive Strength, 24 hrs, psi | 2000 (Minimum) | — |
| 10 | Stability test : Difference in densities of top and bottom cement of set column, gm/cc | 0.05 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 17. ONGC/CCA/24/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY – V (90-110°C BHCT)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:15 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a) Solid Additives : The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Solubility/ Miscibility / Dispersibility of the Additives as per recommended dosage indicated in the package in Distilled water at 24±2°C. (a) Preparation of slurry: Prepare 46% slurry with API Class ‘G’ Cement, 35% (BWOC) Silica flour, recommended dosage of the vendor’s additives and laboratory tap water. (b) Test Conditions: Pressure: 6000 psi Temperature: 110°C, Raising Time: 40 minutes, BHST: 1.4 times of BHCT | Shall be soluble /miscible/ dispersible | — |
| 3 | Specific Gravity | 1.97±0.02 | — |
| 4 | Thickening Time, minutes | 300±30 | — |
| 5 | Initial Consistency, Bc | 20 (Maximum) | — |
| 6 | Filtration Loss, ml | 100 (Maximum) | — |
| 7 | Free Fluid, percent by volume | 0.1 (Maximum) | — |
| 8 | Critical Velocity (3” Diameter), ft/sec | 8 (Maximum) | — |
| 9 | Compressive Strength, 24 hrs, psi | 2000 (Minimum) | — |
| 10 | Stability test : Difference in densities of top and bottom of set cement column, gm/cc | 0.05 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 18. ONGC/CCA/25/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY–VI (90-110°C BHCT) GAS TIGHT SLURRY

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:25 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a) Solid Additives : The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Solubility/ Miscibility / Dispersibility of the Additives as per recommended dosage indicated in the package in Distilled water at 24±2°C. (a) Preparation of slurry: Prepare 46% slurry with API Class ‘G’ Cement, 35% (BWOC) Silica flour, recommended dosage of the vendor’s additives and laboratory tap water. (b) Test Conditions: Pressure 6000 psi, Temperature: 110°C, Rising Time: 40 minutes, BHST: 1.4 times BHCT (contd.) | Shall be soluble /miscible/ dispersible | — |
| 3 | Specific Gravity | 1.97±0.02 | — |
| 4 | Thickening Time, minutes | 300±30 | — |
| 5 | Initial Consistency, Bc | 20 (Maximum) | — |
| 6 | Filtration loss, ml | 50 (Maximum) | — |
| 7 | Free Fluid, percent by volume | Nil | — |
| 8 | Critical Velocity (3” Diameter), ft/sec | 9 (Maximum) | — |
| 9 | Compressive Strength, 24 hrs, psi | 2000 (Minimum) | — |
| 10 | Stability test: Difference in densities of top and bottom of set cement column, gm/cc | 0.05 (Maximum) | — |
| 11 | Static Gel Strength (SGS) test: Transition time from 100 to 500 lbf/100 sq.ft, minutes | 30 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 19. ONGC/CCA/26/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY–VII (110-140°C BHCT)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:26 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a)SolidAdditives: The material shall be in the powder, free impurities. form from of fine visible b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Solubility/ Miscibility / Dispersibility of the Additives as per recommended dosage indicated in the package in Distilled water at 24±2°C. (a) Preparation of slurry: Prepare 46% slurry with API Class ‘G’ Cement, 35% (BWOC) Silica flour, recommended dosage of the vendor’s additives and laboratory tap water. Mixing Fluid: 46% BWOC. (b) Test Conditions: Pressure-10000 psi, Temperature-140°C, Raising Time-40 minutes, BHST- 1.4 times BHCT | Shall be soluble /miscible/ dispersible. | — |
| 3 | Specific Gravity | 1.97±0.02 | — |
| 4 | Thickening Time, minutes | 350±30 | — |
| 5 | Initial Consistency, Bc | 20 (Maximum) | — |
| 6 | Filtration loss, ml | 75 (Maximum) | — |
| 7 | Free Fluid, percent by volume | 0.1 (Maximum) | — |
| 8 | Critical Velocity (3” Diameter), ft/sec | 8 (Maximum) | — |
| 9 | Compressive Strength, 24 hrs, psi | 2000 (Minimum) | — |
| 10 | Stability test : Difference in densities of top and bottom of set cement column, gm/cc | 0.05 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 20. ONGC/CCA/27/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY–VIII (110-140°C BHCT) GAS TIGHT HEAVY WEIGHT SLURRY

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:28 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a) Solid Additives: The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Solubility/ Miscibility / Dispersibility of the Additives as per recommended dosage in Distilled water at 24±2°C. (a) Preparation of slurry: Prepare the cement slurry with API Class ‘G’ Cement, 35% (BWOC) Silica flour, required dosage of heavy weight additives, recommended dosage of the vendor’s additives and laboratory tap water to achieve the required density. (b) Test Conditions: Pressure-10000 psi Temperature - 140°C, Raising Time - 40 minutes, BHST: 1.4 times BHCT | Shall be soluble /miscible/ dispersible | — |
| 3 | Specific Gravity | 2.15±0.02 | — |
| 4 | Thickening Time, minutes | 350±30 | — |
| 5 | Critical Velocity (3” Diameter), ft/sec | 9 (Maximum) | — |
| 6 | Initial Consistency, Bc | 20 (Maximum) | — |
| 7 | Filtration loss, ml | 50 (Maximum) | — |
| 8 | Free Fluid, percent by volume | Nil | — |
| 9 | Compressive Strength, 24 hrs, psi | 2000 (Minimum) | — |
| 10 | Stability test : Difference in densities of top and bottom of set cement column, gm/cc | 0.05 (Maximum) | — |
| 11 | Static Gel Strength (SGS) test, Transition time from 100 to 500, lbf/ 100 sq.ft, minutes | 30 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 21. ONGC/CCA/28/2026 — SILICA FUME

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:35 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of free flowing powder, free from visible impurities. | — |
| 2 | Bulk Density, g/litre | 600 ± 50 | — |
| 3 | Density at 24±2°C, g/cc | 2.1 ± 0.2 | — |
| 4 | Moisture content at 105±2°C, % (mass) | 3.0 (Maximum) | — |
| 5 | Loss on Ignition at 750±50°C, % (mass) | 6.0 (Maximum) | — |
| 6 | Silica Content as SiO2, % (mass) | 85.0 (Minimum) | — |
| 7 | Initial consistency of blended cement slurry (18 % Silica Fume by weight of cement) during 15 min to 30 min after the initiation of the test at 24±2°C and atmospheric pressure, Bc | 30 (Maximum) | — |
| 8 | Compressive Strength neat cement slurry after 24 hrs curing at 60°C and atmospheric pressure, psi | Record the Compressive Strength | — |
| 9 | Compressive Strength of blended cement slurry (25% Silica Fume by weight of cement) after 24 hrs curing at 60°C and atmospheric pressure, psi | Shall not be less than 140% of the value of neat slurry | — |
| 10 | Filtration loss of neat cement slurry at 60 °C and 1000 psi, as per API Test Procedure, ml | Record the filtration loss of the neat slurry | — |
| 11 | Filtration loss of blended slurry (25% Silica Fume by weight) at 60°C and 1000 psi, as per API test, ml | Shall not be more than 50% of value obtained for the neat slurry | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 22. ONGC/CCA/29/2026 — METAKAOLIN

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:37 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material as received shall be fine powder, free from visible impurities. | — |
| 2 | Specific Gravity | 2.45 ± 0.05 | — |
| 3 | Bulk density, g/litre | 320 ± 40 | — |
| 4 | Material retained when sieved through 300 BSS mesh by wet process. % by mass | 1.0 (Maximum) | — |
| 5 | Water soluble matter, % by weight | 0.5 (Maximum) | — |
| 6 | Chemical Composition by XRF: SiO2, % by mass | 47.0 (Minimum) | — |
| 7 | Chemical Composition by XRF: Al2O3, % by mass | 43.0 (Minimum) | — |
| 8 | Chemical Composition by XRF: Fe2O3, % by mass | 1.0 (Maximum) | — |
| 9 | Compressive strength of neat cement slurry cured for 06 hrs at 60°C /1 Atm, psi | Record the Compressive strength | — |
| 10 | Compressive strength of composition with matakaolin cured for 06 hrs at 60°C /1 atm, psi | Should be minimum 40% more than neat cement slurry | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 23. ONGC/CCA/30/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY–IX (140-170°C BHCT) FOR GAS TIGHT HEAVY WEIGHT SLURRY

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:39 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a) Solid Additives: The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities | — |
| 2 | Solubility/ Miscibility / dispersibility of the Additives as per recommended dosage in Distilled water at 24±2°C | Shall be soluble /miscible/ dispersible | — |
| 3 | Strength Retrogression additives (BWOC) | 40% (Minimum) | — |
| 4 | Dispersibility of Heavy Weight Additive, Tri-Manganese Tetra-Oxide (Mn3O4) in laboratory tap water (salinity < 500 ppm) | Dispersible | — |
| 5 | DensityofTri-ManganeseTetra- Oxide (Mn3O4), gm/cc | 4.68 (Minimum) | — |
| 6 | Mn content of Tri-Manganese Tetra- Oxide (Mn3O4), percent by mass | 68.0 (Minimum) | — |
| 7 | Consistency of slurry after 45 minutes of break (after raising temperature & pressure), Bc | Hump shall not be more than 70 Bc & shall not last for more than 30 sec from the time motor is switched on again | — |
| 8 | Specific Gravity | 2.20 ± 0.02 | — |
| 9 | Thickening time, minutes | 300 ± 30 | — |
| 10 | Initial consistency, recorded after 5 minutes conditioning at ambient temperature, Bc | 20 (Maximum) | — |
| 11 | Fluid loss, ml /30 minutes | 50 (Maximum) | — |
| 12 | Free Fluid, ml | Nil | — |
| 13 | Compressive Strength after 48 hrs, psi | 2000 (Minimum) | — |
| 14 | Stability test : Difference in densities of Top and Bottom of set cement column, gm/cc | 0.05 (Maximum) | — |
| 15 | Static Gel Strength (SGS) test : Transition time from 100 to 500 lbf/100 sq.ft, minutes | 45 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 24. ONGC/CCA/31/2026 — CEMENT ADDITIVE PACKAGE FOR CATEGORY–X (170-200°C BHCT) FOR GAS TIGHT HEAVY WEIGHT SLURRY

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | a) Solid Additives : The material shall be in the form of fine powder, free from visible impurities. b) Liquid Additives: The material shall be in the form of liquid, free from visible impurities | — |
| 2 | Solubility/ Miscibility / dispersibility of the Additives as per recommended dosage in Distilled water at 24±2°C | Shall be soluble /miscible/ dispersible | — |
| 3 | Strength Retrogression additives (BWOC) | 40% (Minimum) | — |
| 4 | Dispersibility of Heavy Weight Additive, Tri-Manganese Tetra-Oxide (Mn3O4) in laboratory tap water (salinity < 500 ppm) | Dispersible | — |
| 5 | Density of Tri-ManganeseTetra-Oxide (Mn3O4), gm/ cc | 4.68 (Minimum) | — |
| 6 | Mn content of Tri-ManganeseTetra- Oxide (Mn3O4), percent by mass. Test Conditions: Pressure 15000 psi, BHST: 230 °C, BHCT 200°C, Raising Time: 70 minutes | 68.0 (Minimum) | — |
| 7 | Consistency of slurry after 45 minutes of break (after raising temperature & pressure.) | Hump shall not be more than 70 Bc & shall not last for more than 30 sec from the time motor is switched on again | — |
| 8 | Specific Gravity | 2.35 ± 0.02 | — |
| 9 | Thickening Time, minutes | 330 ± 30 | — |
| 10 | Initial consistency recorded after 5 minutes conditioning at ambient temperature, Bc | 25 (Maximum) | — |
| 11 | Fluid Loss / 30 minutes, ml | 50 (Maximum) | — |
| 12 | Free Fluid, ml | Nil | — |
| 13 | Compressive Strength after 48 hrs, psi | 2000 (Minimum) | — |
| 14 | Stability test : Difference in densities of Top and Bottom of set cement column, gm/cc | 0.05 (Maximum) | — |
| 15 | Static Gel Strength (SGS) test : Transition time from 100 to 500 Ibf/100 sq.ft, minutes | 45 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 25. ONGC/CCA/32/2026 — TRI MANGANESE TETROXIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:43 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material as received shall be fine powder, free from dirt and foreign matter. | — |
| 2 | Density at 24±2 0C, gm/cc | 4.68 (Minimum) | — |
| 3 | Moisture content at 105 ±2 0C, percent by mass | 0.5 (Maximum) | — |
| 4 | Matter soluble in water, percent by mass | 0.5 (Maximum) | — |
| 5 | Sieve Analysis, Wet Method 100 Mesh BSS( or equivalent) Retention, percent by mass | 2.0 (Maximum) | — |
| 6 | Purity, Mn, percent by mass | 68.0 (Minimum) | — |
| 7 | Purity, Fe2O3, percent by mass | 3.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 26. ONGC/CCA/33/2026 — DEAD BURNT MAGNESITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:50 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material as received shall be fine light brown powder, free from dirt and foreign matter. | — |
| 2 | Physical Properties: Fineness(sieve analysis) - Retained on 100 BSS mesh, percent by mass | 5.0 (Maximum) | — |
| 3 | Physical Properties: Fineness(sieve analysis) - Retained on 200 BSS mesh, percent by mass | 20.0 (Maximum) | — |
| 4 | Physical Properties: Moisture content at 105 ±2 degC, percent by mass | 1.0 (Maximum) | — |
| 5 | Physical Properties: Loss on ignition at 1000 degC,: percent by mass | 2.0 (Maximum) | — |
| 6 | Chemical composition: MgO, percent by mass | 85.0 (Minimum) | — |
| 7 | Chemical composition: SiO2, percent by mass | 4.0 (Maximum) | — |
| 8 | Chemical composition: CaO, percent by mass | 4.0 (Maximum) | — |
| 9 | Chemical composition: Fe2O3, percent by mass | 5.0 (Maximum) | — |
| 10 | Reactivity test Time taken by the DBM sample to: change from white to pink colour in 0.025 M Citric Acid solution in presence of phenolphthalein indicator at 25±2 0C, seconds | 900 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 27. ONGC/CCA/34/2026 — PVC RESIN

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:56 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material as received shall be free flowing powder consisting of spherical particles and free from visible impurities. | — |
| 2 | Bulk Density, gm/ml | 0.53 to 0.59 | — |
| 3 | Sieve Analysis (DryMethod) | 0.5 (Maximum) | — |
| 4 | Sieve Analysis (DryMethod): Retained on ASTM 40 Mesh | Traces | — |
| 5 | Sieve Analysis (DryMethod): Retained on ASTM 60 Mesh | 10 % (Maximum) | — |
| 6 | Sieve Analysis (DryMethod): Passing through ASTM 140 Mesh | 15% (Maximum) | — |
| 7 | Performance Test [Cement Slurry Composition: 100gms API Class ‘G’ HSR Type Cement + 70% PVC Resin (BWOC) + 35% Silica Fume (BWOC) + 100% Tap Water (BWOC)]. The compressive strength of the slurry at 60 degC raised in 40min / 2000: psi in 24 hours | 1200 psi (Minimum) | — |
| 8 | Performance Test [Cement Slurry Composition: 100gms API Class ‘G’ HSR Type Cement + 70% PVC Resin (BWOC) + 35% Silica Fume (BWOC) + 100% Tap Water (BWOC)]. The compressive strength of the slurry at 60 degC raised in 40min / 2000 psi in 96 hours | 1800 psi (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 28. ONGC/CCA/35/2026 — WEIGHTED SPACER SURFACTANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:56 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of clear liquid free from visible impurities | — |
| 2 | Miscibility of 5% (w/v) of sample in distilled water at 24 ± 2 0C | Shall be freely miscible | — |
| 3 | pH of 1% (w/v) of sample in distilled water | 6.5 – 8.5 | — |
| 4 | Specific Gravity at 29.5 oC | 1.02 – 1.05 | — |
| 5 | Wettability Test | Shall be water wet | — |
| 6 | Surface Tension of 1% (w/v) in distilled at 24 ± 2 0C, mN/m | 26 - 32 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 29. ONGC/CCA/36/2026 — OIL WELL CEMENT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 14:59 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | MgO content, % by mass | 6.0 (Maximum) | — |
| 2 | Sulphur Trioxide (SO3) Content, percentage | 3.0 (Maximum) | — |
| 3 | Loss on Ignition , percentage | 3.0 (Maximum) | — |
| 4 | Insoluble Residue, percentage | 0.75 (Maximum) | — |
| 5 | Tricalcium Silicate (C3S), percentage | 48.0 - 65.0 | — |
| 6 | Tricalcium Aluminate (C3A) | 3.0 (Maximum) | — |
| 7 | Tetracalcium Aluminoferrite (C4AF) plus twice the Tri calcium aluminate (C3A), percentage | 24.00 (maximum) | — |
| 8 | Total Alkali content expressed as Sodium oxide (Na2O) equivalent, percentage | 0.75 (Maximum) | — |
| 9 | Free Fluid content, percentage | 5.9 (Maximum) | — |
| 10 | Compressive strength, eight hours curing time at atmospheric pressure and 38 °C (100 °F), lbf/in2 | 300 (Minimum) | — |
| 11 | Compressive strength, eight hours curing time at atmospheric pressure and 60 °C (140 °F), lbf/in2 | 1500 (Minimum) | — |
| 12 | Thickening time, as per Sch. No. 5 API spec 10 A, minutes | 90-120 | — |
| 13 | Maximum consistency 15-30 minutes Stirring, Bc | 30 (Maximum) | — |
| 14 | Particle Size D-90, microns | 75-140 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 30. ONGC/CCA/37/2026 — Graphite for Cement Slurries

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:04 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder or flakes with metallic lustre, free from visible impurities. | — |
| 2 | Fineness : Fraction passing through 72 Mesh BSS or equivalent sieve, percent by mass | 100.0 | — |
| 3 | Fraction passing through 120 Mesh BSS or equivalent sieve, percent by mass | 95.0 (Minimum) | — |
| 4 | Loss on heating, as determined at 105±2°C, percent by mass | 1.25 (Maximum) | — |
| 5 | Acidity of water extract | Filtrate should be pink or red in colour | — |
| 6 | Water soluble matter, percent by mass | 1.25 (Maximum) | — |
| 7 | Ash Content, as determined at 825 ± 25 °C, percent by mass | 6.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 31. ONGC/DFC/01/2026 — ALUMINIUM STEARATE

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 16:32 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Moisture content at 105 ± 2°C, percent by mass | 1.5 (Maximum) | — |
| 3 | Inorganic Acidity / Alkalinity | No change of colour of Methyl Orange / Bromo-Cresol Purple indicator | — |
| 4 | Acidity of Acetone extractable, as CH3(CH2)16COOH, percent by mass | 10.0 (Maximum) | — |
| 5 | Aluminium Stearate content as Al2O3, percent by mass | 10.0 (Minimum) | — |
| 6 | Dispersion in Benzene | Forms a clear gel | — |
| 7 | Iron Content as Fe2O3, percent by mass | 0.10 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 32. ONGC/DFC/03/2026 — BARYTES

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:34 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | 1. Density, g/ml [Baryte API 4.1] | 4.10 (Minimum) | — |
| 2 | 1. Density, g/ml [Baryte API 4.2] | 4.20 (Minimum) | — |
| 3 | 2. Water-soluble alkaline earth metals as calcium, mg/kg, [Baryte API 4.1] | 250 (Maximum) | — |
| 4 | 2. Water-soluble alkaline earth metals as calcium, mg/kg, [Baryte API 4.2] | 250 (Maximum) | — |
| 5 | 3. Residue greater than 75 µm, mass [Baryte API 4.1] | 3.0 (Maximum) | — |
| 6 | 3. Residue greater than 75 µm, mass [Baryte API 4.2] | 3.0 (Maximum) | — |
| 7 | 4. Particles less than 6 µm in equivalent spherical diameter, mass fraction % [Baryte API 4.1] | 30 (Maximum) | — |
| 8 | 4. Particles less than 6 µm in equivalent equivalent spherical diameter, mass fraction % [Baryte API 4.2] | 30 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 33. ONGC/DFC/04/2026 — BENTONITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 12.0 (Maximum) | — |
| 3 | Sand Content by Wet Method: Fraction retained on 200 Mesh BSS or equivalent sieve, percent by mass | 2.0 (Maximum) | — |
| 4 | Dry Screen Analysis: Fraction passing through 100 Mesh BSS or equivalent sieve, percent by mass | 98.0 (Minimum) | — |
| 5 | Apparent Viscosity of 7.5% (w/v) suspension, aged for 24 hrs at 24±2ºC, cP | 15 (Minimum) | — |
| 6 | Plastic Viscosity of 7.5% (w/v) suspension, aged for 24 hrs, at 24±2ºC, cP | 6 (Minimum) | — |
| 7 | Yield Point of 7.5% (w/v) Suspension, aged for 24 hrs, at 24±2ºC, lbs /100 sq. ft | Yield Point of the suspension not more than four times Plastic Viscosity | — |
| 8 | Filtration Loss (30 minutes at 100 psi) of 7.5% (w/v) suspension, aged for 24 hrs, at 24±2ºC, ml | 15.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 34. ONGC/DFC/07/2026 — CALCIUM CARBONATE (COARSE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of coarse particle, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 2.0 (Maximum) | — |
| 3 | Solubility in 15% (w/w) Hydrochloric Acid at 24±2°C, (20 g in 100 ml acid), percent by mass | 93.0 (Minimum) | — |
| 4 | Sieve test (wet method): Fraction retained on 6 mesh BSS or equivalent sieve, percent by mass | 2.0 (Maximum) | — |
| 5 | Sievetest (wet method):Fraction retained on 16 mesh BSS or equivalent sieve, percent by mass | 10.0 (Maximum) | — |
| 6 | Sievetest (wet method):Fraction retained on 44 mesh BSS or equivalent sieve, percent by mass | 90.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 35. ONGC/DFC/09/2026 — CALCIUM CARBONATE (MEDIUM)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:42 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 2.0 (Maximum) | — |
| 3 | Solubility in 15% (w/w) Hydrochloric Acid at 24±2°C, (20 g in 100 ml acid), percent by mass | 93.0 (Minimum) | — |
| 4 | Sieve test (wet method) : Fraction passing through 44 Mesh BSS or equivalent sieve, percent by mass | 98.0 (Minimum) | — |
| 5 | Sieve test (wet method) : Fraction passing through 200 Mesh BSS or equivalent sieve, percent by mass | 10.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 36. ONGC/DFC/10/2026 — CALCIUM CARBONATE (MICRONISED)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:43 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Specific Gravity at 24±2°C | 2.60 (Minimum) | — |
| 3 | Purity as CaCO3, percent by mass | 96.0 (Minimum) | — |
| 4 | Water soluble content, percent by mass | 0.35 (Maximum) | — |
| 5 | Solubility in 15% (w/w) HCl, percent by mass | 96.0 (Minimum) | — |
| 6 | Particle Size Distribution - D 10, microns | 4 (Maximum) | — |
| 7 | Particle Size Distribution - D 50, microns | 4 – 15 | — |
| 8 | Particle Size Distribution - D 90, microns | 15 – 60 | — |
| 9 | Fraction retained on 200 Mesh BSS or equivalent sieve, percent by mass | 2.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 37. ONGC/DFC/100/2026 — CLAY FREE KCL-PHPA –POLYOL (60-72°C)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:13 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), SG | 1.38 ± 0.01 | — |
| 2 | Plastic Viscosity, cP | 25 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq.ft | 20 - 35 | — |
| 4 | Gel lbs/100 sq.ft | 5 - 10 | — |
| 5 | Gel lbs/100 sq.ft | 8 - 16 | — |
| 6 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 7 | pH at 75±4°F (BHR) | 8.5 - 9.0 | — |
| 8 | Specification wide Rheological parameters measured at | 115±4 °F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 38. ONGC/DFC/101/2026 — CLAY FREE KCl-PHPA –POLYOL (75-87°C)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:14 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), SG | 1.38 ± 0.01 | — |
| 2 | Plastic Viscosity, cP | 25 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq.ft | 20 - 35 | — |
| 4 | Gel lbs/100 sq.ft | 5 - 10 | — |
| 5 | Gel lbs/100 sq.ft | 8 - 16 | — |
| 6 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 7 | pH at 75±4°F (BHR) | 8.5 - 9.0 | — |
| 8 | Specification wide Rheological parameters measured at | 115±4 °F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 39. ONGC/DFC/103/2026 — CLAY FREE NDDF SYSTEM

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:15 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), SG | 1.06 ± 0.01 | — |
| 2 | Plastic Viscosity, cP | 30 (Maximum) | — |
| 3 | Yield point, lbs/100 sq.ft | 20 - 35 | — |
| 4 | Gel lbs/100 sq.ft | 8 - 12 | — |
| 5 | Gel lbs/100 sq.ft | 10 - 16 | — |
| 6 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 7 | pH at 75±4°F (BHR) | 8.5 - 9.0 | — |
| 8 | Specification wide Rheological parameters measured at | 115±4°F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 40. ONGC/DFC/104/2026 — FORMATE BASED NON

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:16 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud weight at 75±4°F (BHR), SG | 1.20 ± 0.01 | — |
| 2 | Plastic Viscosity, cP | 40 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq.ft | 20 - 40 | — |
| 4 | 6 RPM LSRV, Dial reading | 8 - 12 | — |
| 5 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 6 | pH at 75±4°F (BHR) | 9.5 - 10.5 | — |
| 7 | Specification wide Rheological parameters measured at | 115±4°F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 41. ONGC/DFC/105/2026 — HIGH PERFORMANCE EP LUBRICANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:20 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing liquid at 24±2ºC, free from visible impurities. | — |
| 2 | Lubricity coefficient of the treated NDDF (Composition: Distilled water + KCl 5% (Mixing time 5 Min.) + Biocide- 1000 ppm (Mixing time 5 Min.) + XC Polymer 0.45% w/v (Mixing time 20 Min.) + Pregelatinised Starch 3% w/v (Mixing time 10 Min.) + Micronized Calcium Carbonate - 6% w/v (Mixing time 10 Min.); pH- 8.5 - 9.0 + add 2.0% w/v of the Material, stir in a Hamilton Beach Mixer for 10 min.) by using a lubricity tester | 0.10 (Maximum) | — |
| 3 | Extreme Pressure film strength at 300 in- lb load and 1000 RPM of treated NDDF, psi | 12000 (Minimum) | — |
| 4 | Lubricity coefficient after hot rolled (100±2ºC, 16 hrs) treated 2.0% (w/v) NDDF | Should not be more than 0.02 unit of the value at Sl no. 2 | — |
| 5 | Film strength of the hot rolled (100 ±2ºC, 16 hrs) treated 2.0% (w/v) NDDF, psi | Film strength of the treated NDDF should not be less than 25000 psi | — |
| 6 | Foam test: Specific Gravity of the treated fresh water mud | 0.70 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 42. ONGC/DFC/106/2026 — BASE OIL FOR LTSOBM

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:24 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Specific Gravity at 24ºC (as per D-1298) | 0.77 – 0.82 | — |
| 2 | Kinematic Viscosity at 40ºC (as per D- : 445), cSt | 3.0 (Maximum) | — |
| 3 | Initial Boiling Point (IBP) (as per D-86), ºC | 185 (Minimum) | — |
| 4 | Flash Point (as per D-93), ºC | 85 (Minimum) | — |
| 5 | Aniline Point (as per D-611), ºC | 76 (Minimum) | — |
| 6 | Pour Point (as per D-97), ºC | 0 (Maximum) | — |
| 7 | Aromatic Content (as per D-1319), percent | < 1 | — |
| 8 | Fluorescence (By Flouroscope) | Nil | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 43. ONGC/DFC/107/2026 — STEARIC ACID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:24 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white crystalline powder or flakes | — |
| 2 | Saponification Value | 195 (Minimum) | — |
| 3 | Acid Value | Shall not differ from Saponification value by more than 15 | — |
| 4 | Iodine Value | 15 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 44. ONGC/DFC/108/2026 — OLEIC ACID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:24 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of colourless to pale yellow liquid | — |
| 2 | Moisture Content, % by mass | 1 (Maximum) | — |
| 3 | Saponification Value | 195 (Minimum) | — |
| 4 | Acid Value | Shall not differ from Saponification value by more than 8 | — |
| 5 | Iodine Value | 85 - 95 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 45. ONGC/DFC/109/2026 — LIGHT MAGNESIUM OXIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:25 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white odourless, free flowing powder | — |
| 2 | Moisture Content, % by mass | 2 (Maximum) | — |
| 3 | Matter soluble in water, % by mass | 2 (Maximum) | — |
| 4 | Magnesium Oxide, % by mass | 87 (Minimum) | — |
| 5 | Calcium Oxide, % by mass | 2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 46. ONGC/DFC/11/2026 — CALCIUM CHLORIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:44 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder/ granules/ flakes/ lumps of maximum 2″ size, free from visible impurities. | — |
| 2 | Purity as CaCl2, percent by mass | 90.0 (Minimum) | — |
| 3 | Alkalinity as Ca(OH)2, percent by mass | 0.5 (Maximum) | — |
| 4 | Alkali Chlorides as NaCl, percent by mass | 0.5 (Maximum) | — |
| 5 | Matter insoluble in water, percent by mass | 0.4 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 47. ONGC/DFC/110/2026 — LIQUID POLY VINYL ALCOHOL (20%)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:28 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of viscous free flowing liquid | — |
| 2 | Volatile Matter at 105 ± 2 degC | 80 % (Maximum) | — |
| 3 | pH of 20% Suspension (w/v) of sample in deionized / distilled water | 7.0 – 9.0 | — |
| 4 | Apparent Viscosity of 20% Solution (w/v) of sample at 24 ± 2 degC | 18 cp (Minimum) | — |
| 5 | Loss of Ignition : Residue left in silica crucible after heating in Muffle Furnace at 600 degC for one hour | 1% (Maximum) | — |
| 6 | Presence of Starch | Sample should be free from starch | — |
| 7 | Identification of Gum | Sample should be free from gum | — |
| 8 | Stiff Gel Formation Test : Addition of 20ml of 20% Borax solution to 10% sample solution | Stiff gel is formed | — |
| 9 | LSRV of Stiff Gel | 4500 cp (Minimum) | — |
| 10 | Degree of Hydrolysis | 87% (Minimum | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 48. ONGC/DFC/111/2026 — ECO FRIENDLY DEFOAMER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:31 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material should be homogeneous Liquid, free from visible impurities | — |
| 2 | Foam Quality, Percentage: [300 ml D/W + 2% (w/v) Sulphonated Asphalt + 1% (v/v) Drilling Detergent + 1% (w/v) Chrome Free Deflocculant. Mix it for 5 minutes in Silverson Mixer] | Record the Foam quality of Base Fluid | — |
| 3 | Foam Quality, Percentage : [300 ml D/W + 2% (w/v) Sulphonated Asphalt + 1% (v/v) Drilling Detergent + 1% (w/v) Chrome Free Deflocculant. Mix it for 05 minutes in Silverson Mixer + 0.04% (v/v) Defoamer sample] | Foam quality after 20 mins should not be more than 20% of recorded value for base fluid | — |
| 4 | Biodegradability Test (Note: Vendor must submit Biodegradability Test report from a NABL accredited lab with a validity of six months) | Should be more than 50 % of 0.1 % solution as per OECD 302B Test. | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 49. ONGC/DFC/112/2026 — SINGLE SACK LOSS CONTROL

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:35 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | It should be free flowing Solid/ powdered/ granular/ fibrous material and free from visible impurities such as metal, glass or any cementing additives/ material | — |
| 2 | Moisture content at 105±2°C | 10 % (Maximum) percent by mass | — |
| 3 | pH of 5% suspension in deionized / distilled water | 7.0-9.5 | — |
| 4 | Screening test/sieve analysis : [Residue on 2 mesh screen (ASTM) after manual sieving for a period of 10 minutes] | Should not retain any particulate / granular material | — |
| 5 | Performance Test: (a) Base Drilling Fluid: Fresh water + 5% KCl (w/v) + 0.3% XCP (w/v) + 0.4% PHPA (w/v) +1.2% PAC (LVG) (w/v) + 6% Micronized Calcium Carbonate (w/v), Maintain pH 8.5-9.5 + Barite up to 1.20 SG (b) Loss Circulation test: Take 500 ml Base Drilling Fluid [Composition at 5(a)]. Treat with 60 ppb concentration of LCM sample and agitate for 5 min in Hamilton Beach Mixer. Keep this slurry mixture for 1 hour at 24±2 °C for hydration. Fill 400 ml slurry mixture in LCM evaluating Cell through the side wall with the help of spatula as to avoid air gaps in cylinder. Place the disc with slit opening 5000 µ x 3 slot on top of slurry mixture. Assemble rest part of the assembly. Invert the equipment and pressurize the cell slowly up to 500 psi in pressure batches of 50 psi with nitrogen. | LCM Slurry should hold 500 psi pressure for 30 min | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 50. ONGC/DFC/113/2026 — SAW DUST

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material should be in the form of powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 20.0 (Maximum) | — |
| 3 | Sieve analysis | 100 % of sample should pass through 10 BSS mesh sieve | — |
| 4 | Residue on ignition ( at 800 °C for two hours), percent by mass | 5.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 51. ONGC/DFC/16/2026 — CAUSTICISED LIGNITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:46 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | pH of 2% (w/v) solution in Distilled water | 9.5 (Minimum) | — |
| 4 | Water Soluble content, percent by mass | 65.0 (Minimum) | — |
| 5 | Apparent Viscosity of base mud (adjusted to 50-55 cP) at 24±2ºC, cP | Record Apparent Viscosity | — |
| 6 | Yield Point of base mud at 24±2ºC, lbs/100 sq. ft | Record Yield Point | — |
| 7 | Apparent Viscosity of treated (1.5% w/v, of sample) base mud at 24±2ºC, cP | Not more than 45% of the value obtained for base mud | — |
| 8 | Yield point of treated (1.5% w/v, of sample) base mud, lbs/100 sq. ft | Not more than 25% of the value obtained for base mud | — |
| 9 | Apparent Viscosity of hot rolled (160 ±2°C for 24 hrs) base mud at 24±2ºC, cP | Record Apparent Viscosity | — |
| 10 | Yield Point of hot rolled (160±2°C for 24 hrs) base mud at 24±2ºC, lbs/100 sq. ft | Record Yield Point | — |
| 11 | Apparent Viscosity of treated (1.5% w/v, of sample) and hot rolled (160±2°C for 24 hrs) base mud at 24±2ºC, cP | Not exceed more than 45% of the value obtained for hot rolled base mud | — |
| 12 | Yield point of treated (1.5% w/v, of sample) and hot rolled (160 ±2°C for 24 hrs) base mud at 24±2ºC, lbs/100 sq. ft | Not more than 25% of the value obtained for hot rolled base mud | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 52. ONGC/DFC/18/2026 — CHROME FREE DEFLOCCULANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:47 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | Solubility of 5% (w/v) of sample in Distilled water at 24±2°C | Solution should not leave any residue | — |
| 4 | Lignosulphonate group test | Positive | — |
| 5 | Chromium Content | Absent | — |
| 6 | Apparent Viscosity of the fresh water base mud (adjusted to 50 - 55 cP) at 24±2ºC, cP | Record Apparent Viscosity | — |
| 7 | Yield Point of the fresh water base mud, lbs/100 sq. ft | Record Yield Point | — |
| 8 | Apparent Viscosity of the treated (1.0% w/v, of sample) fresh water base mud at 24±2ºC, cP | Not exceed 33% of the value obtained for the fresh water base mud | — |
| 9 | Yield Point of the treated (1.0% w/v, of sample) fresh water base mud, lbs/100 sq. ft | Not exceed 10% of the value obtained for the fresh water base mud | — |
| 10 | Apparent Viscosity of the hot rolled (160±2°C for 24 hrs) fresh water base mud at 24±2ºC, cP | Record Apparent Viscosity | — |
| 11 | Yield Point (at 24±2°C) of the hot rolled (160±2°C for 24 hrs) fresh water base mud, lbs/100 sq. ft | Record Yield Point | — |
| 12 | Apparent Viscosity of treated (1.0% w/v, of sample) and hot rolled (160±2 °C for 24 hrs) fresh water base mud at 24±2ºC, cP | Not exceed 50% of the value obtained for the hot rolled fresh water base mud | — |
| 13 | Yield Point (at 24±2°C) of the treated (1.0% w/v, of sample) and hot rolled (160±2°C for 24 hrs) fresh water base mud, lbs/100 sq. ft | Not exceed 33% of the value obtained for the hot rolled fresh water base mud | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 53. ONGC/DFC/25/2026 — DRILLING DETERGENT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:53 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a soapy homogenous liquid at 24±2°C, free from visible impurities and shall be miscible with water. | — |
| 2 | Density at 24±2°C, g / cc | 1.00 - 1.10 | — |
| 3 | Surface Tension of 0.25% (v/v) solution of the sample in Distilled water at 25±1°C, dynes / cm | 35.0 (Maximum) | — |
| 4 | pH of 1% (v/v) solution of the sample | 7.5 - 10.5 | — |
| 5 | Emulsion Stability test with 1.0 ml of sample : Immediate separation of HSD oil | There should be no immediate separation of HSD oil | — |
| 6 | Emulsion Stability test: Separation of HSD Oil after 24hrs at room temperature | Separation of HSD oil should not be more than 2 ml | — |
| 7 | Lubricity Coefficient of the treated (0.5% v/v) and defoamed mud | 0.20 (Maximum) | — |
| 8 | Foaming Tendency test | Increase in volume not be more than 5% | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 54. ONGC/DFC/27/2026 — E. P. LUBRICANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:54 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing liquid at 24 ± 2°C, free from visible impurities. | — |
| 2 | Lubricity Coefficient of the treated (0.5% w/v) fresh water mud | 0.15 (Maximum) | — |
| 3 | Lubricity Coefficient of the treated (0.5% w/v) salt water mud | 0.20 (Maximum) | — |
| 4 | Film strength of the treated (0.5% w/v) fresh water mud, psi | 25000 (Minimum) | — |
| 5 | Film strength of the treated (0.5% w/v) salt water mud, psi | 20000 (Minimum) | — |
| 6 | Foam Test : Specific Gravity of the treated fresh water mud | 0.80 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 55. ONGC/DFC/31/2026 — HAEMATITE FOR DRILLING FLUIDS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:55 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Specific Gravity at 24±2°C | 4.90 (Minimum) | — |
| 3 | Water Soluble Matter, percent by mass | 0.1 (Maximum) | — |
| 4 | Purity as Fe2O3, percent by mass | 94.0 (Minimum) | — |
| 5 | Wet Screen Analysis : Fraction passing through 200 Mesh BSS or equivalent sieve, percent by mass | 95.0 (Minimum) | — |
| 6 | Wet Screen Analysis | 90.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 56. ONGC/DFC/33/2026 — HYDRATED LIME FOR DRILLING FLUIDS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:56 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from lumps and visible impurities. | — |
| 2 | Available Lime content as CaO, percent by mass | 55.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 57. ONGC/DFC/37/2026 — LIMESTONE POWDER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:56 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Specific Gravity at 24±2°C | 2.65 (Minimum) | — |
| 3 | Water soluble content, percent by mass | 0.5 (Maximum) | — |
| 4 | Purity as CaCO3, percent by mass | 95.0 (Minimum) | — |
| 5 | Wet Sieve Analysis : Fraction passing through 200 Mesh BSS or equivalent sieve, percent by mass | 90 (Minimum) | — |
| 6 | Wet Sieve Analysis : Fraction passing through 300 Mesh BSS or equivalent sieve, percent by mass | 85 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 58. ONGC/DFC/41/2026 — MICA FLAKES

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 10:57 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of flakes, free from visible impurities. | — |
| 2 | Dry Sieve Analysis : Retained on 5 Mesh BSS or equivalent sieve, percent by mass | 2.0 (Maximum) | — |
| 3 | Passing through 52 Mesh BSS or equivalent sieve, percent by mass | 10.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 59. ONGC/DFC/42/2026 — MODIFIED GUAR GUM

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:00 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from lumps and visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 15.0 (Maximum) | — |
| 3 | pH of 1% (w/v) solution of the material in Distilled water | 6.5 – 7.5 | — |
| 4 | Dispersibility in Bentonite Suspension : Residue left on the 60 Mesh BSS or equivalent sieve. 15.0 (Maximum) 6.5 – 7.5 | Should not exceed 2.5% with respect to the weight of the sample added | — |
| 5 | Apparent Viscosity of 1.0% (w/v) Sample suspension at 24±2°C in Distilled water, cP | 65 (Minimum) | — |
| 6 | Apparent Viscosity of 1.0% (w/v) Sample suspension at 24±2°C in synthetic sea water, cP | 65 (Minimum) | — |
| 7 | Apparent Viscosity of 1.0% (w/v) Sample suspension at 24±2°C in saturated salt water, cP | 75 (Minimum) | — |
| 8 | Apparent Viscosity of 1.0% (w/v) Sample in 5 % (w/v) CaCO3 (pH 9.8 – 10.0) at 24±2ºC, cP | 65 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 60. ONGC/DFC/43/2026 — OXALIC ACID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:00 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of crystals, free from visible impurities. | — |
| 2 | Purity as Oxalic acid, percent by mass | 99.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 61. ONGC/DFC/45/2026 — PHPA FOR DRILLING FLUIDS (HIGH TEMPERATURE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:01 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of free flowing powder, free from lumps and visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 7.0 (Maximum) | — |
| 3 | Ionic Character | Anionic | — |
| 4 | Relative Dispersibility of Bentonite pellets in 0.2% (w/v) polymer solution at 60±5°C with respect to distilledwater | 175 (Maximum) | — |
| 5 | Degree of Hydrolysis, as determined by electrometric titration, percent by mass | 20.0 to 40.0 | — |
| 6 | Apparent Viscosity of 0.2% (w/v) polymer solution in Distilled water at 24±2°C, cP | 9 (Minimum) | — |
| 7 | Apparent Viscosity (at 24±2ºC) of 0.2% (w/v) polymer solution after ageing at 110±2°C for 18 hrs | Not less than 80% of the value obtained without ageing | — |
| 8 | Apparent Viscosity of 4 cP Bentonite suspension with 0.2% (w/v) polymer concentration at 24±2°C and pH 9.0, cP | 15 (Minimum) | — |
| 9 | Apparent Viscosity (at 24±2ºC) of 4 cP Bentonite Suspension with 0.2% (w/v) polymer concentration after ageing at 140±2°C for 24 hrs, cP | Not less than 80% of the value obtained without ageing (contd.) | — |
| 10 | Apparent Viscosity of 0.4% (w/v) polymer solution in Distilled water at 24±2ºC, cP | To be determined | — |
| 11 | Apparent Viscosity of 0.4% (w/v) polymer solution in Distilled water in presence of 100 ppm Ca++ at 24±2ºC, cP | Not less than 60% of the value obtained without Ca++ treatment | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 62. ONGC/DFC/46/2026 — PHPA FOR DRILLING FLUIDS (LOW TEMPERATURE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of free flowing powder, free from lumps and visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 7.0 (Maximum) | — |
| 3 | Ionic Character | Anionic | — |
| 4 | Relative Dispersibility of Bentonite Pellets in 0.2% (w/v) polymer solution at 60±5°C with respect to Distilled water | 175 (Maximum) | — |
| 5 | Degree of Hydrolysis, as determined by electrometric titration, percent by mass | 20.0 to 40.0 | — |
| 6 | Apparent Viscosity of 0.2% (w/v) polymer solution in Distilled water at 24±2°C, cP | 9 (Minimum) | — |
| 7 | Apparent Viscosity of 0.2% (w/v) polymer solution in Distilled waterafter ageing at 110±2°C for 18 hrs at 24±2ºC, cP | Not less than 80% of the value obtained without ageing | — |
| 8 | Apparent Viscosity of 4 cP Bentonite suspension with 0.2% (w/v) polymer concentration at 24±2°C and pH 9.0, cP | 15 (Minimum) | — |
| 9 | Apparent Viscosity of 4 cP Bentonite suspension with 0.2% (w/v) polymer concentration after ageing at 110±2°C for 24 hrs at 24±2ºC, cP | Should not be less than 80% of the value obtained without ageing | — |
| 10 | Apparent Viscosity of 0.4%(w/v) polymer in Distilled water at 24±2ºC, cP | To be determined | — |
| 11 | Apparent Viscosity of 0.4% (w/v) polymer solution in Distilled water in presence of 100 ppm Ca++ at 24±2ºC, cP | Not less than 60% of the value obtained without Ca++ treatment | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 63. ONGC/DFC/48/2026 — POLY ANIONIC CELLULOSE (LOW VISCOSITY GRADE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:04 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of free flowing powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | Apparent Viscosity of 1.0% (w/v) suspension of sample in Distilled water at 24±2ºC, cP | 20 (Maximum) | — |
| 4 | Apparent Viscosity of 1.0% (w/v) suspension of sample in 4% (w/v) NaCl (LR Grade) solution at 24±2ºC, cP | 16 (Maximum) | — |
| 5 | Yield of 15 cP (Apparent Viscosity) suspension in Distilled water, m3 / MT | 90 (Minimum) | — |
| 6 | Yield of 15 cP suspension prepared in 4% (w/v) NaCl solution in Distilled water, m3 /MT | 70 (Minimum) | — |
| 7 | Sodium Carboxy Methyl Cellulose content on dry basis, percent by mass | 85.0 (Minimum) | — |
| 8 | Degree of substitution | 0.90 (Minimum) | — |
| 9 | Apparent Viscosity of fresh water base mud (adjusted to 15-20 cP) at 24±2ºC, cP | Record Apparent Viscosity | — |
| 10 | Yield Point of fresh water base mud at 24±2ºC, lbs/100 sq.ft | Record Yield Point | — |
| 11 | API filtration loss of fresh water base mud, ml | Record API Filtration Loss | — |
| 12 | Apparent Viscosity of treated (0.5% w/v, sample) fresh water base mud at 24±2ºC, cP | Not more than 2.5 times the value obtained for the fresh water base mud | — |
| 13 | Yield Point of treated (0.5%, w/v sample) fresh water base mud at 24±2ºC, lbs/100 sq.ft | Not more than 1.5 times the value for the fresh water base mud | — |
| 14 | API Filtration Loss of treated (0.5% w/v, sample) fresh water base mud, ml | Not more than 50% of the value for the fresh water base mud | — |
| 15 | Apparent Viscosity of treated (0.5% w/v, sample) hot rolled (120±2°C for 24 hrs) fresh water base mud at 24±2ºC, cP | Not more than 2.0 times the value for the fresh water base mud | — |
| 16 | Yield Point of treated (0.5% w/v, sample) hot rolled (120±2°C for 24 hrs) fresh water base mud, lbs/100 sq. ft | Not more than 1.5 times the value for the fresh water base mud | — |
| 17 | API Filtration Loss of treated (0.5% w/v, sample) hot rolled (120±2°C for 24 hrs) fresh water base mud, ml | Not more than 50% of the value for the fresh water base mud | — |
| 18 | Apparent Viscosity of salt water base mud (adjusted 15-20 cP) at 24±2ºC, cP | Record Apparent Viscosity | — |

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 19 | Yield Point of salt water base mud, lbs/100 sq.ft | Record Yield Point | — |
| 20 | Record API Filtration Loss of salt water base mud, ml | Record API Filtration Loss | — |
| 21 | Apparent Viscosity of treated (0.5% w/v, sample) salt water base mud at24±2ºC, cP | Not more than 2.0 times the value obtained for the salt water base mud | — |
| 22 | Yield Point of treated (0.5% w/v, sample) salt water base mud, lbs/100sq.ft | Not more than 1.5 times the value for the salt water base mud | — |
| 23 | API Filtration Loss of treated (0.5% w/v, sample) salt water base mud, ml | Not more than 25% of the value for the salt water base mud | — |
| 24 | Borate Sensitivity test | No stiff gel formation | — |
| 25 | Presence of Starch | Absent | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 64. ONGC/DFC/49/2026 — POLY ANIONIC CELLULOSE (REGULAR GRADE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:07 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of freeflowing powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | Apparent Viscosity (24±2ºC) of 1.0% (w/v) suspension of sample in Distilled water, cP | 60 (Minimum) | — |
| 4 | Apparent Viscosity (24±2ºC) of 1.0% (w/v) suspension of sample in 4% (w/v) NaCl (LR Grade) solution in Distilled water, cP | 50 (Minimum) | — |
| 5 | Yield of 15 cP (Apparent Viscosity) | 250 (Minimum) | — |
| 6 | Yield of 15 cP (Apparent Viscosity) suspension prepared in 4% (w/v) NaCl (LR Grade solution in Distilled water, m3 /MT | 200 (Minimum) | — |
| 7 | Sodium CarboxyMethyl Cellulose Content on dry basis, percent by mass | 85.0 (Minimum) | — |
| 8 | Degree of Substitution | 1.0 (Minimum) | — |
| 9 | Apparent Viscosity of fresh water base mud (adjusted to 15-20 cP) at 24±2ºC, cP | Record Apparent Viscosity | — |
| 10 | Yield Point of fresh water base mud, lbs/100 sq. ft | Record Yield Point | — |
| 11 | API Filtration Loss of fresh water base mud, ml | Record API Filtration loss. | — |
| 12 | Apparent Viscosity of treated (0.5% w/v, sample) fresh water base mud at 24±2ºC, cP | Not less than 4.0 times the value obtained for fresh water base mud | — |
| 13 | Yield Point of treated (0.5% w/v, sample) fresh water base mud, lbs/100 sq. ft | Not less than 4.0 times the value obtained for the fresh water base mud | — |
| 14 | Filtration Loss of treated (0.5% w/v, sample) fresh water base mud, ml | Not more than 40% of the value obtained for the fresh water base mud | — |
| 15 | Apparent Viscosity of treated (0.5% w/v, sample) hot rolled (120±2°C for 24 hrs) fresh water base mud at 24±2ºC, cP | Not less than 3.0 times the value obtained for the fresh water base mud | — |
| 16 | Yield Point of treated (0.5% w/v, sample) hot rolled (120±2°C for 24 hrs) fresh water base mud, lbs/100 sq.ft | Not less than 3.0 times the value obtained for the fresh water base mud | — |
| 17 | API Filtration Loss of treated (0.5% w/v, sample) hot rolled (120±2°C for 24 hrs) fresh water base mud, ml | Not more than 45% of the value obtained for the fresh water base | — |
| 18 | Apparent Viscosity of salt water base mud (adjusted to 15-20 cP) at 24±2ºC, cP | Record Apparent Viscosity | — |
| 19 | Yield Point of salt water base mud, lbs/100 sq. ft | Record Yield Point | — |

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 20 | API Filtration Loss of salt water base mud, ml | Record API Filtration Loss | — |
| 21 | Apparent Viscosity of treated (0.5% w/v, sample) salt water base mud at24±2ºC, cP | Not less than 2.0 times the value obtained for salt water base mud | — |
| 22 | Yield Point of treated (0.5% w/v, sample) salt water base mud, lbs/100sq. ft | Not less than 1.5 times the value obtained for salt water base mud | — |
| 23 | Filtration Loss of treated (0.5% (w/v sample) salt water base mud, ml | Not more than 20% of the value obtained for salt water base mud | — |
| 24 | Borate Sensitivity test | No stiff gel formation | — |
| 25 | Presence of Starch | Absent | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 65. ONGC/DFC/51/2026 — POLYOL (GRADE-I)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:24 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of liquid at 24±2°C, free from visible impurities. | — |
| 2 | Moisture content, % by mass | 10 (Maximum) | — |
| 3 | Miscibility of 3% (v/v) sample in 5% (w/v) KCl solution in distilled water at room temperature (24±2 ■C) | Should be miscible | — |
| 4 | pH of 3% (v/v) sample in 5 % (w/v) KCL solution in distilled water, dynes/ cm | 6.0-7.5 | — |
| 5 | Surface Tension of 3% (v/v) sample in 5% (w/v) KCl solution in Distilled water, dynes / cm | 35 ± 5 | — |
| 6 | Hydroxyl Value, mg KOH /g of sample | 150-300 | — |
| 7 | Iodofrom test for confirmation of presence of α-carbon in sample | Presence of pale yellow precipitate should be observed. | — |
| 8 | Apparent Viscosity of hot rolled (100 °C, 18 hrs) base mud, (AV adjusted to 10-15 cP) at 24±2ºC, cP | Record Apparent Viscosity | — |
| 9 | Yield Point of hot rolled (100°C, 18 hrs) base mud, lbs/100 sq. ft | Record Yield Point | — |
| 10 | Lubricity Coefficient of hot rolled (100°C, 18 hrs) base mud | Record Lubricity Coefficient | — |
| 11 | HPHT filtration loss (500 psi, 100 °C) of hot rolled (100 °C , 18 hours) base mud, ml | Record HPHT filtration loss | — |
| 12 | Apparent viscosity of treated (3 % v/v sample) hot rolled (100 °C, 18 hours) rolled base mud base mud at 24±2ºC, cP | Not less than the value obtained for hot rolled base mud | — |
| 13 | Yield point of treated (3% v/v sample) hot rolled (100°C, 18 hrs)base mud, lbs / 100 sq.ft | Not less than the value obtained for hot rolled base mud | — |
| 14 | Lubricity Coefficient of treated (3 % v/v sample) hot rolled (100 °C, 18 hours) base mud, lbs/100 sq.ft | Not more than 80% of the value obtained for hot rolled base mud | — |
| 15 | HPHT Filtration Loss (500 psi, 100 °C) of treated (3% v/v, sample) hot rolled (100°C. 18 hours) base mud, ml | Not more than 80% of the value obtained for hot rolled base mud | — |
| 16 | Cloud Point of 3% (v/v) sample in 5% (w/v) KCl in Distilled water, °C | 60-72 | — |
| 17 | Foaming Test : Carry out the foam test by taking 3% Polyol in 10% KCl in a 250 ml measuring cylinder and giving it 8 to 10 shakes. Observe the foam above liquid immediately and after 5 minute | All foam should subside within 5 minutes | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 66. ONGC/DFC/52/2026 — POLYOL (GRADE-II)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of liquid at 24±2°C, free from visible impurities | — |
| 2 | Moisture content, % by mass | 10 (Maximum) | — |
| 3 | Miscibility of 3% (v/v) sample in 10% (w/v) KCl solution in distilled water at room temperature (24±2 ■C) | Should be miscible | — |
| 4 | pH of 3% (v/v) sample in 10 % (w/v) KCL solution in distilled water, dynes/ cm | 6.0-7.5 | — |
| 5 | Surface Tension of 3% (v/v) sample in 10% (w/v) KCl solution in Distilled water, dynes / cm | 40 ± 5 | — |
| 6 | Hydroxyl Value, mg KOH /g of sample | 300 - 450 | — |
| 7 | Iodofrom test for confirmation of presence of α-carbon in sample | Presence of pale yellow precipitate should be observed | — |
| 8 | Apparent Viscosity of hot rolled (100 °C, 18 hrs) base mud at 24±2ºC, cP | Record Apparent Viscosity | — |
| 9 | Yield Point of hot rolled (100°C, 18 hrs) base mud, lbs/100 sq. ft | Record Yield Point | — |
| 10 | Lubricity Coefficient of hot rolled (100°C, 18 hrs) base mud | Record Lubricity Coefficient | — |
| 11 | HPHT filtration loss (500 psi, 100 °C) of hot rolled (100 °C , 18 hours) base mud, ml | Record HPHT Filtration Loss | — |
| 12 | Apparent viscosity of treated (3 % v/v, sample) hot rolled (100 °C, 18 hours) base mud at 24±2ºC, cP | Not less than the value obtained for hot rolled base mud | — |
| 13 | Yield point of treated (3% v/v sample) hot rolled (100°C, 18 hrs) base mud, lbs/100 sq. ft | Not less than the value obtained for hot rolled base mud | — |
| 14 | Lubricity Coefficient of treated (3 % v/v sample) hot rolled (100 °C, 18 hours) base mud | Not more than 75% of the value obtained for hot rolled base mud | — |
| 15 | HPHT Filtration Loss (500 psi, 100 °C) of treated (3% v/v, sample) hot rolled(100°C. 18 hours) base mud, ml | Not more than 80% of the value obtained for hot rolled base mud | — |
| 16 | Cloud Point of 3% (v/v) sample in 5%(w/v) KCl in Distilled water, °C | 75-87 | — |
| 17 | Foaming Test : Carry out the foam test by taking 3% Polyol in 10% KCl in a 250 ml measuring cylinder and giving it 8 to 10 shakes. Observe the foam above liquid immediately and after 5 minutes | — | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 67. ONGC/DFC/55/2026 — POTASSIUM HYDROXIDE FOR DRILLING FLUIDS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of pellets or flakes free from visible impurities. | — |
| 2 | Total Alkalinity as KOH, percent by mass | 87.0 (Minimum) | — |
| 3 | Carbonates as K2CO3, percent by mass | 1.0 (Maximum) | — |
| 4 | Sodium as Na, percent by mass | 5.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 68. ONGC/DFC/56/2026 — POTASSIUM LIGNITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:38 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Water Soluble content, percent by mass | 55.0 (Minimum) | — |
| 3 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 4 | pH of 2% (w/v) solution of material in Distilled water | 9.0 (Minimum) | — |
| 5 | Potassium content, percent by mass | 4.0 (Minimum) | — |
| 6 | Chromium content, ppm | 100 (Maximum) | — |
| 7 | Apparent Viscosity of base mud (adjusted to 50-55 cP) at 24±2ºC, cP | Record Apparent Viscosity of base mud | — |
| 8 | Yield Point of base mud, lbs/100 sq. ft | Record Yield Point of base mud | — |
| 9 | Apparent Viscosity of treated (1.5% w/v, sample) base mud at 24±2ºC | Not more than 45% of the value obtained for base mud | — |
| 10 | Yield Point of treated (1.5% w/v, sample) base mud, lbs/100 sq. ft | Not more than 30% of the value obtained for base mud | — |
| 11 | Apparent Viscosity of hot rolled (160±2°C, 24 hrs) base mud at 24±2°C, cP | Record Apparent Viscosity | — |
| 12 | Yield Point of hot rolled (160±2°C, 24 hrs) base mud, lbs/100 sq. ft | Record Yield Point | — |
| 13 | Apparent Viscosity of treated (1.5% w/v, sample) and hot rolled (160±2°C, 24 hrs) base mud at 24±2ºC, cP | Not more than 45% of the value obtained for hot rolled base mud | — |
| 14 | Yield Point of treated (1.5% w/v, sample) and hot rolled (160±2°C, 24 hrs) base mud, lbs/100 sq. ft | Not more than 25% of the value obtained for the hot rolled base mud | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 69. ONGC/DFC/57/2026 — PREGELATINIZED STARCH

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:39 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of free flowing powder, free from lumps and visible impurities | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | pH of 2% (w/v) solution of material in Distilled water | 10.0 (Minimum) | — |
| 4 | pH of 2% (w/v) solution of material in Distilled water after ageing at (24±2ºC) for 120 hrs | Drop in pH should not be more than 2.0 units | — |
| 5 | Apparent Viscosity of 2% (w/v) Solution in Distilled water at 24±2ºC, cP | 20.0 (Maximum) | — |
| 6 | Apparent Viscosity of 2% (w/v) Solution in Distilled water after ageing at (24±2ºC) for 120 hrs at 24±2ºC, cP | Drop in Apparent Viscosity should not be more than 3.0 cP as compared to Apparent Viscosity without ageing | — |
| 7 | Qualitative test for presence of Starch | Positive | — |
| 8 | Apparent Viscosity of (NDDF) base mud (10% KCl + 0.4% XCP + 6% DFCC in Distilled water) at 24±2ºC, cP | 25.0 (Maximum) | — |
| 9 | API Filtration Loss of (NDDF) base mud (10% KCl + 0.4% XCP + 6% DFCC in Distilled water), ml | To be recorded | — |
| 10 | Apparent Viscosity of treated (3.0% w/v, sample) base mud at 24±2ºC, cP | 35.0 (Maximum) | — |
| 11 | API Filtration Loss of treated (3.0% w/v, sample) base Mud, ml | 45% (Maximum) of base mud value | — |
| 12 | Apparent Viscosity of treated (3.0% w/v, sample) base mud after ageing at (24±2ºC) for 120 hrs at 24±2ºC, cP | Maximum variation of ± 5 CP from treated base mud | — |
| 13 | API Filtration Loss of treated (3.0% w/v, sample) base mud after ageing at (24±2ºC) for 120 hrs, ml | 50% (Maximum) of base mud | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 70. ONGC/DFC/59/2026 — RESINATED LIGNITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:40 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | Water Soluble content, percent by mass | 70.0 (Minimum) | — |
| 4 | Apparent Viscosity (24±2ºC) of 2% (w/v) solution in Distilled water, cP | 3.0 (Maximum) | — |
| 5 | Chemical Assay, elemental Iron, percent by mass | 1.8 (Maximum) | — |
| 6 | Chemical Assay, elemental Chromium, percent by mass | 0.1 (Maximum) | — |
| 7 | Apparent Viscosity of hot rolled (160±2°C, 24 hrs) fresh water base mud (adjusted to 50-55 cP) at 24±2ºC, cP | Record Apparent Viscosity | — |
| 8 | HT-HP Filtration Loss (at 160 0C and 500 psi differential pressure) of hot rolled (160±2°C, 24 hrs) fresh water base mud, ml | Record HP-HT Filtration Loss | — |
| 9 | Apparent Viscosity of treated (2.0% w/v, of sample) and hot rolled (160±2°C, 24 hrs) freshwaterbase mud at 24±2ºC, cP | Not more than 40% of the value obtained for hot rolled fresh water base mud | — |
| 10 | HT-HP Filtration Loss of treated (2.0% w/v, of sample) hot rolled (160±2°C, 24 hrs) fresh water base mud, ml | Not more than 50% of the value obtained for hot rolled fresh water base mud | — |
| 11 | Apparent Viscosity of hot rolled (160±2°C, 24 hrs) salt water base mud (adjusted to 30-35 cP) at 24±2°C, cP | Record Apparent Viscosity | — |
| 12 | HT-HP Filtration Loss (at 160 0C and 500 psi differential pressure) of hot rolled (160±2°C, 24 hrs) salt water base mud, ml | Record HP-HT Filtration Loss | — |
| 13 | Apparent Viscosity of treated (2.0% w/v, sample) and hot rolled (160±2°C, 24 hrs) salt water base mud at 24±2ºC, cP | Not more than the value obtained for hot rolled salt water base mud | — |
| 14 | HT-HP Filtration Loss of treated (2.0% w/v, of sample) and hot rolled(160±2°C, 24 hrs) salt water (160±2°C, 24 hrs) base mud, ml | Not more than 50% of the value obtained for hot rolled salt water base mud | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 71. ONGC/DFC/60/2026 — SODA ASH

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Solubilityof materialin Distilled water at 24±2°C | Shall be readily soluble | — |
| 3 | Volatile Matter, as determined by heating at 260–270°C for 30 minutes, percent by mass | 2.0 (Maximum) | — |
| 4 | Purity as Na2CO3, as determined after removal of volatile matter, by heating at 260 –270°C for 30 minutes, percent by mass | 98.5 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 72. ONGC/DFC/61/2026 — SODIUM BICARBONATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of crystalline powder / powder, free from visible impurities. | — |
| 2 | Total Alkalinity as NaHCO3, percent by mass | 99.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 73. ONGC/DFC/64/2026 — SODIUM HYDROXIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:42 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of flakes and shall be free from visible impurities. | — |
| 2 | Purity as NaOH, percent by mass | 95.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 74. ONGC/DFC/67/2026 — SPOTTING FLUID (NON-WEIGHTED)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:47 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be homogeneous free flowing liquid at 24±2°C, free from visible impurities. | — |
| 2 | Miscibility with HSD Oil | Completely miscible | — |
| 3 | Interfacial Tension of Distilled water: HSD Oil containing 2.5% (w/v) Spotting Fluid, dynes / cm | 13 (Maximum) | — |
| 4 | Lubricity Coefficient of treated (1% w/v, of sample) 15 cP Bentonite suspension | 0.11 (Maximum) | — |
| 5 | Mud Cake cracking test : Time required for collection of 100 ml filtrate, with treated (2.5%, w/v) HSD oil, minutes | 50 (Maximum) | — |
| 6 | Sticking test: Torque required for release of the stuck plate, with treated (2.5%, w/v) HSD oil, inch-pounds | 65 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 75. ONGC/DFC/68/2026 — SPOTTING FLUID (WEIGHTED)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:50 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a homogeneous free flowing liquid at 24±2°C, free from visible impurities. | — |
| 2 | Lubricity Coefficient of Treated (1% w/v) 10 cP, Bentonite suspension | 0.25 (Maximum) | — |
| 3 | Interfacial Tension of untreated HSD- Water system at room temperature, dyne /cm | Record the Interfacial tension | — |
| 4 | Interfacial Tension of treated HSD- Water system, containing 2.5% (w/v) Spotting Fluid, dyne /cm | Shall not be more than 50% of the value obtained for untreated system | — |
| 5 | Apparent Viscosity of Spotting Fluid slug at 49±3°C, cP | Record Apparent Viscosity of base mud | — |
| 6 | Plastic Viscosity of Spotting Fluid slug at 49±3°C, cP | Record Plastic Viscosity of base mud | — |
| 7 | Yield Point of Spotting Fluid slug at 49±3°C, lbs/100 sq. ft | Record Yield Point of base mud | — |
| 8 | Gel0 of the Spotting Fluid slug at 49±3°C, lbs/100 sq. ft | Record Gel0 of the base mud | — |
| 9 | Gel10 of the Spotting Fluid slug at 49±3°C, lbs/100 sq. ft | Record Gel10 of the base mud | — |
| 10 | Apparent Viscosity of the hot rolled (100°C, 4 hrs) spotting fluid slug at 49±3°C, cP | Variation shall not be more than ± 20% compared to the value of the base mud | — |
| 11 | Plastic Viscosity of the hot rolled (100°C for 4 hrs) spotting fluid slug at 49±3°C, cP | Variation shall not be more than ± 20% compared to the value of the base mud | — |
| 12 | Yield Point of the hot rolled (100°C, 4 hrs) spotting fluid slug at 49±3°C, lbs/100 sq. ft | Variation shall not be more than ± 20% compared to the value of the base mud | — |
| 13 | Gel0 of the hot rolled (100°C, 4 hrs) spotting fluid slug at 49±3°C, lbs/100 sq. ft | Variation shall not be more than ± 20% compared to the value of the base mud | — |
| 14 | Gel10 of the hot rolled (100°C, 4 hrs) spotting fluid slug, at 49±3°C, lbs/100 sq. ft | Variation shall not be more than ± 20% compared to the value of the base mud | — |
| 15 | Weight Stability test : Difference in the specific gravities of top and bottom slug sample | 0.02 (Maximum) | — |
| 16 | Filter Cake Cracking test | Filter cake should develop extensive cracks | — |

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 17 | Torque required for release of the stuck plate, inch-pounds | 75 (Maximum) | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 76. ONGC/DFC/69/2026 — SULPHONATED ASPHALT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:51 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of flakes powder, free from visible impurities. | — |
| 2 | Moisturecontentat105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | Soluble matter in Distilled water, percent by mass | 65.0 (Minimum) | — |
| 4 | Soluble matter in Dimethyl Sulphoxide, percent by mass | 30.0 (Minimum) | — |
| 5 | pHof 2% (w/v) solution of the sample in Distilled water at 24±2°C | 8.5 - 9.5 | — |
| 6 | Qualitative test for presence of Sulphonate group | Positive | — |
| 7 | Lubricity Coefficient of the treated (2% w/v, sample) 15 cP Bentonite suspension | 0.30 (Maximum) | — |
| 8 | Apparent Viscosity of base mud at 24±2°C, cP | Record Apparent Viscosity of base mud | — |
| 9 | Yield Point of base mud, lbs/ 100 sq. ft | Record Yield Point of base mud | — |
| 10 | Apparent Viscosity of treated (3% w/v, sample) base mud at 24±2ºC, cP | Not more than 35% of the value obtained for base mud | — |
| 11 | Yield Point of treated (3% w/v, sample) base mud, lbs/ 100 sq. ft | Not more than 15% of the value obtained for base mud | — |
| 12 | Apparent Viscosity of hot rolled (65 °C, 18 hrs) base mud at 24±2ºC, cP | Record Apparent Viscosity | — |
| 13 | Yield Point of hot rolled (65°C, 18 hrs) base mud, lbs/ 100 sq. ft | Record Yield Point | — |
| 14 | Apparent Viscosity of treated (3% w/v, sample) and hot rolled (65°C, 18 hrs) base mud at 24±2ºC, cP | Not less than 40% of hot rolled base mud | — |
| 15 | Yield Value of treated (3% w/v, sample) and hot rolled (65°C, 18 hrs) base mud, lbs/ 100 sq. ft | Not less than 25% of hot rolled base mud | — |
| 16 | Barium Chloride test | No settling of black coloured precipitate | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 77. ONGC/DFC/72/2026 — WALNUT SHELL / COCONUT SHELL

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 11:52 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be coarse ground with maximum size of about 5 mm and shall be free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 15.0 (Maximum) | — |
| 3 | Dry Sieve Analysis : Retained on 8 Mesh BSS or equivalent sieve, percent by mass | 50.0 ± 5.0 | — |
| 4 | Dry Sieve Analysis : Retained on 100 Mesh BSS or equivalent sieve, percent by mass | 95.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 78. ONGC/DFC/73/2026 — XC POLYMER FOR DRILLING FLUIDS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:00 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of free flowing powder, free from lumps and visible impurities | — |
| 2 | Qualitative Starch test / Iodine test | Should be absent/ Negative | — |
| 3 | Moisture content at 105±2°C, percent by mass | 15.0 (Maximum) | — |
| 4 | Apparent Viscosity of suspension in NaCl at 24±2 ° C, cP | 15-25 | — |
| 5 | Gel0 of the suspension in NaCl at 24±2 °C, lbs/100 sq. ft | 5.0 (Minimum) | — |
| 6 | ‘n’ value (at 200 & 100 rpm) of the suspension at 24±2 °C | 0.4 (Maximum) | — |
| 7 | Apparent Viscosity of treated Bentonite suspension at 24±2 ºC, cP | Record the Apparent Viscosity | — |
| 8 | Yield Point of treated Bentonite suspension at 24±2 °C, lbs/100 sq.ft | Record Yield Point | — |
| 9 | API Fluid loss of treated Bentonite suspension at 24±2 °C, ml | Record API Filtration Loss | — |
| 10 | Apparent Viscosity of hot rolled (100±5°C, 18 hrs) treated Bentonite suspension at 24±2 ºC, cP | Should not decrease after hot rolling | — |
| 11 | Yield Point of hot rolled (100±5°C, 18 hrs) treated Bentonite suspension at 24±2 °C, lbs/100 sq.ft | Should not decrease after hot rolling | — |
| 12 | API Fluid loss of hot rolled (100±5°C, 18 hrs) treated Bentonite suspension at 24±2 °C, ml | Should not increase after hot rolling | — |
| 13 | 600 rpm dial reading before addition of borax solution at 24±2 °C | Record 600 rpm dial reading | — |
| 14 | 300 rpm dial reading before addition of borax solution at 24±2 °C | Record 300 rpm dial reading | — |
| 15 | 600 rpm dial reading after addition of borax solution at 24±2 °C | Should not increase more than 5 unit of S. No. 13 | — |
| 16 | 300 rpm dial reading after addition of borax solution at 24±2 °C | Should not increase more than 5 unit of S. No. 14 | — |
| 17 | Rotational viscometer with F0.2 torsion spring, 300 r/min, mPa.s (cP) | 11 (Minimum) | — |
| 18 | Rotational viscometer with F0.2 torsion spring, 6 r/min, mPa.s (cP) | 180 (Minimum) | — |
| 19 | Rotational viscometer with F0.2 torsion spring, 3 r/min, mPa.s (cP) | 320 (Minimum) | — |
| 20 | Brookfield viscometer, 1.5 rpm/min, mPa.s (cP) | 1950 (Minimum) | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 79. ONGC/DFC/74/2026 — ZINC CARBONATE (BASIC)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:00 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of crystalline powder or powder, free from visible impurities. | — |
| 2 | Purity as ZnCO3, percent by mass | 95.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 80. ONGC/DFC/75/2026 — SUPERIOR GRADE SODIUM CHLORIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:00 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of crystals or powder, free from visible impurities. | — |
| 2 | Moisturecontent,as140-150°C, percent by mass | 6.0 (Maximum) | — |
| 3 | Purity as NaCl on dry basis (dried at 500°C), percent by mass | 98.0 (Minimum) | — |
| 4 | Matter insoluble in water on dry basis (dried at 140-150°C), percent by mass | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 81. ONGC/DFC/77/2026 — POTASSIUM FORMATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:03 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white granular or crystalline powder, free from visible impurities. | — |
| 2 | Specific Gravity of saturated solution at 24 ±2°C | 1.57 (Minimum) | — |
| 3 | pH of 5% (w/v) solution in Distilled Water | 7.0 - 10.0 | — |
| 4 | Potassium Formate (calculated), percent by mass | 96.0 (Minimum) | — |
| 5 | Chloride as KCl, percent | 0.50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 82. ONGC/DFC/78/2026 — SODIUM FORMATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:04 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white granular powder or crystalline powder, free from visible impurities. | — |
| 2 | Sodium Formate (calculated), percent by mass | 95.0 (Minimum) | — |
| 3 | Volatile matter, percent by mass | 4.0 (Maximum) | — |
| 4 | Matter insoluble in water, percent by mass | 0.50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 83. ONGC/DFC/79/2026 — HIGH TEMPERATURE DEFLOCCULANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:09 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of homogeneous liquid at 24±2°C free from visible impurities. | — |
| 2 | Miscibility | Should be miscible with water | — |
| 3 | Specific Gravity at 24±2°C | 1.30 ± 0.05 | — |
| 4 | pH of the sample | 7.0 - 7.5 | — |
| 5 | Apparent Viscosity of base mud at 24±2ºC, cP | 50.0 – 55.0 | — |
| 6 | Yield Point of base mud, lbs/100 sq. ft | Record the YP | — |
| 7 | Apparent Viscosity of treated (0.25% v/v, of sample) base mud at 24±2ºC, cP | Should not exceed 25% of the base mud | — |
| 8 | Yield Point of treated (0.25% v/v, of sample) base mud , lbs/100 sq. ft | Should not exceed 6 % of the base mud | — |
| 9 | Apparent Viscosity of hot rolled (225±2°C, 20 hrs) base mud at 24±2ºC, cP | To be determined | — |
| 10 | Yield Point of hot rolled (225±2°C, 20 hrs) base mud, lbs/100 sq. ft | To be determined | — |
| 11 | Apparent Viscosity of hot rolled (225±2°C, 20 hrs) treated base mud at 24±2ºC, cP | Should not exceed 25 % of the value at hot rolled base mud | — |
| 12 | Yield Point of hot rolled (225±2°C,: 20 hrs) treated base mud, lbs/100 sq. ft | Should not exceed 6% of hot rolled base mud | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 84. ONGC/DFC/82/2026 — CLAY HYDRATION SUPPRESSANT (POLYAMINE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:13 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be clear colourless / pale yellow liquid, free from visible impurities. | — |
| 2 | Miscibility of 2% (v/v) of CHS with water | Completely miscible | — |
| 3 | Miscibility of 2% (v/v) of CHS with 3 % KCl solution | Completely miscible | — |
| 4 | Specific Gravity at 24±2°C | 1.01 – 1.10 | — |
| 5 | pH | ≥ 6.5 | — |
| 6 | Qualitatively determine Na+, K+ and Ca++ in 2% CHS / Polyamine solution in Distilled water | Should be less than 20 ppm for each element | — |
| 7 | Chemical Assay : Reinecke Salt gravimetric method, percent by mass | 20.0 (Maximum) | — |
| 8 | Swelling test : Swelling by 2 % (w/v) solution of the sample by LSM against Bentonite pellets compressed to 10,000 psi in a 02 hrs test, percent | 24.0 (Maximum) | — |
| 9 | Apparent Viscosity of Bentonite suspension (450 ml Distilled water +45gms Bentonite powder)at 24±2°C, cP | Record Apparent Viscosity | — |
| 10 | Apparent Viscosity of treated (2% w/v of CHS) Bentonite suspension at 24±2ºC, cP | Should not be more than 15 % of base mud | — |
| 11 | MBC of Bentonite slurry (2 ml Bentonite slurry + 5 ml Distilled water, Stir for 30 minutes, ml | Record MBC | — |
| 12 | MBC of treated Bentonite slurry (2 ml Bentonite slurry + 5 ml Distilled water + 5 ml (2% Polyamine solution in Distilled water), Stir for 30 minutes, ml | Should be 65% (Maximum) of Bentonite slurry | — |
| 13 | Amine Content, mg of KOH/ gm | 30 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 85. ONGC/DFC/83/2026 — HIGH TEMPERATURE AND HIGH-PRESSURE FLUID LOSS REDUCING POLYMER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:14 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of homogeneous free flowing powder, freefrom visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 12.0 (Maximum) | — |
| 3 | HPHT Filtration loss (at 160±2°C and 500 psi pressure difference) of hot rolled (225°C for 16 hrs) treated (1.5% w/v, sample) mud, ml | 25.0 (Maximum) | — |
| 4 | Yield point of hot rolled (225°C for 16 hrs) treated (1.5% w/v, sample), lb/100 sq.ft at 66 ±2 °C | 25-45 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 86. ONGC/DFC/84/2026 — NON-INVASIVE FLUID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:17 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be free flowing powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | pH of 5%(w/v) suspension in deionized / distilled water | 7.0 ± 1.0 | — |
| 4 | Sieve Analysis : Rresidue on 100 mesh (ASTM) screen after sieving @ 3000 vibrations /minute for 10 minutes, percent by mass | 15 (Maximum) | — |
| 5 | Loss on Ignition : Residue left in silica crucible after heating in muffle furnace for 2 hours at 600 ° C, percent by mass | 10 (Maximum) | — |
| 6 | Yield Point of base mud, lbs/100 sq ft | To be recorded | — |
| 7 | API Filtrate of Hot rolled (100 °C for 16 Hrs) base mud, ml | To be recorded | — |
| 8 | Invasion test of hot rolled (100°C for 16 hrs) base mud in sand bed test cell at 500 psi for 30 minutes, cm | To be recorded | — |
| 9 | Yield Point of 2% (w/v) NIF treated mud, lbs/100 sq ft | Should not increase by more than 20% of value recorded at Sl. No. 6 | — |
| 10 | Yield Point of Hot rolled (100 °C for 16 Hrs) 2% (w/v) NIF treated mud, lbs/100 sq ft | Should not be more than treated pre hot rolled mud at S. No. 9 | — |
| 11 | API Filtrate of Hot rolled (100 °C for 16 Hrs) 2% (w/v) NIF treated mud, ml | Should be equal to or less than at S. No. 7 | — |
| 12 | Invasion test of hot rolled (100°C for 16 hrs) 2% w/v NIF treated mud in sand bed test cell at 500 psi for 30 minutes, cm | Should be 50% or less than invasion at S. No. 8 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 87. ONGC/DFC/85/2026 — BACTERICIDE FOR DRILLING FLUIDS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:22 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a homogeneous free flowing liquid, free from visible impurities. | — |
| 2 | Resorcinol test for Aldehydes | Negative | — |
| 3 | ApparentViscosity(24±2ºC)of NDDF, cP | To be determined | — |
| 4 | Plastic Viscosity of NDDF, cP | To be determined | — |
| 5 | Yield point of NDDF, lbs/100sq. ft | To be determined | — |
| 6 | API Filtration Loss of NDDF, ml | To be determined | — |
| 7 | Apparent Viscosity (24±2°C) of NDDF after keeping in closed container at 36- 40°C for 10 days, cP | Reduction should be 5 units maximum from 1st day | — |
| 8 | Plastic Viscosity of NDDF after keeping in closed container at 36- 40°C for 10 days, cP | Reduction should be 5 units maximum from 1st day | — |
| 9 | Yield point of NDDF after keeping in closed container at 36-40°C for 10 days, lbs/100sq. ft | Reduction should be 5 units maximum from 1st day | — |
| 10 | API Filtration Loss of NDDF after keeping in closed container at 36- 40°C for 10 days, ml | Increase should be 0.5 ml maximum from 1st day | — |
| 11 | Apparent Viscosity (24±2ºC) of hot rolled (90°C, 18 hrs) NDDF, cP | Reduction should be 5 units maximum from 1st day | — |
| 12 | Plastic Viscosity of hot rolled (90°C, 18 hrs) NDDF, cP | Reduction should be 5 units maximum from 1st day | — |
| 13 | Yield point of hot rolled (90°C, 18 hrs) NDDF, lbs/100 sq.ft | Reduction should be 5 units maximum from 1st day | — |
| 14 | API Filtration Lossofhot rolled (90°C, 18 hrs) NDDF, ml | Increase should be 0.5 ml maximum from 1st day | — |
| 15 | Apparent Viscosity (24±2ºC) of DF 1, cP | To be determined | — |
| 16 | Plastic Viscosity of DF1, cP | To be determined | — |
| 17 | Yield point of DF1, lbs/100sq.ft | To be determined | — |
| 18 | API Filtration Loss of DF1, ml | To be determined | — |
| 19 | Apparent Viscosity (24±2ºC) of DF1 after keeping in closed container at 36- 40°C for 10 days, cP | Reduction should be 5 units maximum from 1st day | — |
| 20 | Plastic Viscosity of DF1 after keeping in closed container at 36-40°C for 10days, cP | Reduction should be 5 units maximum from 1st day | — |
| 21 | Yield point of DF1 after keeping in closed container at 36-40°C for 10 days, lbs/100 sq. ft | Reduction should be 5 units maximum from 1st day | — |
| 22 | API Filtration Loss of DF1 after keeping in closed container at 36-40°C for 10 days, ml | Increase should be 0.5 ml. maximum from 1st day | — |

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 23 | Apparent Viscosity (24±2ºC) ofhot rolled (90°C, 18 hrs) NDDF, cP | Reduction should be 5 units maximum from 1st day | — |
| 24 | Plastic Viscosity ofhot rolled (90°C, 18 hrs) NDDF, cP | Reduction should be 5 units maximum from 1st day | — |
| 25 | Yield point of hot rolled (90°C, 18 hrs) NDDF, lbs/100 sq. ft | Reduction should be 5 units maximum from 1st day | — |
| 26 | API Filtration Loss of hot rolled (90°C,: 18 hrs) NDDF, ml | Increase should be 0.5 ml maximum from 1st day | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 88. ONGC/DFC/86/2026 — LTSOBM FORMULATION (10 ppg) (OFFSHORE & ONSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 20:25 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), ppg | 10.0 ± 0.1 | — |
| 2 | Plastic Viscosity, cP | 40 (Maximum) | — |
| 3 | Yield Point, lbs /100 sq. ft | 25 – 35 | — |
| 4 | Gel0, lbs /100 sq. ft | 12 – 20 | — |
| 5 | Gel10, lbs /100 sq. ft | 16 – 30 | — |
| 6 | 6 rpm LSRV, Dial reading | 10 - 18 | — |
| 7 | O:W ratio | 69-71:31-29 | — |
| 8 | WPS (Cl-), g/l | 170 - 190 | — |
| 9 | Emulsion Stability at 120±5°F, volts | 550 (Minimum) | — |
| 10 | HPHT Filtration Loss (30 mins at 300 °F/ 500 psi as per API, all oil), ml | 5.0 (Maximum) | — |
| 11 | Specification wide Rheological parameters measured at | 120±4°F after hot rolling at 250 ±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 89. ONGC/DFC/87/2026 — LTSOBM FORMULATION (12 ppg) (OFFSHORE & ONSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:33 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Rheological parameters measured at | 120±4°F after hot rolling at 250±4°F for 16 hrs | — |
| 2 | Mud Weight at 75±4°F (BHR), ppg | 12.0 ± 0.1 | — |
| 3 | Plastic Viscosity, cP | 45 (Maximum) | — |
| 4 | Yield Point, lbs /100 sq. ft | 25 - 40 | — |
| 5 | Gel0, lbs /100 sq. ft | 12 - 20 | — |
| 6 | Gel10, lbs /100 sq.ft | 16 - 30 | — |
| 7 | O:W ratio | 69 - 71 : 31-29 | — |
| 8 | WPS (Cl-), g/l | 170 - 190 | — |
| 9 | Emulsion Stability at 120±5°F, volts | 550 (Minimum) | — |
| 10 | HPHT Filtration Loss (30 mins at 300°F/ 500 psi as per API, all oil), ml | 5.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 90. ONGC/DFC/88/2026 — LTSOBM FORMULATION FOR HPHT WELLS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:45 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Rheological parameters measured at | 150±4°F after hot rolling at 400±4°F for 16 hrs | — |
| 2 | Mud Weight at 75±4°F (BHR), ppg | 16.7 ± 0.1 | — |
| 3 | Plastic Viscosity, cP | 65 (Maximum) | — |
| 4 | Yield Point, lbs /100 sq.ft | 20 - 35 | — |
| 5 | Gel0, lbs /100 sq.ft | 10 - 18 | — |
| 6 | Gel10, lbs /100 sq.ft | 15 - 25 | — |
| 7 | O:W ratio | 79 - 81 : 21 - 19 | — |
| 8 | WPS (Cl-), g/l | 170 - 190 | — |
| 9 | Emulsion Stability at 120±5°F, volts | 550 (Minimum) | — |
| 10 | HPHT Filtration Loss (30 mins at 300°F/ 500 psi as per API, all oil), ml | 5.0 (Maximum) | — |
| 11 | SAG Factor | 0.50-0.53 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 91. ONGC/DFC/89/2026 — LTSOBM FORMULATION FOR FLAT RHEOLOGY

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:53 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), ppg | 10.0 ± 0.1 | — |
| 2 | Plastic.Viscosity at 120°±4°F, cP | 45 (Maximum) | — |
| 3 | Yield Point at 120°±4°F, lbs /100 sq.ft : | 15 - 35 | — |
| 4 | Yield Point at 39°±4°F, lbs /100 sq.ft : | Increase should not be more than 15% of Sl. No. (3) | — |
| 5 | Gel0 at 120°±4°F, lbs /100 sq.ft : | 8 - 18 | — |
| 6 | Gel10 at 120°±4°F, lbs /100 sq.ft : | 12 - 30 | — |
| 7 | Gel10 at 39°±4°F, lbs /100 sq.ft : | Increase should not be more than 15% of S. No. (6) | — |
| 8 | 6 rpm LSRV at 120°±4°F, Dial reading : | 8 - 16 | — |
| 9 | O:W ratio : | 75:25 | — |
| 10 | WPS (Cl-), g/l : | 170 - 190 | — |
| 11 | Emulsion Stability at 120±5°F,volts : | 550 (Minimum) | — |
| 12 | HPHT Filtration Loss (30 mins at : | 5.0 (Maximum) | — |
| 13 | Specification Wide Rheological parameters measured at | 120±4°F after hot rolling at 250±4°F for 16 hours | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 92. ONGC/DFC/90/2026 — SPUD DRILLING FLUID (OFFSHORE & ONSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:55 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight, ppg / SG at 75±4°F | 8.6 ± 0.1 / 1.03± 0.01 | — |
| 2 | Plastic Viscosity, cP | 5 (Minimum) | — |
| 3 | Yield Point, lbs/100 sq. ft | 20 (Minimum) | — |
| 4 | API Filtration Loss, ml | 15.0 (Maximum) | — |
| 5 | pH at 75±4°F | 8.5-9.5 | — |
| 6 | Specification Wide Rheological parameters measured at | 75±4°F after ageing at 75±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 93. ONGC/DFC/91/2026 — CLAY FREE KCL-PHPA –POLYOL

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:57 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), ppg | 11 ± 0.1 | — |
| 2 | Plastic Viscosity, cP | 25 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq. ft | 20 - 40 | — |
| 4 | Gel lbs/100 sq. ft | 5 - 10 | — |
| 5 | Gel 10, lbs/100 sq. ft | 8 - 16 | — |
| 6 | API Filtration Loss, ml | 10.0 (Maximum) | — |
| 7 | pH at 75±4°F (BHR) | 8. 5 - 9.0 | — |
| 8 | Specification wide Rheological parameters measured at | 115±4°F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 94. ONGC/DFC/92/2026 — CLAY FREE KCL-PHPA–POLYOL DRILLING FLUID FOR LOWER SECTION (OFFSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 12:59 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), (ppg) | 11.5 ± 0.1 | — |
| 2 | Plastic Viscosity, cP | 25 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq. ft | 20 - 35 | — |
| 4 | Gel0, lbs/100 sq. ft | 5 - 10 | — |
| 5 | Gel10, lbs/100 sq. ft | 8 - 16 | — |
| 6 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 7 | pH at 75 ±4°F (BHR) | 8.5 - 9.0 | — |
| 8 | Specification wide Rheological parameters measured at | 115±4 °F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 95. ONGC/DFC/93/2026 — HPHT POLYMERIC BASED DRILLING FLUID SYSTEM (OFFSHORE & ONSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), ppg/SG | 16.6 ± 0.1 / 1.99 ± 0.01 | — |
| 2 | Plastic Viscosity, cP | 60.0 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq. ft | 20-45 | — |
| 4 | Gel0, lbs/100 sq. ft | 6-12 | — |
| 5 | Gel10, lbs/100 sq. ft | 10-25 | — |
| 6 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 7 | HPHT Filtration Loss (150°C/ 500 psi as per API), ml | 15.0 (Maximum) | — |
| 8 | pH at 75±4°F (BHR) | 8.5-10.0 | — |
| 9 | Sag Factor | 0.50 – 0.53 | — |
| 10 | Specification wide Rheological parameters measured at | 150± 4°F after hot rolling at 392±4 °F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 96. ONGC/DFC/94/2026 — GEL POLYMER DRILLING FLUID SYSTEM (OFFSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:04 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), ppg | 8.8 ± 0.1 | — |
| 2 | Plastic Viscosity, cP | 40 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq. ft | 20 - 40 | — |
| 4 | Gel0 , lbs/100 sq. ft | 6 - 10 | — |
| 5 | Gel10, lbs/100 sq. ft | 12 - 25 | — |
| 6 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 7 | pH at 75±4°F (BHR) | 8.5 - 9.5 | — |
| 8 | Specification wide Rheological parameters measured at | 115±4°F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 97. ONGC/DFC/95/2026 — CLAYFREE NON-DAMAGING DRILLLING FLUID SYSTEM (OFFSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:06 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), ppg | 8.8 ± 0.1 | — |
| 2 | Plastic Viscosity, cP | 30 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq. ft | 20 - 35 | — |
| 4 | Gel0, lbs/100 sq. ft | 8 - 12 | — |
| 5 | Gel10, lbs/100 sq. ft | 10 - 16 | — |
| 6 | API Filtration loss, ml | 5.0 (Maximum) | — |
| 7 | pH at 75±4°F (BHR) | 8.5 - 9.0 | — |
| 8 | Specification wide Rheological parameters measured at | 115±4°F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 98. ONGC/DFC/96/2026 — FORMATE BASED NON- DAMAGING DRILLING FLUID SYSTEM (OFFSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:08 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Density at 75±4°F (BHR), ppg | 12.0 ± 0.1 | — |
| 2 | Plastic Viscosity, cP | 40 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq. ft | 20 - 40 | — |
| 4 | 6 RPM LSRV, Dial reading | 8 - 12 | — |
| 5 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 6 | pH at 75±4°F (BHR) | 9.5 - 10.5 | — |
| 7 | Specification wide Rheological parameters measured at | 115±4°F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 99. ONGC/DFC/98/2026 — GEL –POLYMER DRILLING FLUID SYSTEM (ONSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:10 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud Weight at 75±4°F (BHR), SG | 1.08 ± 0.01 | — |
| 2 | Plastic Viscosity, cP | 15.0 (Maximum) | — |
| 3 | Yield point, lbs/100 sq. ft | 20 - 35 | — |
| 4 | 6 RPM LSRV, Dial reading | 6 - 10 | — |
| 5 | API Filtration Loss, ml | 12 (Maximum) | — |
| 6 | pH at 75±4°F (BHR) | 8.5-9.0 | — |
| 7 | Specification wide Rheological parameters measured at | 115±4°F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 100. ONGC/DFC/99/2026 — DISPERSED DRILLING FLUID SYSTEM (ONSHORE AREAS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 13:12 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Mud weight at 75 ±4°F (BHR), SG | 1.20 ± 0.01 | — |
| 2 | Plastic Viscosity, cP | 25 (Maximum) | — |
| 3 | Yield Point, lbs/100 sq. ft | 20 - 35 | — |
| 4 | Gel0, lbs/100 sq.ft | 5 - 10 | — |
| 5 | Gel10, lbs/100 sq. ft | 8 - 16 | — |
| 6 | API Filtration Loss, ml | 5.0 (Maximum) | — |
| 7 | pH at 75± 4°F (BHR) | 8.5 - 9.0 | — |
| 8 | Rheological parameters measured at | 115±4°F after hot rolling at 194±4°F for 16 hrs | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 101. ONGC/LPG/01/2026 — ACTIVATED ALUMINA (GRADE I AND II)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 11:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of white spherical balls, free from visible impurities. | — |
| 2 | Moisture content at 250±5°C, percent by mass | 2.0 (Maximum) | — |
| 3 | pH Value | 4.0 - 8.0 | — |
| 4 | Grade-1: Sodium and its compounds as Na2O3, percent by mass | 0.8 (Maximum) | — |
| 5 | Grade-2: Sodium and its compounds as Na2O3, percent by mass | 1.0 (Maximum) | — |
| 6 | Water Soluble Sulphates as (SO4)2-, percent by mass | 0.7(Maximum) | — |
| 7 | Loss on Ignition, percent by mass | 6.5 (Maximum) | — |
| 8 | Grade-1: Water Adsorption capacity, percent by mass | 16.0 (Maximum) | — |
| 9 | Grade-2: Water Adsorption capacity, percent by mass | 14.0 (Maximum) | — |
| 10 | Grade-1: Loss on Attrition, percent by mass | 0.75 (Maximum) | — |
| 11 | Grade-2: Loss on Attrition, percent by mass | 1.0 (Maximum) | — |
| 12 | Bulk Density, g /ml | 0.8 (Minimum) | — |
| 13 | Grade-1: Bed Crushing Strength, percent by mass | 80 (Minimum) | — |
| 14 | Grade-2: Bed Crushing Strength, percent by mass | 75(Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 102. ONGC/LPG/04/2026 — ACTIVATED CARBON FOR AMINE FILTRATION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 11:31 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of granular or cylindrical pellets, free from visible impurities. | — |
| 2 | Fraction retained on US No. 8 or equivalent sieve, percent by mass | 10 (Maximum) | — |
| 3 | Fraction passing through US No. 16 or equivalent sieve, percent by mass | 4 (Maximum) | — |
| 4 | Hardness No., as per IS 877 | 70 (Minimum) | — |
| 5 | Moisture content at 105±2°C, percent by mass | 5 (Maximum) | — |
| 6 | Bulk Density, g/ml | 0.50 - 0.60 | — |
| 7 | Pore volume, cm3/g | 0.80 (Minimum) | — |
| 8 | Ash content, percent by mass | 10 (Maximum) | — |
| 9 | Iodine adsorption capacity, mg/g | 900 (Minimum) | — |
| 10 | Total active surface area, m2/g | 900 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 103. ONGC/LPG/06/2026 — AQUEOUS SULPHOLANE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 11:33 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a clear liquid at 10°C, free from visible impurities. | — |
| 2 | Water content by IP - 358 / ASTM D-4006 Method, percent by volume | 3.5 (Maximum) | — |
| 3 | Density at 30°C by IP - 190: 2005 Method, g /cc | 1.251 (Minimum) | — |
| 4 | Recovery up to 270°C (Distillation under atmospheric pressure, using a modified distillation unit), percent by volume | 5.0 (Maximum) | — |
| 5 | Recovery up to 295°C, (Distillation under atmospheric pressure, using a modified distillation unit), percent by volume | 95.0 (Minimum) | — |
| 6 | Refractive Index at 30°C by ASTM D 1218 – 2002 Method | 1.475 -1.479 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 104. ONGC/LPG/07/2026 — CAUSTIC SODA LYE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 11:34 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a colourless liquid, free from visible impurities. | — |
| 2 | Purity as NaOH on as received basis, percent by mass | 46.0 (Minimum) | — |
| 3 | Specific Gravity at 24±2°C | 1.43 (Minimum) | — |
| 4 | Chloride as NaCl, percent by mass | 0.10 (Maximum) | — |
| 5 | Sulphates as Na2SO4, percent by mass | 0.10 (Maximum) | — |
| 6 | Silicates as SiO , percent by mass | 0.02 (Maximum) | — |
| 7 | Iron as Fe, percent by mass | 0.002 (Maximum) | — |
| 8 | Carbonates as Na2CO3, percent by mass | 0.40 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 105. ONGC/LPG/08/2026 — ETHYL MERCAPTAN

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 11:35 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of clear liquid with characteristic pungent odour and shall be free from visible impurities. | — |
| 2 | Purity as C2H5SH by GC Analysis, percent by mass | 98.5 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 106. ONGC/LPG/09/2026 — METHANOL (COMMERCIAL GRADE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 11:35 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a clear and colourless liquid, free from matter in suspension. | — |
| 2 | Miscibility with water | The material shall show no turbidity | — |
| 3 | Relative density at 27°C /27°C | 0.798 (Maximum) | — |
| 4 | Distilate volume collected 65±2°C by distillation Range at 760 mm pressure, percent by volume | 95 (Minimum) | — |
| 5 | Residue on evaporation, percent by mass | 0.015 (Maximum) | — |
| 6 | Alkalinity (as NH ), percent by mass | 0.0003 (Maximum) | — |
| 7 | Acidity as acetic acid, percent by mass | 0.006 (Maximum) | — |
| 8 | Aldehydes and Ketones as Acetone, percent by mass | 0.100 (Maximum) | — |
| 9 | Water content, percent by mass | 0.5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 107. ONGC/LPG/10/2026 — METHYL DI-ETHANOL AMINE (MDEA)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 11:38 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a colourless to light coloured liquid readily soluble in water and Benzene and be free from visible impurities. | — |
| 2 | Purity, percent by mass | 98.0 (Minimum) | — |
| 3 | Specific Gravity at 20 °C / 20 °C | 1.038 - 1.044 | — |
| 4 | Initial Boiling Point (as per ASTM D - 1078 Method), °C | 235 (Minimum) | — |
| 5 | End Point (as per ASTM D - 1078 Method), °C | 260 (Maximum) | — |
| 6 | Water Content (Karl Fisher), percent by mass | 0.5 (Maximum) | — |
| 7 | Refractive Index at 20 °C | 1.46 - 1.50 | — |
| 8 | Flash point, °C | 120 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 108. ONGC/LPG/12/2026 — MOLECULAR SIEVE TYPE - 4Ao FOR NATURAL GAS AND LIQUID DRIERS (3 MM AND 1.5 MM DIAMETER PELLETS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:01 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of cylindrical pellets, free from visible impurities. | — |
| 2 | For Gas Dryer: Pellet Size, mm | 2.9 – 3.5 | — |
| 3 | For Liquid Dryer: Pellet Size, mm | 1.4 – 1.7 | — |
| 4 | X-ray Diffraction Characteristics | Shall Satisfy requirements, as per Table 2 of BIS Specification No. IS 14211: 1994 (Reaffirmed 1999) for molecular sieve | — |
| 5 | Moisture content at 350±5°C, percent by mass | 2.0 (Maximum) | — |
| 6 | Adsorption capacity at 30°C and 15% Relative Humidity, percent by mass | 18.0 (Minimum) | — |
| 7 | Adsorption capacity at 30°C and 15% Relative Humidity after thermal ageing at 600°C for 1 hour, percent by mass | 18.0 (Minimum) | — |
| 8 | Bulk Density after exposure to 95% Relative Humidity, kg / litre | 0.78 (Minimum) | — |
| 9 | For Gas Dryer: Loss on Attrition: A-7, percent by mass | 0.40 (Maximum) | — |
| 10 | For Liquid Dryer: Loss on Attrition: A-7, percent by mass | 0.15 (Maximum) | — |
| 11 | Bed Crushing Strength, percent by mass | 80 (Minimum) | — |
| 12 | For Gas Dryer: Loss on Attrition: A-8, percent by mass | 1.50 (Maximum) | — |
| 13 | For Liquid Dryer: Loss on Attrition: A-8, percent by mass | 0.80 (Maximum) | — |
| 14 | Accelerated Degradation Test: (a) Fines Generated in 120 cycle | Not more than 0.3 - 0.5% | — |
| 15 | Accelerated Degradation Test: (b) Fines Generated in 600 cycle | Not more than 1% | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 109. ONGC/LPG/14/2026 — MONOETHYLENE GLYCOL (MEG)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:03 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a free flowing liquid, free from visible impurities. | — |
| 2 | Water solubility at 24±2°C | Miscible in all proportions | — |
| 3 | Initial Boiling Point, °C | 193.0 (Minimum) | — |
| 4 | Dry Point, °C | 206.0 (Maximum) | — |
| 5 | Acidity as Acetic Acid, percent by mass | 0.005 (Maximum) | — |
| 6 | Water content, percent by mass | 0.3 (Maximum) | — |
| 7 | Ash content, percent by mass | 0.010 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 110. ONGC/LPG/15/2026 — NITROGEN (IOLAR – 3 GRADE OR EQUIVALENT)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:08 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of compressed gas filled in a cylinder. | — |
| 2 | Oxygen, ppm | 6.0 (Maximum) | — |
| 3 | Moisture content, ppm | 6.0 (Maximum) | — |
| 4 | Carbon Dioxide, ppm | 1.0 (Maximum) | — |
| 5 | Carbon Mono-oxide, ppm | 1.0 (Maximum) | — |
| 6 | Oxides of Nitrogen, ppm | 1.0 (Maximum) | — |
| 7 | Hydrogen, ppm | 1.0 (Maximum) | — |
| 8 | Argon, ppm | 10.0 (Maximum) | — |
| 9 | Hydrocarbons, ppm | 1.0 (Maximum) | — |
| 10 | Sulphur compounds, ppm | 0.5 (Maximum) | — |
| 11 | Mercury, ppm | Nil | — |
| 12 | Chlorine, ppm | Nil | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 111. ONGC/LPG/17/2026 — POTASSIUM HYDROXIDE FOR SULPHUR RECOVERY UNIT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:09 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of pellets or flakes, free from visible impurities. | — |
| 2 | Total Alkalinity as KOH, percent by mass | 87.0 (Minimum) | — |
| 3 | Carbonate as K2CO3 , percent by mass | 1.0 (Maximum) | — |
| 4 | Sodium as Na, percent by mass | 5.0 (Maximum) | — |
| 5 | Nitrate Compounds, percent by mass | 0.01 (Maximum) | — |
| 6 | Chlorides as KCl, percent by mass | 0.025 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 112. ONGC/LPG/18/2026 — SPHERICAL CERAMIC ALUMINA BALLS (TYPE - I AND II) FOR URAN AND HAZIRA PLANTS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:23 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of round shaped balls, free from visible impurities. TYPE - I TYPE - II | — |
| 2 | TYPE-1: Diameter size, mm | 4 ± 1 | — |
| 3 | TYPE-2: Diameter size, mm | 6 ± 1 | — |
| 4 | Individual Bulk Density, kg/litre | 2.9 (Minimum) | — |
| 5 | TYPE-1: Bulk Density, kg/litre | 1.85 - 1.90 | — |
| 6 | TYPE-2: Bulk Density, kg/litre | 1.85 - 2.0 | — |
| 7 | Water absorption, percent by mass | 7.0 (Maximum | — |
| 8 | Apparent Porosity, percent by Volume | 20.0 (Maximum) | — |
| 9 | TYPE-1: Cold Crushing Strength, (Average Point Load), kilograms | 50.0 (Minimum) | — |
| 10 | TYPE-2: Cold Crushing Strength, (Average Point Load), kilograms | 75.0 (Minimum) | — |
| 11 | A12O3 , percent by mass | 99.0 (Minimum) | — |
| 12 | SiO2, percent by mass | 0.20 (Maximum) | — |
| 13 | Fe2O3 , percent by mass | 0.20 (Maximum) | — |
| 14 | TYPE-1: Na2O + K2O, percent by mass | 0.35 (Maximum) | — |
| 15 | TYPE-2: Na2O + K2O, percent by mass | 0.30 (Maximum) | — |
| 16 | TiO2 , percent by mass | 0.30 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 113. ONGC/LPG/19/2026 — STRONG ACID CATION EXCHANGE RESINS FOR USE IN DE- MINERALISATION / SOFTENING PLANTS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:50 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of moist spherical beads, free from visible impurities. | — |
| 2 | Ionic form | Sodium | — |
| 3 | Total Exchange Capacity, milliequivalent/ml | 2.0 (Minimum) | — |
| 4 | Bulk Density in Sodium form, g/ litre | 800 - 870 | — |
| 5 | Moisture content, percent by mass | 43 - 47 | — |
| 6 | Particle size, mm | 0.3 - 1.2 | — |
| 7 | Uniformity coefficient | 1.5 1.8 | — |
| 8 | Wet Screen Grading | 14 - 52 Mesh BSS or equivalent | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 114. ONGC/LPG/20/2026 — STRONG BASE ANION EXCHANGE RESINS (TYPE- I) FOR USE IN DE- MINERALISATION PLANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:52 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of moist spherical beads, free from visible impurities. | — |
| 2 | Ionic form | Chloride | — |
| 3 | Total Exchange Capacity, milli-equivalents/ml | 1.3 ± 0.1 | — |
| 4 | Bulk Density in Chloride form, g/litre | 700 (Minimum) | — |
| 5 | Moisture content, percent by mass | 50 ± 3 | — |
| 6 | Particle Size, mm | 0.3 - 1.2 | — |
| 7 | Uniformity Coefficient | 1.5 - 1.9 | — |
| 8 | Wet Screen Grading | 14 - 52 Mesh BSS or equivalent | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 115. ONGC/LPG/21/2026 — TRIETHANOL AMINE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:52 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of clear liquid, free from visible impurities. | — |
| 2 | Triethanolamine content, percent by mass | 85 (Minimum) | — |
| 3 | Moisture content, percent by mass | 0.5 (Maximum) | — |
| 4 | Equivalent mass | 140 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 116. ONGC/LPG/22/2026 — WEAK BASE ANION EXCHANGE RESINS FOR USE IN DE-MINERALISATION PLANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:53 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of moist spherical beads, free from visible impurities. | — |
| 2 | Ionic form | Free base | — |
| 3 | Total Exchange Capacity, milli-equivalents/ ml | 1.6 - 1.7 | — |
| 4 | Bulk Density, g/litre | 700 ± 30 | — |
| 5 | Moisture content, percent by mass | 45 – 47 | — |
| 6 | Particle Size, mm | 0.3 - 1.2 | — |
| 7 | Uniformity Coefficient | 1.60- 1.65 | — |
| 8 | Wet Screen Grading | 14 - 52 Mesh BSS or equivalent | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 117. ONGC/LPG/23/2026 — ACCELERATED AMINE MIXTURE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:54 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a homogeneous liquid at 24±2ºC, free from visible impurities. | — |
| 2 | Colour, APHA, by ASTM D - 1209 | 150 (Maximum) | — |
| 3 | Odour | Charateristic amine / ammonical odour | — |
| 4 | Solubility in water | Completely miscible | — |
| 5 | Composition Methyl Diethanol Amine percent by weight | 80.0 (Minimum) | — |
| 6 | Composition Piperazine, percent by weight | 13.0 (Minimum) | — |
| 7 | Water, percent by weight | 7.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 118. ONGC/LPG/24/2026 — STORAGE STABILITY ADDITIVES FOR HSD

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:57 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a homogeneous, free flowing liquid, free from visual impurities. | — |
| 2 | Miscibility of 10% additive with Hazira HSD at 24±2°C | The material shall be completely miscible | — |
| 3 | Total sediments after dosing the Hazira HSD with recommended dosages of additives, (ASTM-D2274), mg/100 ml | 1.5 (Maximum) | — |
| 4 | Effect on other parameters after dosing the Hazira HSD with recommended dosages of additives | HSD shall remain conforming to other parameters of Hazira HSD | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 119. ONGC/LPG/25/2026 — PIPERAZINE AQUEOUS SOLUTION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 12:58 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical appearance | The material shall be a free flowing clear liquid free from visible Impurities. | — |
| 2 | Piperazine by Titrometric method, percent (w/w) | 15.0 (Minimum) | — |
| 3 | Water Content (by Dean Stark Apparatus), percent (w/w) | 83-85 | — |
| 4 | Purity of Piperazine by GC, percent (w/w) | 99.0 (Minimum) | — |
| 5 | Impurities / loss on evaporation, percent (w/w) | 1.5 (Maximum) | — |
| 6 | Colour (APHA) by ASTM D -1209 | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 120. ONGC/LPG/26/2026 — FILTER CLAY (ATTAPULGITE CLAY FOR ATF POLISHING)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 13:00 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Fraction retained between ASTM 30-60 mesh sieve, percent by mass | 90 (Minimum) | — |
| 2 | Fraction passing through ASTM 60 mesh sieve, percent by mass | 5.0 (Maximum) | — |
| 3 | Moisture content at 105±2°C, percent by mass | 2.0 (Maximum) | — |
| 4 | Bulk Density, g/cc | 0.56 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 121. ONGC/LPG/27/2026 — ROCK SALT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 13:01 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | Granular free from visible impurities | — |
| 2 | Fraction between 8mm and 2.8mm normal aperture size (BIS), percent by mass | 85 (Minimum) | — |
| 3 | Purity as NaCl on dry basis (after drying at 500°C ) , percent by mass | 90 (Minimum) | — |
| 4 | Moisture content at 141±2°C, percent | 1.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 122. ONGC/LPG/28/2026 — STRONG BASE ANION EXCHANGE RESINS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 13:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of moist spherical beads, free from visible impurities. | — |
| 2 | Ionic form | Chloride | — |
| 3 | Total Exchange Capacity, milli-equivalents/ ml | 1.15 (Minimum) | — |
| 4 | Bulk Density in Chloride form, g / litre | 670 - 720 | — |
| 5 | Moisture content, percent by mass | 53 - 58 | — |
| 6 | Particle Size, mm | 0.3 - 1.2 | — |
| 7 | Uniformity Coefficient | 1.5 - 1.8 | — |
| 8 | Wet Screen Grading, Mesh BSS or | 14 - 52 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 123. ONGC/LPG/29/2026 — SCALE INHIBITOR, URAN PLANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 13:03 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Appearance | Clear liquid at 24± 2 degC, free from visible impurities | — |
| 2 | Specific Gravity | 1.10 – 1.39 @ 25 degC | — |
| 3 | pH | 2 - 5 | — |
| 4 | Viscosity | < 40 cp @ 25 degC | — |
| 5 | Efficiency When evaluated for performance as per NACE standard TM0374 – 2001, item no. 21208 | 80 % (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 124. ONGC/LPG/32/2026 — ACID ACTIVATED MONTMORILLONITE CLAY

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 13:06 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Free Moisture at 85±3°C, % by mass | 6 % (Maximum) | — |
| 2 | Loose Bulk Density, g/lit | 800 - 950 | — |
| 3 | Surface Area, m2/gm | 125 (Minimum) | — |
| 4 | pH (5% Solid) | 3 - 6 | — |
| 5 | Particle Size Distribution (a): > 2 mm (fraction retained on 8 BSS mesh or equivalent sieve), percentage by mass | 10 (Maximum) | — |
| 6 | Particle Size Distribution (b): 0.25 mm to 2 mm (fraction retained between 8 BSS mesh and 60 BSS mesh or equivalent sieve), percentage by mass | 85 (Minimum) | — |
| 7 | Particle Size Distribution (c): < 0.25 mm (fraction passing through 60BSS mesh or equivalent sieve), percentage by mass | 5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 125. ONGC/PC/01/2026 — CHROMIUM ACETATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:06 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a grayish green or bluish green powder, free from visible impurities. | — |
| 2 | Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 3 | Chromium content, percent by mass | 19.0 (Minimum) | — |
| 4 | Solubility of material 1% (w/v) in Distilled water solution. | Readily soluble and form greenish gray | — |
| 5 | pH of 1% (w/v) Solution in Distilled water | 4.0 - 6.0 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 126. ONGC/PC/02/2026 — CORROSION INHIBITOR FOR COMPRESSED GAS LINES OF AHMEDABAD ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:09 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogenous liquid at 24±2°C, free from visible impurities | — |
| 2 | Viscosity of the product at 300 rpm, cP | 200 (Maximum) | — |
| 3 | Corrosivity of the neat product, mpy | 1.0 (Maximum) | — |
| 4 | Miscibility / Dispersibility of the inhibitor (1% w/v) in test Brine (1% w/v NaCl solution in Distilled water Saturated with CO2) | Completely miscible / dispersible | — |
| 5 | Thermal stability at 80±2 0C for 2 hrs | No turbidity, precipitate or separation of layers | — |
| 6 | Inhibition efficiency of the corrosion inhibitor (25 ppm) under static test conditions, percent | 80 (Minimum) | — |
| 7 | Inhibition efficiency of the corrosion inhibitor (25 ppm) under dynamic test conditions, percent | 80 (Minimum) | — |
| 8 | Visual examination of the condition of the Coupons after each test | Inhibited coupons shall be free from pits on visual inspection, under both test conditions | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 127. ONGC/PC/03/2026 — CORROSION INHIBITOR FOR GAS LINE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:11 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogenous liquid at 24±2°C, free from visible impurities | — |
| 2 | Viscosity of the product at 300 rpm | 200 (Maximum) | — |
| 3 | Corrosivity of the neat product, mpy | 1.0 (Maximum) | — |
| 4 | Compatibility and Emulsification tendency of the product | Compatible with mixture and not form emulsion, interface sludge pad thickness not be more than 5% after five hrs. | — |
| 5 | Thermal Stability test 80±2 °C | The material shall be stable | — |
| 6 | Inhibition efficiency of the corrosion inhibitor (50 ppm) under static test conditions when coupons fully immersed, percent | 90 (Minimum) | — |
| 7 | Inhibition efficiency of the corrosion inhibitor (50 ppm) under dynamic test conditions, percent | 90 (Minimum) | — |
| 8 | Visual examination of the condition of the Coupons after each test | Inhibited coupons shall be free from pits and scratches on visual inspection, under static as well as dynamic conditions | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 128. ONGC/PC/04/2026 — CORROSION INHIBITOR FOR OIL LINE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:14 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogenous liquid at 24±2°C, free from visible impurities. | — |
| 2 | Viscosity of the product at 300 rpm, cP | 200 (Maximum) | — |
| 3 | Corrosivity of the neat product, mpy | 1.0 (Maximum) | — |
| 4 | Compatibility and Emulsification Tendency of the product with a mixture of untreated Crude oil mix | Compatible with the mixture and not form emulsion and interface sludge padthickness not be more than 5% after five hrs. | — |
| 5 | Thermal Stability test up to 80±2, °C | The material shall be stable | — |
| 6 | Inhibition efficiency of the corrosion inhibitor (35 ppm) under static test conditions, percent | 80 (Minimum) | — |
| 7 | Inhibition efficiency of the corrosion inhibitor (35 ppm) under dynamic test conditions, percent | 80 (Minimum) | — |
| 8 | Visual examination of the condition of | Inhibited Coupons free frpm pits and scratches | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 129. ONGC/PC/05/2026 — CORROSION INHIBITOR FOR OIL AND GAS LINES IN PRESENCE OF HYDROGEN SULPHIDE (H2S)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:16 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogenous liquid at 24±2°C, free from visible impurities. | — |
| 2 | Viscosity of the product at 300 rpm, cP | 200 (Maximum) | — |
| 3 | Corrosivity of the neat product, mpy | 1.0 (Maximum) | — |
| 4 | Compatibility and Emulsification tendency with a mixture of untreated Crude Oil mix and Brine Corrodant | Compatible with mixture and not form emulsion, interface sludge pad thickness not be more than 5% (v/v) after five hrs | — |
| 5 | Thermal stability test up to 120±2 °C | The material shall be stable | — |
| 6 | Inhibiton efficiency of the corrosion inhibitor (100 ppm) under Dynamic test Conditions (Wheel test), percent | 90 (Minimum) | — |
| 7 | Visual examination of the coupons under Dynamic test conditions (Wheel test) | Inhibited Coupons shall be free from pits and scratches | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 130. ONGC/PC/06/2026 — DEMULSIFIER FOR AHMEDABAD ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:22 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogenous liquid at 5°C, free from visible impurities. | — |
| 2 | Solubility of 2% (w/v) of sample Xylene / Toluene (LR Grade) at 20 °C | Solution should be clear | — |
| 3 | Performance Test KALOL GGS-V [Dosing Temp: 40±2 °C, Curing Temp: 80±2 °C, Curing time: 120minutes, Demulsifier Dose:150 (mg/lit)] - Water Content of Treated Oil, percent by volume | 1.0 (Maximum) | — |
| 4 | Performance Test JHALORA GGS-I [Dosing Temp: 40±2 °C, Curing Temp: 78±2 °C, Curing time: 60minutes, Demulsifier Dose:200 (mg/lit)] - Water Content of Treated Oil, percent by volume | 1.0 (Maximum) | — |
| 5 | Organic Chloride content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 131. ONGC/PC/07A/2026 — DEMULSIFIER FOR ANKLESHWAR FIELD, ANKLESHWAR ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | committee_1 |
| **Last Updated** | 10 Mar 2026, 13:32 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State : Water Soluble | The material shall be free flowing homogenous liquid at 20°C, free from visible impurities. | — |
| 2 | Physical State : Oil soluble | The material shall be free flowing homogenous liquid at 5°C, free from visible impurities. | — |
| 3 | Solubility in 2% (w/v) solution in Distilled water at 20°C | Should be clear solution | — |
| 4 | Solubility of 2% (w/v) solution with Xylene/ Toluene at 20°C | Should be clear solution | — |
| 5 | Water content of supernatant oil column after Centrifuge test, percent by volume [Test Conditions: Emulsion- Untreated Emulsion of Ankleshwar GGS-III; Emulsion Volume (ml)-100; Dose (mg/ litre)- 50; Dosing Temperature (°C) - 50±2; Curing Temperature (°C) - 60±2; Curing time (Minutes)-120] | 1.0 (Maximum) | — |
| 6 | Organic Chloride content (for oil soluble), ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 132. ONGC/PC/07B/2026 — DEMULSIFIER FOR GANDHAR FIELD, ANKLESHWAR ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | committee_1 |
| **Last Updated** | 10 Mar 2026, 13:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State (For Water soluble) | The material shall be free flowing homogenous liquid at 20°C, free from visible impurities. | — |
| 2 | Physical State (For Oil soluble) | The material shall be free flowing homogenous liquid at 5°C, free from visible impurities. | — |
| 3 | Solubility of 2% (w/v) solution in Distilled water at 20°C | Should be clear | — |
| 4 | Solubility of 2% (w/v) solution with Xylene / Toluene at 20°C | Should be clear | — |
| 5 | Organic Chloride Content (for oil soluble), ppm | 100 (Maximum) | — |
| 6 | Water content of supernatant liquid, percent by volume [Test Conditions: Source of emulsion- Composite Low Pressure Emulsion of Gandhar field; Emulsion Volume (ml)- 100; Dose (mg / litre)- 50; Dosing Temperature (°C)- 50±2; Curing Temperature (°C)- 60±2; Curing time (Minutes) - 60], | 0.20 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 133. ONGC/PC/08/2026 — WATER SOLUBLE DEMULSIFIER FOR LAKWA FIELD OF ASSAM ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:26 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing homogeneous liquid at 20°C, free from visible impurities. | — |
| 2 | Solubility of 5% (v/v) of the product in Distilled water at 24±2°C | Solution should be clear and homogenous | — |
| 3 | Laboratory Evaluation: Installation LAKWA GGS - III [Test conditions- Dosing Temperature (°C): 45 ± 2, Curing Temperature (°C): 60 ± 2, Curing time: 60 minutes, Demulsifier Dose (mg/litre): 120] - Water Content, percentage (v/v) | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 134. ONGC/PC/09/2026 — DEMULSIFIER FOR KATHANA FIELD, CAMBAY ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:28 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing homogenous liquid at 5°C, free from visible impurities. | — |
| 2 | Solubility of 2% (w/v) of sample in Xylene / Toluene at 20°C | Solution should be clear | — |
| 3 | Water content of treated oil, percent by volume [Test Conditions: Composite Emulsion of Kathana Field from Kathana GGS; Emulsion Volume (ml)- 200; Dose (mg / litre)- 200; Dosing Temperature (°C)- 50±2; Curing Temperature (°C)- 70±2; Curing time (Minutes)- 60] | 1.0 (Maximum) | — |
| 4 | Organic Chloride Content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 135. ONGC/PC/10/2026 — DEMULSIFIER FOR RAJAHMUNDRY ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:28 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be free flowing homogenous liquid at 5 °C, free from visible impurities. | — |
| 2 | Solubility of sample (2%, w/v) in Xylene (LR) / Toluene (LR) at 20°C | Solution should be clear | — |
| 3 | Associated Water Content in the Separated Oil Layer (Middle), percent by volume [Test Conditions: Kesanapalli (West) crude emulsion sample, having associated water content of approx. 30% (v/v). Emulsion Volume: 200 ml; Demulsifier Dose: 50 mg/l; Dosing temp: 50±2 ºC; Curing temp: 70±2; Curing time: 60 minutes)] | 0.2 (Maximum) | — |
| 4 | Separation Efficiency | Water should be separated as distinct phase | — |
| 5 | Organic Chloride Content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 136. ONGC/PC/11/2026 — DEMULSIFIER FOR MEHSANA ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 13:54 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogenous liquid at 5°C, free from visible impurities.Solution should be clear. | — |
| 2 | Solubility of 2% (w/v) in Xylene /: Toluene (LR Grade) at 20°C | Solution should be clear | — |
| 3 | Organic Chloride Content, ppm | 100 (Maximum) | — |
| 4 | Performance Test, (a): Installation North Kadi CTF, Water Content % (v) Test Conditions Dosing Temperature (°C): 40 ± 2 Curing Temperature (°C): 70 ± 2 Curing Time (minutes): 80 Demulsifier Dose (mg/litre): 300 | 1.0 (Maximum) | — |
| 5 | Performance Test, (b): Installation North Kadi GGS - II, Water Content % (v) Dosing Temperature (°C): 40 ± 2 Curing Temperature (°C): 80 ± 2 Curing Time (minutes): 150 Demulsifier Dose (mg/litre): 600 | 1.0 (Maximum) | — |
| 6 | Performance Test, (c): Installation North Kadi GGS - III, Water Content % (v) Dosing Temperature (°C): 40 ± 2 Curing Temperature (°C): 57 ± 2 Curing Time (minutes): 90 Demulsifier Dose (mg/litre): 500 | 1.0 (Maximum) | — |
| 7 | Performance Test, (d): Installation North Santhal CTF, Water Content % (v) Dosing Temperature (°C): 40 ± 2 Curing Temperature (°C): 75 ± 2 Curing Time (minutes): 120 Demulsifier Dose (mg/litre): 300 | 1.0 (Maximum) | — |
| 8 | Performance Test, (e): Installation South Santhal CTF, Water Content % (v) Dosing Temperature (°C): 40 ± 2 Curing Temperature (°C): 70 ± 2 Curing Time (minutes): 60 Demulsifier Dose (mg/litre): 250 | 1.0 (Maximum) | — |
| 9 | Performance Test, (f): Installation: Sobhasan CTF, Water Content % (v) Dosing Temperature (°C): 40 ± 2 Curing Temperature (°C): 85 ± 2 Curing Time (minutes): 90 Demulsifier Dose (mg/litre): 400 | 1.0 (Maximum) | — |
| 10 | Performance Test, (j): Installation Sobhasan GGS - II, Water Content % (v) Dosing Temperature (°C): 40 ± 2 Curing Temperature (°C): 80 ± 2 Curing Time (minutes): 60 Demulsifier Dose (mg/litre): 50 | 1.0 (Maximum) | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 137. ONGC/PC/11B/2026 — DEMULSIFIER FOR BECHARAJI GGS-I, MEHSANA ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | committee_1 |
| **Last Updated** | 10 Mar 2026, 13:58 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing homogenous liquid at 5°C, free from visible impurities. | — |
| 2 | Solubility of 2% (w/v) of sample in Xylene / Toluene at 20°C | Solution should be clear | — |
| 3 | Water Content of treated oil, percent by volume [Test Conditions: Emulsion Volume (ml)- 200; Dose (mg / litre)- 400; Dosing Temperature (°C)- 40±2; Curing Temperature (°C)- 80±2; Curing time (Minutes) - 90] | 1.0 (Maximum) | — |
| 4 | Organic Chloride content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 138. ONGC/PC/12/2026 — DEMULSIFIER FOR MUMBAI ASSETS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:29 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a clear homogenous liquid at 20°C, free from visible impurities. | — |
| 2 | Miscibility with Xylene at 25°C | Should form a clear solution | — |
| 3 | Demulsification efficiency, percent by volume [Test Conditions: Emulsion from Heera Platform; Emulsion Vol. (ml)- 100; Dose (mg/litre)- 40; Curing Temp.(°C) - 70±2; Curing time (Min.) – 15, Settling Temperature (°C)-30±2; Settling Time (Min.)-5], | 60 (Minimum) | — |
| 4 | Organic Chloride Content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 139. ONGC/PC/13/2026 — DEOILER FOR ASSAM ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | liquid, free from visible impurities. | — |
| 2 | Solubility in Distilled water | Soluble in all proportions | — |
| 3 | Flash Point, °C | 50 (Minimum) | — |
| 4 | Oil removal efficiency of the Deoiler in the treated effluent at the specified dosage, percent [Test Conditions: Stock Solution of Deoiler: 0.1% (v/v) in Distilled Water; Emulsified Oil in Effluent: 1000-3000 mg/litre; Dose - 10 mg/litre; Oil content by Spectro-photometric method] | 83 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 140. ONGC/PC/14/2026 — DE-OILER FOR GANDHAR FIELD,

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:31 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be free flowing, homogeneous liquid at 24±2°C, free from visible impurities. | — |
| 2 | Nature | Organic | — |
| 3 | Miscibility of 1% (w/v) of the sample | Miscible with Distilled water at 24±2°C | — |
| 4 | Oil removal efficiency of the Deoiler in the treated effluent at the specified destabilization concentration, percent [Test Conditions: Stock Solution of Deoiler: 0.1% (v/v) in Distilled Water; Emulsified Oil in Effluent: 500-1000 mg / litre; Destabilization Concentration of Sample: 10 mg / litre; Oil Content by Spectroscopic Method] | 75 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 141. ONGC/PC/16/2026 — DEOILER FOR NORTH SANTHAL FIELD,

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:31 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a clear, homogenous liquid, free from visible impurities. | — |
| 2 | Nature | Organic | — |
| 3 | Miscibility of 1% (w/v) of the sample | Miscible with Distilled water | — |
| 4 | Oil removal efficiency of the Deoiler in the treated effluent at the specified destabilization concentration, percent [Test Conditions: Stock Solution of Deoiler: 0.1% (v/v) Solution in DW; Emulsified Oil in Effluent: 200- 800mg/litre; Destabilization Conc. of Sample: 20 mg/litre] | 70 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 142. ONGC/PC/17/2026 — DEOILER FOR RAJAHMUNDRY ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:32 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a clear, homogeneous liquid or solid powder, free from visible impurities. | — |
| 2 | Miscibility of 0.1% (w/v) of sample with Distilled water at 20-45°C | Should form a clear solution. | — |
| 3 | Oil and Grease removal efficiency of the Deoiler in the treated effluent at specified destabilization dose, percent [Test Conditions: Stock Solution of Deoiler:0.1% (v/v) in DW; Emulsified Oil in Effluent: 50-150 mg/litre; Destabilization Concen. of Sample:10 mg/litre] | 50 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 143. ONGC/PC/18/2026 — DEOILING POLYELECTROLYTE FOR

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:33 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing powder, free from visible impurities. | — |
| 2 | Nature and Type | Organic and Anionic | — |
| 3 | Solubility of 0.1% (w/v) of sample in Distilled water | Soluble | — |
| 4 | Oil content of the treated effluent, mg/l [Test Conditions: Stock Solution of Deoiler: 0.1% (v/v) in DW; Emulsified Oil in Effluent: 100-500 mg / litre; Conc. of Ferric Chloride Hexahydrate: 25 mg/litre; Conc. of Sodium hydroxide: 10 mg/litre; Conc. of Polyelectrolyte: 2 mg/litre] | 10 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 144. ONGC/PC/20/2026 — DE-WATERING POLYELECTROLYTE FOR WASTE WATER TREAMENT PLANT, GANDHAR FIELD, ANKLESHWAR ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:34 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing powder, free from visible impurities. | — |
| 2 | Nature and Type | Organic and Cationic | — |
| 3 | Solubility of 0.1% (w/v) of sample in Distilled water | Soluble | — |
| 4 | Reduction in total suspended solids by polyelectrolyte treatment, percent [Test Conditions: Stock Solution of Deoiler: 0.1% (v/v) in DW; Characteristic of Mixed Sludge: Dry Solids: 20 – 40% (w/w), Volatile Solids: 15 - 35% (w/w); Conc. of Dewatering Polyelectrolyte: 5 mg/litre] | 60 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 145. ONGC/PC/24/2026 — MAGNESIUM CHLORIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:35 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of crystals free from visible impurities. | — |
| 2 | Magnesium Chloride as MgCl .6H O, | 95.0 (Minimum) 2 2 percent by mass | — |
| 3 | Sulphate as SO 2 -, percent by mass | 1.6 (Maximum) | — |
| 4 | Calcium as Ca2 +, percent by mass | 1.0 (Maximum) | — |
| 5 | Alkali Chloride as NaCl, percent by mass | 2.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 146. ONGC/PC/25/2026 — PHPA FOR WATER SHUT OFF (HIGH TEMPERATURE)

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:35 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of free flowing granular powder, free from visible impurities. | — |
| 2 | Nature of Polymer | Anionic | — |
| 3 | Moisture content at 105±2°C, percent by mass | 12.0 (Maximum) | — |
| 4 | pH of 0.5% (w/v) Solution of Polymer in Distilled water at 24±2 °C | 5.5 - 8.5 | — |
| 5 | Carboxyl content as CH =CH-COOH, on dry basis, percent by mass | 3.0 - 15.0 | — |
| 6 | Solubility of Polymer 1.0% (w/v) in 4% NaCl (LR grade) solution, after stirring for 6 hrs on a Magnetic Stirrer at high speed at 24±2°C | Completely soluble without any fish eye | — |
| 7 | Viscosity of Polymer 1.0% (w/v) Polymer in 4% NaCl (LR grade) solution at 24±2°C, after 16 hrs continuous stirring measured on Brookefield Viscometer, Model LVT, Spindle No. 2 at 60 rpm, cP (contd.) | 300 (Maximum) | — |
| 8 | Gelation time and temperature | Polymer should not form non-flowable gel immediately when cross-linked at 24± 2°C Should not form thick gel and it should only be slightly more viscous (flowable) than initially treated polymer solution upto 7 hrs time at 140 ± 2°C | — |
| 9 | Gel quality | The Gel should be thick, highly viscous and should not flow out of the glass tube upon inversion in 7 to 48 hrs at 140±2 °C | — |
| 10 | Gel stability | The Cross-linked Gel should be thermally stable at 140±2°C for a minimum period of 15 days | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 147. ONGC/PC/26/2026 — PHPA FOR WATER SHUT OFF (LOW TEMPERATURE)

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | committee_1 |
| **Last Updated** | 09 Mar 2026, 08:40 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a free flowing granular powder, free from visible impurities. | — |
| 2 | Nature of Polymer | Anionic | — |
| 3 | Moisture content at 105±2°C, percent by mass | 12.0 (Maximum) | — |
| 4 | pH of 0.5% (w/v) Solution of Polymer in Distilled water at 24±2°C | 5.5 - 8.5 | — |
| 5 | Carboxyl content as CH2=CH-COOH, on Dry Basis, percent by mass | 3.0 - 15.0 | — |
| 6 | Solubility of 1% (w/v) Polymer (on Dry Basis) in 1% NaCl Solution, after stirring for 16 hrs on a Magnetic Stirrer at high speed | Should be completely soluble without any fish eye | — |
| 7 | Viscosity of 1% (w/v) Polymer (on Dry Basis) in 1.0% NaCl Solution after continuous stirring for 16 hrs on Magnetic Stirrer at high speed, Spindle No. 1 or 2 at 60 rpm (7.3 shear rate) (24±2 °C), cP | 400 (Maximum) | — |
| 8 | Intrinsic Viscosity at 24±2 °C by Canon Fensky (75 No.) in 1% NaCl, cP | 20 (Maximum) | — |
| 9 | Insoluble Residue, Percentage | 0.2 (Maximum) | — |
| 10 | Total Ionic Content, ppm | 100 (Maximum) | — |
| 11 | Gelation time and temperature | The polymer should not form viscous non-flowable gel immediately when cross-linked with hexamine hydroquinone at 24 ±2 °C Should not form gel and should only be slightly more viscous (flowable) solution up to 8 hrs time at 80 ±1 °C. | — |
| 12 | Gel quality (a) | The Gel should be tonguing, highly viscous and should not flow out of the glass tube on inversion in 3 8 to 100 hrs at 80 ± 1 °C | — |
| 13 | Gel quality (b) | The gel should turn into hard gel in 4- 8 days at 80 ± 1 °C | — |
| 14 | Gel quality (c) | The gel should turn into hard gel in 4- 6 days at 110 ± 1 °C | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 148. ONGC/PC/27/2026 — POLY ALUMINIUM CHLORIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:50 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a homogeneous liquid, free from visible impurities. | — |
| 2 | Specific Gravity at 27°C / 27°C | 1.32 ± 0.03 | — |
| 3 | pH of 5% (w/v) solution in Distilled water at 24±2°C | 4.0 (Maximum) | — |
| 4 | Misciblity of 1 g of the sample in 100 ml of distilled water | Shall be miscible | — |
| 5 | Aluminium as Al 2 O 3 , percent by mass | 13 - 15 | — |
| 6 | Chloride as Cl-, percent by mass | 18 - 23 | — |
| 7 | Sulphate as SO 4 2-, percent by mass | 2 .0 (Maximum) | — |
| 8 | Iron as Fe, (100 ppm, Maximum by Colour matching with standard Iron solution solution) | Colour of sample match with standard | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 149. ONGC/PC/28/2026 — POUR POINT DEPRESSANT (PPD) FOR GOPAVARAM CRUDE, RAJAHMUNDRY ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:52 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be free flowing liquid at 25°C, free from visible impurities. | — |
| 2 | Solubility of 5% (w/v) in Xylene (LR) /Toluene (LR) homogeneous solution | Should form clear and stable | — |
| 3 | Pour Point of the doped Gopavaram Crude Oil (doped with 300 ppm (w/v) (Maximum) of PPD at 50±1°C and determined, as per IP-441 / ASTM D- 5853 standard method), °C | 18 (Maximum) | — |
| 4 | Pour Point of treated Crude oil after ageing for 7 days at ambient temperature | Characteristics of the treated crude should be maintained at least for 7 days of ageing at ambient temperature | — |
| 5 | Organic Chloride content, ppm | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 150. ONGC/PC/29/2026 — POUR POINT DEPRESSANT (PPD)/ FLOW IMPROVER FOR ASSAM ASSET)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:54 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be homogenous free flowing liquid at 25°C, free from visible impurities. | — |
| 2 | Solubility of 10% (w/v) sample in Xylene (LR) | Solution should be clear | — |
| 3 | Modified Pour Point Crude Oil (Geleky GGS-II composite) doped with 400 ppm (w/v) (Max) of Flow Improver / PPD at 60±1°C and determined, as per IP-441 / ASTM D- 5853 standard method), ° C | 18 (Maximum) | — |
| 4 | Plastic Viscosity of the treated crude as measured at 20°C, cP | 30 (Maximum) | — |
| 5 | Yield Value of the treated crude as measured at 20°C, dynes/cm2 | 10.2 (Maximum) | — |
| 6 | Parameters (Pour point, PV, Yield value) of treated crude oil after ageing for 7 days at ambient temperature | Parameters remain same after ageing | — |
| 7 | Organic Chloride content, ppm | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 151. ONGC/PC/34/2026 — THERMAL FLUID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:56 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a bright and clear liquid, free from visible impurities. | — |
| 2 | Corrosion, Copper Strip test, as per IP-154-93/ASTM D-130-94 (3 hrs test at 100°C) | 1 (Maximum) | — |
| 3 | Density at 15°C, g/cc | 0.87 ± 0.02 | — |
| 4 | Initial Boiling point (Distillation temperature at 10 mm Hg (Temperature converted to Atmospheric Pressure at 760 mm Hg), °C | 310 (Minimum) | — |
| 5 | Temperature at 95% recovery, °C | 472 ± 2 | — |
| 6 | Flash point as per ASTM D–93 Method, °C | 200 (Minimum) | — |
| 7 | Viscosity at 37.8°C (100°F) as per | 140 - 170 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 152. ONGC/PC/35/2026 — TRIETHYLENE GLYCOL

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 21:57 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a transparent liquid, free from visible impurities. | — |
| 2 | Miscibility with water | Should be miscible in all proportions | — |
| 3 | Specific Gravity at 20°C / 20°C | 1.12 - 1.13 | — |
| 4 | Distillation up to 275°C, percent by volume | 2 (Maximum) | — |
| 5 | Distillation up to 300°C, percent by volume | 98 (Minimum) | — |
| 6 | Acidity as Acetic acid, percent weight by weight | 0.05 (Maximum) | — |
| 7 | Water content, percent by volume | 0.5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 153. ONGC/PC/36/2026 — TOLUOLE (INDUSTRIAL TOLUENE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | committee_1 |
| **Last Updated** | 08 Mar 2026, 22:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a clear, colourless liquid, free from visible impurities. | — |
| 2 | Specific Gravity at 15.5°C / 60°F | 0.860 to 0.875 | — |
| 3 | Specific Gravity at 27°C / 80.6°F | 0.850 to 0.865 | — |
| 4 | Volume of distillate collected upto 105 °C (as per ASTM D850-21), % (v) | 2 (Maximum) | — |
| 5 | Volume of distillate collected upto 115°C (as per ASTM D850-21), % (v) | 97 (Minimum) | — |
| 6 | Residue on evaporation, mg / 100 ml | 10 (Maximum) | — |
| 7 | Organic Chloride content, ppm | 5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 154. ONGC/PC/37/2026 — WAX DISPERSANT / INHIBITOR FOR GANDHAR FIELD, ANKLESHWAR ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 22:03 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogeneous liquid at 20 ± 2°C, free from visible impurities. | — |
| 2 | Miscibility of 5% (w/v) of the sample in Xylene | Solution should be clear | — |
| 3 | Inhibition Efficiency (evaluated by Cold Finger test methodology for Wax Deposition inhibition by maintaining cold probe at 35±1°C), percent | 60 (Minimum) | — |
| 4 | Organic Chloride content, ppm | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 155. ONGC/PC/39/2026 — MIXED XYLENE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | committee_1 |
| **Last Updated** | 08 Mar 2026, 22:08 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a clear, colourless liquid, free from visible impurities. | — |
| 2 | Specific Gravity 15.5°C / 60°F | 0.860 - 0.875 | — |
| 3 | Specific Gravity At 27°C / 80.6°F | 0.850 - 0.865 | — |
| 4 | IBP °C (ASTM D850-21), °C | 135 (Minimum) | — |
| 5 | Dry Point (ASTM D850-21), °C | 144.5 (Maximum) | — |
| 6 | Purity by GC (Ethyl Benzene & p, m, o-Xylene) | 97.0% (Minimum) | — |
| 7 | Residue on evaporation, mg /100 ml | 10 (Maximum) | — |
| 8 | Organic Chloride content, ppm | 5 (Maximum) | — |
| 9 | Ethyl Benzene Content | 25.0% (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 156. ONGC/PC/40/2026 — HEXAMINE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 22:10 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of colorless, lustrous crystal or a white crystalline free flowing powder, free from visible impurities. | — |
| 2 | Purity as Hexamine (On dry basis), percent by mass | 98 (Minimum) | — |
| 3 | pH aqueous extract solution | 8.0-9.0 | — |
| 4 | Solubility | Completely soluble in water | — |
| 5 | Water insoluble, percent by mass | 0.05 (Maximum) | — |
| 6 | Sulphated Ash, percent by mass | 0.1 (Maximum) | — |
| 7 | Loss on drying, percent by mass | 0.5 (Maximum) | — |
| 8 | Sulphates as SO 2-, (0.005% (m), maximum by colour comparision) | Turbidity produced with material not greater than control test | — |
| 9 | Iron content as Fe, (0.005% (m), maximum by comparing the intensity of colour of the Butanol layer | Not exceeds colour of test solution | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 157. ONGC/PC/41/2026 — HYDROQUINONE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 22:12 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form ofshining white or creamish white needles, free from visible impurities. | — |
| 2 | Hydroquinone content, percent by mass | 98.5 (Minimum) | — |
| 3 | Melting Point (°C) | 171 - 175 | — |
| 4 | Residue on Ignition, percent by mass | 0.10 (Maximum) | — |
| 5 | Sulphates as SO 2-, (0.075% (m), maximum by turbidity comparision) | Turbidity produced with material not greater than control test | — |
| 6 | Iron contentas Fe, (0.002%(m), maximum by comparing the intensity of colour of the Butanol layer) | Not exceeds colour of test solution | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 158. ONGC/PC/42/2026 — NAPHTHALENE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | committee_1 |
| **Last Updated** | 08 Mar 2026, 22:19 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | Material shall be white to light brown powder, free from visible impurities. | — |
| 2 | Crystallising Point,°C | 78.5 (Minimum) | — |
| 3 | Moisture Content, percent by mass | 0.2 (Maximum) | — |
| 4 | Ash, percent by mass | 0.02 (Maximum) | — |
| 5 | Matter Insoluble in Toluene, percent by mass | 0.1 (Maximum) | — |
| 6 | Non Volatile matter at 160°C, percent by mass | — | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 159. ONGC/PC/46/2026 — Low Temperature Demulsifier for MH Asset

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 22:26 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a clear homogenous liquid at 20°C, free from visible impurities. | — |
| 2 | Miscibility with Xylene at 25°C | Should form a clear solution | — |
| 3 | Water content in demulsified /treated oil middle layer, percent by volume [Test Conditions: Emulsion from ICPR Platform; Emulsion Vol. (ml)-200; Dose (mg/litre)- 20; Dosing temp(°C) 40±1- Curing Temp.(°C) - 40±1; Curing time (Min.) – 06; Settling Time (Min.) -2 ] | 1.0 (Maximum) | — |
| 4 | Demulsification efficiency, percent [Test Conditions: Emulsion from ICPR Platform; Emulsion Vol.(ml)- 200; Dose (mg/litre)- 20; Dosing temp(°C) 40±1- Curing Temp.(°C) - 40±1; Curing time (Min.) – 06; Settling Time (Min.) -2] | 65.0 (Minimum) | — |
| 5 | Organic Chloride Content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 160. ONGC/PC/47/2026 — WAX INHIBITOR/DISPERSANT FOR JOTANA FIELD OF MEHSANA ASSET

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:42 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing homogeneous liquid at 25±1°C free from visible impurities. | — |
| 2 | Miscibility of 5% (w/v) of the sample in xylene | Solution should be clear | — |
| 3 | Wax dispersion / inhibition efficieny by cold finger test apparatus, percent [Test Conditions: 100°C distillation residue of composite crude of Jotana field; Dose-1000 ppm of neat product; Dosing temperature- 70±2 °C; Curing time-30 minutes; Cold probe temperature-40±1°C; Water bath temp.- 70±2°C ; Test Duration- 6 Hrs ] | 40 (Minimum) | — |
| 4 | Viscosity of dehydrated neat crude at 30°C and 10 sec-1 shear rate by Plate and Cone Rheometer, centipoise [Test Conditions: Dehydrated crude of Jotana field; Curing time-60 minutes at 70±2 °C followed by 24 hours at ambient temperature] | Record Viscosity | — |
| 5 | Yield Strength of neat dehydrated crude at 30 °C by Plate and Cone Rheometer, Pascal [Test Conditions: Dehydrated crude of Jotana field; Curing time-60 minutes at 70±2 °C followed by 24 hours at ambient temperature] | Record Yield Strength | — |
| 6 | Reduction in Viscosity of treated crude, percent [Test Conditions: Dehydrated crude of Jotana field dosed with 1000ppm of neat product at 70±2 ° C followed by curing conditions as in serial 4] | 80 (Minimum) | — |
| 7 | Reduction of Yield Strength of treated crude, percent [Test Conditions: Dehydrated crude of Jotana field; Dose -1000 ppm neat product; Dosing & curing temperature-70±2 °C; Curing time-60 minutes; followed by 24 hours at ambient temperature] | 80 (Minimum) | — |
| 8 | Organic chloride content, ppm | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 161. ONGC/PC/48/2026 — Linear Alkyl Benzene Sulphonic Acid

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 22:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be free flowing pale brown to brown homogenous liquid at 20 °C free from visible impurities. | — |
| 2 | Active matter as alkyl benzene sulphonic acid, percent by mass | 95.0 (Minimum) | — |
| 3 | Free acidity (As H2SO4 ), percent by mass | 2.0 (Maximum) | — |
| 4 | Free alkyl benzene, percent by mass | 2.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 162. ONGC/PC/49/2026 — NONYL PHENOL ETHOXYLATE (9.5 MOLE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 22:31 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be free flowing colourless homogeneous liquid at 20°C free from visible impurities | — |
| 2 | pH (5% v/v in distilled water) | 6.0 - 8.0 | — |
| 3 | Solubility (10% v/v in distilled water) | Clear solution | — |
| 4 | Cloud Point (1% v/v in distilled water), °C | 57.5 - 59.0 | — |
| 5 | Moisture Content by K/F method, Percent volume | 0.5 (Maximum) | — |
| 6 | OH value | 85 - 91 | — |
| 7 | HLB (Hydrophile-Lipophile Balance) | 13.0 - 13.4 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 163. ONGC/PC/51/2026 — OIL SOLUBLE DEMULSIFIER FOR ASSAM ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 22:37 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be free flowing homogenous liquid at 5 I C, free from visible impurities | — |
| 2 | Solubility of 2% (w/v) of sample in Xylene / Tolune (LR Grade) at 20 degC | Solution should be clear | — |
| 3 | Laboratory Evaluation [Test Conditions : Installation GELEKY GGS-II i. Dosing Temperature, degC : 40 ± 2, ii. Curing Temperature, degC : 55 ± 2, iii. Curing Time, minutes : 45, iv. Demulsifier Dose, mg/l : 65] - Water Content, % (v/v) | 0.2 (Maximum) | — |
| 4 | Organic Chloride Content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 164. ONGC/PC/52/2026 — FLOW IMPROVER / PPD FOR B-193 OF B&S; ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 06:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogeneous liquid at 24 ± 2°C free from visible impurities | — |
| 2 | Miscibility of 5% (w/v) of sample in Xylene (LR Grade) at 25 degC | Solution should be clear | — |
| 3 | Smell | The material should not have an obnoxious/ unpleasant smell | — |
| 4 | Organic chloride content (ppm) | 50 (Maximum) | — |
| 5 | Flash Point ( I C) | 20 (Minimum) | — |
| 6 | Performance Test : The Flow improver shall be evaluated on composite crude oil having pour point 39±3 °C collected from production manifold/ different wellheads (free from condensate) of B-193 platform from B&S Asset, (6A). Test Condition for Cold Finger Dose : 1000 ppm Dose temperature : 50±2°C Curing temperature : 50±2°C Curing time : 30 minutes Cold probe temperature : 25±1°C Hot water bath temperature : 45±2°C Test Duration : 5.0 hrs., (6B). Test Condition for Viscosity and Pour Point measurement: Viscosity measurement by BOB Rotor Viscometer and Pour point by IP 441/ ASTM D5853 method or equivalent | Measurement of Viscosity and Pour Point of dehydrated crude a. Untreated b. Treated with 1000 ppm of Flow Improver | — |
| 7 | Results Required: (a) Required depression in Pour point of treated crude | 6 °C (Minimum) | — |
| 8 | Results Required: (b) Required reduction in Viscosity at 35 °C, shear rate 10-11 sec -1 | 55% (Minimum) | — |
| 9 | Results Required: (c) Required reduction in deposition by CFT after treatment | 40 % (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 165. ONGC/PC/53/2026 — Alkali (Soda Ash) for EOR

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 06:40 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white granular or Powder, free from visible impurities | — |
| 2 | Volatile Matter, as determined by IS: 251-1998, percent by mass | 2.0 (Maximum) | — |
| 3 | Solubility of material in distilled water at 24±2 degC, gm/lit | More than 180 | — |
| 4 | Solution Properties of 1.5% (w/v) solution in distilled water (a): pH | 10 – 12 | — |
| 5 | Solution Properties of 1.5% (w/v) solution in distilled water (b): Turbidity, NTU | 1.0 (Maximum) | — |
| 6 | Solution Properties of 1.5% (w/v) solution in distilled water (c): Insoluble Matter, % by mass (Filtration through G-4) | 0.1 (Maximum) | — |
| 7 | Solution Properties of 1.5% (w/v) solution in distilled water (d): Total Alkalinity as Na2CO3, determined by IS: 251-1998, percent by mass | 98.5 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 166. ONGC/PC/54/2026 — POLYMER for EOR

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 06:59 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of free flowing granular powder free from visible impurities | — |
| 2 | Moisture Content, % by mass | 10 (Maximum) | — |
| 3 | Intrinsic Viscosity at 40 degC, dl/gm | 17.0 – 27.0 | — |
| 4 | Solution properties in 2% NaCl (AR Grade) at pH 8.0 ± 0.05 (polymer concentration 1000 ppm) (a): Relative viscosity (Cannon Fenske) at 40 degC, cp | 3.10 (Minimum) | — |
| 5 | Solution properties in 2% NaCl (AR Grade) at pH 8.0 ± 0.05 (polymer concentration 1000 ppm) (b): Brook field viscosity at 40 degC - i) Spindle 1 at 60 rpm, cp | 5.30 (Minimum) | — |
| 6 | Solution properties in 2% NaCl (AR Grade) at pH 8.0 ± 0.05 (polymer concentration 1000 ppm) (b): Brook field viscosity at 40 degC - ii) UL Adapter at 60 rpm, cp | 3.20 (Minimum) | — |
| 7 | Solution properties in 2% NaCl (AR Grade) at pH 8.0 ± 0.05 (polymer concentration 1000 ppm) (c): Screen Factor at 40 degC | 19.0 – 30.0 | — |
| 8 | Solution properties in 2% NaCl (AR Grade) + 0.05% CaCl2 . 2H2O (AR Grade) at pH 8.0 ± 0.05 (polymer concentration 1000 ppm) (a) : Relative viscosity (Cannon Fenske) at 40 degC, cp | 2.80 (Minimum) | — |
| 9 | Solution properties in 2% NaCl (AR Grade) + 0.05% CaCl2 . 2H2O (AR Grade) at pH 8.0 ± 0.05 (polymer concentration 1000 ppm) (b): Brook field viscosity at 40 degC, i) Spindle 1 at 60 rpm, cp | 4.90 (Minimum) | — |
| 10 | Solution properties in 2% NaCl (AR Grade) + 0.05% CaCl2 . 2H2O (AR Grade) at pH 8.0 ± 0.05 (polymer concentration 1000 ppm) (b): Brook field viscosity at 40 degC, ii) UL Adapter at 60 rpm, cp | 2.90 (Minimum) | — |
| 11 | Solution properties in 2% NaCl (AR Grade) + 0.05% CaCl2 . 2H2O (AR Grade) at pH 8.0 ± 0.05 (polymer concentration 1000 ppm) (c): Screen Factor at 40 degC | 17.0 – 26.0 | — |
| 12 | Insoluble Residue a) In 2% NaCl (AR Grade), % by mass | 0.30 (Maximum) | — |

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 13 | Insoluble Residue b)In 2% NaCl (AR Grade) + 0.05% CaCl2. 2H2O (AR Grade), % by mass | 0.30 (Maximum) | — |
| 14 | Thermal Stability at 80 ± 2 degC (i): Initial value of Relative viscosity at zero date (Cannon Fenske) at 40 degC, cp [Polymer Concentration : 1000 ppm, Prepared polymer solution in hard brine (2% NaCl (AR Grade) + 0.05% CaCl2.2H2O (AR Grade) in distilled water filtered through 0.45 Micron filter + Nitrogen purging] | To be determined | — |
| 15 | Thermal Stability at 80 ± 2 degC (ii): Relative viscosity after 7 days (Cannon Fenske) at 40 degC, cp | To be determined | — |
| 16 | Thermal Stability at 80 ± 2 degC (iii): Retention in Relative Viscosity ((ii) * 100)/(i) , % | 75 (Minimum) | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 167. ONGC/PC/55/2026 — SURFACTANT for EOR

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 07:07 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of homogeneous liquid free from visible impurities | — |
| 2 | Nature of Surfactant | Anionic | — |
| 3 | Active Matter Content, wt % | 37 (Minimum) | — |
| 4 | Pour Point, degC | 12 (Maximum) | — |
| 5 | Solubility (1 % solution in distilled water at 24 ± 2 degC) | Homogeneous solution without any precipitation | — |
| 6 | Solution Properties (2000 ppm of surfactant in distilled water) (a) : pH | 8 – 10 | — |
| 7 | Solution Properties (2000 ppm of surfactant in distilled water) (b): Turbidity, NTU | 3 (Maximum) | — |
| 8 | Thermal Stability at 80 ± 2 degC, (i): Initial value (Zero date), ml [Titre value of 0.004 M Hyamine – 1622 with 2000 ppm of surfactant solution in distilled water] | 1.50 (Minimum) | — |
| 9 | Thermal Stability at 80 ± 2 degC, (ii): After 7 days , ml | Should not be less than 90 % of (i) value | — |
| 10 | Critical Micelle Concentration (CDFC) ppm, Conductance Method | 1100 – 1700 | — |
| 11 | Interfacial Tension (IFT), m- dyne/cm at 80 ± 2 degC IFT between Surfactant solution (2000 ppm) and n- Decane Hydrocarbon at 80 ± 2 degC | Less than 5500 | — |
| 12 | Emulsion Formation (2000 ppm Surfactant solution from emulsion with n-Decane Hydrocarbon in Dynamic / Static condition at 80 ± 2 degC) | Emulsion should form in dynamic & static condition at 80 ± 2 degC up to 7 days | — |
| 13 | Compatibility Study, Turbidity, NTU [2000 ppm of surfactant in Brine (1.5% NaCl + 250 ppm Ca2+ and 150 ppm Mg2+) at 80±2 °C] | 10 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 168. ONGC/PC/56/2026 — PPD/FLOW IMPROVER FOR KATHANA GGS OF CAMBAY ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 07:17 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be homogenous liquid at 25±1 ° C, free from visible impurities. | — |
| 2 | Solubility of 5 % (w/v) of sample in Xylene / Toluene(LR or GR Grade) | Solution should be clear | — |
| 3 | Performance Test, (i): Reduction in Pour point of treated crude on Day-1 [Source of crude oil: The PPD/Flow Improver shall be evaluated for its performance on composite crude oil of Kathana GGS dispatch line having water content ≤ 1 % (v/v) and Pour Point, 39±3 °C.] and [Test Conditions: (i). Dose of product: 4000 mg/lit (ii). Curing Temperature:60±2 degC (iii). Curing Time: 30 Minutes] and [Pour Point Measurement by IP-441/ASTM D5853] | 12 ■C (Minimum) | — |
| 4 | Performance Test, (ii): Reduction in Pour point of treated crude on Day-3 | 9 ■C (Minimum) | — |
| 5 | Performnace Test, (iii): % Reduction in the viscosity at 30 °C after Day-1 [Viscosity Measurement by Plate & Cone Rheometer] and [Viscosity of the Blank and Treated samples shall be measured at shear rate of 10 sec-1 at 30 °C on day 1 and 3] | 80 (Minimum) | — |
| 6 | Performnace Test, (iv): % Reduction in the viscosity at 30 °C after Day-3 | 70 (Minimum) | — |
| 7 | Organic chloride content, ppm | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 169. ONGC/PC/57/2026 — LIQUID HYDROGEN SULPHIDE SCAVENGER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 07:18 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall homogeneous liquid, free from visible impurities | — |
| 2 | Specific Gravity at 24 ± 2 oC | 1.05 - 1.20 | — |
| 3 | pH | 9 - 12 | — |
| 4 | Pour Point, oC | 15 (Maximum) | — |
| 5 | Solubility in water | Soluble | — |
| 6 | Tertiary Amine Content, % by weight | 50 (Minimum) | — |
| 7 | Percentage Active Matter w.r.t. Total Amine Value | 60 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 170. ONGC/PC/58/2026 — PPD/FLOW IMPROVER FOR ANKLAV

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:44 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be homogenous liquid at 25±1 ° C, free from visible impurities. | — |
| 2 | Solubility of 5 % (w/v) of sample in Xylene / Toluene (LR or GR Grade) | Solution should be clear | — |
| 3 | Performance Test, (i): Reduction in Pour point of treatedcrude on Day-1 [Source of crude oil: The PPD/Flow Improver shall be evaluated for its performance on composite crude oil of Anklav Field having water content ≤ 2 % (v/v) and Pour Point, 39±3 °C] and [Pour point and Viscosity measurement, Test Conditions (i) Dose of product: 5000 mg/lit, (ii) Curing Temperature: 60±2■C, (iii) Curing Time: 30 Minutes] and [Pour Point Measurement by IP- 441/ASTM D5853] | 9 ■C (Minimum) | — |
| 4 | Performance Test, (ii): Reduction in Pour point of treatedcrude on Day-3 | 6 ■C (Minimum) | — |
| 5 | Performance Test, (iii): % Reduction in the viscosity at 33 degC on Day-1 [Viscosity Measurement by Plate &Cone Rheometer: Viscosity of the Blank and Treated samples shall be measured at shear rate of 10 sec-1 at 33 °C on day 1 and 3] | 75 (Minimum) | — |
| 6 | Performance Test, (iv): % Reduction in the viscosity at 33 degC on Day-3 | 65 (Minimum) | — |
| 7 | Organic Chloride Content | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 171. ONGC/PC/59/2026 — PPD/FLOW IMPROVER FOR JOLWA GGS OF ANKLESHWAR ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 07:33 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be homogenous liquid at 25±1 ° C, free from visible impurities. | — |
| 2 | Solubility of 5 % (w/v) of sample in Xylene / Toluene (LR or GR Grade) | Solution should be clear | — |
| 3 | Performance Test, (i): Reduction in Pour point of treatedcrude on day 1 [Source of crude oil: The PPD/Flow Improver shall be evaluated for its performance on composite crude oil collected from dispatch line of Jolwa GGS dehydrated to water content ≤ 1 % (v/v) and Pour Point, 39±3 ° C] and [Pour point and Viscosity measurement Test Conditions: i. Dose of product: 2000 mg/lit ii. Curing Temperature: 60±2 ■C iii. Curing Time: 30 Minutes] and [Pour Point Measurement by IP-441/ASTM D5853] | 12 ■C (Minimum) | — |
| 4 | Performance Test, (ii): Reduction in Pour point of treated crude on day 3 | 9 ■C (Minimum) | — |
| 5 | Performance Test, (iii): % Reduction in the viscosity at 33 °C on day-1 [Viscosity Measurement by Plate &Cone Rheometer: Viscosity of the Blank and Treated samples shall be measured at shear rate of 10 sec-1 at 33 °C on day 1 and 3] | 80 (Minimum) | — |
| 6 | Performance Test, (iv): % Reduction in the viscosity at 33 °C on day-3 | 70 (Minimum) | — |
| 7 | Organic chloride content, ppm | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 172. ONGC/PC/60/2026 — DEMULSIFIER FOR COMPOSITE EMULSION OF ANKLAV FIELD

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 07:38 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing homogeneous liquid at 15 ± 1 degC, free from visible impurities | — |
| 2 | Solubility of 2% (w/v) of sample in Xylene / Toluene (AR / LR Grade) at 20 ± 1 degC | Solution should be clear | — |
| 3 | Performance Test, Water content of treated oil, % by volume [Test Conditions: (i) Source of Emulsion: Composite Emulsion of Anklav Field (ii) Demulsifier Dose, mg/lit : 300 (iii) Dosing Temperature, degC : 50 ± 2 (iv) Curing Temperature, degC : 60 ± 2 (v) Curing Time, minutes : 60] | 1.0 (Maximum) | — |
| 4 | Organic Chloride Content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 173. ONGC/PC/61/2026 — CORE FOAM STICKS FOR GAS WELLS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 07:40 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of Solid Sticks | — |
| 2 | Size : Length (inch) / Diameter (inch) | 15 (Maximum) / 1.25 (Maximum) | — |
| 3 | Odour | No odour to mild pleasant odour | — |
| 4 | Bulk Density, g/cc | 1.05 ± 0.05 | — |
| 5 | Solubility | 100% soluble without any residue | — |
| 6 | pH of 1% solution in distilled water | 8 (Minimum) | — |
| 7 | Foam Height, ml | 600 (Minimum) | — |
| 8 | Half-life of foam, sec | 140 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 174. ONGC/PC/62/2026 — LIQUID CATIONIC POLYELECTROLYTE FOR MEHSANA ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 07:53 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing liquid, free from visible impurities at 24±2 °C temperature | — |
| 2 | Nature | Organic | — |
| 3 | Type | Cationic | — |
| 4 | Miscibility / Solubility of 0.1 % (w/v) of sample in distilled water at 24 ±2 ° C | Miscible/ Soluble | — |
| 5 | Performance Test: (To be conducted on Effluent of Sobhasan Oil Field) (a) Stock solution in distilled water (i) Polyelectrolyte (Cationic): 0.1% (w/v) (ii) Poly Aluminium Chloride: 1.0 % (w/v) (b) Effluent Characteristics: Emulsified Oil in Effluent: 90-200 mg/ litre (c) Concentration of Poly Aluminium Chloride: 100 mg/ litre (d) Concentration of Polyelectrolyte sample: 7 mg/ litre (e) Jar Test Take 500 ml of effluent devoid of free oil in one liter capacity square jar. Treat with requisite concentration of Poly Aluminium Chloride as specified at 5c. Mix rapidly at 200 rpm for 2 minutes utilizing a flocculator. Slow down mixing to 30 rpm and add requisite concentration of Polyelectrolyte sample, as specified in (d). Continue mixing at 30 rpm for 20 minutes. Keep the jar in quiescent condition for 45 minutes. Withdraw 100 ml of water from the middle of the jar with the help of syringe and determine its Oil Content by Spectroscopic Method (API-RP 45) (Note: test is carried out at 24±2 °C) | Oil Content of the treated effluent should be 10 mg/ l (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 175. ONGC/PC/63/2026 — DEMULSIFIER FOR CAUVERY ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 07:54 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing homogeneous liquid at 5 ° C, free from visible impurities | — |
| 2 | Solubility of sample (2%,w/v) in Xylene (LR)/ Toluene (LR) at 20 °C | Solution should be clear | — |
| 3 | Associated water content in the separated oil layer (middle), % by volume [Test Condition: Emulsion of North Kovilkalappal field, Emulsion Volume (ml): 200, Dosage (mg/litre): 200, Dosing Temperature (°C): 50 ± 2, Curing Temperature (°C): 70 ± 2 and Curing Time (minutes): 60] | 0.2 (Maximum) | — |
| 4 | Organic Chloride Content, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 176. ONGC/PC/64/2026 — Flow Improver for Ratna (R-Series) Crude, NH Asset

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:01 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall a free flowing homogenous liquid at 25±1 °C, free from visible impurities. | — |
| 2 | Smell | The material shall not have any obnoxious / unpleasant smell | — |
| 3 | Miscibility of 5%(w/v)of sample in Xylene(LR Grade)at 25 ºC | Should give a clear solution | — |
| 4 | Organic Chloride content, ppm | 50 (Maximum) | — |
| 5 | Flash Point, ºC | 20 (Minimum) | — |
| 6 | Performance test, (i): Required depression in pour point after dosing, ºC (Dosing shall be 1000 ppm for CFT, Viscosity, and Pour Point Test) | 9 (Minimum) | — |
| 7 | Performance Test, (ii): Required reduction in viscosity after dosing, % [Viscosity measurement: Test condition (i) Temperature (ºC): 37 (ii) Shear rate (sec-1): 10-11 (Shear rate shall remain exactly same in untreated and treated oil) | 55 (Minimum) | — |
| 8 | Performance Test, (iii): Required reduction in wax deposition by CFT after dosing, % [Cold Finger Test : Test condition (i) Crude: Composite crude oil of R-7(R-series)crude having pour point of ~39 ºC (i) Dose of Flow Improver (ppm): 1000 (iii) Dosing Temperature (ºC): 55 ±2 (iv) Curing Temperature(ºC): 55 ±2 (v) Curing Time (Minutes): 30 (vi) CFT Temperature Gradient : Cold finger at 25 ºC, Oil at 45 ºC. (vii) CFT test duration (Hours): 5] | 45 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 177. ONGC/PC/65/2026 — Flow Improver for Asphaltic Crude

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:05 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be homogenous liquid at 25±2 ºC and free from visible impurities. | — |
| 2 | Pour Point, ºC | 15 (Maximum) | — |
| 3 | Solubility of 5 % (w/v) of sample in Xylene/ Toluene (LR Grade) | Solution should be clear | — |
| 4 | Performance Test: Reduction in viscosity, percent a. Source of emulsion: The flow improver shall be evaluated for its performance on crude oil emulsion from Becharaji GGS-I having water content 55% v/v (minimum) b. Dose: 0.50 ml of test solution/ 100 ml of emulsion Test solution: i) Flow improver sample: 10.2 gm ii) Demulsifier of Becharaji GGS-I: 8.2 gm iii) EGMBE: 40.8 gm iv) Xylene: 40.8 gm c. Dosing and curing temperature: 40±2 ºC d. Curing time: 30 minutes e. Viscosity (by Plate and Cone Rheometer) i) Untreated crude at 30 ºC temperature & 10 sec-1 shear rate ii) Treated crude at 30 ºC temperature & 10 sec-1 shear rate | 75 (Minimum) | — |
| 5 | Organic Chloride, ppm | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 178. ONGC/PC/66/2026 — Demulsifier for Padra GGS of Cambay Asset

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:11 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The Material shall be a free flowing homogeneous liquid at 15±1 °C, free from visible impurities | — |
| 2 | Solubility of 2% (w/v) of Sample in Xylene/Toluene (AR/LR Grade) at 20±1 ºC | Solution should be Clear | — |
| 3 | Performance Test, (i): Water Content of Treated Oil, percent by volume [Test Conditions i. Source of Emulsion: Composite emulsion of Padra GGS ii. Demulsifier Dose (mg/Lit): 300 iii. Dosing Temperature (ºC): 40±2 iv. Curing Temperature (ºC): 55±2 v. Curing Time (minutes): 30] | 1.0 (Maximum) | — |
| 4 | Performance Test, (ii): Separation, % volume | 70 (Minimum) | — |
| 5 | Organic Chloride, ppm | 100 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 179. ONGC/PC/67/2026 — OVERHEAD CORROSION INHIBITOR FOR TATIPAKA REFINERY

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:17 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State at 24±1 °C. | The material shall be free flowing homogeneous liquid, free from visible impurities. | — |
| 2 | Pour Point, °C | 6 (Maximum) | — |
| 3 | Flash Point, °C | 40 (Minimum) | — |
| 4 | Miscibility with hydrocarbons at 24±1 ° C | It should be completely miscible with Xylene/ Toluene/ HSD in all proportions. | — |
| 5 | pH | 9-12 | — |
| 6 | Tertiary Amine Content, mg KOH/g | 70-100 | — |
| 7 | Total Amine Value, mg KOH/g | 200-300 | — |
| 8 | Inhibition Efficiency (%) In dynamic condition Dosage: 10 ppm | 70 (Minimum) | — |
| 9 | Performance Test: The chemical will be tested in mini-refinery, Tatipaka, Rajahmundry. i) Dose: 10 ppm (In the overhead column flow) ii) Dosing point: Overhead flow of column iii) Testing : Iron will be measured in boot water (condensate water) after dosing. iv) Frequency of testing: Minimum two times a day and minimum 10 samples throughout the test period, with a minimum 6 hrs gap between two tests in a day. v) Test duration: 3 days (Minimum) | Minimum 90% of the samples during the test duration should pass the test, i.e., iron content should be less than 0.5 ppm. | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 180. ONGC/PC/68/2026 — LOW TEMPERATURE DEMULSIFIER FOR HEERA PLATFORM EMULSION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:19 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a clear homogeneous liquid at 20±1°C, free from visible impurities | — |
| 2 | Miscibility with Xylene at 25±1 I | Should form a clear solution | — |
| 3 | Organic Chloride Content, ppm | 100 (Maximum) | — |
| 4 | Viscosity of Demulsifier at 30°C, cP | 60 (Maximum) | — |
| 5 | Performance Test, Demulsification Efficiency, percent (v/v) [Test Conditions: (i) Source of Emulsion: Composite (ii) Emulsion (Train A,B,C & D) (iii) Emulsion Volume (ml): 200 (iv) Demulsifier Dose (mg/litre): 40 (v) Dosing Temperature (■): 50±1 (vi) Curing Temperature (■): 50±1 (vii) Curing Time (minutes): 15 (viii) Settling Time (minutes): 2] | 70 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 181. ONGC/PC/69/2026 — PPD/ FLOW IMPROVER FOR CRUDE OIL OF JOTANA FIELD OF MEHSANA ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 08:26 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be homogeneous liquid, free from visible impurities | — |
| 2 | Freezing Point | The material should have freezing point < = 12 °C | — |
| 3 | Solubility of 5% (w/v) of sample in Xylene/ Toluene (LR/ GR grade) | Solution should be clear | — |
| 4 | Performance Test, (i): Reduction in Pour Point of treated Crude on day 1 Source of Crude Oil: The PPD/ Flow Improver shall be evaluated for its performance on composite crude oil of Jotana field having water content < 2% v/v and Pour Point, 39 ± 3 °C Pour Point and Viscosity measurement a. Test Conditions i. Dose of Test Solution: 4000 mg/ lit (4000 ppm of 20 % w/v test solution of product in xylene/ toluene AR/ LR Grade) ii. Curing Temperature: 60 ± 2 °C iii. Curing Time: 30 minutes b. Pour Point Measurement by IP441/ ASTM D5853 | 12 °C (Minimum) | — |
| 5 | Performance Test, (ii): Reduction in Pour Point of treated Crude on day 4 | 12 °C (Minimum) | — |
| 6 | Performance Test, (iii): % Reduction in the viscosity at 30 °C on day 1 [Viscosity Measurement by Plate & Cone Rheometer Viscosity of the Blank and treated samples shall be measured at shear rate of 10 sec-1 at 30 °C on day 1 & 4] | 85 (Minimum) | — |
| 7 | Performance Test, (iv): % Reduction in the viscosity at 30 °C on day 4 | 75 (Minimum) | — |
| 8 | Organic Chloride Content, ppm | 50 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 182. ONGC/UTL/04/2026 — ANTISCALENT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 08:59 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a free flowing liquid at ambient temperature, free from visible impurities. | — |
| 2 | Miscibility with the source water at the site of application at ambient temperature | Should be completely miscible. | — |
| 3 | Compatibility with other chemicals used for treatment of source water | Should be compatible | — |
| 4 | Inhibition Efficiency of the Scale Inhibitor for CaCO Scale, percent | 92 (Minimum) | — |
| 5 | Inhibition Efficiency of the Scale Inhibitor for CaSO scale, percent | 92 (Minimum) | — |
| 6 | Toxicity | The firm should furnish results on toxicity of the product and certificate from Govt. of India approved agency that the product is not toxic for human consumption | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 183. ONGC/UTL/05/2026 — CHLORINE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 08:59 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Purity as Chlorine, percent by volume | 99.8 (Minimum) | — |
| 2 | Moisture, ppm | 150 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 184. ONGC/UTL/06/2026 — DI-AMMONIUM PHOSPHATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:00 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of free flowing white / off white crystals/ crystalline powder and shall be free from visible impurities. | — |
| 2 | Moisture content, percent by mass | 1.5 (maximum) | — |
| 3 | pH of 1 % solution at room temperature (24 ± 2 ° C) | 7.8-9.0 | — |
| 4 | Total Nitrogen, percent by mass | 20.0 (Minimum) | — |
| 5 | Total Phosphorus as P2O5 , percent by mass | 49.0 (Minimum) | — |
| 6 | Matter Insoluble in water, percent by mass | 0.5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 185. ONGC/UTL/09/2026 — HEDP

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:01 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be colourless to pale yellow, clear liquid at 24±2°C, free from visible impurities. | — |
| 2 | Specific Gravity at 24°C / 24°C | 1.30 (Minimum) | — |
| 3 | pH of 1% (w/v) solution of the material in Distilled water at 24±2°C | 2 (Maximum) | — |
| 4 | Active Acid content, percent by mass | 50 (Minimum) | — |
| 5 | Calcium sequestering value of the material at 24±2°C and 11 pH, mg CaCO / g | 400 (Minimum) | — |
| 6 | Miscibility in Distilled water at | Miscible in all proportions | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 186. ONGC/UTL/10/2026 — HYDRATED LIME

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Available Lime as CaO, percent by mass | 65-76 | — |
| 3 | Acid insoluble matter as SiO , percent | 1 .0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 187. ONGC/UTL/11/2026 — HYDRAZINE HYDRATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a colourless liquid, free from visible impurities. | — |
| 2 | Hydrazine Hydrate content, percent by | 55 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 188. ONGC/UTL/12/2026 — HYDROCHLORIC ACID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:03 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a clear, colourless or light yellow liquid, free from dirt & other visible impurities. | — |
| 2 | Total Acidity as HCl, percent by mass | 30. 0 (Minimum) | — |
| 3 | Residue on Ignition, percent by mass | 0.1 (Maximum) | — |
| 4 | Iron as Fe3+, (Thiocyanate Method, 02, maximum, percent by mass) | Colour intensity of the sample in the Butanol layers not greater than in test cylinders | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 189. ONGC/UTL/14/2026 — LIQUOR AMMONIA

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:03 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a colourless liquid, free from visible impurities. | — |
| 2 | Ammonia Content, percent by mass | 20.0 (Minimum) | — |
| 3 | Residue on Evaporation, percent by | 0.1 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 190. ONGC/UTL/15/2026 — MORPHOLINE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:04 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a colourless liquid, free from visible impurities. | — |
| 2 | Initial Boiling Point (as per ASTM D-1078 / IP-195 Method), °C | 125 (Minimum) | — |
| 3 | Dry Point (as per ASTM D-1078 / IP-195 Method), °C | 130 (Maximum) | — |
| 4 | Purity, percent by mass | 99 (Minimum) | — |
| 5 | Suspended matter, percent by mass | 1.0 (Maximum) | — |
| 6 | Miscibility of 10% (v/v) of the Product | Should be completely miscible | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 191. ONGC/UTL/16/2026 — SAND FOR GRAVITY FILTERS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:05 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form ofrounded and smooth grains, free from visible impurities. | — |
| 2 | Fraction retained on 16 Mesh ASTM or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 3 | Fraction passing through 36 Mesh ASTM or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 4 | Soluble fraction in 15% (w/w) Hydro-chloric acid, percent by mass | 2.0 (Maximum) | — |
| 5 | Uniformity coefficient | 1.3 - 1.7 | — |
| 6 | Silica content as SiO , percent by mass | 98 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 192. ONGC/UTL/17/2026 — SAND FOR PRESSURE FILTERS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:06 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of rounded and smooth grains, free fromvisible impurities. | — |
| 2 | Effective size of sand, mm | 1.5 - 3 | — |
| 3 | Soluble fraction in 15% (w/w) Hydro-chloric acid, percent by mass | 2.0 (Maximum) | — |
| 4 | Uniformity Coefficient | 1.3-1.7 | — |
| 5 | Silica content as SiO , percent by mass | 98 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 193. ONGC/UTL/18/2026 — SODIUM ACID PYROPHOSPHATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:06 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a free flowing impurities. | — |
| 2 | Assay, percent by mass | 90 (Minimum) | — |
| 3 | Water insoluble matter, percent by mass | 0.1 (Maximum) | — |
| 4 | Iron by AAS, percent by mass | 0.02 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 194. ONGC/UTL/19/2026 — SODIUM BISULPHITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:34 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be a dry powder free from visible impurities. | — |
| 2 | Matter insoluble in water, percent by mass | 0.05 (Maximum) | — |
| 3 | Purity as SO2 content, percent by mass | 64.0 (Minimum) | — |
| 4 | Iron as Fe, (Thiocyanate method, 0.005, maximum, percent by mass) | Colour intensity of sample in the Butanol layers not greater than in test cylinders | — |
| 5 | Heavy Metals as Pb, (by colour comparision, 0.005, maximum, percent by mass) | Colour intensity in the test with the material is not greater than that of control test | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 195. ONGC/UTL/20/2026 — SODIUM HEXAMETAPHOSPHATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:35 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Matter insoluble in water, percent by mass | 0.20 (Maximum) | — |
| 3 | Soluble Iron compounds as Fe, percent by mass | 0.03 (Maximum) | — |
| 4 | Phosphate as P2O5, percent by mass | 63.0 (Minimum) | — |
| 5 | Loss on ignition, percent by mass | 3.0 (Maximum) | — |
| 6 | Sequestering power | To pass the test | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 196. ONGC/UTL/22/2026 — SODIUM SULPHITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a granular powder, free from visible impurities. | — |
| 2 | Sodium Sulphite as Na2SO3 , percent by mass | 92.0 (Minimum) | — |
| 3 | Free Alkali as Na2O, percent by mass | 2.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 197. ONGC/UTL/23/2026 — SULPHURIC ACID FOR COOLING

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:37 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a liquid, free from visible impurities. | — |
| 2 | Acidity as H2SO4 , percent by mass | 98.0 (Minimum) | — |
| 3 | Iron as Fe, (Bipyridyl Method, spectrophotometer), percent by mass | 0.05 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 198. ONGC/UTL/24/2026 — TRISODIUM PHOSPHATE (ANHYDROUS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:39 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a crystalline powder or in the form of easily friable small lumps, free from visible impurities. | — |
| 2 | Matter insoluble in water, percent by mass | 0.5 (Maximum) | — |
| 3 | Phosphate as P2O5 on Dry Basis at 400°C, percent by mass | 41.0 (Minimum) | — |
| 4 | Carbonates as Na2CO3 , percent by mass | 2.0 (Maximum) | — |
| 5 | Free Sodium Hydroxide as NaOH, percent by mass | 3.2 (Maximum) | — |
| 6 | Soluble Iron compounds as Fe (by Colorimetry method), percent by mass | 0.02 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 199. ONGC/UTL/25/2026 — UREA

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:42 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of prills or pellets or shot, free from visible impurities. | — |
| 2 | Fraction passing through 6 Mesh BSS or equivalent sieve, percent by mass | 90 (Minimum) | — |
| 3 | Fraction retained on 16 Mesh BSS or equivalent sieve, percent by mass | 90 (Minimum) | — |
| 4 | Moisture content at 105±2°C, percent by mass | 1.0 (Maximum) | — |
| 5 | Total Nitrogen, percent by mass | 45.0 (Minimum) | — |
| 6 | Biuret, percent by mass | 1.5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 200. ONGC/UTL/26/2026 — ZINC SULPHATE HEPTAHYDRATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:46 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of crystalline solid, free from visible impurities. | — |
| 2 | Matter insoluble in water, percent by mass | 0.1 (Maximum) | — |
| 3 | Zinc Sulphate As Zn2+, percent by mass | 22.5 (Minimum) | — |
| 4 | Zinc Sulphate As SO42-, percent by mass | 33.0 (Minimum) | — |
| 5 | Iron as Fe (Thiocyanate method 0.02, maximum, percent by mass) | Colour intensity produced with thematerial is not greater than that in the control test | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 201. ONGC/UTL/27/2026 — BLEACHING POWDER (STABLE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:47 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be white to a lightly yellowish white powder and free from hard lumps and any visible impurity. It shall be dry and free flowing. | — |
| 2 | Moisture, Percent by mass | 0.5 (Max.) | — |
| 3 | Particle size (passing through 1.70 mm IS sieve), percent by weight | 99.0 (Min.) | — |
| 4 | Available Chlorine Percent by weight | 32.0 (Min.) | — |
| 5 | Stability, loss of chlorine on the basis of initial available chlorine | 1/11 (Max.) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 202. ONGC/UTL/28/2026 — CLEANING AND DEGREASING AGENT FOR

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:48 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | Pourable liquid at 24 ± 2°C and free from suspended foreign matter | — |
| 2 | Odour | Should not have pungent smell | — |
| 3 | Miscibility in water at 25°C | Should be soluble or dispersible in water | — |
| 4 | Specific gravity at 27/27°C | 0.80 - 1.10 | — |
| 5 | pH | 6.5 - 8.5 | — |
| 6 | Corrosion, Cu strip test as per IP-154 (3 hrs test at 100°C) | 2e (Maximum) | — |
| 7 | Flash point, °C | 40 (Minimum) | — |
| 8 | Performance test: Solubility of semi-solid oily waste in the sample in 1: 10 ratio | 75 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 203. ONGC/UTL/29/2026 — CYCLOHEXYLAMINE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:48 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | Liquid free from any visible impurity | — |
| 2 | Purity, % by mass | 99.0 (Minimum) | — |
| 3 | Relative Density 20/20 °C | 0.860 - 0.870 | — |
| 4 | Boiling Range | 95% by volume between 130 and 135 °C | — |
| 5 | Residue on Evaporation, mg/l | 0.01 (Maximum) | — |
| 6 | Ash Content, g/100ml | 0.003 (Maximum) | — |
| 7 | Miscibility with Water | No opalescence when one volume is mixed at 15 °C with 10 volumes of water | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 204. ONGC/UTL/30/2026 — SODIUM CHLORITE 25% SOLUTION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:49 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Purity, % by mass | 25 (Minimum) | — |
| 2 | Physical state | Liquid | — |
| 3 | pH | 11 - 13 | — |
| 4 | Specific Gravity | 1.23 - 1.26 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 205. ONGC/UTL/31/2026 — Poly Aluminum Chloride (Solid)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:54 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be in the form of pale yellow powder and shall be free from organic contaminants | — |
| 2 | Aluminium as Al2O3 , percent by mass | 28.0 (Minimum) | — |
| 3 | Relative Basicity, percent | 35 (Minimum) | — |
| 4 | Chloride as Cl, percent by mass | 37.5 (Maximum) | — |
| 5 | Sulphate as SO , percent by mass | 10.0 (Maximum) | — |
| 6 | Bulk Density, g/ml | 0.65 (Minimum) | — |
| 7 | Total organic Carbon (TOC), ppm | 240 (Maximum) | — |
| 8 | Insolubles, percent by mass | 1.5 (Maximum) | — |
| 9 | pH of 5% solution (w/v) | 2.5 - 4.5 | — |
| 10 | Toxic Substances a) Mercury as Hg, ppm | 0.6 (Maximum) | — |
| 11 | Toxic Substances b) Arsenic as As, ppm | 15 (Maximum) | — |
| 12 | Toxic Substances c) Cadmium as Cd, ppm | 18 (Maximum) | — |
| 13 | Toxic Substances d) Lead as Pb, ppm | 90 (Maximum) | — |
| 14 | Toxic Substances e) Iron as Fe, ppm | 240 (Maximum) | — |
| 15 | Toxic Substances f) Manganese as Mn, ppm | 60 (Maximum) | — |
| 16 | Toxic Substances g) Chromium as Cr, ppm | 45 (Maximum) | — |
| 17 | Toxic Substances h) Selenium as Se, ppm | 24 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 206. ONGC/UTL/32/2026 — Hydrogen Peroxide

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 09:55 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of Clear, colourless liquid, free from suspended impurities and dust particles | — |
| 2 | Purity of Hydrogen peroxide, percent | 50 (Minimum) | — |
| 3 | Stability, ml O2 / minute | 0.3 (Maximum) | — |
| 4 | Acidity (as H2SO4 ), g/ 100 ml | 0.015 - 0.030 | — |
| 5 | Residue on evaporation, g/ 100 ml | 0.2 (Maximum) | — |
| 6 | Residue on ignition, g/ 100 ml | 0.05 (maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 207. ONGC/WCF/01/2026 — CALCIUM BROMIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:04 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of crystalline powder, free from visible impurities. | — |
| 2 | Purity as CaBr2, percent by mass | 95.0 (Minimum) | — |
| 3 | Chloride as CaCl2, percent by mass | 3.0 (Maximum) | — |
| 4 | Water Insoluble Matter, percent by mass | 0.03 (Maximum) | — |
| 5 | Specific Gravity at 24±2°C | 3.30 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 208. ONGC/WCF/02/2026 — CALCIUM BROMIDE -ZINC BROMIDE SOLUTION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:05 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of liquid, free from visible impurities. | — |
| 2 | Assay: Zinc Bromide, percent by mass | 52 – 55 | — |
| 3 | Assay: Calcium Bromide, percent by mass | 19 – 22 | — |
| 4 | Density at 24±2 degC, g/cc | 2.3 (Minimum) | — |
| 5 | pH of Solution diluted with Distilled: water (1:10) | 4.5 - 6.5 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 209. ONGC/WCF/03/2026 — THIOUREA

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 13:10 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Solubility of the sample (10% w/v) in Distilled water at 24±2°C colourless | Solution should be clearand | — |
| 3 | Assay as NH2-CS-NH2, percent by mass | 97.0 (Minimum) | — |
| 4 | Melting Point, °C | 173 – 177 | — |
| 5 | Sulphated Ash, percent by mass | 0.10 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 210. ONGC/WCF/04/2026 — ZINC BROMIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:06 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Purity as ZnBr2, percent by mass | 95 (Minimum) | — |
| 3 | Water Insoluble Matter, percent by | 0.03 (Maximum) | — |
| 4 | Specific Gravity at 24±2 °C | 4.20 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 211. ONGC/WIC/01/2026 — AMMONIUM BISULPHITE SOLUTION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:28 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a clear solution, free from visible impurities. | — |
| 2 | Ammonium Bisulphite Content as NH4 HSO3, percent by mass | 65 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 212. ONGC/WIC/02/2026 — AMMONIUM THIOCYANATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of colourless deliquescent crystals, free from visible impurities. | — |
| 2 | Assay as NH4 SCN, percent by mass | 97.0 (Minimum) | — |
| 3 | pH of 5 % (w/v) solution of the material in Distilled water | 4.5 - 6.0 | — |
| 4 | Chloride as NH4Cl, (0.1% (m), maximum, by turbidity comparision) | Turbidity in the test solution not greater than that produced in control solution | — |
| 5 | Residue on Ignition, percent by mass | 0.1 (Maximum) | — |
| 6 | Iron as Fe, (5 ppm, maximum, by colour comparision | Colour produced in solution not greater than control solution . | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 213. ONGC/WIC/03/2026 — ANTHRACITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:33 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be granular and shall be free from visible impurities. | — |
| 2 | Density, g / cm3 | 1.40 (Minimum) | — |
| 3 | Bulk Porosity, percent by volume | 30.0 (Minimum) | — |
| 4 | Moisture content at 105±2°C, percent by mass | 5.0 (Maximum) | — |
| 5 | Carbon Content, percent by mass | 80.0 (Minimum) | — |
| 6 | Hardness, mho's scale | 3 (Minimum) | — |
| 7 | Dry Sieve Analysis: Fraction retained on ASTM No. 10 or equivalent sieve, percent by mass | 5.0 (Maximum) | — |
| 8 | Dry Sieve Analysis: Fraction retained between ASTM No. 10 / 18 or equivalent sieve, percent by mass | 80.0 (Minimum) | — |
| 9 | Dry Sieve Analysis: Fraction passing through ASTM No. 18 or equivalent sieve, percent by mass | 5.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 214. ONGC/WIC/04/2026 — BACTERICIDE (ALDEHYDE TYPE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a homogenous, free flowing liquid at 24±2°C, free from visible impurities. | — |
| 2 | Turbidity of the Neat sample, NTU | 3 (Maximum) | — |
| 3 | Miscibility of 1% (w/v) sample in Fine Filtered Injection Water | Should be completely miscible | — |
| 4 | Turbidity of the Filtered Injection Water treated with Other Water Injection Chemicals when mixed with 100 ppm of Bactericide sample, NTU | 1 (Maximum) | — |
| 5 | Thermal Stability test up to 90±5 °C | Should be stable | — |
| 6 | Aldehyde Group test (Schiff's or Tollen's test) | Negative | — |
| 7 | Amine Group test (Nitrous acid test) | Negative | — |
| 8 | Performance test on Sulphate Reducing Bacteria (Incubation period 28 days at 35±1°C and at atmospheric pressure) | None of the bottles should show blackening till the end of the incubation period | — |
| 9 | Performace test on Aerobic Bacteria (Incubation period 96 hrs at 35±1°C till the end of the incubation period and at Atmospheric Pressure) | None of the bottles should show turbidity | — |
| 10 | pH of neat sample | Should be greater than 3 | — |
| 11 | Corrosivity (mpy) | Should be less than 1 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 215. ONGC/WIC/05/2026 — BACTERICIDE (AMINE TYPE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a homogenous, free flowing liquid at 24±2°C, free from visible impurities. | — |
| 2 | Turbidity of the neat sample, NTU | 5 (Maximum) | — |
| 3 | Miscibility of 1% (w/v) sample in fine filtered injection water | Should be completely miscible | — |
| 4 | Turbidity of the filtered injection water treated with other Water Injection chemicals when mixed with 100 ppm of Bactericide sample, NTU | 1 (Maximum) | — |
| 5 | Thermal Stability test up to 90 ± 5°C | Should be stable | — |
| 6 | Amine Group test (Nitrous acid test) | Positive | — |
| 7 | Aldehyde Group test (Schiff's or Tollen's test) | Negative | — |
| 8 | Performance test on Sulphate Reducing Bacteria (Incubation is carried out for 28 days at 35 ± 1°C and at atmospheric pressure) | None of the bottles should show blackening till the end of the incubation period | — |
| 9 | Performance test on Aerobic Bacteria (Incubation is carried out for 96 hrs at 35±1°C and at Atmospheric Pressure) | None of the bottles should show turbidity till the end of the incubation period | — |
| 10 | pH of neat sample | Should be greater than 3 | — |
| 11 | Corrosivity (mpy) | Should be less than 1 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 216. ONGC/WIC/06/2026 — CALCIUM CARBONATE SCALE INHIBITOR

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:42 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be in the form of a free flowing liquid at 24±2°C, free from visible impurities. | — |
| 2 | Miscibility with Injection Water and Formation Water | Should be completely miscible and compatible in all proportions | — |
| 3 | Compatibility Test with other Water Flood chemicals | Should pass compatibility test | — |
| 4 | Inhibition efficiency of the Scale Inhibitor, percent | 92 (Minimum) | — |
| 5 | pH | 5 - 8 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 217. ONGC/WIC/07/2026 — CORROSION INHIBITOR FOR EFFLUENT USED

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:44 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a homogenous liquid at 24±2 ° C and shall be free from visible impurities. | — |
| 2 | Nature | Organic | — |
| 3 | Miscibility of 1% (w/v) material with 0.45 µm filtered oil field effluent used at In-Situ Combustion Plant | Shall be completely miscible | — |
| 4 | Compatibility of 10 mg / litre solution of Corrosion Inhibitor with other injection additives | Shall be compatible | — |
| 5 | Thermal Stability test at 65±2°C for 24 hrs | Shall be stable | — |
| 6 | Inhibition efficiency of the corrosion inhibitor, percent | 60 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 218. ONGC/WIC/09/2026 — CORROSION INHIBITOR FOR WATER INJECTION IN MUMBAI ASSETS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:46 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a homogenous and free flowing liquid at 24±2°C and shall be free from visible impurities. | — |
| 2 | Miscibility and Compatibility with Sea Water | Should be miscible and compatible | — |
| 3 | Compatibility with Other Water Injection Chemicals in use | Should pass compatibility test | — |
| 4 | Thermal Stability test up to 90±5°C | Should be stable | — |
| 5 | Viscosity of Neat Corrosion Inhibitor at 300 rpm, cP | 200 (Maximum) | — |
| 6 | Corrosivity of Neat Product with API Steel Coupon when exposed for 7 days at ambient temperature under open conditions, mpy | 1.0 (Maximum) | — |
| 7 | Inhibition Efficiency of the corrosion inhibitor under Static test, percent | 80 (Minimum) | — |
| 8 | Inhibition Efficiency of the corrosion inhibitor under Dynamic test, percent | 80 (Minimum) | — |
| 9 | Visual examination of test coupons: condition under Static as well as Dynamic test conditions | Free from pits and scratches | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 219. ONGC/WIC/10/2026 — DEFOAMER FOR WATER INJECTION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:48 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a free flowing liquid at 24±2°C and shall be free from visible impurities. | — |
| 2 | Miscibility with Sea water | Should be miscible or highly dispersible | — |
| 3 | Compatibility test with other Water Flood chemicals in use | Should pass compatibility test | — |
| 4 | Resistance to residual free Chlorine | Should be resistant | — |
| 5 | Measure the Foam collapse time under the agitated condition, seconds | 30 (Maximum) | — |
| 6 | Measure foam height after defoamer treatment, ml | 425 ± 25 | — |
| 7 | Observe foam reappearance, if any, on further agitation for further 4 minutes | Foam should not reappear | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 220. ONGC/WIC/11/2026 — EDTA - DISODIUM SALT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:50 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a crystalline powder, free from visible impurities. | — |
| 2 | Active ingredient as Disodium EDTA, percent by mass | 95.0 (Minimum) | — |
| 3 | Chelation value at pH 11, mg of CaCO3 / g of Chelating agent | 255.2 (Minimum) | — |
| 4 | pH of 1.0% (w/v) solution in Distilled water at 25 ± 1°C | 4.0 - 5.5 | — |
| 5 | Solubility of 40 g of material in 100 ml of 20% (w/v) NaOH solution at 25±1°C | Shall give a clear and colourless solution | — |
| 6 | Iron as Fe (0.005, maximum, percent by mass, A - 4 Method of IS-7220 by colour comparison) | Red colour produced with sample not deeper than that of standard iron solution | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 221. ONGC/WIC/12/2026 — FERRIC CHLORIDE HEXAHYDRATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:52 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of Crystalline lumps, free from visible impurities. | — |
| 2 | Ferric Chloride as FeCl , percent by mass | 59.0 (Minimum) | — |
| 3 | Free Acid as HCl, percent by mass or Basicity as Fe2O3 , percent by mass | 0.03 (Maximum) | — |
| 4 | Ferrous Salts as FeCl2 , (0.1, percent by mass, Maximum) | No blue colour is produced | — |
| 5 | Insoluble Matter, percent by mass | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 222. ONGC/WIC/13/2026 — FERRIC CHLORIDE (LIQUID)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:53 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing liquid, free from visible impurities. | — |
| 2 | Purity as FeCl , percent by mass | 43.0 (Minimum) | — |
| 3 | Ferrous Salts as FeCl , (0.1% mass, Max) | No blue colour is produced | — |
| 4 | Insoluble Matter, percent by mass | 0.05 (Maximum) | — |
| 5 | pH of 5% (v/v) solution in Distilled water | 1.0 - 3.0 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 223. ONGC/WIC/14/2026 — FERRIC SULPHATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:55 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of crystals or powder, free from visible impurities. | — |
| 2 | Ferric Sulphate as Fe2 (SO4)3 .9H2O, percent by mass | 70 (Minimum) | — |
| 3 | Free acid as H2SO4, percent by mass or Basicity as Fe2O3 , percent by mass | 0.04 (Maximum) | — |
| 4 | Ferrous Salt as FeSO (0.1, maximum, percent by mass, by qualitative method) | No blue colour is produced | — |
| 5 | Insoluble matter, percent by mass | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 224. ONGC/WIC/15/2026 — GARNET (COARSE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 09:57 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be granular and round shaped and shall be free from visible impurities. | — |
| 2 | Grain Density, g / ml | 3.8 - 4.2 | — |
| 3 | Bulk Porosity, percent by volume | 35 - 45 | — |
| 4 | Hardness, mho's scale | 7 - 8 | — |
| 5 | Dry Sieve analysis: Fraction retained on 7 Mesh BSS or equivalent sieve, percent by mass | Nil | — |
| 6 | Dry Sieve analysis: Fraction retained on 16 Mesh BSS or equivalent sieve, percent by mass | 95.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 225. ONGC/WIC/16/2026 — GARNET (FINE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 10:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be flowing and round shaped and shall be free from visible impurities. | — |
| 2 | Grain Density, g/ml | 3.8 - 4.2 | — |
| 3 | Bulk Porosity, percent by volume | 35 - 45 | — |
| 4 | Hardness, mho's scale | 7 - 8 | — |
| 5 | Dry Sieve analysis : Fraction retained on 16 Mesh BSS or equivalent sieve, percent by mass | Nil | — |
| 6 | Dry Sieve analysis : Fraction retained on 25 Mesh BSS or equivalent sieve, percent by mass | 95.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 226. ONGC/WIC/18/2026 — POLYELECTROLYTE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 10:43 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a clear free flowing liquid at 24±2°C, free from visible impurities. | — |
| 2 | Miscibility with synthetic sea water | Completely miscible in all proportions at ambient temperature | — |
| 3 | Compatibility with other Water Flood Chemicals | Should pass compatibility test | — |
| 4 | Filtration efficiency for suspended particles of size greater than 2 micron, percent | 98 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 227. ONGC/WIC/20/2026 — STRONTIUM SULPHATE SCALE INHIBITOR

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 10:45 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be in the form of a free flowing liquid at 24±2°C, free from visible impurities. | — |
| 2 | Miscibility with Sea Water and formation water | Should be completely miscible and compatible in all proportions | — |
| 3 | Compatibility test with other Water Flood chemicals | Should pass compatibility test | — |
| 4 | Inhibition efficiency of the Scale Inhibitor at 10 mg/lit dose, percent | 90 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 228. ONGC/WIC/21/2026 — BACTERICIDE NON-ALDEHYDE NON-AMINE TYPE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 10:48 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be in the form of a free flowing liquid at 24±2°C, free from visible impurities. | — |
| 2 | Miscibility of 1 % (w/v) sample in | Completely miscible fine filtered injection water | — |
| 3 | Compatibility test: Turbidity of the filtered injection water treated with other water injection chemicals, NTU | 1 (Maximum) | — |
| 4 | Thermal Stability test up to 90±5°C | Should be stable | — |
| 5 | Aldehyde Group test (Schiffs or Tollen's test) | Negative | — |
| 6 | Amine Group test (Nitrous acid test) | Negative | — |
| 7 | Performance test on Sulphate Reducing Bacteria (Incubation period 28 days at 35°C and at atmospheric pressure | No blackening till the end of the incubation period | — |
| 8 | Performance test on Aerobic Bacteria (Incubation period 4 days at 35°C and at atmospheric pressure) | No turbidity till the end of the incubation period | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 229. ONGC/WIC/22/2026 — CORROSION INHIBITOR FOR WATER INJECTION, GANDHAR FIELD, ANKLESHWAR

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 10:51 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material as received shall be a clear free flowing homogenous liquid at 24±2°C, free from visible impurities. | — |
| 2 | Nature | Organic | — |
| 3 | Miscibility of 1% (w/v) material with 0.45µm filtered injection water and formation water at 24±2°C | Shall be completely miscible | — |
| 4 | Compatibility test of 10 mg/L solution of Corrosion Inhibitor at 24±2°C when used in combination with other water injection chemicals | Shall be compatible | — |
| 5 | Thermal Stability test at 90±2°C | Shall be completely stable | — |
| 6 | Corrosivity of neat product with API Steel coupon when exposed for 7 days at ambient temperature under open conditions, mpy | 1.0 (Maximum) | — |
| 7 | Qualitative test for presence of Chromium | Negative | — |
| 8 | Performance test : Percent Inhibition w.r.t. Corrodant media, percent | 65 (Minimum) | — |
| 9 | Visual Examination | Inhibited test Coupons shall be free from pits and scratches on visual inspection | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 230. ONGC/WIC/23/2026 — CORROSION INHIBITOR FOR WATER INJECTION IN ASSAM ASSET

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 10:54 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a homogeneous liquid and free flowing at 24±2°C and shall be free from visible impurities. | — |
| 2 | Miscibility of 1% (w/v) material with 0.45µ filtered injection water at 24±2°C | Shall be completely miscible | — |
| 3 | Compatibility test of 20 mg/lit of Corrosion Inhibitor at 24±2°C when used in combination with other water injection chemicals | Shall be compatible solution | — |
| 4 | Thermal Stability test at 90±5°C for 24 hrs | Completely stable | — |
| 5 | Corrosivity of neat product with API Steel coupon when exposed for 7 days at ambient temperature under open conditions, mpy | 1.0 (Maximum) | — |
| 6 | Inhibition Efficiency of the Corrosion Inhibitor under Stagnant Conditions (comparing the Weight Loss of the Coupon in Inhibited System with that in Unhibited System), percent | 80 (Minimum) | — |
| 7 | Visual Examination of inhibited | Inhibited test Coupons should be free from pits and scratches | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 231. ONGC/WIC/24/2026 — CORROSION INHIBITOR FOR WATER INJECTION FOR WESTERN ONSHORE ASSETS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 10:57 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of a homogeneous liquid at 24±2 ° C and shall be free from visible impurities | — |
| 2 | Nature | Organic | — |
| 3 | Qualitative test for presence of Chromium | Negative | — |
| 4 | Miscibility of 1 % (w/v) material with 0.45 µm filtered treated injection water and formation water | Shall be completely miscible | — |
| 5 | Compatibility of 20 mg/litre solution of Corrosion Inhibitor with other water injection chemicals | Shall pass the compatibility test | — |
| 6 | Thermal Stability Test at 50±2 °C for 24 hours | Shall be stable | — |
| 7 | Corrosivity of neat product, mpy | 1 (maximum) | — |
| 8 | Inhibition efficiency of the corrosion inhibitor under static conditions, Percentage [Test conditions: Corrodant media 1% (NaCl), Temperature: 50±2 °C, DO content :< 0.1 ppm, Corrosion Inhibitor Dose: 20 mg/L, Exposure period: 96 hrs] | 70% (Minimum) | — |
| 9 | Inhibition efficiency of the corrosion inhibitor under dynamic conditions, Percentage [Test conditions: Corrodant media 1% (NaCl), Temperature: 50±2 °C, DO content: 0.6-0.8 ppm, Corrosion Inhibitor Dose: 20 mg/L, Exposure period: 24 hrs] | 70% (Minimum) | — |
| 10 | Visually examine the condition of the Coupon after each test (Static & Dynamic) | Inhibited Test Coupons shall be free from pits on visual inspection, under both test condition | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 232. ONGC/WIC/25/2026 — Glutaraldehyde

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 10:58 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a homogenous free flowing liquid at 24± 2 ºC, free from visible impurities | — |
| 2 | Specific Gravity, at 20 ± 2 ºC | 1.12 - 1.13 | — |
| 3 | Turbidity of the neat sample, NTU | 3.0 (Maximum) | — |
| 4 | Miscibility of 1%(w/v) sample in fine filtered injection water | Should be completely miscible | — |
| 5 | pH of neat sample | 3.0-4.5 | — |
| 6 | Compatibility Test The increase in turbidity of the filtered injection water treated with other water injection chemicals available in the Asset /Basin when mixed with 200 ppm of Glutaraldehyde sample, NTU | 1.0 (maximum) | — |
| 7 | Thermal Stability Test up to 90 ± 2 ºC | Should be stable | — |
| 8 | Active Content of Glutaraldehyde | 50% (Minimum) | — |
| 9 | Formaldehyde Content, % by mass | 0.05 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 233. ONGC/WIC/26/2026 — Tetrakis (Hydroxymethyl) Phosphonium Sulphate (THPS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 11:00 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a homogenous free flowing liquid free from visible impurities | — |
| 2 | pH of neat sample | 4.0 to 5.0 | — |
| 3 | Turbidity of the neat sample, NTU | 5.0 (Maximum) | — |
| 4 | Miscibility of 1%(w/v) sample in fine filtered injection water | Should be completely miscible | — |
| 5 | Compatibility Test The increase in turbidity of the filtered injection water treated with other water injection chemicals available in the Asset /Basin when mixed with 200ppm of THPS sample, NTU | 1.0 (maximum) | — |
| 6 | Active content of THPS, % by mass | 75 (Minimum) | — |
| 7 | Thermal Stability, up to 90 ± 2 ºC | Should be stable | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 234. ONGC/WIC/27/2026 — NITRITE BASED CORROSION INHIBITOR FOR KAKINADA

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 11:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Nature of Corrosion Inhibitor | It shall be a formulation of Nitrite, Borate & Polymer based | — |
| 2 | Physical State | The material shall be in the form of homogeneous and free flowing liquid at 24 ±2 °C and shall be free from visible impurities and suspended matter | — |
| 3 | Miscibility and Compatibility with DM Water | Miscible with potable and technical water in all proportions and should be miscible and compatible with bactericides in use | — |
| 4 | Thermal Stability Test (Stable up to 90 ± 5°C ) | The material should be stable | — |
| 5 | Nitrite content as (NO2-) in 1000 mg/lit (ppm) solution of the product in DM Water | Should be 250 mg/lit (minimum) | — |
| 6 | pH of 1000 mg/lit solution of the product in DM Water | 8.5 (Minimum) | — |
| 7 | Visual examination of the condition of the coupons after each test | Inhibited Coupons free from pits and scratches | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 235. ONGC/WIC/28/2026 — ISOTHIAZOLIN BASED NON-OXIDISING BIOCIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 11:03 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Nature of Bactericide | It shall be Isothiazolin based Non-oxidising Biocide | — |
| 2 | Physical State | The material shall be in the form of homogeneous and free flowing liquid at 24 ±2 °C and shall be free from visible impurities and suspended matter | — |
| 3 | Total Bacterial count, col/ml | < 50000 | — |
| 4 | SRB Count, col/100 ml | < 50 | — |
| 5 | Note | Supplier has to submit the undertaking that no slime should develop in Coolers / condensers during warranty period. | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 236. ONGC/WIC/29/2026 — IMIDAZOLE BASED

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 09 Mar 2026, 11:04 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Nature of Bactericide | It shall be Imidazole based Non-oxidising Biocide | — |
| 2 | Physical State | The material shall be in the form of homogeneous and free flowing liquid at 24 ±2 °C and shall be free from visible impurities and suspended matter | — |
| 3 | Total Bacterial count, col/ml | < 50000 | — |
| 4 | SRB Count, col/100 ml | < 50 | — |
| 5 | Note | Supplier has to submit the undertaking that no slime should develop in Coolers / condensers during warranty period. | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 237. ONGC/WM/03/2026 — CAUSTIC SODA FOR WATER MAKER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 08:52 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of solid pellets or flakes, free from visible impurities. | — |
| 2 | Purity as Sodium Hydroxide on dry basis, percent by mass | 99 (Minimum) | — |
| 3 | Chloride as NaCl on dry basis, percent by mass | 0.10 (Maximum) | — |
| 4 | Sulphates as Na2SO4 on dry basis, percent by mass | 0.10 (Maximum) | — |
| 5 | Iron as Fe, (20 ppm, maximum, by Colour comparision method) | Colour produced with sample match with standard | — |
| 6 | Carbonates as Na2CO3 on dry basis, percent by mass | 0.40 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 238. ONGC/WM/04/2026 — CITRIC ACID FOR WATER MAKER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 08:54 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form of odourless crystals or granules or fine crystalline powder. | — |
| 2 | Solubility in Water | Should form a clear solution | — |
| 3 | Purity as Citric Acid Monohydrate, percent by mass | 99.5 (Minimum) | — |
| 4 | Halides as Chloride, 10 ppm, maximum, by Turbidity comparision | Opalescence/Turbidity produced with material not greater than that obtained in the control test | — |
| 5 | Heavy Metals as Lead, (10 ppm, maximum, by Colour comparision method) | Colour produced with sample not greater than that produced in the control test | — |
| 6 | Oxalates Neutralise 10 ml of 5% (w/v) Solution of the material with dilute Ammonium Hydroxide. Add 5 drops of dilute Acetic Acid, cool and add 2 ml of Calcium Chloride solution | No turbidity should be produced | — |
| 7 | Arsenic Content, ppm | 1 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 239. ONGC/WM/14/2026 — SODIUM HYPOCHLORITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 10 Mar 2026, 08:56 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a clear liquid, free from visible impurities & shall not produce any sludge or dust when mixed with Distilled water. | — |
| 2 | Relative Density at 25°C | 1.2 (Minimum) | — |
| 3 | Available Chlorine as Cl, percent by mass by volume | 10.0 (Minimum) | — |
| 4 | Free Alkali as NaOH, g/litre | 5.0 (Minimum) | — |
| 5 | Free Sodium Carbonate as Na2CO3, g/litre | 2 (Maximum) | — |
| 6 | Iron as Fe, (1.0 ppm, maximum, by Colour comparision) | Match the colour of control solution | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 240. ONGC/WS/01/2026 — ACETIC ACID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:09 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a clear liquid, free from visible impurities. | — |
| 2 | Purity as CH3 COOH, percent by mass | 98.0 (Minimum) | — |
| 3 | Residue on Evaporation, percent by mass | 0.02 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 241. ONGC/WS/02/2026 — ACID CORROSION INHIBITOR(GRADE I,II, III, IV and IA)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:18 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a free flowing homogenous liquid at 24±2°C, free from visible impurities. | — |
| 2 | Qualitative test for the Presence of Arsenic | Should be negative | — |
| 3 | Pour Point, °C | 12 (Maximum) | — |
| 4 | Grade - I: Corrosion rate at 175 ± 2 °C in 15% HCl (w/w) treated with 30 ml/litre of Grade-I Inhibitor, g/cm2 | 0.044 (Maximum) | — |
| 5 | Grade - IA: Corrosion rate at 150 ± 2 °C in 15% HCl (w/w) treated with 30 ml/litre of Grade-I Inhibitor, g/cm2 | 0.024 (Maximum) | — |
| 6 | Grade - II: Corrosion rate at 120 ± 2 °C in 15% HCl (w/w) treated with 30 ml/litre of Grade-I Inhibitor, g/cm2 | 0.024 (Maximum) | — |
| 7 | Grade - III: Corrosion rate at 100 ± 2 °C in 15% HCl (w/w) treated with 10 ml/litre of Grade-I Inhibitor, g/cm2 | 0.024 (Maximum) | — |
| 8 | Grade - IV: Corrosion rate at 80 ± 2 °C in 15% HCl (w/w) treated with 2 ml/litre of Grade-I Inhibitor, g/cm2 | 0.005 (Maximum) | — |
| 9 | Visual examination of test coupons after test | Free from pits and scratches | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 242. ONGC/WS/07/2026 — AMMONIUM BIFLUORIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:21 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of crystals or flakes or powder, free from visible impurities. | — |
| 2 | Ammonical Nitrogen as NH3, percent by mass | 27.0 (Minimum) | — |
| 3 | Fluoride as F-, percent by mass | 60.0 (Minimum) | — |
| 4 | Solubility of 10% (w/v) sample in 15% (w/w) HCl at 24±2°C | Soluble | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 243. ONGC/WS/08/2026 — AMMONIUM CHLORIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:25 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white crystals or pellets with a perceptible odour and shall be free from visible impurities. | — |
| 2 | Moisture content (Determined by drying for 24 hrs in a vacuum desiccator over H2 SO4 ), percent by mass | 1.0 (Maximum) | — |
| 3 | Ammonium Chloride as NH4Cl on Dry Basis, percent by mass | 98.5 (Minimum) | — |
| 4 | Iron as Fe, percent by mass | 0.01 (Maximum) | — |
| 5 | Sulphates as (NH4 )2 SO4 (Turbidity method 0.30 (Max), percent by mass | Turbidity with the material is not greater than that produced in control test | — |
| 6 | Matter insoluble in water, percent by mass | 0.20 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 244. ONGC/WS/09/2026 — AMMONIUM PERSULPHATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:26 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white granular crystals or crystalline powder, free from visible impurities. | — |
| 2 | Presence of Ammonium ion (NH4+) | Positive | — |
| 3 | Presence of Persulphate ion (S2O8 -2) | Positive | — |
| 4 | Purity as Ammonium Persulphate, percent by mass | 98.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 245. ONGC/WS/12/2026 — BENZOIC ACID

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 20:34 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of flakes, free from visible impurities. | — |
| 2 | Purity as C6H5COOH on Dry Basis (Dried over Silica Gel for 3 hrs), percent by mass | 99.0 (Minimum) | — |
| 3 | Melting Point, °C | 120 ± 2 | — |
| 4 | Specific Gravity 15°C / 4°C | 1.27 ± 0.05 | — |
| 5 | Type-1: Sieve Analysis - Retention on ASTM No. 4 or equivalent, percent by mass | 90 (Minimum) | — |
| 6 | Type-2: Sieve Analysis - Retention in between ASTM No. 4 / 20 or equivalent, percent by mass | 90 (Minimum) | — |
| 7 | Type-3: Sieve Analysis - Retention in between ASTM No. 20 / 40 or equivalent, percent by mass | 90 (Minimum) | — |
| 8 | Note: | Sieve analysis may be carried out at the place where material is offered. The three types of material, conforming to the specifications at Sl. No. 5, 6 & 7 above may be mixed in proportion of 12%, 65% and 23% respectively and packed as per packing clause. | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 246. ONGC/WS/13/2026 — BORAX

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:39 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of crystals or granules or powder, free from visible impurities. | — |
| 2 | Matter Insoluble in Water, percent by mass | 0.10 (Maximum) | — |
| 3 | pH of 38 g / litre Solution of sample in Distilled water at 24±2°C | 9.0-9.5 | — |
| 4 | Purity as Sodium Tetra Borate DecaHydrate, percent by mass | 99.5 - 105 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 247. ONGC/WS/14/2026 — CITRIC ACID MONOHYDRATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:40 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form crystals or crystalline powder, free from visible impurities. | — |
| 2 | Purity as Citric Acid Monohydrate, percent by mass | 99.5 (minimum) | — |
| 3 | Water Content, percent by mass | 9.0 (maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 248. ONGC/WS/17/2026 — ETHYL ACETATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of clear, colourless liquid with a characteristic odour and shall be free from visible impurities. | — |
| 2 | Relative Density at 27°C/ 27 °C | 0.874 - 0.898 | — |
| 3 | Residue on evaporation, percent by mass | 0.02 (Maximum) | — |
| 4 | Ester Content as Ethyl Acetate, percent by mass | 94 (Minimum) | — |
| 5 | Initial Boiling Point (Distillation range at 760 mm Hg), °C | 71.0 (Minimum) | — |
| 6 | Dry Point, (Distillation range at 760 mm Hg), °C | 82.0 (Maximum) | — |
| 7 | Water content, percent by mass | 0.5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 249. ONGC/WS/18/2026 — ETHYLENE GLYCOL MONO BUTYL

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 15:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a clear liquid, free from visible impurities. | — |
| 2 | Miscibility in fresh water at 24±2°C | Shall be miscible in all proportions | — |
| 3 | Specific Gravity at 20°C/ 4°C | 0.901 - 0.905 | — |
| 4 | Volume of distillate collected upto 168 °C, percent volume | 2.0 (Maximum) | — |
| 5 | Volume of distillate collected between 168 -174°C, percent volume | 96.0 (Miminum) | — |
| 6 | Acidity as CH COOH, percent by mass | 0.02 (Maximum) | — |
| 7 | Water Content, percent by mass | 0.3 (Maximum) | — |
| 8 | Organic Chloride content, ppm | 5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 250. ONGC/WS/21/2015 — GELLING AGENTS (GRADE I, II, III)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 16:11 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing powder, free from visible impurities. | — |
| 2 | Dispersibility of sample in 3% (w/v) KCl brine in freshly boiled and cooled Distilled water at 24±2°C for 45 minutes | Highly dispersible | — |
| 3 | Grade-I: Moisture content at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 4 | Grade-II: Moisture content at 105±2°C, percent by mass | 5.0 (Minimum) | — |
| 5 | Grade-III: Moisture content at 105±2°C, percent by mass | 10.0 (Minimum) | — |
| 6 | Grade-I: Residue content on dry basis, percent by mass | 1.0 (Maximum) | — |
| 7 | Grade-II: Residue content on dry basis, percent by mass | 4.0 (Maximum) | — |
| 8 | Grade-III: Residue content on dry basis, percent by mass | 6.0 (Maximum) | — |
| 9 | Grade-I: Test for Complex gel formation | Positive at pH 4 – 6 | — |
| 10 | Grade-II: Test for Complex gel formation | Positive at pH 8 - 10 | — |
| 11 | Grade-III: Test for Complex gel formation | Positive at pH 8 - 10 | — |
| 12 | Grade-I : Viscosity of (511 sec-1 shear rate) Gel (0.7 % in 3 % KCl solution) after 45 minutes stirring at 24±2°C, cP | 50 (Minimum) | — |
| 13 | Grade-II : Viscosity of (511 sec-1 shear rate) Gel (0.6 % in 3 % KCl solution) after 45 minutes stirring at 24±2°C, cP | 55 (Minimum) | — |
| 14 | Grade-III : Viscosity of (511 sec-1 shear rate) Gel (0.9 % in 3 % KCl solution) after 45 minutes stirring at 24±2°C, cP | 55 (Minimum) | — |
| 15 | Grade-I : Viscosity of (511 sec-1 shear rate) Gel after ageing for 48 hrs at 40±2°C | 45 (Minimum) | — |
| 16 | Grade-II: Viscosity of (511 sec-1 shear rate) Gel after ageing for 48 hrs at 40±2°C | 45 (Minimum) | — |
| 17 | Grade-III: Viscosity of (511 sec-1 shear rate) Gel after ageing for 48 hrs at 40±2°C | 50 (Minimum) | — |
| 18 | Grade-I : Viscosity of (511 sec-1 shear rate) Gel after ageing for 4 hrs at 90±2°C | 15 (Minimum) | — |
| 19 | Grade-II : Viscosity of (511 sec-1 shear rate) Gel after ageing for 4 hrs at 90±2°C | 20 (Minimum) | — |

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 20 | Grade-III : Viscosity of (511 sec-1 shear rate) Gel after ageing for 4 hrs at 90±2°C | 20 (Minimum) | — |
| 21 | Grade-I : Viscosity of (511 sec-1 shear rate) Complexed Gel containing 0.1 gm Ammonium Persulphate per litre Gel after ageing for 4 hrs at 90±2°C | 5 (Maximum) | — |
| 22 | Grade-II : Viscosity of (511 sec-1 shear rate) Complexed Gel containing 0.1 gm Ammonium Persulphate per litre Gel after ageing for 4 hrs at 90±2°C | 5 (Maximum) | — |
| 23 | Grade-III : Viscosity of (511 sec-1 shear rate) Complexed Gel containing 0.1 gm Ammonium Persulphate per litre Gel after ageing for 4 hrs at 90±2°C | 5 (Maximum) | — |
| 24 | Grade-I: Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel after 45 minutes stirring at 24±2°C | 0.5 (Maximum) | — |
| 25 | Grade-II: Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel after 45 minutes stirring at 24±2°C | 0.5 (Maximum) | — |
| 26 | Grade-III: Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel after 45 minutes stirring at 24±2°C | 0.4 (Maximum) | — |
| 27 | Grade-I : Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel after ageing for 48 hrs. at 40±2°C | 0.55 (Maximum) | — |
| 28 | Grade-II : Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel after ageing for 48 hrs. at 40±2°C | 0.55 (Maximum) | — |
| 29 | Grade-III : Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel after ageing for 48 hrs. at 40±2°C | 0.55 (Maximum) | — |
| 30 | Grade-I : Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel ageing for 4 hrs.at 90±2°C | 0.70 (Maximum) | — |
| 31 | Grade-II : Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel ageing for 4 hrs.at 90±2°C | 0.70 (Maximum) | — |
| 32 | Grade-III : Flow Behavior Index (n') at 1022/511 sec-1 shear rate of gel ageing for 4 hrs.at 90±2°C | 0.70 (Maximum) | — |
| 33 | Grade-I: Flow Behavior Index (n') at 1022/511 sec-1 shear rate of complexed gel containing 0.1gm Ammonium Persulphate per litre after ageing for 4 hrs at 90±2°C | 0.99 - 1.00 | — |
| 34 | Grade-II: Flow Behavior Index (n') at 1022/511 sec-1 shear rate of complexed gel containing 0.1gm Ammonium Persulphate per litre after ageing for 4 hrs at 90±2°C | 0.99 - 1.00 | — |
| 35 | Grade-III: Flow Behavior Index (n') at 1022/511 sec-1 shear rate of complexed gel containing 0.1gm Ammonium Persulphate per litre after ageing for 4 hrs at 90±2°C | 0.99 - 1.00 | — |
| 36 | Grade-I: Ash Content on dry basis, percent by mass | 1.5 (Maximum) | — |
| 37 | Grade-II: Ash Content on dry basis, percent by mass | 1.0 (Maximum) | — |
| 38 | Grade-III: Ash Content on dry basis, percent by mass | 1.5 (Maximum) | — |

### *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 251. ONGC/WS/22/2026 — HIGH STRENGTH PROPPANT CERAMIC/SINTERED BAUXITE (12/20 AND 20/40)

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 20:40 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of single grains. | — |
| 2 | Size Designation : Type -1 | ASTM No. 12 / 20 or equivalent | — |
| 3 | Size Designation : Type -2 | ASTM No. 20 / 40 or equivalent | — |
| 4 | Fraction retained between the designated sieve sizes, percent by mass | 90.0 ( Minimum) | — |
| 5 | Type-1 : Fraction retained on ASTM No. 8 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 6 | Type-2 : Fraction retained on ASTM No. 16 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 7 | Type-1 : Fraction retained on ASTM No. 30 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 8 | Type-2 : Fraction retained on ASTM No. 50 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 9 | Type-1: Proppant grain clusters, percent by count | < 1 | — |
| 10 | Type-2: Turbidity, NTU | 250 (Maximum) | — |
| 11 | Krumbein Sphericity | 0.7 (Minimum) | — |
| 12 | Krumbein Roundness | 0.7 (Minimum) | — |
| 13 | Type-1: Acid Solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 5.5 (Maximum) | — |
| 14 | Type-2: Acid Solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 7.0 (Maximum) | — |
| 15 | Visual inspection (After Crush Resistance at 10,000 psi) | Proppant grains are separated and do not form lumpy / sticky mass | — |
| 16 | Fines (crush resistance at 10,000 psi), percent by mass | 4.0 (Maximum) | — |
| 17 | Visual inspection: Loss on Ignition (After heating at 927± 2 °C) | Proppant grains are separated and should not be charred or deformed. | — |
| 18 | Loss on Ignition (After heating at 927± 2 °C), percent weight loss | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 252. ONGC/WS/24/2026 — HYDROCHLORIC ACID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 16:22 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a clear, colourless or light yellow liquid, free from dirt & other visible impurities. | — |
| 2 | Total Acidity as HCl, percent by mass | 30.0 (Minimum) | — |
| 3 | Residue on Ignition, percent by mass | 0.10 (Maximum) | — |
| 4 | Iron as Fe+3, percent by mass | 0.02 (Maximum) | — |
| 5 | Fluoride (Qualitative test) | Negative | — |
| 6 | Sulphate (Qualitative test) | Negative | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 253. ONGC/WS/25/2026 — HYDROXY ETHYL CELLULOSE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 16:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a free flowing powder, free from visible impurities. | — |
| 2 | Dispersibility of 0.7% (w/v) sample in freshly boiled and cooled Distilled water in 45 minutes at 24±2°C | Highly dispersible | — |
| 3 | Moisture content of sample at 105±2°C, percent by mass | 10.0 (Maximum) | — |
| 4 | Residue Content on Dry Basis, percent by mass | 0.5 (Maximum) | — |
| 5 | Insoluble Matter (on Dry Basis), in 15% (w/w) HCl, percent by mass | 0.3 (Maximum) | — |
| 6 | Viscosity (511 sec-1 shear rate) of 0.7% (w/v) sample in 3% (w/v) KCl solution. After dispersion for 45 minutes at 24±2°C, cP | 50 (Minimum) | — |
| 7 | Viscosity (511 sec-1 shear rate) of 0.7% (w/v) sample in 3% (w/v) KCl solution after ageing for 48 hrs at 40 ± 2°C, cP | 20 (Minimum) | — |
| 8 | Viscosity (511 sec-1 shear rate) of 0.7% (w/v) sample in 3% (w/v) KCl solution after ageing for 2 hrs at 90 ± 2°C, cP | 45 (Minimum) | — |
| 9 | Viscosity (511 sec-1 shear rate) of 0.7% (w/v) sample in 3% (w/v) KCl solution after ageing for 2 hrs at 90 ±2 °C by treating with 0.40% (v/v) of 15% (w/w) HCl, cP | 5 (Maximium) | — |
| 10 | Flow Behaviour Index (n') (1022/511 sec-1 shear rate) after dispersion for 45 minutes at 24±2°C | 0.5 (Maximum) | — |
| 11 | Flow Behaviour Index (n') (1022/511 sec-1 shear rate) after ageing for 48 hrs at 40±2°C | 0.51 (Maximum) | — |
| 12 | Flow Behaviour Index (n') (1022/511 sec-1 shear rate) after ageing for 2 hrs at 90±2°C. | 0.55 (Maximum) | — |
| 13 | Flow Behaviour Index (n') (1022 / 511 sec-1 shear rate) after ageing for 2 hrs at 90±2°C by treating with 0.40% (v/v) of 15% (w/w) HCl. | 0.99 - 1.00 | — |
| 14 | Foaming observation : 0.7% (w/v) sample in 3% (w/v) KCl solution at high shear rate | No Foaming | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 254. ONGC/WS/26/2026 — ISOPROPYL ALCOHOL

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 16:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a clear liquid with characteristic odour and shall be free from visible impurities. | — |
| 2 | Odour of residue on evaporation | Odourless | — |
| 3 | Specific Gravity at 27°C / 27°C | 0.781 - 0.785 | — |
| 4 | Amount of distillate at 82.4±2°C, percent by volume | 95.0 (Minimum) | — |
| 5 | Acidity as CH COOH, percent by mass | 0.002 (Maximum) | — |
| 6 | Residue on evaporation, g/litre | 0.04 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 255. ONGC/WS/27/2026 — LOW STRENGTH PROPPANT

| | | | |
|---|---|---|---|
| **Version** | v2 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:20 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of single grains | — |
| 2 | Sieve Analysis: Size Designation LSP 12/20 | ASTM No. 12 / 20 or equivalent | — |
| 3 | Sieve Analysis: Size Designation LSP 20/40 | ASTM No. 20 / 40 or equivalent | — |
| 4 | Sieve Analysis: Size Designation LSP 40/70 | ASTM No. 40 / 70 or equivalent | — |
| 5 | Fraction retained between the designated sieves sizes, percent by mass | 90.0 (Minimum) | — |
| 6 | LSP 12/20: Fraction retained on ASTM No. 8 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 7 | LSP 20/40: Fraction retained on ASTM No. 16 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 8 | LSP 40/70: Fraction retained on ASTM No. 30 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 9 | LSP 12/20: Fraction passing through ASTM No. 30 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 10 | LSP 20/40: Fraction passing through ASTM No. 50 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 11 | LSP 40/70: Fraction passing through ASTM No. 100 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 12 | Sand Grain Clusters, percent by count | < 1 | — |
| 13 | Krumbein Sphericity | 0.6 (Minimum) | — |
| 14 | Krumbein Roundness | 0.6 (Minimum) | — |
| 15 | LSP 12/20: Acid solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 2.0 (Maximum) | — |
| 16 | LSP 20/40: Acid solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 2.0 (Maximum) | — |
| 17 | LSP 40/70: Acid solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 3.0 (Maximum) | — |
| 18 | Turbidity on dry basis, NTU | 250 (Maximum) | — |
| 19 | LSP 12/20: Crush resistance at 3000 psi fines, percent by mass | 16 (Maximum) | — |
| 20 | LSP 20/40: Crush resistance at 4000 psi fines, percent by mass | 14 (Maximum) | — |
| 21 | LSP 40/70: Crush resistance at 5000 psi fines, percent by mass | 8 (Maximum) | — |
| 22 | Clay and soft particle content, percent by volume | 1 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 256. ONGC/WS/28/2026 — MONOETHYLENE GLYCOL FOR WELL

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:21 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material should be a free flowing liquid having mild odour, free from visible impurities. | — |
| 2 | Water miscibility at 24±2 °C | Miscible in all proportions | — |
| 3 | Relative density at 24±2°C / 24±2°C | 1.1070 - 1.1150 | — |
| 4 | Distillation upto 192°C, percent by volume | 5 (Maximum) | — |
| 5 | Distillation upto 206°C, percent by volume | 95 (Minimum) | — |
| 6 | Acidity as Acetic Acid, percent by mass | 0.005 (Maximum) | — |
| 7 | Ash content, percent by mass | 0.010 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 257. ONGC/WS/33/2026 — NON-EMULSIFIER FOR WATER BASE FRACTURING FLUIDS

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:27 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a homogeneous liquid, free from visible impurities | — |
| 2 | Miscibility of 0.5% (v/v) sample with Water at 24±2°C | Miscible | — |
| 3 | Pour Point, °C | 21 (Maximum) | — |
| 4 | Demulsification Efficiency : [Test Temperature: 90 ±2 °C, Test duration: 12 hrs; dosage of the Non-Emulsifier added for demulsification of the emulsion formed by utilizing freshly prepared conventional water base gel (Gelling Agent Grade II/ III having 50-55 cP Viscosity at 511 sec-1 shear rate and Specific Crude: 5 ml/litre)], percent | 100 | — |
| 5 | Wettability characteristics with clean sand | Preferentially water wet | — |
| 6 | Compatibility with additives: Formation of precipitate | Negative | — |
| 7 | Compatibility with additives: Wettability characteristics | Preferably water wet | — |
| 8 | Ionic nature | Non Ionic / Anionc | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 258. ONGC/WS/35/2026 — POTASSIUM CHLORIDE FOR WELL STIMULATION

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:28 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of crystalline solid or powder, free from visible impurities. | — |
| 2 | Moisture content at 110±2°C, percent by mass | 2.0 (Maximum) | — |
| 3 | Matter insoluble in water (on dry basis), percent by mass | 0.10 (Maximum) | — |
| 4 | Calcium as Ca++ on dry basis, ppm | 200 (Maximum) | — |
| 5 | Purity as KCl on dry basis, percent by mass | 96.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 259. ONGC/WS/36/2026 — POTASSIUM IODIDE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:29 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical state | The material shall be in the form ofcrystals or granules or powder, free from visible impurities | — |
| 2 | Loss on drying at 105±2°C, percent by mass | 1.0 (Maximum) | — |
| 3 | pH of 50 g/litre solution of material in Distilled water | 9.2 (Maximum) | — |
| 4 | Purity as Potassium Iodide on dry basis, percent by mass ) | 99.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 260. ONGC/WS/41/2026 — SODIUM ACETATE (ANHYDROUS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities. | — |
| 2 | Insoluble matter in Distilled water, as Calcium, Magnesium and Ammonium Hydroxide precipitates, percent by mass | 0.5 (Maximum) | — |
| 3 | Visual Clarity of 100 g / litre Solution of the sample in Distilled water at 24±2°C | Shall be a clear solution | — |
| 4 | Purity as Sodium Acetate (Anhydrous), percent by mass | 99.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 261. ONGC/WS/42/2026 — SODIUM NITRITE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:31 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of clear deliquescent crystals or lumps or sticks of pale yellow colour and shall be free from visible impurities. | — |
| 2 | Moisture and Volatile matter at 110 ± 2°C, percent by mass | 2.0 (Maximum) | — |
| 3 | Assay as NaNO2 on dry basis, percent by mass | 97.0 (Minimum) | — |
| 4 | Matter insoluble in water, percent by mass | 0.01 (Maximum) | — |
| 5 | Alkalinity as Na2CO3 , percent by mass | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 262. ONGC/WS/44/2026 — SODIUM THIOSULPHATE FOR HYDROFRACTURING

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:33 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of crystals or powder, free from visible impurities. | — |
| 2 | Sodium Thiosulphate (Na2S2O3. 5H2O), percent by mass | 90.0 (Minimum) | — |
| 3 | pH of 10% (w/v) solution of sample in Distilled water | 6.5 - 9.5 | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 263. ONGC/WS/46/2026 — SURFACTANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of a homogenous liquid, free from visible impurities. | — |
| 2 | Miscibility of 0.1% (v/v) sample with 15% (w/w) HCl and 28% (w/w) HCl at 24±2°C | Miscible | — |
| 3 | Pour Point, °C | 12 (Maximum) | — |
| 4 | Surface Tension of 15% (w/w) Hydrochloric Acid containing 200 ppm of the Surfactant at 25°C, dynes / cm | 35 (Maximum) | — |
| 5 | Wettability Characteristics with clean sand | Preferentially water wet | — |
| 6 | Wettability Characteristics with Limestone | Preferentially water wet | — |
| 7 | Compatibility with acid additives : Formation of precipitate with Surfactant (0.1% v/v) | Negative | — |
| 8 | Surface Tension at 25°C for 200 ppm of Surfactant in 15% w/w HCl with above additives, dynes / cm | 35 (Maximum) | — |
| 9 | Ionic Nature | Non-ionic | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 264. ONGC/WS/47/2026 — WATER FOAMER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 18:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a homogeneous liquid, free from visible impurities. | — |
| 2 | Miscibility of 1% (v/v) sample with 3% (w/v) Potassium Chloride solution in Distilled water at 24±2°C | Miscible | — |
| 3 | Pour Point, °C | 12 (Maximum) | — |
| 4 | Foam Quality, with 1% (v/v) concentration of Foamer in 3% (w/v) solution of Potassium Chloride at 24±2°C, percent by volume | 75 (Minimum) | — |
| 5 | Half life with 1% (v/v) concentration of Foamer in 3% (w/v) solution of Potassium Chloride at 24±2 0C, minutes | 5 ( Minimum) | — |
| 6 | Foam Quality, with 1% (v/v) concentration of Foamer in conventional water base gel at 24±2°C, percent by volume | 65 ( Minimum) | — |
| 7 | Half Life with 1% (v/v) concentration of Foamer in conventional water base gel at 24±2°C, minutes | 5 (Minimum) | — |
| 8 | Viscosity of the treated gel (S. No. 6) at 511 sec-1 shear rate, cP | 75 (Minimum) | — |
| 9 | Flow Behavior Index (n') of the treated gel at 1022/511 sec-1 shear rate | 0.45 (Maximum) | — |
| 10 | Wettability characteristics with clean sand | Preferentially water wet | — |
| 11 | Compatibility with other additives : Formation of precipitate | Negative | — |
| 12 | Compatibility with other additives : Foam test | Foam Quality and Half Life should not change | — |
| 13 | Ionic Nature | Non-ionic / Anionic | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 265. ONGC/WS/48/2015 — INTERMEDIATE STRENGTH PROPPANT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:02 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of single grains | — |
| 2 | Size Designation : Type-1 | ASTM No. 12 / 20 or equivalent | — |
| 3 | Size Designation : Type-2 | ASTM No. 20 / 40 or equivalent | — |
| 4 | Fraction retained between the designated sieve sizes, percent by mass | 90.0 ( Minimum) | — |
| 5 | Type-1: Fraction retained on ASTM No. 8 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 6 | Type-2: Fraction retained on ASTM No. 16 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 7 | Type-1: Fraction passing through ASTM No. 30 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 8 | Type-2: Fraction passing through ASTM No. 50 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 9 | Proppant Grain Clusters, percent by count | < 1 | — |
| 10 | Type-2: Turbidity, NTU | 250 (Maximum) | — |
| 11 | Krumbein Sphericity | 0.7 (Minimum) | — |
| 12 | Krumbein Roundness | 0.7 (Minimum) | — |
| 13 | Type-1: Acid solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 5.5 (Maximum) | — |
| 14 | Type-2: Acid solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 7.0 (Maximum) | — |
| 15 | Visual inspection ( After Crush Resistance at 7,500 psi) | Proppant grains are separated and do not form lumpy / sticky mass | — |
| 16 | Type-1: Fines Crush Resistance at 7500 psi, percent by mass | 5.0 (Maximum) | — |
| 17 | Type-1: Fines Crush Resistance at 7500 psi, percent by mass | 4.0 (Maximum) | — |
| 18 | Visual inspection: Loss on Ignition (After heating at 927± 2 °C) | Proppant grains are separated and should not be charred or deformed. | — |
| 19 | Loss on Ignition (After heating at 927± 2°C), percent weight loss | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 266. ONGC/WS/49/2026 — DIETHYLENE TRIAMINE PENTA- ACETIC ACID (DTPA)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:04 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white powder free from visible impurities. | — |
| 2 | Assay | 98 % (Minimum) | — |
| 3 | pH of saturated solution at 30°C | 2.0 - 3.0 | — |
| 4 | Chelation value (pH-11 mgs. of CaCO3 per gm) | 250 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 267. ONGC/WS/50/2026 — POLY OXYETHYLENE SORBITAN MONO OLEATE (TWEEN-80)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:05 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing amber coloured homogenous liquid, free from visible impurities. | — |
| 2 | Solubility of sample in Methanol, Ethanol and water | Should give a clear solution | — |
| 3 | Specific gravity | 1.06 - 1.09 | — |
| 4 | Viscosity at 25°C (Ostwald viscometer), centistokes | 300 - 500 | — |
| 5 | OH Value | 65 - 80 | — |
| 6 | Saponification value | 45 - 55 | — |
| 7 | Acid value | 2.0 (Maximum) | — |
| 8 | Residue on ignition, percent by mass | 0.25 (Maximum) | — |
| 9 | Water content, percent by mass | 3.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 268. ONGC/WS/51/2026 — SORBITAN MONO OLEATE (SPAN-80)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:07 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing amber coloured homogenous liquid, free from visible impurities. | — |
| 2 | Solubility of sample in Ethanol and Water | Should give a clear solution with Ethanol and should be dispersible in water | — |
| 3 | OH Value | 190 - 215 | — |
| 4 | Saponification value | 145 - 160 | — |
| 5 | Acid value | 8.0 (Maximum) | — |
| 6 | Iodine value | 62 - 76 | — |
| 7 | Water content, percent by mass | 1.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 269. ONGC/WS/52/2026 — SODIUM GLUCONATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:08 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white to yellowish crystalline powder, free from visible impurities. | — |
| 2 | Purity of Sodium Gluconate, percent by mass | 97.0 (Minimum) | — |
| 3 | Solubility of 2.0% of the sample in Distilled water | Forms a clear solution | — |
| 4 | Sulphate as SO2-, percent by mass | 0.10 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 270. ONGC/WS/53/2026 — SODIUM BROMATE

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:09 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of white crystalline powder, free from visible impurities. | — |
| 2 | Purity of Sodium Bromate, percent by mass | 98.0% (minimum) | — |
| 3 | pH of 5% aqueous solution in freshly prepared Distilled water | 7.0 - 8.5 | — |
| 4 | Loss on drying at 120°C for 3 hrs, percent by mass | 0.2 (Maximum) | — |
| 5 | Sulphate as SO -2, percent by mass | 0.10% (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 271. ONGC/WS/54/2016 — FAST HYDRATING GUAR GUM

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:30 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing powder, free from visible impurities. | — |
| 2 | Dispersibility of Sample (0.6% w/v) in 3% (w/v) KCl brine in freshly boiled and cooled distilled water at 24 ± 2 0C for 03 minutes | Dispersible | — |
| 3 | Moisture Content at 105±2 °C, percent by mass | 5.0 (Maximum) | — |
| 4 | Residue Content on Dry Basis, percent by mass | 4.0 (Maximum) | — |
| 5 | Test for Complex Gel Formation at pH 8 – 10 | Positive | — |
| 6 | Viscosity of (511 sec-1 shear rate) Gel : (0.6 w/v FHGG ) in 3 % KCl solution after 03 minutes stirring at 24±2°C, cP | 50 (Minimum) | — |
| 7 | Viscosity of (511 sec-1 shear rate) Gel as at S. No. 6 after ageing for 48 hours at at 40 ± 2°C | 50 (Minimum) | — |
| 8 | Viscosity of (511 sec-1 shear rate) Gel as at S.no.6 after ageing for 4 hours at 90 ± 2°C | 25 (Minimum) | — |
| 9 | Viscosity of (511 sec-1 shear rate) Complexed Gel (as at S.no.6) containing 0.1 g Ammonium Persulphate per litre Gel after ageing for 4 hours at 90 ± 2°C, cP | 5 (Maximum) | — |
| 10 | Flow Behavior Index (n') at 1022/511 sec-1 shear rate of Gel after 03 minutes stirring at 24 ± 2°C | 0.5 (Maximum) | — |
| 11 | Flow Behavior Index (n') at 1022/511 sec-1 shear rate of Gel after ageing for 48 Hrs. at 40 ± 2°C | 0.55 (Maximum) | — |
| 12 | Flow Behavior Index (n') at 1022/511 sec-1 shear rate of Gel ageing for 4 Hrs. at 90 ± 2°C | 0.70 (Maximum) | — |
| 13 | Flow Behavior Index (n') at 1022/511 sec-1 shear rate of Complexed Gel containing 0.1 g Ammonium Persulphate per litre after ageing for 4 hours at 90 ± 2°C | 0.99 - 1.00 | — |
| 14 | Ash Content on Dry Basis, percent by mass | 1.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 272. ONGC/WS/55/2019 — INTERMEDIATE STRENGTH PROPPANT 30/50 (CERAMIC / SINTERED BAUXITE)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:36 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of single grains. | — |
| 2 | Sieve Analysis: Size Designation | ASTM No. 30 / 50 or Equivalent | — |
| 3 | Fraction Retained between the designated sieves sizes, percent by mass | 90 (Minimum) | — |
| 4 | Fraction Retained on ASTM No. 20 or Equivalent Sieve, percent by mass | 0.1 (Maximum) | — |
| 5 | Fraction Passing through ASTM No. or Equivalent Sieve, percent by mass | 1.0 (Maximum) 70 | — |
| 6 | Turbidity , NTU | 250 (Maximum) | — |
| 7 | Proppant grain clusters, percent by count | < 1 | — |
| 8 | Krumbein Sphericity | 0.7 (Minimum) | — |
| 9 | Krumbein Roundness | 0.7 (Minimum) | — |
| 10 | Acid Solubility in 12% (w/w) HCl + 3% (w/w) HF on Dry Basis, percent by mass. | 7.0 (Maximum) | — |
| 11 | Visual inspection : After Crush Resistance at 7,500 psi | Proppant grains are separated and do not form lumpy/sticky mass | — |
| 12 | Fines (Crush resistance at 7500 psi), percent by mass | 3.0 (Maximum) | — |
| 13 | Visual Inspection Loss on ignition (After heating at 927±2 degC) | Proppant grains are separated and should not be charred or deformed | — |
| 14 | Loss on ignition (After heating at 927±2 degC), percent weight loss | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 273. ONGC/WS/56/2026 — GELLANT SUSPENDING AGENT

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:17 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be a free flowing fine powder, free from visible impurities | — |
| 2 | Dispersibility of 10% (w/v) sample in Diesel | Highly dispersible on agitation High Speed | — |
| 3 | Moisture Content of sample at 105±2°C, percent by mass Sieve Analysis: Size Designation | 5.0 (Maximum) | — |
| 4 | Fraction retained on ASTM No. 50 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 5 | Fraction passing through ASTM No. 100 or equivalent sieve, percent by mass | 85.0 (Minimum) | — |
| 6 | Swelling of dry GSA(1.0% w/v) after 24 hrs in High Speed Diesel, percent increase in volume | 250 (Minimum) | — |
| 7 | Test for Flowability of Diesel–FHGG (1.0:0.8) slurry containing GSA (3 wt% w.r.t. FHGG) after 48 hrs | The FHGG admix should remain in suspended form and should not remain stuck to the bottom of the container and should flow when it is tilted on its side | — |
| 8 | Viscosity (at 511 sec-1 shear rate) of linear gel : a) 2.0 ml of Diesel- FHGG (1:0.8) and GSA (3.0 wt % w.r.t. FHGG) slurry in 200 ml of 3 wt% KCl solution in distilled water with stirring at 24±2oC after 15 minutes. b) 2.0 ml of Diesel- FHGG (1:0.8) slurry in 200 ml of 3 wt% KCl solution in distilled water with stirring at 24±2oC after 15 minutes | The viscosity of linear gel prepared with or without the addition of GSA should be same or similar i.e. in the range of ±2 cP. | — |
| 9 | Viscosity (at 511 sec-1 shear rate) of linear gel: c)Test for Complex gel formation | Positive at pH 8-10 | — |
| 10 | Viscosity ( 511 sec-1 shear rate) of complexed gel (as Sr No.8.a) containing 0.1g Ammonium persulphate per litre gel after ageing for 4 hrs at 90±2 0C, cP | 5 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 274. ONGC/WS/57/2026 — N-Methly-2-Pyrrolidone

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:18 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical Appearance | The material shall be clear colourless liquid, free from visible impurities | — |
| 2 | Specific Gravity at 24±2 degC | 1.025 to 1.045 | — |
| 3 | Initial Boiling Point, ASTM D86 | Not less than 185 degC | — |
| 4 | Purity, by GC | 99 % (Minimum) | — |
| 5 | Water Content, by KF Method | 0.1 % (Maximum) | — |
| 6 | Organic Chloride, by ASTM D4929 (Method B) | 5 ppm (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 275. ONGC/WS/58/2026 — LIGHT WEIGHT PROPPANT 20/40

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:39 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of single grains | — |
| 2 | Bulk Density, gm / cm3 | 1.57 ± 0.02 (Maximum) | — |
| 3 | Sieve Analysis : Size Designation | ASTM No. 20/40 or Equivalent | — |
| 4 | Fraction retained between the designated sieves, % by mass | 90 (Minimum) | — |
| 5 | Fraction retained on ASTM No. 16 or equivalent sieve, % by mass | 0.1 (Maximum) | — |
| 6 | Fraction passing through ASTM No. 50 or equivalent sieve, % by mass | 1.0 (Maximum) | — |
| 7 | Proppant Grain Clusters, % by count | 1.0 (Maximum) | — |
| 8 | Turbidity on dry basis, NTU | 250 (Maximum) | — |
| 9 | Krumbein Sphericity | 0.8 (Minimum) | — |
| 10 | Krumbein Roundness | 0.8 (Minimum) | — |
| 11 | Acid solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, % by mass | 5.0 (Maximum) | — |
| 12 | Visual Inspection (After Crush Resistance at 7500 psi) | Proppant grains are separated and do not form lumpy / sticky mass | — |
| 13 | Fines (Crush resistance at 7500 psi) | 6.0 (Maximum) | — |
| 14 | Visual Inspection : Loss on Ignition (After heating at 927 ± 2 degC) | Proppant grains are separated and should not be charred or deformed | — |
| 15 | Loss on Ignition (After heating at 927 ± 2 degC), % weight loss | 0.2 (maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 276. ONGC/WS/60/2026 — POLY LACTIC ACID POWDER

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:40 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of powder, free from visible impurities | — |
| 2 | Polymer Identification with FTIR, DSC and TG Analysis | Polylactic Acid with maximum residue content of 4% | — |
| 3 | Moisture Content at 105 ± 2 °C | 5.0 (Maximum) | — |
| 4 | Hydrolysis in 15 % HCl at 90 °C in 24 hours, percent by mass | 90.0 (Minimum) | — |
| 5 | Specific Gravity at 24± 2 ° C | 1.2 (Minimum) | — |
| 6 | Particle Size Distribution- D-50, microns | 125 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 277. ONGC/WS/61/2025 — Intermediate Strength Proppant 16/30 @6000 psi

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 20:12 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of single grains. | — |
| 2 | Sieve Analysis: Size designation | ASTM No. 16/ 30 Mesh or equivalent | — |
| 3 | Fraction retained between the designated sieve sizes, percent by mass | 90 (Minimum) | — |
| 4 | Fraction retained on ASTM No. 12 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 5 | Fraction passing through ASTM No. 40 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 6 | Proppant Grain Clusters, percent by count | < 1.0 | — |
| 7 | Turbidity on dry basis, NTU | 250 (Maximum) | — |
| 8 | Krumbein Sphericity | 0.8 (Minimum) | — |
| 9 | Krumbein Roundness | 0.8 (Minimum) | — |
| 10 | Acid solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 7.0 (Maximum) | — |
| 11 | Visual Inspection (After Crush Resistance at 6000 psi) | Proppant grains are separated and do not form lumpy/ sticky mass | — |
| 12 | Fines (Crush Resistance at 6000 psi), percent by mass | 8.0 (Maximum) | — |
| 13 | Visual Inspection : Loss on Ignition (after heating at 927 +/- 2 degC) | Proppant grains are separated and do not form lumpy/ sticky mass | — |
| 14 | Loss on Ignition (after heating at 927 +/- 2 degC), percent weight loss | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 278. ONGC/WS/62/2025 — Intermediate Strength Proppant 12/20 @6000 psi (INDIGENOUS)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 20:16 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of single grains. | — |
| 2 | Sieve Analysis : Size designation | ASTM No. 12/ 20 Mesh or equivalent | — |
| 3 | Fraction retained between the designated sieve sizes, percent by mass | 90 (Minimum) | — |
| 4 | Fraction retained on ASTM No. 8 or equivalent sieve, percent by mass | 0.1 (Maximum) | — |
| 5 | Fraction passing through ASTM No. 30 or equivalent sieve, percent by mass | 1.0 (Maximum) | — |
| 6 | Proppant Grain Clusters, percent by count | 1.0 (Maximum) | — |
| 7 | Turbidity on dry basis, NTU | 250 (Maximum) | — |
| 8 | Krumbein Sphericity | 0.8 (Minimum) | — |
| 9 | Krumbein Roundness | 0.8 (Minimum) | — |
| 10 | Acid solubility in 12% (w/w) HCl + 3% (w/w) HF on dry basis, percent by mass | 7.0 (Maximum) | — |
| 11 | Visual Inspection (After Crush Resistance at 6000 psi) | Proppant grains are separated and do not form lumpy/ sticky mass | — |
| 12 | Fines (Crush Resistance at 6000 psi), percent by mass | 10.0 (Maximum) | — |
| 13 | Visual Inspection : Loss on Ignition (after heating at 927 +/- 2 degC) | Proppant grains are separated and should not be charred or deformed | — |
| 14 | Loss on Ignition (after heating at 927 +/- 2 degC), percent weight loss | 0.2 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 279. ONGC/WS/63/2025 — GUAR GUM FOR STIMULATION (80 °C)

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 20:23 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | Free flowing powder & free from visible impurities. | — |
| 2 | Dispersibility of 0.6 % (w/v) sample in 3% (w/v) KCl brine in freshly prepared & cooled distilled water at 24+2 °C for 15 minutes | Highly Dispersible | — |
| 3 | Moisture Content at 105+2 deg C, percent by mass | 6.0 (Maximum) | — |
| 4 | Residue content on dry basis, percent by mass | 4.0 (Maximum) | — |
| 5 | Test for complex gel formation at pH 8-10 | Positive | — |
| 6 | Performance Test (i) Viscosity of (511 S-1 shear rate) linear gel (0.6% w/v sample) in 3% (w/v) KCl solution after 15 minutes stirring at 24+2 deg C, cP | 52 (Minimum) | — |
| 7 | Performance Test (ii) Flow behavior Index (n') at 1052/511 sec-1 shear rate of linear gel at 24+2 °C | 0.5 (Maximum) | — |
| 8 | Performance Test (iii) Viscosity of (511 Sec-1 shear rate) linear gel (as at Sl. No. 6i) after aging for 4 hrs at 80+2 °C, cP | 25 (Minimum) | — |
| 9 | Performance Test (iv) Flow behavior Index (n') at 1052/511 sec-1 shear rate of linear gel after aging for 4-hrs at 80+2 °C | 0.7 (Maximum) | — |
| 10 | Performance Test (v) Viscosity of (511 Sec-1 shear rate) complex gel containing 0.02% (w/v) APS after ageing for 4-hrs at 80+2 °C, cP | 5.0 (Maximum) | — |
| 11 | Performance Test (vi) Flow behavior Index (n') at 1052/511 sec-1 shear rate of complex gel containing 0.02% (w/v) APS after ageing for 4-hrs at 80+2 °C | 0.99 - 1.00 | — |
| 12 | Ash Content on dry basis, % by mass | 1.0 (Maximum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |

# 280. ONGC/WS/64/2026 — BORIC ACID

| | | | |
|---|---|---|---|
| **Version** | v1 | **Stage** | Published |
| **Status** | Master Data | **Issue Date** | — |
| **Committee** | Chemical Specification Committee | **Prepared By** | Dinesh Reddy_106228 |
| **Last Updated** | 08 Mar 2026, 19:41 IST | **Impact Grade** | — |

| Operational | Safety | Supply | No Sub | Total | Grade | Reviewed By |
|---|---|---|---|---|---|---|
| — | — | — | — | — | — | — |

| | |
|---|---|
| **Operational Note** | — |
| **Safety / Environmental Note** | — |
| **Supply Risk Note** | — |
| **No Substitute Context** | Not flagged. |

## *Vital*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Vital parameters | — | — |

## *Essential*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| 1 | Physical State | The material shall be in the form of fine powder, or crystals, free from visible impurities | — |
| 2 | Moisture Content at 40 ± 2 °C (Determined as per IS 10116-1982 Reaffirm 1999 procedure), percent by mass | 0.5 (Maximum) | — |
| 3 | Boric Acid as H3BO3, percent by mass | 99.0 (Minimum) | — |

## *Essential-Informational*

| S. No. | Parameter Name | Required Value | Test Procedure Text |
|---|---|---|---|
| — | No Essential-Informational parameters | — | — |