PPG Industrial Coatings
Liquid Coatings

Spectracron™
SPU71099
4:1 Genie Blue

Highlights

Industrial liquid coatings include a variety of platforms and custom formulations ranging from UV cure technology to high-solids/ low-bake and waterborne finishes, all designed to increase applied cost efficiency and help manufacturers to achieve their coatings goals.

PPG has an integrated global team of professional color stylists, chemists and technical application experts to help manufacturers to commercialize products through complex global supply chains. PPG's dedicated work cells, using state-of-the-art software and dispensing equipment, allows PPG to help customers to achieve quick turnaround times.

Physical Properties (Unblended)

Product Code:	**SPU71099**	**GXH1090**
Product Desc:	4:1 Genie Blue	
Solids % by Weight	55.6 +/- 2 % Theoretical	90 +/- 2 % Theoretical
Solids % by Vol	46.2 +/- 2 % Theoretical	87.1 +/- 2 % Theoretical
Weight / Gallon	9.2 +/- 0.3 lbs/gal	9.45 +/- 0.3 lbs/gal
V.O.C.	3.2 lbs/gal Less Exempts	0.95 lbs/gal Theoretical
Package Viscosity	20-23 sec # 3 EZ Zahn Cup @ 77° F	
ShelfLife	12 Months (Closed Container)	6 Months (Closed Container)

Physical Properties (Blended)

Blend Ratio by Volume	4 : 1 SPU71099 : GXH1090
Solids % by Weight	62.6 +/- 2 % Theoretical
Solids % by Volume	54.4 +/- 2 % Theoretical
Weight / Gallon	9.3 +/- 0.3 lbs/gal
Coverage	877 ft squared per mil per gallon @ 100% efficiency
60° Gloss	55 Min 65 Max
V.O.C.	2.7 lbs/gal Less Exempts

Application Data

Application Method	Conventional Air Spray / HVLP
Viscosity	15-17 sec # 3 EZ Zahn Cup @ ambient (70 to 80 ; 25 C)° F
Substrate	Aluminum / Steel : Cleaned and Chemically Pretreated
Primer	PPG Approved Primers
Pot Life	30 minutes when blended
Dry Film Per Coat	1.2-1.5 mils
Clean Up	Ketones

PPG Provides custom blended Purges, Cleaners, and Reducers for your complete paint line systems. Please contact your local Sales/Service Representative or contact our PPG PT & EP team @ 800-627-6015 for assistance.

Cure Schedules

BAKE

Flash Time	10 Minutes
Time at Temp	20 Minutes
Oven Temp	180° F

*Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is suitable for the user's purposes, including without limitation substrate, application process, pasteurization and/or processing, and end use. No testing, suggestions or data offered by PPG to the user shall relieve the user of this responsibility. PPG does not warrant freedom from patent infringement in the use of any formula or processes set forth herein.

PPG Industries Oak Creek Plant 10800 S. 13th Street Oak Creek, WI 53154 414-574-7273
PPG Industries Springdale Plant 125 Colfax St. Springdale, PA 15144 724-274-7900
Issued: 1/17/2013
Printed: 5/10/2016

Additional Information

Mix thoroughly before using.
Blended product contains isocyanate. Consult MSDS for proper protective equipment.
Product must be catalyzed to cure.

*Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is suitable for the user's purposes, including without limitation substrate, application process, pasteurization and/or processing, and end use. No testing, suggestions or data offered by PPG to the user shall relieve the user of this responsibility. PPG does not warrant freedom from patent infringement in the use of any formula or processes set forth herein.