



检验报告

TEST REPORT

中心编号(No.): 201708AW134



样品名称: LC5.0 轻集料混凝土

Sample Name

委托单位: 中科永泰 (北京) 科技有限公司

Client

检验类别:

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







150002283084 (国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201708AW134

第1页共2页

C5.0 轻集料混凝土 中科永泰 (北京) 科技有限公司	检验类别商标	委托检验	
	商标	PETPPE	
	The second secon	174477	
中科永泰(北京)科技有限公司	等级	LC5.0	
	样品编号		
2017年08月10日	规格型号	話記記	
	样品状态	块状	
JGJ 51-2002《轻骨料混凝土技术规程》			
1. 抗压强度			
结构保温轻骨料混凝土(强度等级 LC:	5.0) 的技术指标 钥: 2017年 08	要求。* 3月16日	
アイル・アイ・アイ・アイ・アイ・アイ・アイ・アイ・アイ・アイ・アイ・アイ・アイ・アイ・	7. 江水 3元 水	186年11	
	*经检验,送检样品的抗压强度的 吉构保温轻骨料混凝土 (强度等级 LC:	*经检验,送检样品的抗压强度的检验结果符合标告构保温轻骨料混凝土(强度等级 LC5.0)的技术指标	

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告


TEST REPORT

中心编号(No.): 201708AW134

第2页 共2页

序号	检验项目	标准要求 (结构保温轻 骨料混凝土)	检验结果	单项结论
	抗压强度/MPa (强度等级 LC5.0)	≥5.0	5.6	合格

(以下空白)



备注: 试件由委托方成型并养护到期。

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>

