



检验报告

TEST REPORT

中心编号(No.): 201703AC457




样品名称:	挤塑板
Sample Name	
受检单位: Client	北京通佳建材有限公司
检验类别:	抽样检验
Test Type	たりもよりもようしてとのもよりもようのも

(国家)建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AC457

第1页共2页

The second second			73 1 25 75 25				
产品名称	挤塑板	检验类别	抽样检验				
受检单位	北京通佳建材有限公司	生产日期	視射距視				
生产单位	北京通佳建材有限公司	规格型号	X150				
抽样地点	企业成品库房	商标	自己的结束				
抽样人	孙士震 谷冰莹	等级	B ₂ 级				
抽样日期	2017年03月22日	抽样数量	8块				
样品状态	块状	抽样基数	30m ³				
抽样单位	建筑材料工业干混砂浆产品质量监督检验测试中心						
检验依据	GB/T 10801.2-2002《绝热用挤塑聚苯乙烯泡沫塑料(XPS)》 GB 8624-2012《建筑材料及制品燃烧性能分级》 GB/T 6343-2009《泡沫塑料及橡胶 表观密度的测定》						
检验项目	1. 允许偏差 2. 压缩强度 3. 导热系数 4. 燃烧性能等级 5. 表观密度						
检验结论	*经检验,抽检样品的允许偏,标准 GB/T 10801.2-2002 中 X150 的果符合标准 GB 8624-2012 中平板的技术指标要求;依据标准 GB/T 观密度的检验结果见第 2 页。*	的技术指标要。 状建筑材料 B ₂ 6343-2009 规划	k;燃烧性能等级的检验结 (E)级可燃材料(制品)				

备注: 抽样尺寸: 1200mm×600mm×80mm

山上

批准:多如之

核: 沙利

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AC457

第2页 共2页

序号	检验项目			标准要求 (X150)	检验结果	单项结论
	類。		长度(1000≤ L <2000)	±7.5	-2~+2	合格
	允许(扁差,	宽度 (L<1000)	±5	1-1-1-	合格
	m	m	厚度(h≥50)	13 13 13	0~+1	合格
	超到		对角线差 (1000≤T<2000)	≤70	15256	合格
2	压缩强度, kPa		≥150	160	合格	
3	导热系数, W/(m·K)		≤0.030	0.029(平均温 度 25.00℃)	合格	
性 4 等 (I	燃烧 性能 E	20s 内的焰尖高度, mm	≤150	139	合格	
	等级 (B ₂	等级 级	20s 内燃烧滴落物引 燃滤纸现象	无引燃滤纸 现象	无引燃滤纸 现象	符合
	级)	氧指数值,%	≥26	26.6	合格	
5	表观密度, kg/m³			3922	31.0	TH

(以下空白)

备注:燃烧性能等级试验结果只与制品的试样在特定试验条件下的性能相关,不能作 为评价该制品在实际使用中潜在火灾危险性的唯一依据。

电话: 010-51164723

邮编: 100024

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>