





检验报告

TEST REPORT

中心编号(No.): 201303AW014

样品名称: 聚合物粘结砂浆

Sample Name

委托单位: 北京博盛达装饰工程有限公司

Client

检验类别: 委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201303AW014

第1页共2页

合物粘结砂浆 京博盛达装饰工程有限公司 京博盛达装饰工程有限公司	检验类别 商 标	委托检验			
	10 13 6 P 14	博盛达			
京博盛达装饰工程有限公司	10 7404				
	等级				
13 年 02 月	样品编号	481			
13年03月05日	规格型号	干粉型			
kg 13 de la	样品状态	粉状,无结块			
JG 149-2003《膨胀聚苯板薄抹灰外墙外保温系统》					
1. 拉伸粘接强度(与水泥砂浆)					
	· 要求。*	类水			
357	生JG 149-2003 中胶粘剂的技术指标	住JG 149-2003 中胶粘剂的技术指标要求。*			

备注: (此处空白)

批准: Smot

审核: 于支机

编制:



检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201303AW014

第2页 共2页

序号	检验项目		标准要求 (胶粘剂)	检验结果	单项结论
	拉伸粘接强度 (与水泥砂浆)	原强度	≥0,60	0.83	合格
認		耐水	≥0.40	0.66	合格

(以下空白)

备注: 配比: 粉:水=4:1。

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。

Any doubt should inform us within 15 days after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>sj13146197542@126.com</u>