



存档

检验报告

TEST REPORT

中心编号(No.): 201303EW104

可归归红

+4	15	II.	
1干	1	称:	

工艺编织墙纸

Sample Name

委托单位:

浙江东南墙纸有限公司

Client

检验类别:_

委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

LO12)建材所脱认字(24号)

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

中心编号(No.): 201303EW104 第1页 共2页

	- (el). = 010 00 H 10 1		20 1 20 1 20 20				
样品名称	工艺编织墙纸	检验类别	委托检验				
委托单位	浙江东南墙纸有限公司	商标	东南				
生产单位	浙江东南墙纸有限公司	等级	建工程				
生产日期	2012年11月12日	样品编号					
来样日期	2013年03月28日	规格型号	(0.91×9.2) m				
样品数量	3m ²	样品状态	编织墙纸				
检验依据	GB 8624-1997《建筑材料燃烧性能分级方法》 GB/T17591-2006《阻燃织物》						
检验项目	1. 燃烧性能						
检验结论	*依据 GB 8624-1997 规定的检验结果符合标准 GB/T17591-		3.级技术指标要求。*				

备注: 委托方要求使用 GB 8624-1997 检验。

制: 批



(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告


TEST REPORT

中心编号(No.): 201303EW104

第2页共2页

序号	检验	项目 标准要求 (B ₂ 级)		检验结果	单项结论
燃烧性能 (装饰用织物)		损毁长度/mm	≤200	158	合格
	续燃时间/s	≤15	6	合格	
		阴燃时间/s	≤15	7.8	合格
试件说明			试样是 1mm	厚编织墙纸。	

(样品照片)



备注: (此处空白)

(国家)建筑材料工业技术监督研究中心

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期怨不 受理。

Any doubt should inform us within 15 days after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告采用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): si13146197542@126.com