



验报告

TEST REPORT

中心编号(No.): 201706AW286



样品名称:

BM连锁砌块专用砂浆

Sample Name

委托单位: 北京通富源建筑材料有限公司

Client

检验类别:

委托检验

Test Type

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar









150002283084(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706AW286

第1页共2页

备注: (此处					
	签发日期: 2017年 07月 30日 (检验测试章)				
检验结论	*经检验,送检释品的抗压强度、保水性、凝结时间的检验结果符合标准 JC/T 860-2008 中强度等级 Mb7.5 的技术指标要求。*				
检验项目	1. 抗压强度 2. 保水性 3. 凝结时间				
检验依据	JC/T 860-2008《混凝土小型空心砌块和混凝土砖砌筑砂浆》				
样品数量	20kg	样品状态			
来样日期	2017年06月30日	规格型号	干紛型		
生产日期		样品编号			
生产单位	北京通富源建筑材料有限公司	等级	Mb7.5		
委托单位	北京通富源建筑材料有限公司	商标	金星牌		
样品名称	BM 连锁砌块专用砂浆	检验类别	委托检验		

编制苏亮

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706AW286

第2页共2页

序号	检验项目	标准要求 (强度等级 Mb7.5)	检验结果	单项结论
强	抗压强度/MPa	27.5	8.8	含格。
2	保水性%	\$88 € 5	90.2	含格。
	凝结时间加	1/4-8	6.0	**************************************

(以下空白)

备注: 配比: 粉:水=1.0:0.18。

说。明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address)、北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话(Tel):(010)51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询(TeI):(010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



