



# 检验

告

TEST REPORT

中心编号(No.): 201703AW259

	Land Company	had to proper	Total I	and the same	
COPYLIA VI	THE .	1111	1	and I down	
- ( )	1	140	1	-	-
HIJT-	The state of	-1	-		
the training	HAKY.		34		HILL WHILL
	March 1 Towns		7-1-1	7	
		Comment of the second	1	1 14	
1111		The state of the s			The second name of

样品名称:\_

3D基材地面砂浆

Sample Name

委托单位:

河南国隆实业有限公司

Client

检验类别:

委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

五项证例4川里

2000年



#### 150002283084(国家)建筑材料工业技术监督研究中心

# 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201703AW259

第1页共2页

認能	*经检验,送检样品所检项目的中干混地面砂浆 M15 的技术指标	的检验结果符合标准	GB/T 25181-2010		
检验项目	1. 外观 2. 保水率 3. 凝结时间 4. 2h 稠度损失率 5. 抗冻性 (25 次冻融循环) 6. 28d 抗压强度				
检验依据	GB/T 25181-2010《预拌砂浆》	語語語			
样品数量	20kg	样品状态	粉状		
来样日期	2017年03月09日	规格型号	千粉型		
生产日期	超級銀銀銀	样品编号	認思		
生产单位	河南国隆实业有限公司	等级	DS M15		
委托单位	河南国隆实业有限公司	商标	388		
样品名称	3D基材地面砂浆	检验类别	委托检验		

备注:(此处空白)

批准: 5

、审核: 我和

编制: 书、亮



检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

### (国家)建筑材料工业技术监督研究中心

# 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

#### TEST REPORT

中心编号(No.): 201703AW259

第2页 共2页

-				カムパスム火		
序号	检验项目		标准要求 (干混地面 砂浆 M15)	(千混地面 检验结果		
	外观		均匀、无结块	均匀、无结块		
2	保水率/%		≥88	90.8	合格	
32	凝结时间/h		/3~9	4.8	合格	
4	2h 稠度损失率/%		€30	20.4	合格	
游戏	抗冻性 (25次 冻融循 环)	强度损失率	≤25		10000000000000000000000000000000000000	
		质量损失率	\$2.55 \$1.55		17 00 15 15 15 15 15 15 15 15 15 15 15 15 15	
6	28d 抗压强度/MPa		≥15.0	16.2	合格。	

(以下空白)

备注: 配比: 粉: 水=1.0: 0.14。

#### 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
  This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
  This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>