



150002283084

存档

检 验 报 告

TEST REPORT

中心编号(No.): 201611FW124

DMTC

样品名称: 混凝土用水

Sample Name

委托单位: 北京韩建河山管业股份有限公司朔州分公司

Client

检验类别: 委托检验

Test Type

建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

检验检测专用章

1100000064791



建筑材料工业技术监督研究中心
Technical Supervision and Research Center of the Building Materials Industry



Technical Supervision and Research Center of the Building Materials Industry

TEST REPORT

第 1 页 共 2 页

技术
★
检验
1000

编制:

邮编: 100024



建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

检 验 报 告

TEST REPORT

中心编号(No.): 201611FW124

第 2 页 共 2 页

第 2 页 共 2 页

序号	检验项目		标准要求 (混凝土拌合用水- 预应力混凝土)	检验结果	单项结论
1	pH 值		≥ 5.0	7.4	合格
2	不溶物(mg/L)		≤ 2000	132	合格
3	可溶物(mg/L)		≤ 2000	290	合格
4	SO_4^{2-} (mg/L)		≤ 600	33	合格
5	碱含量(按 $\text{Na}_2\text{O}+0.658\text{K}_2\text{O}$ 计 算)(mg/L)		≤ 1500	185	合格
6	水泥凝 结时间 之差 (min)	初凝	≤ 30	+4	合格
		终凝		+15	合格
7	水泥胶 砂抗压 强度比 (%)	3d	≥ 90	99	合格
		28d		98	合格
(以下空白)					
备注: (此处空白)					

检验单位地址: 北京市朝阳区管庄中国建材院北楼

电话: 010-51164723

邮编: 100024



建筑材料工业技术监督研究中心
Technical Supervision and Research Center of the Building Materials Industry

DMTC

说 明 Notice

- 1、本报告无中心“检验测试章”和骑缝章无效。
This test report is invalid without the seal.
- 2、本报告无“编制、审核、批准”签字无效。
This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议，应于收到报告之日起十五个工作日内向本中心提出，逾期恕不受理。
Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供，中心不对真实性负责，委托检验结果仅对来样负责。
The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律責任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张，复印后应带有网络底纹。
This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式：

地址 (Address)：北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code)：100024

电话 (Tel)：(010) 51164723 51164718

传真 (Fax)：(010) 51164724

报告真伪查询 (Tel)：(010) 51164716

网址 (Web)： <http://www.dmtc.org.cn/>

电子邮箱 (E-mail)： dmtc2007@163.com

