



检验报告

TEST REPORT

中心编号(No.): 201609AW012

样品名称:	防火岩棉
Sample Name	
委托单位: Client	河北金旗耐火保温材料有限公司
检验类别:	委托检验
Test Type	非特殊的。 第一

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Conter for Quality Supervision and Test of Dry-mixed Mortar



建筑外数、



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告


TEST REPORT

中心编号(No.): 201609AW012

第1页共2页

			TO IN TO A U				
样品名称	防火岩棉	检验类别	委托检验				
委托单位	河北金旗耐火保温材料有限公司	商 标	THE THE				
生产单位	河北金旗耐火保温材料有限公司	等 级	100kg/m ³				
生产日期	2016年09月08日	样品编号	招想和军				
来样日期	2016年09月19日	规格型号	1200mm×600mm×100mm				
样品数量	4块	样品状态	板状				
检验依据	GB 8624-2012《建筑材料及制品燃烧性能分级》						
检验项目	[目 1. 燃烧性能等级 * 经检验, 送检样品的燃烧性能等级的检验结果符合标准 GB 8624-2012 中平板状建筑材料 A(A ₁)级不燃材料(制品)的技术指标 要求。*						
检验结论			一个限数数				
超越	经经验的	The second secon	6年09月26日 金验测试章)				

备注:(此处空白)





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201609AW012

第2页共2页

序号	PAR	检验项目	标准要求	检验结果	单项结论
	燃烧	炉内温升,℃	€30	6	合格
	性能等级	质量损失率,%	€50	T in T	合格
[A(A ₁) 级]	持续燃烧时间, s	0	45025	合格	
	经	总热值,MJ/kg	€2.0	0.3	合格

(以下空白)

备注:(此处空白)

ALCETACK

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

