



检验报告

TEST REPORT

中心编号(No.): 201709AW119

样品名称:	灌浆料		
Sample Name			
委托单位:	唐山市路南新中盛建材厂		
Client			
检验类别:	委托检验		
Test Type			

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







150002283084 (国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201709AW119

第1页共2页

灌浆料	检验类别	委托检验		
唐山市路南新中盛建材厂	商标			
唐山市路南新中盛建材厂	等 级	_		
	样品编号			
2017年09月06日	规格型号	干粉型		
20kg	样品状态	粉状		
JC/T 986-2005(2017)《水泥基灌浆材料》				
1. 凝结时间 2. 抗压强度 (3d、28d) 3. 流动度(初始流动度)				
经检验,送检样品的凝结时间、抗压强度(3d、28d)、流动度()始流动度)的检验结果符合标准 JC/T 986-2005(2017)的技术指标要求。*				
签发日期: 2017年10月08日 (检验测试章)				
空白)	250	は中心が		
	唐山市路南新中盛建材厂	唐山市路南新中盛建材厂		

批 准:

审核: 兆弘

编制:长高

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201709AW119

第2页共2页


序号	检验项目		标准要求	检验结果	单项结论
1	凝结时间/min	结时间/min 初凝	≥120	180	合格
抗压强度 /MPa	3d	≥40.0	46.2	合格	
	2	/MPa	28d	≥70.0	72.0
3	流动度/mm	初始流动度	≥260	292	合格

(以下空白)

电话: 010-51164723

邮编: 100024

备注: 配比: 粉:水=1.0:0.14。



说 明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>



