



报

REPORT TEST

中心编号(No.): 201705AW138

样品名称:

复合轻集料混凝土

Sample Name

委托单位: 北京程美通达防水保温工程有限公司

Client

检验类别:

委托检验

Test Type

(国家工建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

验报告

TEST REPORT

中心编号(No.): 201705AW138

第1页共2页

170-40 214	D. A. T. A. T. A. D.		TOTALT		
样品名称	复合轻集料混凝土	检验类别	委托检验		
委托单位	北京程美通达防水保温工程有限公司	商。林			
生产单位	北京程美通达防水保温工程有限公司	等级			
生产日期		样品编号			
来样日期	2017年05月03日	规格型号			
样品数量		样品状态			
检验依据	JGJ 51-2002《轻骨料混凝王技术规程》				
检验项目	できる。 1. 1. 1. 1. 1. 1. 1. 1. 1. 1. 1. 1. 1. 1				
检验结论	*经检验,送检样品的干表观 JGJ 51-2002 中结构保温轻滑料混凝的技术指标要求。*	主(密度等级 8 目期: 2017			
备注:(此处			登録がまま		

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

验报告

TEST REPORT

中心编号(No.): 201705AW138

第2页共2页

序号	MATA CHA	标准要求 (结构保温轻 骨料混凝土)	检验结果	単项结论
子密度小		760~850	800	
九五强 2 (强度等的				# # # # # # # # # # # # # # # # # # #

备注: 试件由委托方成型并养护到期。

说。可明

Notice

- Li 本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。

This test report is invalid without the signatures of the related persons.

- 3、本报告涂改、部分复印无效。
 - This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应手收到报告之日起中五个工作目内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5. 委托检验样品和委托信息由委托入提供, 中心不对真实性负责, 委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 - The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伤纸张,复印店应带有网络底纹。

This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话(Tel):(010)51164723 51164718

传真(Fax):(010) 51164724

报告真伪查询(Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn

电子邮箱(E-mail): dmtc2007@163.com



