



# 检验报告

TEST REPORT

中心编号(No.): 201607AW101



样品名称:	加气块专用抹灰砂浆			
Sample Name				
委托单位:Client	筑隆建材科技有限公司			
检验类别:	委托检验			

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





150002283084 (国家)建筑材料工业技术监督研究中心

# 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201607AW101

第1页 #2页

生产单位	筑隆建材科技有限公司	等一级	DCA5		
生产日期	想認認認為	样品编号	超级		
来样日期	2016年07月04日	规格型号	DCA5		
样品数量	20kg - 20	样品状态	粉状		
检验依据	JC 890-2001《蒸压加气混凝土用砌筑砂浆与抹灰砂浆》				
	1. 抗压强度 2. 粘结强度 3. 凝结时间				
检验项目	1. 抗压强度 2. 粘结强度	206773	TO OTHER		
检验项目	1. 抗压强度 2. 粘结强度 *经检验,送检样品的抗压强合标准 JC 890-2001 中抹面砂浆(	度、粘结强度、凝结m 水泥砂浆)的技术指	标要求。*		
	*经检验,送检样品的抗压强合标准 JC 890-2001 中抹面砂浆(	度、粘结强度、凝结肌	标要求。*		

批准: 4:

### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

### 检验报告

#### TEST REPORT

中心编号(No.): 201607AW101

第2页共2页

序号	检验项目	标准要求 [株面砂浆 (水泥砂浆)]	检验结果	单项结论
	抗压强度, MPa	≥5.0	6.2	合格
2	粘结强度, MPa	≥0.15	0.23	合格
3	凝结时间, h	贯入阻力达到 0.5MPa 时, 3~5h	贯入阻力达到 0.5MPa 时, 4.5h	合格

(以下空白)

备注: 配比: 粉:水=1.0:0.20。

检验单位地址:北京市朝阳区管庄中国建材院内北楼 建筑材料工业技术监督研究中心 機関

#### 说明

#### Notice

- 本报告无中心"检验测试章"和骑缝章无效。
   This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
   This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

