



150002283084

存档

检 验 报 告

TEST REPORT

中心编号(No.): 201701DW118

DMTC

样品名称: 灌浆料

Sample Name

委托单位: 唐山瑞特莱建材有限公司

Client

检验类别: 委托检验

Test Type



建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



建筑材料工业技术监督研究中心
Technical Supervision and Research Center of the Building Materials Industry



150002283084

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检 验 报 告

TEST REPORT

中心编号(No.): 201701DW118

第 1 页 共 2 页

样品名称	灌浆料	检验类别	委托检验
委托单位	唐山瑞特莱建材有限公司	商 标	—
生产单位	唐山瑞特莱建材有限公司	等 级	—
生产日期	—	样品编号	—
来样日期	2017年01月13日	规格型号	—
样品数量	15kg	样品状态	粉状
检验依据	GB/T 50448-2015《水泥基灌浆材料应用技术规范》 GB/T 17671-1999《水泥胶砂强度检验方法 (ISO 法)》		
检验项目	1. 截锥流动度 2. 抗压强度 3. 竖向膨胀率 4. 抗折强度		
检验结论	<p>*经检验, 送检样品的截锥流动度、抗压强度、竖向膨胀率的检验结果符合标准 GB/T 50448-2015 中水泥基灌浆料Ⅲ类的技术指标要求; 依据标准 GB/T 17671-1999 规定的试验方法进行检验, 抗折强度的检验结果见第 2 页。*</p> <p style="text-align: right;">签发日期: 2017年02月17日 (检验测试章)</p>		
备注: (此处空白)			

批 准:

审 核:

编 制:

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

建筑材料工业技术监督研究中心
Technical Supervision and Research Center of the Building Materials Industry

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检 验 报 告

TEST REPORT

中心编号(No.): 201701DW118

第 2 页 共 2 页

第 2 页 共 2 页

序号	检验项目		标准要求 (水泥基灌浆料Ⅲ类)	检验结果	单项结论
1	截锥流动度, mm	初始流动度	≥290	310	合格
		30min 流动度保留值	≥260	305	合格
2	抗压强度, MPa	1d	≥20	38.8	合格
		3d	≥40	45.5	合格
		28d	≥60	62.5	合格
3	竖向膨胀率, %	3h	0.1~3.5	0.24	合格
		24h 与 3h 的膨胀值之差	0.02~0.5	0.03	合格
4	抗折强度, MPa	1d	—	5.9	—
		3d	—	10.8	—
		28d	—	12.2	—
(以下空白)					
备注: 配比: 粉: 水=1.0: 0.15。					



说 明 Notice

- 1、本报告无中心“检验测试章”和骑缝章无效。
This test report is invalid without the seal.
- 2、本报告无“编制、审核、批准”签字无效。
This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议，应于收到报告之日起十五个工作日内向本中心提出，逾期恕不受理。
Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供，中心不对真实性负责，委托检验结果仅对来样负责。
The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律責任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张，复印后应带有网络底纹。
This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式：

地址 (Address)：北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code)：100024

电话 (Tel)：(010) 51164723 51164718

传真 (Fax)：(010) 51164724

报告真伪查询 (Tel)：(010) 51164716

网址 (Web)：<http://www.dmtc.org.cn/>

电子邮箱 (E-mail)：dmte2007@163.com

