



检验报告

TEST REPORT

中心编号(No.): 201610AW114



样品名称: Sample Name	轻集料砼		
委托单位:	北京欣东岩建材科技有限公司		
Client 检验类别:	委托检验		
Test Type	女101岁到		

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201610AW114

第1页 共2页

轻集料砼	检验类别	委托检验	
北京欣东岩建材科技有限公司	商标	欣东岩	
北京欣东岩建材科技有限公司	等级	7.5MPa	
	样品编号	1999	
2016年10月12日	规格型号	的结束	
块状	样品状态	18 块	
GB/T 20473-2006《建筑保温砂浆》			
1. 干密度 2. 抗压强度			
干密度、抗压强度的检验结果见第2	2页。* 日期: 2016年	10-月 24.田	
备注:(此处空白) 企业的 企业			
	北京欣东岩建材科技有限公司 北京欣东岩建材科技有限公司 2016年10月12日 块状 GB/T 20473-2006《建筑保温砂浆》 1. 干密度 2. 抗压强度 *依据标准 GB/T 20473-2006 规 干密度、抗压强度的检验结果见第2	北京欣东岩建材科技有限公司	

准:

编制: 状亮

建筑材料工业技术监督研究中心

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201610AW114

第2页共2页

序号	检验项目	标准要求	检验结果	单项结论
	千密度/(kg/m³)		1000	
2	抗压强度/MPa	SHEET SHEET	7.8	

(以下空白)

电话: 010-51164723

邮編: 100024

备注: 试件由委托方成型并养护。

说明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision

and Research Center of the Building Materials Industry.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

